

# Trap levels in persistent phosphors for bio-imaging

**Dirk Poelman**<sup>1,2</sup>, **Olivier Q De Clercq**<sup>1,2</sup>, **Jiaren Du**<sup>1,2</sup>,  
**Aranit Harizaj**<sup>2,3</sup>, **Ine Lentacker**<sup>2,3</sup>, **Kevin Braeckmans**<sup>2,3</sup>

<sup>1</sup> LumiLab, Department of Solid State Sciences, Ghent University, Krijgslaan 281-S1, B-9000 Ghent, Belgium;

<sup>2</sup> Center for Nano- and Biophotonics (NB-Photonics), Ghent University, B-9000 Ghent, Belgium;

<sup>3</sup> Laboratory for General Biochemistry and Physical Pharmacy, Ghent University, B-9000 Ghent, Belgium.

Corresponding author e-mail address: [Dirk.Poelman@ugent.be](mailto:Dirk.Poelman@ugent.be);

## 1. Introduction

Since more than two decades, efficient and long afterglow persistent luminescent materials are available for emergency signalization, road markings and toys. Available emission colors range from violet to red, but longer wavelengths are hard to achieve with rare earth dopants. While near-infrared emitting phosphors could be useful in night vision or security applications, they are especially promising for medical imaging. Next to  $\text{Mn}^{4+}$  [1],  $\text{Cr}^{3+}$  is an excellent dopant for emission in the so-called first optical window for bio-imaging, from 650 to 950 nm [2]. In this work, the spinel  $\text{LiGa}_5\text{O}_8$  is used as the host for  $\text{Cr}^{3+}$  ions, leading to a combination of broadband and narrowband emission around 720 nm [3,4]. Even without any co-dopants, afterglow can be measured for several hours.

## 2. Results

A combination of the initial rise and  $T_{\text{stop}}-T_{\text{max}}$  methods was shown to be an efficient way to retrieve the distribution of trap depths in the persistent phosphor  $\text{LiGa}_5\text{O}_8:\text{Cr}^{3+}$ . A large data set was produced by making a series of TL (thermoluminescence) measurements at different excitation temperatures. All these data were fitted simultaneously using a single set of trapping parameters. The traps were found to consist of three broad Gaussian trap distributions, see figure 1 [5]. This single set of model parameters allowed to accurately describe the experimental afterglow characteristics of the phosphor, as shown in figure 2. In addition, the parameters can be used to predict other effects of fading and the temperature dependence of the afterglow, which was measured independently.




Fig. 1: Trap distribution calculated from the TL data. The expected trap filling factor at 20°C is also indicated.




Fig. 2: Experimental (markers) and predicted afterglow (full line), based on the calculated trap distributions.

## 3. References

- [1] J. Du, O.Q. De Clercq, D. Poelman, Toward near-infrared persistent luminescence of  $\text{Mn}^{4+}$  activated phosphors; *this conference*.
- [2] J. Xu, S. Tanabe, Persistent luminescence instead of phosphorescence: History, mechanism, and perspective; *J. Lumin.* **205** (2019) 581.
- [3] O.Q. de Clercq, L. Martin, K. Korthout, J. Kusakovskii, H. Vrielinck, D. Poelman, Probing the Local Structure of the Near-infrared Emitting Persistent Phosphor  $\text{LiGa}_5\text{O}_8:\text{Cr}^{3+}$ ; *Journal of Materials Chemistry C* **5** (2017) 10861.
- [4] F. Liu, W. Yan, Y-J Chuang, Z. Zhen, J. Xie, Z. Pan, Photostimulated near-infrared persistent luminescence as a new optical read-out from  $\text{Cr}^{3+}$ -doped  $\text{LiGa}_5\text{O}_8$ ; *Scientific Reports* **3** (2013) 1554.
- [5] O.Q. de Clercq, J. Du, P.F. Smet, J.J. Joos, D. Poelman, Predicting the afterglow duration in persistent phosphors: a validated approach to derive trap depth distributions; *Physical Chemistry Chemical Physics* **20** (2018) 30455.