



CRACK BEHAVIOR OF HEAT TREATED SINTERED STEEL
UNDER CYCLIC LOADING

by

AL EMRAN BIN ISMAIL

Thesis submitted in fulfillment
of the Requirements for the Degree of
Master of Science in Mechanical Engineering

UNIVERSITI TEKNOLOGI MARA

2003

TABLE OF CONTENTS

AKNOWLEDGEMENTS	ii
LIST OF TABLES	vi
LIST OF FIGURES	vii
ABSTRACT	x
1. INTRODUCTION	
1.1 Historical Perspectives	1
1.2 Objectives of the Research	3
1.3 Scope of Research	3
2. LITERATURE REVIEW	
2.1 Powder Metallurgy	5
2.1.1 Mechanical Properties	5
2.1.2 Compacting of Powders	6
2.1.3 Sintering Process	8
2.1.4 Comparing Mechanical Properties	9
2.2 Fatigue	9
2.2.1 Prevention of Fatigue Failure	9
2.2.2 Surface Effects on Fatigue	10
2.3 S – N Curve	12
2.4 Stress Ratio Effects	14
2.5 Fatigue Crack Initiation	17
2.5.1 Crack Initiation Mechanisms	17
2.5.2 Microstructural Effects	25

2.6	Toughness	30
2.6.1	Fracture Toughness	30
2.6.2	Toughening Mechanism	32
2.6.3	Effect of Alloying Elements on Fatigue Properties	38
2.6.4	Microstructural Effects	42
3.	RESEARCH METHODOLOGY	
3.1	Material	46
3.2	Biaxial Tensile Test	47
3.2.1	Shape and Dimension	47
3.2.2	Strain Gauge	47
3.2.3	Testing Procedure	49
3.2.2	Mechanical Properties Determination	51
3.3	Fatigue Specimens	52
3.3.1	Specimen Preparation	52
3.3.2	Heat Treatment	54
3.3.3	Hardness Test	55
3.4	Jig and Fixture	58
3.4.1	Jig	58
3.4.2	Fixture	64
3.5	Experimental Procedures of Fatigue Test	65
3.5.1	Samples Preparation and Treatment	65
3.5.2	Testing Parameters	66
3.5.3	Fatigue Testing	67

ABSTRACT

Fatigue crack nucleation and initiation at particles or defects in materials have been the interest of many researchers over the past years. This is because the understanding of these phenomena would provide a better understanding of production of new fatigue resistance materials. In this study a test was developed to evaluate the fatigue properties and to observe fatigue crack nucleation and initiation in sintered steel. The fatigue test was carried out on polished specimens which was based on plate bending gives balanced biaxial tension. The experimental results shows that there were mixed mode of crack nucleation and initiation such that most cracks initiated at the interface of particles and matrix especially at high stress values. Cracks were also observed to initiate at voids and beneath the surface. Quenched specimens which were tempered between temperature range of 300⁰C and 600⁰C shows similar crack initiation mechanisms. The significant difference between as-received and tempered specimens was that the number of cycles to fail due to differences in material hardness and internal defects. The results of the experimentation are discussed in the light of possible micro crack toughening at the crack tip and the presence of residual stresses due to temperature changes. It is believed that some effects of residual stresses at the surface and beneath play a role in the nucleation of crack in sintered steel.

CHAPTER 1

INTRODUCTION

In the last few years, sintered steel has been developed for mass-production for engineering applications that are subjected to large mechanical stresses. It is therefore, necessary to determine the static and dynamic properties of this material. Numerous works have been conducted to understand the properties of crack growth both at sharp notch and notch root specimen. According to the literature review, the behavior have been observed in the relation to fatigue crack growth and crack length have been well understood but limited literature could be found on crack nucleation and short crack mechanisms.

1.1 Historical Perspectives

Metal fatigue has been studied for the past 150 years. Form 1850 to 1875, experiments were conducted to establish a safe alternating stress below which failure would not occur. Nearly 100 years of research has been performed to establish the effect of many variables on the influence of the long life fatigue strength of metal. Many significant contributions were made during the 1960's. Irwin *et al.* (1970) and others pioneered the development of fracture mechanics as a practical engineering tool. Ewing and Humphrey did the first work on fatigue crack initiation around 1900 to 1910. They prepared a specimen and examined the surface grains with an optical microscope during the course of a fatigue test. They observed formation of slip lines across grains and broadening into bands and eventually developed cracks in the broadened bonds. Then in the 1950's, the concept of a two-