ТЕЗИСЫ ДОКЛАДОВ

INTERNATIONAL WORKSHOP

«Multiscale Biomechanics and Tribology of Inorganic and Organic Systems»

МЕЖДУНАРОДНАЯ КОНФЕРЕНЦИЯ

«Перспективные материалы с иерархической структурой для новых технологий и надежных конструкций»

VIII ВСЕРОССИЙСКАЯ НАУЧНО-ПРАКТИЧЕСКАЯ КОНФЕРЕНЦИЯ С МЕЖДУНАРОДНЫМ УЧАСТИЕМ, ПОСВЯЩЕННАЯ 50-ЛЕТИЮ ОСНОВАНИЯ ИНСТИТУТА ХИМИИ НЕФТИ

«Добыча, подготовка, транспорт нефти и газа»

Томск Издательский Дом ТГУ 2019

Секция 2. Неустойчивость и локализация деформации и разрушения в материалах с иерархической структурой

DOI: 10.17223/9785946218412/60

EFFECT OF SHORT-TERM AGING ON THE IMPACT TOUGHNESS OF ADVANCED 10% CR STEEL

Mishnev R., Dudova N., Kaibyshev R. Belgorod State University, Belgorod

Heat-resistant high-chromium martensitic steels are widely used in various critical components of fossil power plants due to their superior creep resistance and high-temperature strength. High fracture toughness is an important property to assure the reliability of steam turbine parts produced from these steels. In this work, the effect of short-term aging (100 h) at 650°C on the temperature dependence of impact toughness and fracture behavior of advanced 10% Cr steel with low N and high B contents was studied. The steel in tempered condition exhibits the ductile-brittle transition temperature (DBTT) of ~10°C and the Charpy V-notch impact energy of 240 J/cm² at room temperature. Aging for 100 h at 650°C leads to the increase in the DBTT to 35°C and decrease in the impact toughness at 20°C to 90 J/cm². Effect of the fine Laves phase particles (with size < 100 nm) precipitated at lath/grain boundaries on the impact toughness is analyzed. The Laves phase particles serve as additional nucleation sites for microcracks/voids facilitating unstable crack propagation. This is the main reason for decreasing the stable crack propagation energy and impact toughness of the steel.