



This item was submitted to Loughborough's Institutional Repository (<https://dspace.lboro.ac.uk/>) by the author and is made available under the following Creative Commons Licence conditions.



CC creative commons
COMMONS DEED

Attribution-NonCommercial-NoDerivs 2.5

You are free:

- to copy, distribute, display, and perform the work

Under the following conditions:

BY: **Attribution.** You must attribute the work in the manner specified by the author or licensor.

Noncommercial. You may not use this work for commercial purposes.

No Derivative Works. You may not alter, transform, or build upon this work.

- For any reuse or distribution, you must make clear to others the license terms of this work.
- Any of these conditions can be waived if you get permission from the copyright holder.

Your fair use and other rights are in no way affected by the above.

This is a human-readable summary of the [Legal Code \(the full license\)](#).

[Disclaimer](#) 

For the full text of this licence, please go to:
<http://creativecommons.org/licenses/by-nc-nd/2.5/>

Mathematical modeling of a continuous solution polymerization reactor: case-study MMA polymerization

B. Benyahia

*Department of Industrial Chemistry, Faculty of Sciences and Engineering
University of M'sila, Algeria
Email: benyahibr@yahoo.com*

Abstract *In this paper, the dynamics of the free radical polymerization of methyl methacrylate (MMA) in a cooling jacketed continuous reactor were investigated. The modeling stage has been conducted regarding several underlying phenomena so to obtain the most accurate model as we can. Like most of the chemical processes, the mathematical model exhibits high interaction and nonlinearity. To control this system several methods can be implemented to control the system. However, the design of an efficient and reliable control strategy requires, in most cases, the linearization and decoupling of the model equations. In this first part of a paper series the process model is developed and validated prior to the implementation of a fuzzy control strategy.*

Keywords: Solution polymerization, molecular weight distribution, modeling

Introduction:

Continuous polymerization reactors are commonly encountered in chemical industry. With an increasing demand for high-quality polymers, it is necessary to build a control strategy to enable a better control of the properties of the polymer product and minimize the production of off-spec polymers particularly during the start-up or grade change operations. However, polymerization processes are difficult to control effectively due to their complexity as well as the severe nonlinearity and interactivity exhibited by their process models [1-3]. As a result, several kinds of nonlinear control strategies have been developed for polymerization processes.

Product quality is a much more complex issue in polymerization than in more conventional short chain reactions. The molecular structure of the polymer is so sensitive to operating conditions that any disturbance in feed conditions, mixing, reactor temperature and initiator concentration can affect the critical molecular properties such as molecular weight, polymer composition distributions, etc. The requirement of an accurate process model for the optimal quality control is very important. To do so we considered all inherent underlying phenomena in order to build a reliable model of the process. The process model of the free radical polymerization of methyl methacrylate (MMA) in a cooling jacketed continuous reactor is used as a case-study [4-6]. The mathematical model of process, developed here, exhibits a highly non-linear interactive behavior.

DEVELOPEMENT OF THE PROCESS MODEL

Let us consider a reactor where methyl methacrylate (MMA), initiator and the Solvent are continuously introduced. This reactor is assumed to be a jacketed, well-mixed tank. A coolant flows through the jacket to remove the heat of copolymerization. Polymer, solvent, unreacted monomer and eventually initiator flow out of the reactor to a separator.

The reaction kinetics are based on the “terminal model” and assumed to follow the free radical polymerization mechanism, including chain transfer reactions to both solvent and monomer, termination by coupling and termination by disproportionation.

The temperature dependence of the rate constants is assumed to follow the Arrhenius law. The kinetic data used for the plant model of this study are taken from the literature.

From the general free radical polymerization mechanism we obtain the reaction rates as follows:

The initiator:

$$R_I = 2f_i k_d I$$

The solvent:

$$R_s = k_s \left(\frac{2f_i k_d I}{k_{tc} + k_{td}} \right)^{0.5} S$$

The monomer (MMA):

$$R_M = -\frac{dM}{dt} = (k_p + k_{trm}) M \left(\frac{2f_i k_d I}{k_{tc} + k_{td}} \right)^{0.5}$$

Reactions heat rate:

$$\Delta H_T = (-\Delta H) k_p \left(\frac{2f_i k_d I}{k_{tc} + k_{td}} \right)^{0.5} M$$

The mass balances for the different compounds are given by

$$\frac{d(IV)}{dt} = q_I I_f - qI - R_I V$$

$$\frac{d(MV)}{dt} = q_M M_f - qM - R_M V$$

$$\frac{d(SV)}{dt} = q_S S_f - qS - R_S V$$

The energy balances for reactor and jacket can be formulated, respectively, as follows:

$$\frac{d(V\rho C_p T)}{dt} = q_M \rho_M C_{pM} (T_f - T) + q_I \rho_I C_{pI} (T_f - T) + q_S \rho_S C_{pS} (T_f - T) + V\Delta H_T - U_r A_r (T - T_j)$$

$$\frac{d(V\rho_c C_{pc} T_j)}{dt} = \rho_c C_{pc} q_f (T_{jin} - T_{jout}) + U_r A_r (T - T_j) - U_j A_j (T_a - T_j)$$

To build up an accurate model as possible it is necessary to introduce molecular weight distribution equations. To do so, it is not necessary to solve the infinite number of equations for the concentrations of polymer chains of different lengths. Instead, the method of moments is adopted to calculate the number-average molecular weight (M_n) and the weight-average molecular weight (M_w). The definitions of the moments are as follows:

$$G_k = \sum_{n=1}^{\infty} n^k R_n(t), \quad F_k = \sum_{n=1}^{\infty} n^k P_n(t) \quad k = 0,1,2$$

where G_k and F_k are the k th moments of living and dead polymer concentrations, R_n and P_n , respectively.

One can derive balance equations for the first three moments of the living and dead polymer concentrations as follows:

$$\begin{aligned} \frac{d(G_0V)}{dt} &= -qG_0 + (2fk_d I - k_t G_0^2)V \\ \frac{d(G_1V)}{dt} &= -qG_1 + [2fk_d I + k_p M G_0 - k_t G_0 G_1 + (k_{trm} M + k_{trs} S)(G_0 - G_1)]V \\ \frac{d(G_2V)}{dt} &= -qG_2 + [2fk_d I + k_p M(G_0 + 2G_1) - k_t G_0 G_2 + (k_{trm} M + k_{trs} S)(G_0 - G_2)]V \\ \frac{d(F_0V)}{dt} &= -qF_0 + [0.5(k_t + k_{td})G_0^2 + (k_{trm} M + k_{trs} S)G_0]V \\ \frac{d(F_1V)}{dt} &= -qF_1 + [(k_t G_0 + k_{trm} M + k_{trs} S)G_1]V \\ \frac{d(F_2V)}{dt} &= -qF_2 + [(k_{td} G_0 + k_{trm} M + k_{trs} S)G_2 + k_{tc}(G_0 G_2 + G_1^2)]V \end{aligned}$$

where the number and weight-average molecular weights are defined by the following equations:

$$\begin{aligned} M_w &= w_M \frac{(G_2 + F_2)}{(G_1 + F_1)} \\ M_n &= w_M \frac{(G_1 + F_1)}{(G_0 + F_0)} \end{aligned}$$

Conclusions:

Modeling of continuous stirred tank reactor of MMA solution polymerization has been conducted in conjunction with several considerations. The mathematical model based on eleven equations is in fact highly interactive and nonlinear which in turn imply a linearization and decoupling strategy.

The mathematical model has been improved by adding the equations of the molecular weight distribution moments, which have been obtained from equations of moments. In spite of dealing with more complex model, this approach enables the control or the optimization of the number average and average molecular weights.

From a practical point of view the key control objectives of the copolymerization reactor are:

- The linearization
- The compensation of interaction
- The preclusion of input multiplicity
- The robustness of the controller (i.e., tolerance to modeling and tuning errors)

Previous works indicate that the input multiplicity issue, should be the central point in the study of the solution copolymerization control problem.

Notations:

I	: initiator concentration, kmol /m ³
I_f	: initiator feed concentration, kmol /m ³
M	: monomer 1, 2 concentrations, kmol /m ³
M_f	: monomer 1, 2 feed concentrations, kmol /m ³
q_M	: monomer 1, 2 feed rates, m ³ /s
q_S, q_I	: solvent and initiator feed rates, m ³ /s
q	: output flow rate, m ³ /s
R_M	: monomer reaction rate, kmol /m ³ .s
R_I, R_S	: initiator and solvent reaction rate, kmol /m ³ .s
S	: solvent concentration, kmol /m ³
S_f	: solvent feed concentration, kmol /m ³
T, T_f, T_j	: reactor, feed-rate and cooling temperatures, K
$T_{jin}, T_{j out}$: input and output cooling liquid, K
V	: reactor volume, m ³
U	: overall heat transfer coefficient, kJ/m ² .s.K
ρ, ρ_c	: average density of the reactor mixture, kg/ m ³
ρ_M, ρ_S, ρ_I	: density of monomer, solvent and initiator kg/ m ³


References

- [1] V. P. Barbosa, M. R. M. Wolf, R. Maciel, "Development of data reconciliation for dynamic nonlinear systems: Application the polymerisation reactors" *Comp. and Chem. Eng.*, 24, p 501-506, 2000
- [2] T. Srinivas, M. Souroush, "Multirate nonlinear state estimation with application to a polymerization reactor". *AIChE J.*, Vol. 45, N°4, p. 769, 1999.
- [3] J. Alvarez, E. R. Suarez, A. Sanchez, "Nonlinear decoupling control of free-radical polymerization continuous stirred tank reactors". *Chem. Eng. Sci.*, Vol. 45, N°11, p. 3341, 1990.
- [4] D. K. Adebekun, F. J. Schork, "Continuous solution polymerization reactor control 1 : Nonlinear reference control of methyl methacrylate polymerization". *Ind. Eng. Chem. Res.*, Vol. 28, p.1308, 1989.
- [5] M. J. Park, H.K. Rhee, "LMI-based robust model predictive control for a continuous MMA polymerization reactor". *Comp. and Chem. Eng.* 25 1513–1520, 2001.
- [6] Benyahia, B, Nacef, S, Krim, F, "Nonlinear model-based control of a solution copolymerization continuous stirred tank reactor". In *First Instrumentation and Measurement in Petroleum Applications Conference (IMPAC 2000)*, Boumerdes, Algeria, pp.192-197, 2000.


Appendix:

Kinetic scheme for free-radical polymerization of MMA


Initiation :




Propagation :




Chain transfer to monomer :



Chain transfer to Solvent :



Termination by combination :



Termination by disproportionation :

