

This item was submitted to Loughborough's Institutional Repository by the author and is made available under the following Creative Commons Licence conditions.



creative commons
COMMONS DEED

Attribution-NonCommercial-NoDerivs 2.5

You are free:

- to copy, distribute, display, and perform the work

Under the following conditions:

 **Attribution.** You must attribute the work in the manner specified by the author or licensor.

 **Noncommercial.** You may not use this work for commercial purposes.

 **No Derivative Works.** You may not alter, transform, or build upon this work.

- For any reuse or distribution, you must make clear to others the license terms of this work.
- Any of these conditions can be waived if you get permission from the copyright holder.

Your fair use and other rights are in no way affected by the above.

This is a human-readable summary of the [Legal Code \(the full license\)](#).

[Disclaimer](#) 

For the full text of this licence, please go to:
<http://creativecommons.org/licenses/by-nc-nd/2.5/>

Binding mechanisms of radionuclides to cement

N.D.M. Evans*

Department of Chemistry, Loughborough University, Loughborough,
Leics, LE11 3TU, UK

*Author for correspondence: n.d.m.evans@lboro.ac.uk

Abstract

Radionuclide solubility is one of the factors that can determine the 'source term' for potential migration to the far field. Hence, the mechanisms of immobilisation of radionuclides in cements need close study in order to quantify the nature of the binding. The nature of the binding forces in a cement matrix is very species sensitive, so it is difficult to produce a general description. This review summarises the main sorption mechanisms and then details immobilisation mechanisms for many elements.

1. Introduction

Radionuclide solubility is one of the factors, along with sorption and inventory, that can determine the 'source term' for potential migration to the far field of a nuclear waste repository. Several processes can affect the concentration of a radionuclide in cement porewater, e.g.:

- a) precipitation as a simple salt;
- b) coprecipitation with other phases;
- c) lattice incorporation in the major cement hydration products (solid solution);
- d) sorption at hydrous surfaces (chemisorption, adsorption);
- e) complex and colloid formation in the aqueous phase [1].

The best case for retardation of radionuclide mobility is to have a low aqueous solubility, with a robust solubility controlling phase. An understanding of interaction mechanisms is important where data are required for performance assessment that are outside the range of experimental systems studied (e.g. pH range, timescales). If the wrong mechanism is assumed, this could lead to inappropriate values being selected on estimation. It should be noted that mechanisms found to occur on laboratory timescales are not necessarily those that will operate on much longer (repository-related) timescales.

One aspect that is not covered in this review is the effect of carbonation of cements on radionuclide immobilisation. This is due to insufficient data being available in the literature used to compile this review.

Sorption is a generic term, which covers the processes of absorption, physical adsorption and chemical adsorption. Sorption mechanisms depend on the chemical speciation of the sorbate, and the chemical and physical properties of the sorbent.

Absorption is the incorporation of a sorbate within the physical or molecular structure of a sorbent, i.e. the sorbate has access to the bulk, not just the surface, of the sorbent.

Physical adsorption can be divided into three types:

- (a) Surface complexation, which is mixture of chemical and electrostatic interactions;
- (b) Ion exchange, which is an example of electrostatic adsorption due to coulombic forces of attraction between charged sorbate species and the sorbent;
- (c) Other mechanisms, e.g. solid-solution formation, co-precipitation.

The most important reactions of cement with waste are those which lead to binding [2], i.e. a chemical reaction. The nature of the binding forces in a cement matrix is species specific, so it is difficult to produce a general description. Many species also form one or more solubility-limiting phases by reaction with cement components. "Solubility-limiting" implies the formation of a phase which would not ordinarily exist in cement, because it contains one or more radioactive species.

2. Review of Reported Immobilisation Mechanisms by Element

2.1 Group I Elements

The sorption of Li, Na, K and Cs on calcium silicate hydrate (CSH) studied by Iwaida *et al.* [3], was found to increase inversely in proportion to the Stokes radius of the hydrated ions for cements with various Ca:Si ratios. The authors concluded that sorption was electrostatic on a negatively charged CSH site. Hong *et al.* have suggested [4] that this is at silanol (Si-OH) sites, arising from the density of silanol bonds and the sites' mean acidity, both of which increased as the Ca:Si ratio decreased [4].

2.1.1 Caesium

The binding capacity of cement for Cs is dependent on chemical composition, as the different phases have different binding capacities [5]. Cs retention has been found to increase with increasing CaO:Al₂O₃ ratio, yet R_d values remain almost constant if the quantity of SiO₂ in the matrix composition increases in the same ratio [5]. However, Cs retention was found to decrease with increasing SiO₂:CaO ratio [5], the opposite effect was found by Noshita and Aggarwal *et al.* [6], but not commented upon by the authors. Sorption decreased further with increasing alumina content, at constant SiO₂:CaO ratio. Similarly, for compositions with constant Al₂O₃:SiO₂ content, an increase in the Ca:Si ratio resulted in a decrease in R_d values, although increasing the CaO content with a constant Al₂O₃:SiO₂ ratio increased Cs retention [5].

Solid-state NMR was used to investigate Cs speciation in cements by Hanna *et al.* [7]. Cs in Ordinary Portland Cement (OPC) appeared to remain in solution, whether or not blast furnace slag (BFS) or Condensed Silica Fume (CSF) were present. Differences due to Cs partly inhabiting semi-crystalline or amorphous solid sites were observed after 1 year in the slag-containing cement, but the majority of the Cs was apparently restricted to partially or fully solvated states in the aqueous phase. However, Atkinson *et al.* [8] concluded that the diffusivity of Cs⁺ ions in OPC was significantly lower than that of Cl⁻ and Na⁺ ions. The use of zeolite as a blending material in cement has been found to cause an 80-fold reduction in Cs leaching [9] [10], and in other studies, the use of slag also had an influence by a factor of 4-5 on leaching [11] [12].

Sorption experiments with ¹³⁷Cs on four types of concrete (normal density, normal density with fuel ash, high density and high density with silica fume) were carried out by Jakubick *et al.* [13] in 3 groundwaters. Cs showed no significant sorption on normal-density concrete and sorption on carbonate aggregates was also very low. Greater sorption occurred along the cleavage planes of gneiss aggregates containing mafic minerals (biotite and pyroxene). The high-density sample showed preferential sorption of Cs on the magnetite aggregates and on the fine grains of specularite, a

variety of haematite characterised by aggregates of silvery, metallic, specular haematite flakes or tabular, anhedral crystals, also known as grey haematite.

The identification of the hydrated phases responsible for Cs incorporation in concrete was investigated by Hoyle *et al.* [14]. Calcium aluminosilicate glasses were mixed with CsOH or CsCl solutions and allowed to hydrate. Glasses exposed to CsOH(aq) were more reactive than their counterparts exposed to CsCl(aq). At least two Cs-containing zeolites were identified in the 90°C CsOH solution; a Cs-containing wairakite ($\text{CaAl}_2\text{Si}_4\text{O}_{12}\cdot 2\text{H}_2\text{O}$) analogue, and another unidentified Cs-containing zeolite. However, strätlingite did not appear to take up Cs.

Noshita *et al.* [15] found that Cs was highly sorbed by calcium silicate compounds (in agreement with [6]). It was sorbed onto those with lower Ca:Si molar ratios, such as CSH. This suggests that sorption was mainly determined by Ca:Si ratios, regardless of crystal structure. Iwaida *et al.* [3] observed a shortening of the silicate chains in CSH which had sorbed Cs, indicating breakage of the silicate chains had occurred. The authors suggested that hydroxide played an important role in this process. Energy dispersive analysis of silica fume clusters in cement by Bar-Nes *et al.* [16] suggested that Cs tends to concentrate inside agglomerated silica particles.

2.1.2 Sodium

Sodium substitutions in CSH phases have been reported [17]. CSH gel dissolution experiments in NaCl(aq) showed an increase in Ca concentration at higher Na concentrations. This was interpreted in terms of an ion exchange process between Ca and Na [18], although an alternative explanation could lie in the formation of chlorocomplexes.

2.2 Actinides

2.2.1 Americium

Experiments [13] using ^{241}Am have indicated preferential sorption in cementitious paste. Normal-density specimens containing fuel ash sorbed more than standard compositions, with voids showing rims of enhanced sorption. Considerable sorption was observed on carbonate aggregates and mafic components of the granitic and gneiss aggregates. A slightly higher sorption on magnetite than on specularite or hematite was observed [13]. Baston *et al.* [19] quantified Am sorption data using a surface complexation model, in which the main surface sites were $>\text{SiO}^-$ and $>\text{SiOCaOH}$, with Am hydroxide species assumed to be the sorbing species. Noshita *et al.* [20], have found that Am is highly sorbed onto CSH gel, and they concluded that Am is anionic in cement.

2.2.2 Curium

Stumpf *et al.* using time-resolved laser fluorescence spectroscopy (TRLFS) [21] identified 4 different Cm(III) species. A non-fluorescing species which corresponds to curium hydroxide real colloids, a fluorescing Cm(III)-portlandite sorption species, and two fluorescing Cm(III)-CSH species. From fluorescence emission lifetimes it was predicted that the two fluorescing Cm(III)-CSH species had 1 to 2, and zero water molecules respectively, in their 1st coordination sphere, suggesting that these species were incorporated in the CSH structure. Measurements on HCP systems in artificial cement pore-water showed that initially Cm(III) is sorbed on the portlandite fraction. With time, two forms of Cm(III) incorporated in the CSH fraction, where it occupies 2 different positions in the CSH structure [22], became dominant.

2.2.3 Neptunium

Sylwester *et al.* [23] observed a reduction from Np(V) to Np(IV) as it interacted with OPC; the amount of reduction increasing with equilibration time. The absence of Np-Np interactions in the extended X-ray absorption fine structure (EXAFS) spectra provided evidence that Np partitioning was controlled by sorption of Np(V), followed by reduction, and not by reduction followed by formation of Np(IV) surface precipitates. Matzen *et al.* [24] identified immobilised Np at, or near, the fracture surface when soluble and colloid-associated Np were eluted into a fractured, hydrothermally altered, concrete core.

2.2.4 Plutonium

Jakubick *et al.* [13] have shown that the surface distribution pattern of Pu follows the concrete structure selectively. Preferential sorption in the cement paste over that on aggregates was characteristic of both normal and high-density concrete. Sorption on carbonate aggregates was slightly higher than, or comparable with, that on gneiss fragments. Sorption patches of Pu were also observed on the mafic components of the granitic aggregates. However, the quartz components remained inactive. In the high-density concrete, the magnetite aggregates proved to be more sorptive than hematite and specularite. Aggarwal *et al.* [6] found that sorption increased with increasing fraction of OPC in PFA/OPC blends. There was a downward trend in R_d with decreasing Ca:Si ratio for C_3S hydrates. Comparison of the sorption on cements with that on CSH, indicated that most sorption occurred on the CSH, but in BFS/OPC blends, other phases may have contributed.

2.2.5 Thorium

Tits *et al.* [25] have shown that the sorption process controlling the retention of Th(IV) on CSH is fast. Sorption distribution ratios in the range of 10^5 to 10^6 $\text{dm}^3 \text{kg}^{-1}$ were found.

2.2.6 Uranium

The reactions between CaO, SiO_2 and schoepite ($\text{UO}_3 \cdot 2\text{H}_2\text{O}$) were studied by Moroni *et al.* [26] in aqueous suspensions at 85°C . Several solubility-limiting, but hitherto uncharacterised, CaO- UO_3 - SiO_2 - H_2O phases were described. It was concluded that weeksite-like and becquerelite-like structures were probably developed. With the formation of crystalline phases, U solubilities declined to the region of 10^{-8} - 10^{-9} mol dm^{-3} . Some slight U sorption into the gel may have occurred. Sylwester *et al.* [23] have shown that U remains in the form of UO_2^{2+} . Evidence of inner-sphere interactions on both treated and untreated cements at all pH values was found, with UO_2^{2+} complexing with the mineral surface via sharing of equatorial oxygens. On

hydrothermally treated cement near-neighbour U-U interactions were also observed, indicating the formation of oligomeric surface complexes, or surface precipitates.

Wet chemistry and EXAFS studies on U(VI) uptake by HCP by Wieland *et al.* [27] showed that sorption was linear up to about $6 \times 10^{-6} \text{ mol dm}^{-3}$. Above this, the immobilisation was due to the formation of a calcium uranate precipitate. A study by Pointeau *et al.* [28] showed that the uptake of U(VI) increased when comparing the least and most degraded cement pastes, whereas the initial composition of the cement had relatively little effect. Sorption isotherms were linear with a slope of 1, indicating the predominance of sorption processes. As sorption and desorption values were close, the uptake mechanism seemed to be reversible.

Harfouche *et al.* [29] either sorbed U(VI) onto previously precipitated CSH phases (sorption samples) or added during C-S-H synthesis (coprecipitation samples). The coordination environment of U(VI) in the sorption samples was independent of CSH Synthesis procedure. The coordination environment of U(VI) in the coprecipitated samples depended on the synthesis method, and the spectra differed from those for the sorption samples.

2.3 'P' Block Elements

2.3.1 Arsenic

Kumarathasan *et al.* [30] observed the replacement of SO_4^{2-} by arsenate in ettringite, and quasi-instantaneous equilibrium ($< 1 \text{ min}$) was observed by Myneni *et al.* [31] for this process. A study by Phenrat *et al.* [32] found As-Fe hydroxide sludge to be immobilised by 3 mechanisms, sorption onto the CSH surface, replacing SO_4^{2-} in ettringite and, predominantly, the formation of solubility-limiting Ca-As compounds.

Stronach *et al.* [33] report that hydrated Portland cement limits the solubility of As(III) to 7.0 mmol kg^{-1} . The authors also observed that this is due to the substantial buffering reserve of $\text{Ca}(\text{OH})_2$, which is in theory able to immobilise 1 As atom per Ca atom by the formation of the sparingly soluble CaAsO_2OH .

2.3.2 Organic Carbon

Batch sorption experiments using acetic acid, formaldehyde, acetaldehyde and arginine were carried out by Matsumoto *et al.* on various types of cementitious mortars [34] at different pHs. The sorption experiments showed that aqueous organic ^{14}C was not sorbed to any great extent on mortar at high pH. In the mortar-acetaldehyde system sorption was not affected by pH. In the mortar-arginine system, it was found that sorption behaviour changed on either side of the isoelectric point of arginine, i.e. sorption of negatively charged arginine above pH 12.5 was low, whereas that of the positively charged species below pH 12.5 was high. Therefore, it was concluded that organic carbon is mainly adsorbed onto the surface of mortar via silanol groups electrostatically, and so sorption will depend on the ionic speciation of the organic carbon species in aqueous solution.

2.3.3 Inorganic Carbon

Inorganic ^{14}C sorption by cementitious materials can be roughly divided into two reactions; (i) adsorption onto a positive site and (ii) precipitation. Noshita *et al.* [35] have suggested that $^{14}\text{CO}_3^{2-}$ was sorbed onto the cement surface electrostatically, due to the reaction between SiO_2 and CaO contained in the cement. That is, SiO_2 was originally anionic (SiO^-), but became cationic through interaction with Ca^{2+} . The ^{14}C K_d was increased from 2,000 to 7,000 ml g^{-1} by adding SiO_2 to OPC. Banba *et al.* [36] also suggested that this immobilisation was also by adsorption onto colloidal compounds in cement.

Noshita *et al.* [15] found that CO_3^{2-} it sorbed onto calcium silicate compounds with lower Ca:Si ratios if the bulk solution was in $\text{NaOH}(\text{aq})$, but that sorption was less in bulk $\text{Ca}(\text{OH})_2$ solution. This indicated that formation of CaCO_3 may affect R_d values, although the initial carbonate concentration was adjusted to below its maximum solubility. In $\text{Ca}(\text{OH})_2$ solution, the order of sorption was gibbsite > brucite > portlandite, which may reflect the tendency of CaCO_3 to flocculate and precipitate as colloids.

2.3.4 Chlorine

Several authors, e.g. Brown *et al.* [37] and Damidot *et al.* [38] have characterised the formation of basic chlorides, (hydr)oxychlorides, in cement systems. The interaction of Cl^- ions with a cement matrix depends on several parameters. Chloride can react with unhydrated aluminate phases to form new compounds such as Friedel's salt [37] [38][39]. Sorption, or secondary phase formation, depends on the type of binder and the nature of the cations in the pore solution [40], [41], [42], [43] as well as on the pore solution concentration and composition. For example, the amount of bound Cl^- added as CaCl_2 has been found to be significantly higher than for Cl^- added as NaCl [44] [45], but the reason for this is not clear. It has been suggested that CaCl_2 interacts with $\text{Ca}(\text{OH})_2$ at low temperatures, and high Cl^- concentrations, to give $\text{CaO-CaCl}_2\text{-H}_2\text{O}$ complex salts with varying compositions [44]. Tang *et al.* [14] observed that the Cl^- binding capacity of HCP strongly depends on the content of CSH gel.

Several possible states of Cl^- in the hydration of tricalcium silicate in the presence of CaCl_2 have been suggested [46]. These include a chemisorbed [46] Cl^- layer on the surface of CSH, in the interlayer space and incorporated in the CSH lattice. Beaudoin *et al.* have suggested that most of the chloride ions are chemisorbed on the surface of hydrated C_3S [47].

^{35}Cl NMR relaxation methods [48] indicated that the majority of the sorbed Cl^- near the surfaces of solid phases such as portlandite and jennite was in a solution-like environment, and was in rapid exchange with free Cl^- in the bulk solution. The total amount of sorbed Cl^- on jennite was substantially greater than could be accommodated by coordination directly to the solid surfaces and the amount predicted to exist in the Stern and diffuse layers based on Gouy-Chapman calculations. The authors postulated that this excess was probably due primarily to formation of metal complexes or ion pairs.

2.3.5 Iodine

The mechanism of Γ^- uptake in cement hydrate phases is sorption and/or incorporation according to Glasser *et al.* [49]. Precipitation as a simple iodide salt is most unlikely, because its salts are either too soluble, or else sufficient insolubilising cations are not normally present in cements (e.g., Ag^+ , Pb^{2+}) [49].

Long-term experiments have shown that Γ^- sorption increases with increasing Ca:Si ratio in CSH gels (in agreement with [6]), despite increased competition from OH^- for sorption sites at higher Ca:Si ratios [15] [49], suggesting that Γ^- was sorbed electrostatically. AF_t behaved similarly to high Ca:Si ratio CSH. AF_m however, has been shown to be a much more efficient scavenger with 70-80% removal from 10^{-3} mol dm^{-3} solutions.

Iodide sorption on three commercial alumina cements mixed with CaSO_4 and/or $\text{Ca}(\text{OH})_2$ was investigated by Toyohara *et al.* [50] [51]. The highest sorption was obtained with CaSO_4 added to alumina cement to a $\text{SO}_4:\text{Ca}$ mole ratio of 0.16. The Γ^- replaced the OH^- in $4\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot 13\text{H}_2\text{O}$ to form the new hydrate $3\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot\text{CaI}_2\cdot 12\text{H}_2\text{O}$. The results of sorption and desorption experiments showed that Γ^- sorption was reversible and independent of concentration up to 1×10^{-2} mol dm^{-3} .

CSH has a much stronger affinity for iodate than iodide. This is probably due to the more complex structure of the iodate anion with the surrounding oxygens acting as bridges with the complex CSH substrate. Slight desorption occurs with time, which is thought to be due to occlusion of aqueous iodate in CSH followed by diffusion of the excess back to solution. A similar phenomenon has been found for sulphate in CSH [44].

2.3.6 Lead

Glasser [52] suggests that Pb will generally replace Ca in cement hydrate phases. Moulin *et al.* [53] found that whereas Pb shows a poor affinity to calcium aluminate phases (due to precipitation of PbO), it was strongly retained by hydrated phases coming from C_4AF hydration, and that the Pb was linked to silica tetrahedra. The authors attributed this strong retention of lead to the hydrated "ferrite" phase.

Sorption isotherms of Pb(II) carried out on C₃S and CSH showed that Pb has differing affinities for calcium silicate in a concentration range lower than the saturation concentration value of PbO [54]. Structural retention mechanisms have been attributed to Q_{1Mc} sites involving Si-O-Pb bonds by Rose *et al.* [55].

Johnson *et al.* [56] have shown that a relatively high proportion of Pb precipitated out on the cement matrix, rather than in the precipitated layer as was the case for Cr, Cu and Zn. It is possible that isomorphic substitution of Ca²⁺ by Pb²⁺ (ionic radii 1.00 and 1.17 Å, respectively) had taken place in the cement matrix.

An investigation by Coleman *et al.* [57] into the interactions of aqueous Pb²⁺ ions with crushed concrete fines (CCF), showed that the surface of Pb-CCF was generally composed of a reticular, lead-bearing, calcium silicate network and, occasionally, lead-bearing, calcium-rich, distorted polygons. Removal of Pb²⁺ from solution took place by diffusion into the cement matrix. The authors postulated that the underlying mechanism was isomorphic substitution by Pb²⁺ for Ca²⁺ in the CSH. The rare, calcium-rich, heavy metal-bearing polygons observed on the surfaces of each of the recovered CCF specimens were suggested to be re-precipitated portlandite crystals, distorted from their normal hexagons by the inclusion of Pb²⁺ ions.

Many authors have examined the influence of Pb on the hydration properties of cement. Thomas *et al.* [58] observed retardation of hydration, due to a rapid precipitation of basic lead compounds. The precipitate that coated the surface of the cement grains was essentially formed of a colloidal gelatinous material. According to Cartledge *et al.* [59], coatings, which hinder cement hydration, can be formed by lead hydroxide, sulphate, and nitrate mixed salts. Cocke *et al.*, [60] [61] [62] have argued that the coatings act as diffusional barriers to water. A charge dispersal model in which the calcium ions induce a charge reversal of the silicate surface allowing Pb(OH)₃⁻ ions to be adsorbed has been proposed for retardation by Yousuf *et al.* [63] and Asavapisit *et al.* [64]. On the other hand, Ortego *et al.* [65] have suggested that the presence of lead could result in a slight enhancement of silicate polymerisation.

Mattus *et al.* [66] have suggested that retardation is due to precipitation of sparingly soluble compounds onto the surface of silicate phases, thus preventing their access to water. However, the retardation effect is concentration-dependent, so that Pb has been shown to be a set accelerator in some cases [67].

2.3.7 Selenium

Selenate sorbs via weakly bonded outer-sphere complexes [68]. Kumarathasan *et al.* [30] and Baur *et al.* [68] have reported the replacement of SO_4^{2-} by selenate in ettringite, and this has also been observed in 'monosulphate' which has a crystalline layer structure derived from that of $\text{Ca}(\text{OH})_2$ by the ordered replacement of one Ca^{2+} ion in three with Al^{3+} or Fe^{3+} . These layers alternate with ones containing anions, which balance the charge (e.g. SO_4^{2-} , OH^- , etc.) and H_2O . The composition is $[\text{Ca}_2(\text{Al,Fe})(\text{OH})_6]\cdot\text{Z}\cdot x\text{H}_2\text{O}$, where Z represents the interlayer anion. [31] [69] [70] [71].

Solem-Tishmack *et al.* [72] have interpreted the more efficient retention of selenite over selenate by the formation of selenite ettringite in cementitious material. However, CaSeO_3 precipitation seems the more likely reason for the retention [65].

Bonhoure *et al.* [73] have shown that Se redox reactions do not influence uptake processes in cementitious systems. EXAFS spectra of Se(IV) and Se(VI) bound to CH, AFt, AFm and CSH were similar to those of SeO_4^{2-} and SeO_3^{2-} in solution, indicating a "solution-like" coordination environment on uptake by cement minerals. The results suggested that the coordination spheres of selenate and selenite are maintained on immobilisation.

2.3.8 Sulphate

Kalousek [1] proposed that SO_4^{2-} ions present in cement eventually enter CSH and experimental studies [74] [75] have demonstrated that sulphate can bind to CSH. Nachbaur [76] showed that the mechanism of sulphate binding was a surface phenomenon. The main quantitative results were obtained by Divet *et al.* [77], who found that sulphate sorption on CSH fitted a Langmuir isotherm, and that sorption

increased with pH and temperature, and that sulphate binding increases with the Ca:Si ratio of CSH.

2.3.9 Tin

A study by Seby *et al.* [78] showed a strong uptake of Sn(IV) by HCP at pH 13.3 at Sn concentrations well below the solubility limit of Ca-stannate. Bonhoure *et al.* [79] have suggested that CSH phases may not be the uptake-controlling phase in the cement matrix. An alternative model was proposed [79] on the assumption that ettringite is the uptake controlling phase. A study of Sn immobilisation by cement and CSH by Wieland *et al.* [27] showed that, on HCP, sorption was linear up to a maximum equilibrium concentration of about $8 \times 10^{-7} \text{ mol dm}^{-3}$. Above this immobilisation was due to the formation of a Ca-stannate precipitate, often described in the literature as CaSn(OH)_6 .

2.4 Transition Elements

2.4.1 Cadmium

Bonen *et al.* [80] have reported ettringite accommodating Cd^{2+} at the M^{2+} site in the crystal structure. Poletini *et al.*, [81] found chemical immobilisation of Cd within CSH at pH >10. Furthermore, the low aqueous Cd concentrations found at high pH may account for its immobilisation within portlandite, as Cd is known to provide nucleation sites both for CSH and portlandite [66].

2.4.2 Chromium

Chromium's oxidation state and its immobilisation by cements are closely related. Kumarathanan *et al.* [30] has reported the replacement of SO_4^{2-} by chromate in ettringite. Moulin *et al.* [53] have observed interactions between Cr and hydrated cement phases. It was found that Cr showed a strong affinity for hydrated C_4AF "ferrite" phases. Cr(III) is structurally incorporated by hydrogarnet phases, but Cr(VI) only showed an affinity for hydrated calcium aluminate phases. For Cr(III), whatever

the cement phases studied, a hydrogarnet phase of variable composition was formed. Cr(VI) was weakly retained by calcium silicate, but more by calcium aluminate and aluminoferrite. According to other results [82] [83] [84], ion-exchange between CrO_4^{2-} and OH^- in the AF_m phase are responsible for immobilisation.

According to Polettini *et al.* [81] Cr(III) is known to be able to increase the amount of heat liberated during early hydration, promoting the formation of ettringite crystals, probably by reducing the degree of supersaturation [85]. There is evidence for the ability of CSH to incorporate Cr^{3+} ions through Si substitution in poorly crystalline structures [81]. Calcium aluminate hydrate phases can also be formed where octahedrally coordinated aluminium is partly replaced by Cr(III) [81].

2.4.3 Cobalt

Bonen *et al.* [80] have reported ettringite accommodating Co^{2+} at the M^{2+} site in the crystal structure, while Noshita *et al.* showed that it was strongly sorbed onto CSH gel [20].

Vespa *et al.* [86] found that, for samples prepared in air, Co(II) is oxidized to Co(III) after 1 h of hydration time and that the relative amount of Co(III) increased with hydration time. Co(II) was predominately present as a Co-hydroxide-like phase and/or Co-phyllosilicates, whereas Co(III) tended to be incorporated into a CoOOH -like phase and/or Co-phylломanganates. Samples prepared in the absence of oxygen revealed solely the presence of Co(II), indicating that oxygen plays an important role in Co oxidation in cement.

2.4.4 Copper

Johnson *et al.* [56] have shown that precipitation, in addition to lowering solubility at elevated pH, is responsible for the immobilisation of Cu. Analysis of Cu-containing crystals showed a Ca to Cu molar ratio of 1:11. Coleman *et al.*'s [57] study of sorption onto crushed concrete fines (CCF) showed 2 distinct Cu-bearing phases on the surface of Cu-CCF, a Cu-rich foliaceous mass and rare, Cu-bearing, Ca-rich, distorted polygons. The principal mechanism of Cu uptake was precipitation of the

foliated crystals onto the surface. No appreciable diffusion of Cu^{2+} into the cement matrix was observed.

2.4.5 Iron

In 1952, Kalousek proposed that all Fe^{3+} ions present in cement eventually enter CSH [1]. Copeland *et al.* [87] provided some support to this theory by suggesting that two Fe^{3+} atoms replace one calcium and one silicon.

2.4.6 Mercury

Poon *et al.* [88] have produced evidence of Hg immobilisation by ettringite.

2.4.7 Molybdenum

Mo(VI) can be immobilised in HCP as both CaMoO_4 , and as a Mo-substituted AF_m phase [2].

2.4.8 Nickel

Bonen *et al.* [80] report ettringite accommodating Ni^{2+} at the M^{2+} site in the crystal structure. Ni sorbed onto calcium silicates was reported by Noshita *et al.* [15] showed no dependence on Ca:Si ratios, eliminating electrostatic adsorption as a mechanism. Coprecipitation or surface complexation via the hydroxyl group have been suggested [89] [90]. Ni has also been found highly sorbed onto hydroxides, probably due to coprecipitation or surface complexation [89] [90] [91]. This finding contradicts the suggestion of an adsorption-type uptake process. Several authors have noted that there is evidence for a solubility-controlled uptake process [92] [93] [94].

Johnson *et al.* [56] found that precipitation mechanisms in addition to the reduction in solubility at elevated pH, are responsible for Ni immobilisation. Analysis showed a Ca:Ni molecular ratio of 1.10 in the botryoidal Ni-containing precipitate. Scheidegger *et al.* [92] showed that mixed Ni-Al layered double hydroxides (LDH) may form in cement systems, and thus, Ni-Al LDHs are regarded as solid phases being potentially

present in the waste matrix and governing nickel uptake, this has been confirmed by Vespa *et al.* [95]. The work of Johnson *et al.*, [93] however, indicates that $\text{Ni}_4\text{Al}_2(\text{OH})_{12}\text{CO}_3 \cdot 2\text{H}_2\text{O}$, which has a LDH-type structure, is unlikely to account for the limited solubility of Ni in cement systems.

2.4.9 Vanadium

Kumarathasan *et al.* [30] has reported the replacement of SO_4^{2-} by vanadate in ettringite.

2.4.10 Zinc

Bonen *et al.* [80] report ettringite incorporating Zn^{2+} at the M^{2+} site. Moulin *et al.* [53] found interactions between hydrated cement phases and Zn, and concluded that Zn showed a strong affinity for hydrated ferrite phases and that it was linked to the silica tetrahedra of CSH. From sorption experiments by Ludwig *et al.* [94], it appears that Zn is strongly retained by CSH. This retention has been attributed to the linkage of tetrahedral Zn to CSH tetrahedral silicate chains [54] [82].

Ziegler *et al.* [96] [97] found that at high Zn(II) concentrations ($> 1 \text{ mmol dm}^{-3}$), the precipitation of $\beta_2\text{-Zn}(\text{OH})_2$ ($< \text{pH } 12$) and calcium zincate $\text{Zn}_2\text{Ca}(\text{OH})_6 \cdot 2\text{H}_2\text{O}$ ($> \text{pH } 12$) occurred, but do not indicate the concentration at which precipitation begins. Surface precipitation was not found. Zn was observed to incorporate into the CSH(I) particles, but it did not appear to substitute for calcium or silicon.

XAFS spectra of the Zn(II) equilibrated with CSH(I) suggested tetrahedral coordination of Zn(II) by 4 oxygen atoms in the atomic shell. This coordination environment was related by the author to the structure of hemimorphite, a naturally occurring zinc silicate, and/or the presence of $\gamma\text{-Zn}(\text{OH})_2$.

Johnson *et al.* [56] found that cubic crystals observed on concrete particles following contact with Zn^{2+} solution were found to be calcium-rich, whereas the underlying precipitate was Zn -rich. Coleman *et al.*'s study [57] of CCF sorption showed a Zn-rich porous 'cancellated' network and occasional, zinc-bearing, calcium-rich,

distorted polygons over which a further diffuse deposit had formed. The authors concluded that the mechanism of uptake of Zn by CCF was characterised by 3 stages. Firstly, deposition of a Zn -rich precipitate on the surface of CCF, a few microns in depth. Secondly, the formation of a second deposit of around 10 μm and, thirdly, a final superficial precipitate. The authors postulated that the different precipitation processes were mediated by pH and the concentration and speciation of Zn^{2+} ions in solution. Zn^{2+} ions did not appear to have penetrated the cement matrix to any appreciable extent.

Zinc has been reported as causing a substantial retardation in the setting of cement by formation of a protective layer over the cement grains. In the case of C_3S , Ortego *et al.* [65] demonstrated that polymerisation was retarded by its presence. Arliguie *et al.* [98] and Gawlicki *et al.* [99] have suggested that this retardation results from precipitation of an amorphous layer of $\text{Zn}(\text{OH})_2$ onto the anhydrous grains, but that the hydration process could be restarted once the Ca concentration in solution was sufficient to induce crystallisation of calcium zinc hydroxide. Yousuf *et al.* [63] [100] suggest that surface formation of $\text{CaZn}_2(\text{OH})_6 \cdot 2\text{H}_2\text{O}$ prevented the necessary material transport for the hydration of C_3S . A similar process was proposed by Asavapisit *et al.* [64] for clinker particles. Others studies [94] [101] seem to indicate that Zn might be incorporated into the CSH framework.

2.5 Lanthanides

2.5.1 Europium

Tits *et al.* [25] described the adsorption of Eu(III) on CSH. The results showed that the sorption process controlling the retention of Eu is fast indicating that uptake is probably controlled by an adsorption process. Very high sorption distribution ratios in the range of 105 to 106 $\text{dm}^3 \text{kg}^{-1}$ were found.

The sorption mechanisms of Eu on CSH phases of hydrated cement were investigated by Pointeau *et al.* [102]. The CSH phases, to simulate long-term behaviour, were chosen to have a Ca:Si ratio corresponding to aged cements and, at the same time,

equal to the ratio of 0.83 in tobermorite. Eu was not precipitated in solution despite its low solubility limit. It was strongly retained on the CSH (more than 99.8% sorbed). Two main sorption sites were characterised. One site, with a long lifetime (>1 ms), was interpreted as Eu substituting for Ca in the framework of the CSH. Another, with a shorter lifetime (>0.4 ms), was interpreted as a site with a high hydroxylated environment, but one that is less than that of $\text{Eu}(\text{OH})_3$, which corresponded to surface complexation or precipitation at around 10^{-10} mol dm^{-3} . The authors thought it reasonable that Eu might be withdrawn from the liquid phase by a simple precipitation process, due to its low solubility limit, but results showed that this was not the case. It was suggested that the presence of CSH causes a dragging force, which prevents normal precipitation. Tits *et al.* [22] have corroborated this.

Eu LIII-edge EXAFS spectra collected by Schlegel *et al.* [103] on samples of Eu sorbed on, or coprecipitated in, CSH differed from that of $\text{Eu}(\text{OH})_3(\text{s})$ expected to precipitate under the pH conditions of CSH waters, ruling out precipitation of pure hydroxide phases, despite total Eu concentrations well above supersaturating conditions. These results indicated that the sorbed or coprecipitated Eu was located at Ca structural sites in a CSH-like environment. Kinetics and spectroscopic results were consistent with either Eu diffusion within CSH particles, or precipitation of Eu with Ca and Si, creating a CSH-like solid phase.

2.6 Group II Elements

2.6.1 Strontium

The behaviour of Sr in cements might be expected to mirror that of Ca. However, it is more soluble in NaOH or KOH, to the extent that $\text{Sr}(\text{OH})_2$ precipitation in cements is unlikely [104]. OPC is a very efficient scavenger for Sr: Atkins *et al.* found that 95% of ^{89}Sr was associated with the solid phase. The hydration products of C_4AF and C_3A can also completely accommodate low Sr levels. At 25 °C, and in the absence of sulphate, the authors suggested that the major product was probably C_4AH_{13} [104]. CSH gels of Ca:Si ratio 1.7 and $\text{Ca}(\text{OH})_2$, appear to be less efficient sorbers, but higher sorption might be expected at lower Ca:Si ratios. This might be expected for

$\beta\text{C}_2\text{S}$, since it hydrates slowly relative to the other clinker phases, but C_3S hydrates at a similar rate and yet only 34% of the strontium was solid-associated.

Possible substitution of Sr in C_3AH_6 has been studied [104]. Analytical electron microscopy (AEM) showed the mean $\text{SrO}:\text{Al}_2\text{O}_3$ mole ratio was 0.052, equivalent to ca. 1.6% substitution of Sr for Ca. All the Sr in the system had been taken up in the solid phase. Higher levels of substitution are probably achievable in more Sr-rich starting materials, e.g. the phase Sr_4AH_6 has been shown to exist.

The major sink for Sr was probably the calcium aluminium (sulphate) hydrates. Appreciable substitution of strontium in AF_t and C_3AH_6 has been demonstrated, and was thought to be likely by the authors in AF_m -type phases [104]. Therefore, cements high in Ca and Al, such as high alumina cement (HAC), will have the best 'sorption' characteristics for Sr. Leach experiments on Sr loaded pastes, in conjunction with consideration of the effect of carbonation, have indicated coprecipitation of SrCO_3 to be a solubility-limiting process for release. An ettringite analogue with Sr replacing Ca has been reported [105].

2.6.2 Barium

Glasser [52] has suggested that Ba will generally replace Ca in cement hydrate phases.

2.7 Group III Elements

2.7.1 Aluminium

Kalousek has proposed that all Al^{3+} ions present in cement eventually enter CSH [1]. Copeland *et al.* [87] concluded that Al^{3+} enters the CSH by joining with a proton to replace an Si atom or by joining with another Al^{3+} ion to replace 3 Ca^{2+} ions.

3 Summary

The various immobilisation mechanisms identified have been summarised in table 1.

Element	Solid Studied	Mechanism	Reference
Group 1	CSH	Electrostatic Sorption ¹	[3]
Group 1	CSH	Electrostatic Sorption to silanol ¹	[4]
Al	CSH	Substitution for Si	[87]
Am	Concrete	Mineralogical control	[13]
Am	Concrete	Surface area control	[13]
Am	OPC	Via hydroxide species	[19]
As	OPC	Sorption onto CSH	[32]
As	OPC	SO ₄ ²⁻ substitution in ettringite	[32] [30]
As	OPC	Ca-As compound formation	[32] [33]
Ba	CSH	Substitution for Ca	[52]
C (Org)	Mortar	Electrostatic Sorption ¹	[34]
Cd	CSH	Immobilisation within CSH structure	[81]
Cl ⁻	HCP	Formation of CaO-CaCl ₂ -H ₂ O	[44]
Cl ⁻	Concrete	Chemisorbed layer on the surface of CSH	[46]
Cl ⁻	CSH	Chemisorbed on hydrated C ₃ S surface	[47]
Cl ⁻	(Synthetic) CSH	Freidel's salt formation	[37] [38] [39]
Cm ³⁺	CSH	Incorporation in CSH	[21] [22]
CO ₃ ²⁻	HCP	Precipitation ²	[15]
CO ₃ ²⁻	Cement	Adsorption on colloids	[36]
CO ₃ ²⁻	HCP	Electrostatic adsorption onto a positive site ¹	[37]
Cr(III)	Hydrogarnet	Incorporation by hydrogarnet	[53]
Cr(III)	CSH	Si substitution in CSH	[81]
Cr(III)	CSH	Al substitution in Ca Aluminate hydrate	[81]
Cr(VI)	Aluminate	Ion-exchange with OH ⁻	[82] [83] [84]
Cr(VI)	OPC	SO ₄ ²⁻ substitution in ettringite	[30]
Cs	CSH Aluminate		[5]
Cs	CSH	Electrostatic Sorption ¹	[15]
Cs	CSH		[6]
Cs	CSH	Breakage of	[3]

		silicate chain	
Cs	Cement	Inside agglomerated silica particles	[16]
Cu	CCF	Precipitation ³	[56] [57]
Eu	CSH	Adsorption	[25]
Eu	CSH	Surface complexation or precipitation ⁴	[102] [22]
Hg	Ettringite		[88]
I ⁻	Alumina Cement	Replacement of OH ⁻	[50]
I ⁻	CSH	Electrostatic Sorption ¹	[15]
I ⁻	OPC	Electrostatic Sorption ¹	[49]
I ⁻	OPC	Incorporation	[49]
Mo(VI)	HCP	CaMoO ₄ and Mo-substituted AF _m phase	[2]
Na	CSH	Substitution	[17]
Na	CSH	Ion exchange	[18]
Ni	CSH		[15]
Ni	CSH	Coprecipitation or surface complexation	[90]
Ni	HCP	Coprecipitation or surface complexation	[56] [91]
Ni	HCP	Formation of LDH	[92]
Np	OPC	Sorption followed by reduction	[23]
Pb	CSH	Linked to silica tetrahedra in ferrite	[53]
Pb	CSH	Formation of Si-O-Pb bonds	[54] [55]
Pb	CCF	Precipitation ⁵	[56]
Pb	OPC	Precipitation ²	[58] [59]
Pb	CSH	Sorption of Pb(OH) ₃ ⁻	[63] [64]
Pb	CCF	Substitution for Ca	[57]
Pu	Concrete	Preferential on cement paste over aggregates	[13]
SeO ₃ ²⁻	Ettringite	Formation of CaSeO ₃	[68]
SeO ₃ ²⁻	Ettringite	Electrostatic sorption ¹	[68]
SeO ₄ ²⁻	Ettringite	Substitution for SO ₄ ²⁻ in ettringite & monosulphate	[69] [71]
Sn	CSH	Ca stannate formation ² Sorption at lower concentrations	[27]
SO ₄ ²⁻	CSH	Surface sorption	[76]

Sr	C ₃ AH ₆	Substitution for Ca	[104]
U(VI)		Formation of solubility limiting Phases with Ca and Si ⁶	[26]
U(VI)	OPC	Inner sphere interactions	[23]
U(VI)	OPC	Formation of oligomeric surface complexes or precipitates ²	[23]
U(VI)	HCP/CSH	Calcium uranate precipitate ²	[27]
U(VI)	CSH	Sorption	[28]
VO ₃ ⁻	OPC	SO ₄ ²⁻ substitution in ettringite	[30]
Zn	CSH	Linked to Si tetrahedra in CSH	[53] [54] [82]
Zn	CCF	Precipitation ⁷	[56]
Zn	Ferrite	Formation of Fe-O-Zn bonds in ferrite	[94]
Zn	CSH	Precipitation of zincate phases ²	[96]

¹ Electrostatic mechanism implies opposite charge on the sorbate. ²No indication of concentration at which precipitation began. ³[Cu(aq)] after precipitation = 1 ppm. ⁴ Solubility limit $\sim 10^{-10}$ mol dm⁻³ [99]. ⁵[Pb(aq)] after precipitation = 9.4 ppm. ⁶[U(VI)(aq)] after precipitation = $10^{-8} - 10^{-9}$ mol dm⁻³. ⁷[Zn(aq)] after precipitation = 27.5 ppm.

4 Acknowledgements

The author would like to acknowledge the help of Professor Peter Warwick (Loughborough University), Dr David Bennett (TerraSalus Ltd) and Dr Tim Heath (UK NIREX) for their help with this manuscript, and especially Dr Les Knight (UK NIREX) who supplied the idea and the funding.

5 References

- [1] O.E. Omotoso, G. Ivey, R. Mikula, Containment mechanism of trivalent chromium in tricalcium silicate, *J Hazard Mater* 60 (1998) 1-28.
- [2] F.P. Glasser, Characterisation of the barrier performance of cements, *Mat Res Soc Symp Proc*, 713 (2002) 721-732.

- [3] T. Iwaida, S. Nagasaki, S. Tanaka, T. Yaita, Sorption of alkali metal ions onto C-S-H (calcium silicate hydrated phases), *Cem Sci Concr Tech* 55 (2001) 21-26.
- [4] S-Y. Hong, F.P. Glasser, Alkali sorption by C-S-H and C-A-S-H gels. Part II. Role of alumina, *Cem Concr Res* 32 (2002) 1101-1111.
- [5] S. Bagosi, L.J. Csetenyil, Cesium-71 immobilization in hydrated calcium-silicate-aluminate systems, *Cem Concr Res* 28 (1988) 1753-1759.
- [6] S. Aggarwal, M.J. Angus, J. Ketchen, Sorption of Radionuclides onto Specific Mineral Phases Present in Repository Cements, Report AEA Technology NSS/R312 (2000) 1-64.
- [7] J.V. Hanna, L.P. Aldridge, E.R. Vance, Cs Speciation in Cements, *Mat Res Soc Symp Proc* 663 (2001) 89-101.
- [8] A. Atkinson, A.K. Nickerson, The diffusion of ions through water-saturated cement, *J Mat Sci* 19 (1984) 3068-3078.
- [9] L.P. Aldridge, R.A. Day, S. Leung, A.S. Ray, M.G. Stevens, R.S. Knight, C.F. Mapson, Cs retention in zeolites immobilized by Portland cement, in: K.L. Scrivener (Ed.), *Mechanisms of Chemical Degradation of Cement-Based Systems*, E&FN Spon, London 1997, 358-365.
- [10] M.I. Plodinec, Evaluation of ^{137}Cs sorbents for fixation in concrete, Report DP-I444, EJ. Du Pont de Nemours and Co., Savannah River Laboratory USA, (1977) 1-25.
- [11] A. Atkinson, A.K. Nickerson A.K., Diffusion and Sorption of Cesium, Strontium and Iodine in Water-Saturated Cement, *Nucl Tech* 81 (1998) 100-113.

- [12] M.W. Barnes, B.E. Scheetz, D.M. Roy, The effect of chemically adjusting cement compositions on leachabilities of waste ions, *Adv Cer, Nucl Waste Manage* 20 (2), (1986) 313-317.
- [13] A.T. Jakubick, R.W. Gillham, I. Kahl, M. Robin, Attenuation of Pu, Am, Cs, and Sr mobility in concrete, *Mat Res Soc Symp Proc.* 84 (1987) 355-368.
- [14] S.L. Hoyle, M.W. Grutzeck, Incorporation of caesium by hydrating calcium aluminosilicates. *J Am Cer Soc*, 72 (10) (1989) 1938-47.
- [15] K. Noshita, T. Nishi, T. Yoshida, H. Fujihara, N. Saito, S. Tanaka, Categorization of Cement Hydrates by Radionuclide Sorption Mechanism *Mat Res Soc Symp Proc* 663 (2001) 115-121.
- [16] S.A. Stronach, F.P. Glasser, Modelling the impact of abundant geochemical components on phase stability and solubility of the CaO-SiO₂-H₂O system at 25°C: Na⁺, K⁺, SO₄²⁻, Cl⁻ and CO₃²⁻, *Adv Cem Res* 9 (1997) 167-181.
- [17] G. BarNes, A. Katz, Y. Bentur, Y. Peled, Y. Zeiri, *Proc Work Mech Model Waste/Cem Interact*, Meiringen, Switzerland, (2005) 13.
- [18] A.V. Chambers, T.G. Heath, F.M.I. Hunter, M.C. Manning, S.J. Williams, The Effect of Sodium Chloride on the Dissolution of Calcium Silicate Hydrate Gels, *Nirex Report, SA/ENN – 0623* (2005) 1-63.
- [19] G.M.N. Baston, J.A. Berry, M. Brownsword, T.G. Heath, C. Tweed, S.J. Williams, Sorption of Plutonium and Americium on repository, backfill and geological materials relevant to the JNFL Low-Level Radioactive Waste Repository at Rokkasho-Mura, *Mat Res Soc Symp Proc*, 353 (1995) 957-964.
- [20] K. Noshita, T. Nishi, M. Matsuda, Improved Sorption Ability for radionuclides by Cementitious Materials, *WM'98 Proc*, Tucson, AZ, USA, (1998) 1880-1886.

- [21] T. Stumpf, J. Tits, C. Walther, E. Wieland, T. Fanghänel, Uptake of trivalent actinides (curium (III)) by hardened cement paste: a time-resolved laser fluorescence spectroscopy study, *J Coll Inter Sci* 276 (2004) 118-124.
- [22] J. Tits, T. Stumpf, T. Rabung, E. Wieland, T. Fanghänel, Uptake of Cm(III) and Eu(III) by Calcium Silicate Hydrates: A Solution Chemistry and Time-Resolved Laser Fluorescence Spectroscopy Study, *Environ Sci Technol*, 37 (2003) 3568-3573.
- [23] E.R. Sylwester, P.G. Allen, P. Zhao, B.E. Viani, Interactions of uranium and neptunium with cementitious materials studied by XAFS. *Mat Res Soc Symp Proc* 608 (2000) 307-312.
- [24] S.L. Matzen, J.M. Beiriger, P.C. Torretto, P. Zhao, B.E. Viani, Uranium(VI) and neptunium(V) transport through fractured, hydrothermally altered concrete, *Radiochim Acta*, 88 (2000) 657-664.
- [25] J. Tits, E. Wieland, M.H. Bradbury, J.P. Dobler, The uptake of Eu(III) and Th(IV) by cement-type minerals in the alkaline disturbed zone of a nuclear waste repository. *Proc 6th Int Cong Appl Mineralogy*, Göttingen, Germany, 2 (2000) 691-694.
- [26] L.P. Moroni, F.P. Glasser, Reactions between cement components and U(VI) oxide *Waste Manage*, 15 (3) (1995) 243-254.
- [27] E. Wieland, I. Bonhoure, T. Fujita, J. Tits, A.M. Scheidegger, Combined wet chemistry and EXAFS studies on the radionuclide immobilisation by cement and calcium silicate hydrates, *Geochim Cosmochim Acta Supp* 67 (18) (2002) 532
- [28] I. Pointeau, C. Landesman, E. Giffaut, P. Reiller, Reproducibility of the uptake of U(VI) onto degraded cement pastes and calcium silicate hydrate phases, *Radiochim Acta*, 92 (9-11) (2004) 645-650.

- [29] M. Harfouche, E. Wieland, R. Daehn, T. Fujita, J. Tits, D. Kunz, M. Tsukamoto, EXAFS study of U(VI) uptake by calcium silicate hydrates. *J Coll Inter Sci* 303 (1) (2006) 195-204.
- [30] P. Kumarathasan, G.J. McCarthy, D.J. Hassett, D.F. Pflughoeft-Hassett, Oxyanion substituted ettringites: synthesis and characterization; and their role in immobilization of As, B, Cr, Se and V, *Mat Res Soc Symp Proc*, 178 (1990) 83-104.
- [31] S.C.B. Myneni, S.J. Traina, T.J. Logan, G.A. Waychunas, Sorption and Desorption of Arsenate in Ettringite, *Environ Sci Technol* 31 (1997) 1761-1768.
- [32] T. Phenrat, T.F. Marhaba, M. Rachakornkij, A SEM and X-ray study for investigation of solidified/stabilized arsenic-iron hydroxide sludge, *J Hazard Mat*, 118 (2005) 185-195.
- [33] S.A. Stronach, N.L. Walker, D.E. Macphee, F.P. Glasser, Reactions between cement and As(III) oxide: The system CaO-SiO₂-As₂O₃-H₂O at 25°C, *Waste Manage* 17 (1997) 9-13.
- [34] J. Matsumoto, T. Banba, Sorption behaviour of organic carbon-14 onto cementitious materials, 7th Int Conf Proc Rad Waste Manage Environ Remed, Nagoya, Japan, (1999) CD-ROM.
- [35] K. Noshita, T. Nishi, M. Matsuda, T. Izumida, Sorption mechanism of carbon-14 by hardened cement paste, *Mat Res Soc Symp Proc* 412 (1996) 435-42.
- [36] T. Banba, J. Matsumoto, S. Muraoka, Adsorption of carbon-14 on Mortar, *Mat Res Soc Symp Proc*, 353 (1994) 1029-1035.

- [37] P. Brown, J. Bothe Jr., The system CaO-Al₂O₃-CaCl₂-H₂O at 23±2 °C and the mechanisms of chloride binding in concrete, *Cem Concr Res* 34 (2004) 1549-1553.
- [38] D. Damidot, U.A. Birnin-Yauri, F.P. Glasser, Thermodynamic investigation of the CaO-Al₂O₃-CaCl₂-H₂O system at 25 °C and the influence of Na₂O, II, *Cemento* 4 (1994) 243-254.
- [39] J.J. Beaudoin, V.S. Ramachandran, R.F. Feldman, Interaction of chloride and C-S-H, *Cem Concr Res*, 20 (1990) 875-883.
- [40] L. Tang, L.O. Nilsson, Chloride binding capacity and binding isotherms of OPC pastes and mortars, *Cem Concr Res*, 23 (1993) 247-253.
- [41] O. Wowra, M.J. Setzer, Sorption of chlorides by hardened cement paste hydrated in jars and by CSH phases, 13th Int Conf Build Mat, Weimar, 1 (1997) 29-37.
- [42] O. Wowra, M.J. Setzer, Sorption of chlorides on hydrated cements and C3S pastes, *RILEM Proc*, 34 (1997) 146-153.
- [43] O. Wowra, M.J. Setzer, About the Interaction of Chloride and Hardened Cement Paste, 3rd Work Bauchemie-Tagung, München, (1997) 3-12.
- [44] O. Wowra, M.J. Setzer, About the Interaction of Chloride and Hardened Cement Paste in the Frost resistance of Concrete, *RILEM Proc*, 34 (1997) 157-173.
- [45] A. Delagrave, J. Marchand, J.-P. Ollivier, S. Julien, K. Hazrati, Chloride binding capacity of various hydrated cement paste systems. *Advn Cem Bas Mat*, 6 (1997) 28-35.
- [46] V.M. Malhotra, V.S. Ramachandran, R.F. Feldman, P.C. Aitcin, Condensed Silica Plume in Concrete, *CRC Press*, (1987) 179–184.

- [47] J.J. Beaudoin, V.S. Ramachandran, R.F. Feldman, Interaction of chloride and C-S-H., *Cem Concr Res*, 20 (6) (1990) 875-883.
- [48] P. Yu, R.J. Kirkpatrick, ³⁵Cl NMR relaxation study of cement hydrate suspensions, *Cem Conc Res* 31 (10) (2001) 1479-1485.
- [49] F.P. Glasser, Immobilization of Radwaste in Cement Based Matrices. DoE/RW/89.133, Aberdeen University, Scotland, 1989
- [50] M. Toyohara, M. Kaneko, H. Ueda, N. Mitsutsuka, H. Fujihara, T. Murase, N. Saito, Iodine sorption onto mixed solid alumina cement and calcium compounds. *J Nucl Sci Tech* 37 (11) (2000) 970-978.
- [51] M. Toyohara, M. Kaneko, H. Ueda, N. Mitsutsuka, H. Fujihara, N. Saito, T. Murase, Contribution to understanding iodine sorption mechanism onto mixed solid alumina cement and calcium compounds, *J Nucl Sci Tech* 39 (9) (2002) 950-956.
- [52] F.P. Glasser, Chemistry of Cement-Solidified Waste Forms, in *Chemistry and Microstructure of Solidified Waste Forms* Ed. Spence R.D., Lewis Publishers, Boca Raton, USA, 1993 1-40.
- [53] I. Moulin, J. Rosea, W. Stone, J.-Y. Bottero, F. Mosnier, C. Haehnel, Lead, zinc and chromium (III) and (VI) speciation in hydrated cement phases, in: G.R. Woolley, J.J.J.M., Goumans, P.J. Wainwright (Eds.), *Waste Materials in Construction*, Elsevier, (2000) 269-280.
- [54] I. Moulin, W.E.E. Stone, J. Sanz, J.-Y. Bottero, F. Mosnier, C. Haehnel, Lead and zinc retention during hydration of tri-calcium silicate: A study by sorption isotherms and ²⁹Si NMR spectroscopy, *Langmuir* 15 (1999) 2829-2835.
- [55] J. Rose, I. Moulin, J.-L. Hazemann, A. Masion, P.M. Bertsch, J.-Y. Bottero, F. Mosnier, C. Haehnel, X-ray absorption spectroscopy study of immobilization

processes for heavy metals in calcium silicate hydrates: 1. Case of Lead, Langmuir 16 (2000) 9900-9906.

- [56] D.C. Johnson, N.J. Coleman, J. Lane, C.D. Hills, A.B. Poole, A preliminary investigation of the removal of heavy metal species from aqueous media using crushed concrete fines, in: G.R. Woolley, J.J.J.M., Goumans, P.J. Wainwright (Eds.), Waste Materials in Construction, Elsevier, (2000) 1044-1049.
- [57] N.J. Coleman, W.E. Lee, I.J. Slipper, Interactions of aqueous Cu^{2+} , Zn^{2+} and Pb^{2+} ions with crushed concrete fines, J Hazard Mat B121 (1-3), 2005, 203-213.
- [58] N.L. Thomas, D.A. Jameson, D.D. Double, The effect of lead nitrate on the early hydration of Portland cement, Cem Concr Res 11 (1981) 143-153.
- [59] F.K. Cartledge, L.G. Butler, D. Chalasani, H.C. Eaton, F.P. Frey, E. Herrera, M.E. Tittlebaum, S.L. Yang, Immobilization mechanisms in solidification/stabilization of cadmium and lead salts using Portland cement fixing agents, Environ Sci Technol 24 (1990) 867-873.
- [60] D.L. Cocke J.D. Ortego, H. McWhinney, K. Lee, S. Shukla, A model for lead retardation of cement setting, Cem Concr Res 19 (1) (1989) 156-159.
- [61] D.L. Cocke, The binding chemistry and leaching mechanisms of hazardous substances in cementitious solidification/stabilization systems, J Hazard Mat 24 (1990) 231-253.
- [62] D.L. Cocke, H.G. McWhinney, G. Hylton, D.C. Dufner, B. Horrell, J.D. Ortego, An XPS and EDS investigation of Portland cement doped with lead(2+) and chromium(3+) cations. Hazard Waste Hazard Mat 6 (3) (1989) 251-257.

- [63] M. Yousuf, A. Mollah, R.K. Vempati, T-C. Lin, D.L. Cocke, The interfacial chemistry of solidification/stabilization of metals in cement and pozzolanic material systems. *Waste Manage* 15 (2) (1995) 137-148.
- [64] S. Asavapisit, G. Fowler, C.R. Cheeseman, Solution chemistry during cement hydration in the presence of metal hydroxide wastes, *Cem. Concr. Res.* 27 (8) (1997) 1249–1260.
- [65] J.D. Ortego, S. Jackson, G.S. Yu, H. McWhinney, D.L. Cocke, Solidification of hazardous substances - a TGA and FTIR study of portland cement containing metal nitrates. *J Environ Sci Health A Environ Sci Eng*, A24 (6) (1989) 589-602.
- [66] C.H. Mattus, A.J. Mattus, Literature review of the interaction of select inorganic species on the set and properties of cement and methods of abatement through waste pre-treatment, in: *Stabilization and Solidification of Hazardous, Radioactive and Mixed Wastes*, T.M. Gilliam, C.C. Wiles C.C., (Eds.), ASTM: Philadelphia, USA, 1996, pp. 609-633.
- [67] J.I. Bhatta, P.B. West, Stabilization of heavy metals in portland cement matrix: Effects on paste properties, in: *Stabilization and Solidification of Hazardous, Radioactive and Mixed Wastes*, T.M. Gilliam, C.C. Wiles (Eds.), ASTM, Philadelphia, USA, 1996, Vol. III, 147-162.
- [68] I. Baur, C.A. Johnson, Sorption of Selenite and Selenate to Cement Minerals. *Environ Sci Technol* 37 (2003) 3442-3447
- [69] P. Kumarathan, G.J. McCarthy, D.J. Hassett, D.F. Pflughoeft-Hasset, Oxyanion substituted ettringites: synthesis and characterization; and their potential role in immobilization of arsenic, boron, chromium, selenium and vanadium. *Mat Res Soc Symp Proc*, 178 (1990) 83-104.
- [70] C.D. Palmer, Precipitates in a Cr(VI)-Contaminated Concrete, *Environ Sci Technol*, 34 (2000) 4185-4192.

- [71] M. Zhang, Incorporation of oxyanionic B, Cr, Mo, and Se into hydrocalumite and ettringite : application to cementitious systems, Ph.D. Thesis, University of Waterloo, Canada, 1995 pp1-172.
- [72] J.K. Solem-Tishmack, G.J. McCarthy, B. Docktor, K.E. Eylands, J.S. Thompson, D.J. Hassett, High-calcium coal combustion byproducts: engineering properties, ettringite formation, and potential application in solidification and stabilization of selenium and boron, *Cem Concr Res* 25 (1995) 658-670.
- [73] I. Bonhoure, I. Baur, E. Wieland, C.A. Johnson, A.M. Scheidegger, Uptake of Se(IV/VI) oxyanions by hardened cement paste and cement minerals: An X-ray absorption spectroscopy study, *Cem Conc Res* 36 (1) (2006) 91-98.
- [74] W. Lerch, F.W. Ashton, R-H. Bogue, The sulfoaluminates. of calcium, *J Nat Bureau Stand*, 2 (4) (1929) 715-731.
- [75] W. Lerch, The influence of gypsum on the hydration and properties of Portland cement pastes, *Res Lab Portland Cem Ass Bull* RX012 (1946) 1-41.
- [76] L. Nachbaur, Etude de l'influence d'electrolytes sur l'hydratation et la prise du silicate tricalcique, composant principal du ciment Portland. Caracterisation des interactions a l'origine de la prise, Ph.D. Thesis, Université de Bourgogne, Dijon, France (1997) pp. 1-141.
- [77] L. Divet, R. Randriambololona, Delayed ettringite formation: the effect of temperature and basicity on the interaction of sulfate and C-S-H phase, *Cem Concr Res* 28 (3) (1998) 357-363.
- [78] F. Séby, M. Potin-Gautier, E. Giffault, O.F.X. Donard, A critical review of thermodynamic data for inorganic tin species, *Geochim Cosmochim Acta* 65 (2001) 3041-3053.

- [79] I. Bonhoure, E. Wieland, A.M. Scheidegger, M. Ochs, D. Kunz, EXAFS Study of Sn(IV) Immobilization by Hardened Cement Paste and Calcium Silicate Hydrates, *Environ Sci Technol* 37 (10) (2003) 2184-2191.
- [80] D. Bonen, S.L. Sarkar, Environmental attack on concrete, *Proc 16th Eng Found Conf, Am Soc Civil Eng New York* (1994) 11-23.
- [81] A. Poletini, R. Pomi, P. Sirini, Fractional Factorial Design To Investigate the Influence of Heavy Metals and Anions on Acid Neutralization Behavior of Cement-Based Products, *Environ Sci Technol* 36 (2002) 1584-1591.
- [82] I. Moulin, Spéciation du plomb, du cuivre, du zinc, du chrome (III) et (VI) dans les hydrates de ciment, Ph.D. Thesis, Université d'Aix-Marseille III, (1998) pp 1-250
- [83] D. Savage, The geochemical behavior of nickel in the repository environment, *Mat Res Soc Symp Proc* 353 (1995) 1159-1166.
- [84] T. Heath, D.J. Ilett, C.J. Tweed, Thermodynamic modeling of the sorption of radioelements onto cementitious materials, *Mat Res Soc Symp Proc* 412 (1996) 443-449.
- [85] E. Wieland, L.R. Van Loon, Cementitious Near-Field Sorption Data Base for Performance Assessment of an ILW Repository in Opalinus Clay, *PSI Bericht* 03-06 14 (2003) 1-74.
- [86] M. Vespa, R Daehn, D Grolimund, E. Wieland, A.M. Scheidegger, Co Speciation in Hardened Cement Paste: A Macro- and Micro-Spectroscopic Investigation, *Environ Sci Tech* 41 (6) (2007) 1902-1908.
- [87] L.E. Copeland, E. Bodor, T.N. Chang, C.H. Weise, Reactions of tobermorite gel with aluminates, ferrites, and sulfates. *J PCA Res Dev Lab*, 9 (1) (1967) 61-74

- [88] C.S. Poon, A.I. Clark, C.J. Peters, R. Perry, Mechanisms of metal fixation and leaching by cement based fixation processes, *Waste Manage Res* 3 (1985) 127-142.
- [89] R. Hietanen, E.-L. Kämäräinen, M. Aluusua, Sorption of Caesium, Strontium, Iodine, Nickel and Carbon in Concrete, Nuclear Waste Commission of Finnish Power Companies, Report YJT 84-04, Helsinki, Finland, (1984) pp.1-25
- [90] M. Ochs, D. Hager, S. Helfer, B. Lothenbach, Solubility of radionuclides in fresh and leached cementitious systems at 22 and 50° C, *Mat Res Soc Symp Proc* 506 (1998) 773-780.
- [91] N. Pilkington, N. Stone, The solubility and sorption of nickel and niobium under high pH conditions, UK Nirex Ltd Report NSS/R186 (1990)
- [92] A.M. Scheidegger, E. Wieland, A. Scheinost, R. Dähn, P. Spieler, Spectroscopic evidence for the formation of layered Ni-Al double hydroxides in cement. *Environ Sci Technol* 34 (2000) 4545-4548.
- [93] C.A. Johnson, F. Glasser, Hydrotalcite-like minerals ($M_2Al(OH)_6(CO_3)0.5H_2O$, where M = Mg, Zn, Co, Ni) in the environment: Synthesis, characterization, and thermodynamic stability, *Clays Clay Min* 51 (1) (2003) 1-8.
- [94] C. Ludwig, F. Ziegler, C.A. Johnson, Heavy metal binding mechanisms in cement-based waste materials, *Stud Environ Sci (Waste Mat Const)* 71 (1997) 459-468.
- [95] M. Vespa, R Daehn, E. Wieland, D Grolimund, A.M. Scheidegger, The influence of hydration time on the Ni uptake by cement, *J Phys* 56D (2006) d599-d607.

- [96] F. Ziegler, R. Giere, C.A. Johnson, Sorption Mechanisms of Zinc to Calcium Silicate Hydrate: Sorption and Microscopic Investigations, *Environ Sci Technol* 35 (2001) 4556-4561.
- [97] F. Ziegler, R.E.M. Scheidegger, C.A. Johnson, R. Daehn, E. Wieland, Sorption Mechanisms of Zinc to Calcium Silicate Hydrate: X-ray Absorption Fine Structure (XAFS) Investigation, *Environ Sci Technol* 35 (2001) 1550-1555.
- [98] G. Arliguie, J. Grandet, Effect of the composition of portland cement on its hydration in the presence of zinc, *Cem Concr Res* 20 (1990) 517-524.
- [99] M. Gawlicki, D.J. Czamarska, Effect of zinc on the hydration of portland cement, *Thermal Anal* 38 (1992) 2157-2161.
- [100] M. Yousuf, A. Mollah, J.R. Parga, D.L. Cocke, An infrared spectroscopic examination of cement-based solidification/stabilization systems - Portland types V and IP with zinc, *J Environ. Sci. Health*, A27 (6) (1992) 1503-1519
- [101] H. Uchikawa, S. Hanehara, H. Hirao, Influence of structural and humidity changes at the inner part of hardened cement paste on autogenous shrinkage, *Am Conc Inst*, SP 2 (1997) 949-964.
- [102] I. Pointeau, B. Piriou, M. Fedoroff, M.-G. Barthes, N. Marmier, F.J. Fromage, Sorption mechanisms of Eu^{3+} on CSH phases of hydrated cements, *J Coll Inter Sci* 236 (2001) 252-259.
- [103] M. Schlegel, I. Pointeau, N. Coreau, P. Reiller, Mechanism of Europium Retention by Calcium Silicate Hydrates: An EXAFS Study, *Environ Sci Technol* 38 (2004) 4423-4431.
- [104] M. Atkins, F.P. Glasser, Application of Portland cement-based materials to radioactive waste immobilization, *Waste Manage* 12 (1992) 105-131

[105] J. Bensted, S.P. Varma, Ettringite and its derivatives, *Cem Technol* 2 (1971) 73-76.