

Composite pairing in a mixed valent two channel Anderson model

Rebecca Flint^{1,3}, Andriy H. Nevidomskyy^{2,3} and Piers Coleman³

¹*Department of Physics, Massachusetts Institute of Technology, Cambridge MA 02139, USA*

²*Department of Physics and Astronomy, Rice University, Houston, TX 77005, USA and*

³*Center for Materials Theory, Rutgers University, Piscataway, NJ 08854, USA*

Using a two-channel Anderson model, we develop a theory of composite pairing in the 115 family of heavy fermion superconductors that incorporates the effects of f -electron valence fluctuations. Our calculations introduce “symplectic Hubbard operators”: an extension of the slave boson Hubbard operators that preserves both spin rotation and time-reversal symmetry in a large N expansion, permitting a unified treatment of anisotropic singlet pairing and valence fluctuations. We find that the development of composite pairing in the presence of valence fluctuations manifests itself as a phase-coherent mixing of the empty and doubly occupied configurations of the mixed valent ion. This effect redistributes the f -electron charge within the unit cell. Our theory predicts a sharp superconducting shift in the nuclear quadrupole resonance frequency associated with this redistribution. We calculate the magnitude and sign of the predicted shift expected in CeCoIn₅.

I. INTRODUCTION

The 115 family of superconductors continue to attract attention for the remarkable rise in the superconducting transition temperature from 0.2 K in the parent compound CeIn₃[1] to 2.3 K in CeCoIn₅[2] and finally to 4.9 K and 18.5 K in the actinide analogues, NpPd₅Al₂[3] and PuCoGa₅[4], respectively. This last rise has often been attributed to the increasing importance of valence fluctuations, and here we seek to make this connection explicit. Although the Ce 115s are local moment systems, neutron studies of crystal fields indicate broad quasi-elastic line-widths comparable to the crystal field splitting, indicating valence fluctuations⁵. The highest T_c 115s, the actinides, involve 5 f shell electrons, which are less localized than their 4 f Ce counterparts, and thus are expected to be even more mixed valent. Recent ²³⁷Np Mössbauer studies of NpAl₂Pd₅ suggest that the valence of the Np ions actually changes as superconductivity develops⁶. However, despite different degrees of mixed valency, both CeCoIn₅ and NpPd₅Al₂ contain the same unusual transition from local moment paramagnetism directly into the superconducting state, shown in Figure 1.

This direct transition suggests that the localized moments play a direct role in the pairing, which previously led us to propose that the 115 materials are *composite pair superconductors*^{7,8}. Composite pair superconductivity is a local phenomenon involving the condensation of bound states between local moments and conduction electrons⁹: it can be thought of as an *intra-atomic* version of a d-wave magnetic pairing, between conduction electrons in orthogonal screening channels rather than on neighboring sites,

$$\Delta_{SC}(j) = \langle \psi_{1j}^\dagger \vec{\sigma}(i\sigma_2) \psi_{2j}^\dagger \cdot \vec{S}_{fj} \rangle. \quad (1)$$

Here $\psi_{1,2j}^\dagger$ create local Wannier states of conduction electrons in two orthogonal symmetry channels at site j , and \vec{S}_{fj} is the local f -moment on the same site. The composite pair combines a triplet pair of conduction electrons




FIG. 1. Local moments are seen in the Curie-Weiss susceptibilities: CeCoIn₅ ($T_c = 2.3K$)¹¹ and NpPd₅Al₂ ($T_c = 4.9K$)³ are reproduced and rescaled by $\chi(T_c)$ to show their similarity (data below T_c not shown).

with a spin-flip of the local moment, such that the overall pair remains a singlet.

While the close vicinity of the Ce 115s to antiferromagnetic order has led to a consensus that pairing in these materials is driven by spin fluctuations, the two superconducting domes in the Ce(Co,Rh,Ir)In₅ phase diagram¹⁰ suggest that composite pairing may provide a second, complementary mechanism in the Ce 115s⁸. The absence of magnetism in the actinide 115 phase diagrams suggests that composite pairing may play a more important role. Composite pairs are predicted to have unique electrostatic signature, resulting in a small redistribution of the f -electron charge within the unit cell and an associated change of the f -valence. Understanding these charge aspects of composite pairing is essential to disentangling the relative importance of magnetic and composite pairing in these compounds.

These observations motivate us to develop a theory of composite pairing incorporating valence fluctuations. Thus far, composite pairing has been studied within a two-channel Kondo model^{7,12}, treating only the local spin degrees of freedom. In this paper, we study composite pairing within a two-channel Anderson model, which

permits us to include the charge degrees of freedom and model the effects of valence fluctuations on the superconductivity in the $5f$ 115 materials. We predict a sharp shift in both the f -electron valence and quadrupole moment at the superconducting transition temperature. The quadrupole moment shift should manifest as a shift either in the nuclear quadrupole resonance (NQR) frequency, for CeMIn_5 or the Mössbauer quadrupole splitting, for NpPd_5Al_2 , and we make concrete predictions for these shifts in Section V.

The two-channel Anderson model is the natural extension of the two-channel Kondo model.

$$H = H_c + \sum_j H_a(j) + \sum_j H_V(j). \quad (2)$$

Here the local atomic Hamiltonian at site j is,

$$H_a(j) = E_0 X_{00}(j) + E_2 X_{22}(j) + \sum_{\sigma} \epsilon_f X_{\sigma\sigma}(j), \quad (3)$$

where the X 's are the Hubbard operators¹³: $X_{00} = |0\rangle\langle 0|$, $X_{22} = |2\rangle\langle 2|$, and $X_{\sigma\sigma} = |\sigma\rangle\langle\sigma|$. The atomic states $|0\rangle$, $|\sigma\rangle$ and $|2\rangle$ are shown in Figure 2, where we take the doubly occupied state to be a singlet containing f -electrons in two orthogonal channels,

$$|2\rangle \equiv |\Gamma_2 \otimes \Gamma_1\rangle_s = \frac{1}{\sqrt{2}} \sum_{\sigma=\pm 1} \text{sgn}(\sigma) f_{\Gamma_2\sigma}^{\dagger} f_{\Gamma_1-\sigma}^{\dagger} |0\rangle. \quad (4)$$

The orthogonality of these two channels is essential to the superconductivity, and we take the Coulomb energy for two electrons in the same channel to be infinite, making this model closer to two copies of the infinite- U Anderson model than to the finite- U model¹⁴. These f -electrons hybridize with a bath of conduction electrons, $H_c = \sum_{\mathbf{k},\sigma} \epsilon_{\mathbf{k}} c_{\mathbf{k}\sigma}^{\dagger} c_{\mathbf{k}\sigma}$ in two different channels

$$H_V(j) = \sum_j V_1 \psi_{1j\sigma}^{\dagger} X_{0\sigma}(j) + \text{h.c.} + V_2 \psi_{2j\sigma}^{\dagger} \tilde{\sigma} X_{-\sigma 2}(j) + \text{h.c.}, \quad (5)$$

where the $\psi_{\Gamma j\sigma}$ are Wannier states representing a conduction electron in symmetry Γ on site j . $X_{0\sigma} = |0\rangle\langle\sigma|$ and $X_{2\sigma} = |2\rangle\langle\sigma|$ are the Hubbard operators between the singly occupied state and empty or doubly occupied states, respectively (see Fig. 3). Here we have adopted the notation of Ce atoms, whose ground state is a $4f^1$ doublet, but this formalism also applies to Np $5f^3$ atoms, where both $|0\rangle \equiv |5f^4\rangle$ and $|2\rangle \equiv |5f^2\rangle$ are $J = 4$ crystal field singlets, while $|\sigma\rangle$ represents one of the $J = 9/2$ crystal field doublets of $5f^3$.

To develop a controlled treatment of superconductivity in the two-channel Anderson model, we introduce a large- N expansion. Preserving the time-reversal symmetries of spins is essential to capture singlet superconductivity in the entire family of large N models, and large N methods based on $SU(N)$ spins, like the usual slave boson approach, will lose time-reversal symmetry for any $N > 2$. Treating superconductivity in the Kondo model




FIG. 2. Virtual charge fluctuations of a two channel Anderson impurity, where the addition and removal of an f -electron occur in channels Γ_1 and Γ_2 of different crystal field symmetry. The ground state is a Kramer's doublet, while the excited states $|0\rangle$, $|2\rangle$ are singlets. The excited doublet $|\Gamma_2 : \alpha\rangle$ represents a higher lying crystal-field level and is excluded from the Hilbert space of the problem. The relevant charge states of Ce^{3+} ($4f^1$), Np^{4+} ($5f^3$) and Pu^{3+} ($5f^5$) are indicated.

therefore requires symplectic spins, the generators of the $SP(N)$ group⁷,

$$S_{\alpha\beta} = f_{\alpha}^{\dagger} f_{\beta} - \tilde{\alpha} \tilde{\beta} f_{-\beta}^{\dagger} f_{-\alpha}. \quad (6)$$

Here N is an even integer and the indices

$$\alpha \in \{\pm 1, \pm 2, \dots, \pm N/2\} \quad (7)$$

are integers running from $-N/2$ to $N/2$, excluding zero. We employ the notation $\tilde{\alpha} \equiv \text{sgn}(\alpha)$. These spin operators invert under time-reversal $\mathbf{S} \rightarrow \theta \mathbf{S} \theta^{-1} = -\mathbf{S}$ and generate rotations that commute with the time-reversal operator⁷.

Physically, the spin fluctuations of a local moment are generated by valence fluctuations. Theoretically, these valence fluctuations can be described by Hubbard operators, and in a symplectic- N generalization of the Anderson model, anticommuting two such Hubbard operators must generate a symplectic spin, satisfying the relations:

$$\begin{aligned} \{X_{0\alpha}, X_{\beta 0}\} &= X_{\alpha\beta} + X_{00} \delta_{\alpha\beta} \\ &= S_{\alpha\beta} + \left(X_{00} + \frac{X_{\gamma\gamma}}{N} \right) \delta_{\alpha,\beta}, \end{aligned} \quad (8)$$

where the last equality follows from the traceless definition of the symplectic spin operator, $S_{\alpha\beta} = X_{\alpha\beta} - \frac{X_{\gamma\gamma}}{N} \delta_{\alpha\beta}$. In Section II, we show that a proper symplectic representation requires the introduction of *two* slave bosons to treat the Hubbard operators in a single channel:

$$\begin{aligned} X_{0\alpha} &= b^{\dagger} f_{\alpha} + a^{\dagger} \tilde{\alpha} f_{-\alpha}^{\dagger} \\ X_{00} &= b^{\dagger} b + a^{\dagger} a. \end{aligned} \quad (9)$$

As we shall demonstrate, these symplectic Hubbard operators maintain the invariance of the Anderson Hamiltonian with respect to the $SU(2)$ particle-hole transformation, $f_\sigma \rightarrow \cos \theta f_\sigma + \text{sign}(\sigma) \sin \theta f_{-\sigma}^\dagger$ ¹⁵. This extension of the slave boson representation with local $SU(2)$ gauge symmetry was originally introduced by Wen and Lee as a mean-field treatment of the $t-J$ model¹⁶. Here we show that these Hubbard operators maintain the $SU(2)$ gauge symmetry for arbitrary $SP(N)$ versions of the infinite U Anderson and $t-J$ models. This $SU(2)$ gauge symmetry is essential for eliminating the false appearance of s-wave superconductivity in the finite- U Anderson model, where the two channels are identical.

What do we learn from this Anderson model picture of composite pairing? A key result is that the amount of composite pairing can be written in a simple gauge-invariant form as

$$\Delta_{\text{SC}} = \langle X_{02} \rangle \propto \langle \psi_1^\dagger \vec{\sigma} (i\sigma_2) \psi_2^\dagger \cdot \vec{S}_f \rangle, \quad (10)$$

where the Hubbard operator $X_{02} = |0\rangle\langle 2|$ mixes the empty and doubly occupied states. This mixing resembles an intra-atomic version of the negative- U pairing state, but double occupancy costs a large, positive energy. The physical consequence of this mixing is a redistribution of the charge in the f -electron orbitals, as the three charge states: empty, singly and doubly occupied, all have different charge distributions. Such a rearrangement not only changes the total charge in the f -shell, a monopole effect, but also will result in a quadrupole moment associated with the superconductivity. This quadrupole moment will lead to modified electric field gradients that should be detectable as a sharp shift in the nuclear quadrupolar resonance (NQR) frequency at the neighboring nuclei, or as a sharp shift in the Mössbauer quadrupolar splitting at the f -electron nuclei.

This paper is organized as follows. First we introduce the symplectic Hubbard operators in section II and demonstrate that the symplectic- N and $SU(N)$ large- N limits are identical for a single channel. We then generalize this formalism to the case of two channels in Section III and show how composite pairing naturally appears as a mixing of the empty and doubly occupied states. The mean-field solution is presented in Section IV, in which we demonstrate how the superconducting transition temperature increases with increasing mixed valence. In Section V, we calculate the charge distribution of the f -orbitals in the state with composite pairing and make a concrete prediction for a shift in the NQR frequency at T_c in CeCoIn₅. Finally, section VI discusses the implications for the finite- U Anderson model and examines the broader implications of our results.

II. SYMPLECTIC HUBBARD OPERATORS

Composite pairing was originally discussed in the two channel Kondo model¹², where it is found in the symplectic- N limit⁷, which maintains the time-inversion

properties of spins in the large N limit by using symplectic spins. Correctly including time-reversal symmetry allows the formation of Cooper pairs, and thus superconductivity. In order to treat composite pairing within a large N Anderson model treatment, we would like to develop a set of Hubbard operators that maintain this time-reversal property in the large N limit. Hubbard operators, like $X_{ab} = |a\rangle\langle b|$, are projectors between the local states, $|0, \sigma\rangle$ of the infinite U Anderson model, describing both charge, $X_{0\sigma}$ and spin, $X_{\sigma\sigma'}$ fluctuations.

Starting from a spin state $|\sigma\rangle$, hopping an electron off and back onto the site generates a spin flip: this condition defines the Hubbard operators within a single channel, where the Hubbard operators must satisfy a graded Lie algebra in which the projected hopping operators anti-commute, satisfying the algebra

$$\{X_{\alpha 0}, X_{0\beta}\} = X_{\alpha\beta} + X_{00}\delta_{\alpha\beta} \quad (11)$$

Now the traceless part of $X_{\alpha\beta}$ defines a spin operator,

$$S_{\alpha\beta} = X_{\alpha\beta} - \frac{\delta_{\alpha\beta}}{N} X_{\gamma\gamma}$$

so that quite generally, Hubbard operators must satisfy an algebra of the form

$$\{X_{\alpha 0}, X_{0\beta}\} = S_{\alpha\beta} + \left(X_{00} + \frac{X_{\gamma\gamma}}{N} \right) \delta_{\alpha\beta} \quad (12)$$

Thus the commutation algebra of the Hubbard operators generates the spin operators of the local moments. In the traditional slave boson approach¹⁷, the Hubbard operators are written $X_{0\alpha} = b^\dagger f_\alpha$. The spin operators generated by this procedure are the generators of $SU(N)$, since

$$\{f_\alpha^\dagger b, b^\dagger f_\beta\} = \overbrace{(f_\alpha^\dagger f_\beta - \frac{n_f}{N} \delta_{\alpha\beta})}^{S_{\alpha\beta}^{SU(N)}} + \left(b^\dagger b + \frac{n_f}{N} \right) \delta_{\alpha\beta} \quad (13)$$

where $S_{\alpha\beta}^{SU(N)}$ is the well-known form of $SU(N)$ spins. It is thus no wonder that this approach cannot treat superconductivity in the large N limit, for there are no spin singlet Cooper pairs for $SU(N)$ with $N > 2$. We require instead that the spin fluctuations generated by Hubbard operators are symplectic spin operators

$$S_{\alpha\beta} = f_\alpha^\dagger f_\beta - \text{sgn}(\alpha\beta) f_{-\beta}^\dagger f_{-\alpha} \quad (14)$$

We now show that the Hubbard algebra(8) can be satisfied with symplectic spins, using the introduction of *two* slave bosons,

$$\begin{aligned} X_{\alpha 0} &= f_\alpha^\dagger b + \tilde{\alpha} f_{-\alpha} a, \\ X_{0\beta} &= b^\dagger f_\beta + a^\dagger \tilde{\beta} f_{-\beta}^\dagger. \end{aligned} \quad (15)$$

These operators satisfy the Hubbard operator algebra (11), but now

$$X_{\alpha\beta} = f_\alpha^\dagger f_\beta + \tilde{\alpha}\tilde{\beta} f_{-\alpha} f_{-\beta}^\dagger = S_{\alpha\beta} + \delta_{\alpha\beta} \quad (16)$$

describes a symplectic spin operator while

$$X_{00} = b^\dagger b + a^\dagger a \quad (17)$$

is the representation of the empty state operator.

At first sight, the expedience of this new representation might be questioned: why exchange the simplicity of the original Hubbard operators, $X_{ab} = |a\rangle\langle b|$ for a profusion of slave boson fields? However, while the original Hubbard operators may appear to be simple, they are singularly awkward to treat in many-body theory¹⁸, due to their noncanonical anti-commutation algebra, (8). The slave boson representation allows us to represent these operators in terms of canonical bosons and fermions. By doubling the number of slave bosons the symplectic character of the spins is preserved at all even values of N , and we shall see that this process encodes the hard-to-enforce Gutzwiller projection as a mathematically tractable $SU(2)$ gauge symmetry.

Physical spins are *neutral*, and thus possess a continuous particle-hole symmetry. This property is maintained by symplectic spin operators, which can be seen most naturally by introducing the generalized pair creation operators,

$$\Psi^\dagger = \frac{1}{2} \sum_{\alpha} \tilde{\alpha} f_{\alpha}^{\dagger} f_{-\alpha}^{\dagger} = \sum_{\alpha>0} f_{\alpha}^{\dagger} f_{-\alpha}^{\dagger}, \quad (18)$$

which allow us to construct the isospin vector, $\vec{\Psi} = (\Psi_1, \Psi_2, \Psi_3)$, where

$$\begin{aligned} \Psi_1 &= (\Psi^\dagger + \Psi), & \Psi_2 &= -i(\Psi^\dagger - \Psi) \\ \Psi_3 &= \sum_{\alpha>0} (f_{\alpha}^{\dagger} f_{\alpha} - f_{-\alpha} f_{-\alpha}^{\dagger}) = n_s - N/2, \end{aligned} \quad (19)$$

and $n_s \equiv \sum_{\alpha} \langle \alpha | f_{\alpha}^{\dagger} f_{\alpha} | \alpha \rangle$ is the fermion number in the singly-occupied states, i.e. n_s plays the role of the number of spins in the above constraint Ψ_3 . The isospin vector commutes with symplectic spins, $[\vec{\Psi}, S_{\alpha\beta}] = 0$, showing that the symplectic spins possess an $SU(2)$ gauge symmetry: a continuous particle-hole symmetry that allows us to redefine the spinon, $f_{\alpha} \rightarrow u f_{\alpha} + v \tilde{\alpha} f_{-\alpha}^{\dagger}$. This symmetry is reflected in the requirement of two types of bosons, as the empty state does not distinguish between zero and two fermions, and thus requires two bosons to keep track of the two ways of representing the empty state, $b^\dagger |\Omega\rangle$ and $a^\dagger f_{\uparrow}^{\dagger} f_{\downarrow}^{\dagger} |\Omega\rangle = a^\dagger \Psi^\dagger |\Omega\rangle$, where $|\Omega\rangle$ is the slave-boson vacuum. Of course, there is only one physical empty state, as becomes clear when we restrict these Hubbard operators to the physical subspace. In order to faithfully represent the symplectic spins, the sum of the spin and charge fluctuations must be fixed, $\vec{S}^2 + \vec{\Psi}^2 = \frac{N}{2}(\frac{N}{2} + 2)[7]$. While this constraint is enforced by setting $\vec{\Psi} = 0$ in the pure spin model, here we must equate our two types of charge fluctuations, by setting

$$Q_3 = \sum_{\alpha} f_{\alpha}^{\dagger} f_{\alpha} - N/2 + b^\dagger b - a^\dagger a = 0$$

$$\begin{aligned} Q_+ &= \sum_{\alpha>0} f_{\alpha}^{\dagger} f_{-\alpha}^{\dagger} + b^\dagger a = 0 \\ Q_- &= \sum_{\alpha>0} f_{-\alpha} f_{\alpha} + a^\dagger b = 0. \end{aligned} \quad (20)$$

The three operators (Q_{\pm}, Q_3) commute with the Hamiltonian, which imposes the constraints associated with the physical Hilbert space. The constraint reflects the neutrality of the spins under charge conjugation: Q_3 conserves total electromagnetic charge, and prevents double occupancy, while Q_{\pm} kills any states with s-wave pairs on-site. From the form of Q_3 , we see that b and a have opposite gauge charges. The gauge invariant states satisfying the constraint (for $N = 2$) are,

$$\begin{aligned} |\alpha\rangle &= f_{\alpha}^{\dagger} |\Omega\rangle \\ |0\rangle &= (b^\dagger + a^\dagger \Psi^\dagger) |\Omega\rangle. \end{aligned} \quad (21)$$

The symplectic Hubbard operators can be written more compactly by using Nambu notation,

$$X_{0\alpha} = B^\dagger \tilde{f}_{\alpha}, \quad X_{00} = B^\dagger B \quad (22)$$

where

$$B = \begin{pmatrix} b \\ a \end{pmatrix}, \quad \tilde{f}_{\alpha} = \begin{pmatrix} f_{\alpha} \\ \tilde{\alpha} f_{-\alpha}^{\dagger} \end{pmatrix}, \quad (23)$$

The constraint becomes $\vec{Q} = B^\dagger \vec{\tau} B + \sum_{\alpha>0} \tilde{f}_{\alpha}^{\dagger} \vec{\tau} \tilde{f}_{\alpha} = 0$. For $N = 2$, these Hubbard operators are the $SU(2)$ slave bosons introduced by Wen and Lee in the context of the $t - J$ model¹⁶. Here, it becomes clear that the $SU(2)$ structure is a consequence of symplectic symmetry, present in both the symplectic- N Kondo and Anderson models, not just for $N = 2$, but for all N . This symmetry can be physically interpreted as the result of valence fluctuations in the presence of a particle-hole symmetric spin.

The Hamiltonian of the one channel, single impurity infinite- U Anderson model can now be expressed via symplectic slave bosons as follows:

$$\begin{aligned} H &= \sum_{\mathbf{k}, \alpha} \epsilon_{\mathbf{k}} c_{\mathbf{k}\alpha}^{\dagger} c_{\mathbf{k}\alpha} + E_0 (b^\dagger b + a^\dagger a) \\ &+ \sum_{\alpha} V \psi_{\alpha}^{\dagger} (b^\dagger f_{\alpha} + a^\dagger \tilde{\alpha} f_{-\alpha}^{\dagger}) + \text{h.c.} \end{aligned} \quad (24)$$

The $SU(2)$ gauge symmetry of this model becomes particularly evident in the field-theoretical formulation, where the partition function is written as a path integral:

$$Z = \int \mathcal{D}[\tilde{\psi}^{\dagger}, \tilde{\psi}, \tilde{f}^{\dagger}, \tilde{f}, B^{\dagger}, B] e^{-S}, \quad (25)$$

where the Euclidean action S is written in Nambu notation as follows

$$S = \int_0^\beta d\tau \sum_{\mathbf{k}, \alpha > 0} \tilde{\psi}_{\mathbf{k}\alpha}^\dagger (\partial_\tau + \epsilon_{\mathbf{k}} \tau_3) \tilde{\psi}_{\mathbf{k}\alpha} + \sum_j \left\{ \frac{1}{2} \text{Tr} \left[\tau_3 \mathcal{A}_j^\dagger (\partial_\tau + E_0 + \vec{\lambda}_j \cdot \vec{\tau}) \mathcal{A}_j \right] + \sum_{\alpha > 0} \left[\tilde{f}_{j\alpha}^\dagger (\partial_\tau + \vec{\lambda}_j \cdot \vec{\tau}) \tilde{f}_{j\alpha} + \left(V \tilde{\psi}_{j\alpha}^\dagger \mathcal{A}_j^\dagger \tilde{f}_{j\alpha} + \text{h.c.} \right) \right] \right\}, \quad (27)$$

where $\tilde{\psi}_\alpha^\dagger = (\psi_\alpha^\dagger, \tilde{\alpha} \psi_{-\alpha})$, $\beta = 1/T$ is the inverse temperature and the $SU(2)$ matrix \mathcal{A}_j of slave bosons is defined as

$$\mathcal{A}_j = \begin{bmatrix} b_j & a_j^\dagger \\ a_j & -b_j^\dagger \end{bmatrix}. \quad (28)$$

The first three terms in Eq. (27) describe the dynamics of conduction electrons $\tilde{\psi}$, f -electrons \tilde{f} and the slave bosons B respectively, with the constraint $\vec{Q} = 0$ imposed by introducing the vector of Lagrange multipliers $\vec{\lambda}$. The last term describes the coupling between the f -atom and conduction electrons.

The action (27) is manifestly invariant under the $SU(2)$ gauge transformation via unitary matrix \hat{g}_j :

$$\begin{aligned} \tilde{f}_j &\rightarrow \hat{g}_j \tilde{f}_j, & \tilde{\psi}_j &\rightarrow \hat{g}_j \tilde{\psi}_j, & \mathcal{A}_j &\rightarrow \hat{g}_j \mathcal{A}_j \\ \vec{\lambda}_j \cdot \vec{\tau} &\rightarrow \vec{\lambda}_j \cdot \vec{\tau} - \hat{g}_j^\dagger \partial_\tau \hat{g}_j \end{aligned} \quad (29)$$

At first sight, the a hybridization term in the Hamiltonian, (24) appears to give rise to $\langle c^\dagger f^\dagger \rangle$ pairing terms, however, the $SU(2)$ symmetry allows to redefine the fields, making the substitution

$$B = \begin{pmatrix} b \\ a \end{pmatrix} \rightarrow \hat{g} B = \begin{pmatrix} b' \\ 0 \end{pmatrix}. \quad (30)$$

This transformation eliminates the composite s -wave pairing, $b^\dagger f_\alpha + a^\dagger f_{-\alpha} \tilde{\alpha} \rightarrow b'^\dagger f'_\alpha$, recovering the usual $U(1)$ slave boson Hamiltonian.

One of the most important physical consequences encoded in this *local* gauge symmetry is the complete suppression of any s -wave pairing in the single channel Anderson model. Indeed, the constraint operator $Q_+ = \sum_{\alpha > 0} f_\alpha^\dagger f_{-\alpha}^\dagger + b^\dagger a$ may be directly interpreted as the on-site s -wave pair creation operator plus a term $b^\dagger a$ that can be removed by the above gauge transformation. In particular, the mean-field constraint

$$\langle Q_+ \rangle \equiv \langle \text{s-wave pair creation operator} \rangle = 0$$

hard-wires the strong suppression of local s -wave pairing into the formalism. In the language of superconductivity, the constraint $Q_\pm = 0$ plays the role of an infinite Coulomb pseudopotential, or renormalized electron-electron interaction, μ^* . It is the satisfaction of this constraint that drives anisotropic composite pairing.

III. THE TWO CHANNEL ANDERSON LATTICE MODEL

We turn now to the two channel lattice Anderson model, where the two channels involve charge fluctuations to the “empty” and “doubly” occupied states; here

we use the language of Ce^{3+} whose ground state configuration is f^1 , but this model captures any system with valence fluctuations from $f^{n-1} \rightleftharpoons f^n \rightleftharpoons f^{n+1}$, where n is odd. For $n = 1$, the empty state, $|0\rangle$ is trivially a singlet, and we choose the doubly occupied state to be a singlet formed from electrons in two orthogonal channels,

$$|2\rangle = \tilde{\alpha} f_{\Gamma_1, \alpha}^\dagger f_{\Gamma_2, -\alpha}^\dagger |0\rangle, \quad (31)$$

where $|\Gamma_1 : \pm\rangle \equiv |\pm\rangle$ is the ground state crystal field doublet, and $|\Gamma_2 : \pm\rangle$ is an excited crystal field doublet. In the finite- U Anderson model, the symmetries of the electron addition and removal processes are identical, but here Hund’s rules force the second electron to be placed in a channel orthogonal to the first.

The local atomic Hamiltonian at site j can be expressed in terms of Hubbard operators,

$$\begin{aligned} H_a(j) &= E_0 X_{00}(j) + E_2 X_{22}(j) + \sum_\sigma \epsilon_f X_{\sigma\sigma}(j) \\ &+ \sum_\sigma \Delta_{CF} X_{\Gamma_2\sigma; \Gamma_2\sigma}, \end{aligned} \quad (32)$$

where the X ’s are the Hubbard operators projecting into the empty, $X_{00} = |0\rangle\langle 0|$ and doubly occupied, $X_{22} = |2\rangle\langle 2|$ states, as well as the projectors into the ground state, $X_{\sigma\sigma} = |\Gamma_1\sigma\rangle\langle \Gamma_1\sigma| \equiv |\sigma\rangle\langle \sigma|$, and excited, $X_{\Gamma_2\sigma; \Gamma_2\sigma} = |\Gamma_2\sigma\rangle\langle \Gamma_2\sigma|$ crystal field doublets. If we measure the energies from the f -electron level, $E_0 = -\epsilon_f$ and $E_2 = U_{12} + \epsilon_f$ are both positive, where U_{12} is the Hubbard U for the doubly occupied state with one electron in Γ_1 and the other in Γ_2 . We take $U_{11}, U_{22} \rightarrow \infty$. The f -electrons hybridize with a bath of conduction electrons, $H_c = \sum_{\mathbf{k}, \sigma} \epsilon_{\mathbf{k}} c_{\mathbf{k}\sigma}^\dagger c_{\mathbf{k}\sigma}$ in two different channels,

$$H_V(j) = \sum_j V_1 \psi_{1j\sigma}^\dagger X_{0\sigma}(j) + V_2 \tilde{\sigma} \psi_{2j\sigma}^\dagger X_{-\sigma 2}(j) + \text{h.c.} \quad (33)$$

The angular momentum dependence is hidden inside the conduction Wannier states,

$$\psi_{\Gamma j\sigma} = \sum_{\mathbf{k}} e^{-i\mathbf{k}\cdot\mathbf{R}_j} [\Phi_{\Gamma\mathbf{k}}]_{\sigma\sigma'} c_{\mathbf{k}\sigma'}, \quad (\Gamma = 1, 2) \quad (34)$$

where the crystal field form-factors $[\Phi_{\Gamma\mathbf{k}}]_{\sigma\sigma'} = \langle k\Gamma\sigma' | \mathbf{k}\sigma \rangle$ are proportional to unitary matrices. $X_{0\sigma} = |0\rangle\langle \Gamma_1\sigma|$ and $X_{2\sigma} = |2\rangle\langle \Gamma_1\sigma|$ are the Hubbard operators between the singly occupied ground state and empty or doubly occupied states, respectively.

The symplectic- N Hubbard operators describing charge fluctuations in the two channels are a simple generalization of those used for a single channel. For a single site, these are given by

$$X_{0\alpha} = b_0^\dagger f_\alpha + a_0^\dagger \tilde{\alpha} f_{-\alpha}^\dagger, \quad X_{00} = b_0^\dagger b_0 + a_0^\dagger a_0,$$

$$X_{2\alpha} = b_2^\dagger f_\alpha - a_2^\dagger \tilde{\alpha} f_{-\alpha}^\dagger, \quad X_{22} = b_2^\dagger b_2 + a_2^\dagger a_2, \quad (35)$$

which can again be written more compactly by using a Nambu notation,

$$\begin{aligned} X_{0\alpha} &= B_0^\dagger \tilde{f}_\alpha, & X_{2\alpha} &= B_2^\dagger \tilde{f}_\alpha \\ X_{00} &= B_0^\dagger B_0, & X_{22} &= B_2^\dagger B_2, \end{aligned} \quad (36)$$

where

$$B_0 = \begin{pmatrix} b_0 \\ a_0 \end{pmatrix}, \quad B_2 = \begin{pmatrix} b_2 \\ -a_2 \end{pmatrix}. \quad (37)$$

We are free to choose the sign of a_2 , and in the above we have chosen the negative sign to preserve continuity with the results from the two channel Kondo model⁷. The doubly occupied state is then,

$$|2\rangle = \left(b_2^\dagger - a_2^\dagger \Psi^\dagger \right) |\Omega\rangle, \quad (38)$$

where $\Psi^\dagger = \sum_{\alpha>0} f_\alpha^\dagger f_{-\alpha}^\dagger$ is the pair creation operator, as before.

In the two channel model case the constraint becomes,

$$\vec{Q} = B_0^\dagger \vec{\tau} B_0 + B_2^\dagger \vec{\tau} B_2 + \tilde{f}_\alpha^\dagger \vec{\tau} \tilde{f}_\alpha = 0. \quad (39)$$

The intersection of the two Hubbard algebras gives rise to an extra doublet,

$$|\Gamma_2\alpha\rangle = \left(b_0^\dagger a_2^\dagger + b_2^\dagger a_0^\dagger \right) f_\alpha^\dagger |\Omega\rangle, \quad (40)$$

which we interpret as the excited crystal field doublet because it is reached by destroying a Γ_1 electron from the doubly occupied state, leaving behind the Γ_2 electron. However, this extra doublet is not killed by X_{00} or X_{22} , which are no longer the projectors within this larger space. The full Hamiltonian term for this state must therefore be quartic in the bosons, and subtract off the contribution from X_{00} , X_{22} and $X_{\sigma\sigma}$,

$$[\Delta_{\text{CF}} - (E_0 + E_2 + \epsilon_f)] \left(b_0^\dagger a_2^\dagger + a_0^\dagger b_2^\dagger \right) (b_0 a_2 + a_0 b_2), \quad (41)$$

where Δ_{CF} is the crystal field effect splitting. We neglect this term for much of our analysis, as it turns out to be irrelevant for the superconducting states of interest.

In addition to an extra state, there are two additional operators,

$$\begin{aligned} X_{20} &= \{X_{2\alpha}, X_{\alpha 0}\} = B_2^\dagger B_0 = b_2^\dagger b_0 - a_2^\dagger a_0 \\ X_{\Gamma_1\alpha; \Gamma_2\beta} &= -\{X_{0\alpha}, X_{2\beta}\} = B_0^\dagger (-i\tau_2) \left[B_2^\dagger \right]_{\tilde{\alpha}} \delta_{\alpha, -\beta} \\ &= \left(b_0^\dagger a_2^\dagger - b_2^\dagger a_0^\dagger \right) \tilde{\alpha} \delta_{\alpha, -\beta}. \end{aligned} \quad (42)$$

The operator $X_{\Gamma_1\alpha; \Gamma_2\beta}$ mixes the ground state and excited crystal field doublets, leading to a composite density wave state, $\langle c_1^\dagger f f^\dagger c_2 \rangle$. As this state mixes two irreducible representations of the point group, it necessarily breaks the crystal symmetry and this phase can also be called a composite nematic. This mixing resembles

the ordered state proposed for URu₂Si₂[19], which mixes ground state and excited singlets.

The operator $X_{20} = |2\rangle\langle 0|$ mixes the empty and doubly occupied states, and can be thought of as a pair creation operator. As we show in the next section, this operator acquires an expectation value when composite pairing develops. The development of an intra-atomic order parameter $\langle X_{02} \rangle$ is reminiscent of pairing in a negative (attractive)- U atom²⁰, but unlike a negative- U atom, the empty and doubly occupied sites are *excited states* of the atomic Hamiltonian, and they are only partially occupied as a result of valence fluctuations. Furthermore, the paired state is an anisotropic singlet with nodes. In the case of the Ce 115 materials, this product has d -wave symmetry⁷.

Again, we should consider the question of suppressing s -wave superconductivity. Here,

$$Q_+ = \sum_{\alpha>0} f_\alpha^\dagger f_{-\alpha}^\dagger + b_0^\dagger a_0 + b_2^\dagger a_2.$$

We know from the one channel model that a_0 can be removed by a gauge transformation, eliminating the middle term, but the $b_2^\dagger a_2$ term cannot be uniformly eliminated. However, it will only be nonzero in a state where both $\langle X_{20} \rangle$ and $\langle X_{\Gamma_1\alpha; \Gamma_2\beta} \rangle$ are nonzero, implying coexisting superconducting and composite nematic order. Under normal circumstances, these two phases repel one another, and s -wave superconductivity is wholly suppressed.

IV. THE LARGE N TWO CHANNEL ANDERSON LATTICE MODEL

We are now able to write the symplectic- N two channel Anderson lattice model in terms of the symplectic Hubbard operators,

$$\begin{aligned} H &= \sum_{\mathbf{k}} \epsilon_{\mathbf{k}} c_{\mathbf{k}\alpha}^\dagger c_{\mathbf{k}\alpha} + \sum_j E_0 B_0^\dagger(j) B_0(j) + E_2 B_2^\dagger(j) B_2(j) \\ &+ \frac{V_1}{\sqrt{N/2}} \sum_j \psi_{1j\alpha}^\dagger B_0^\dagger(j) \tilde{f}_{j\alpha} + \text{h.c.} \\ &+ \frac{V_2}{\sqrt{N/2}} \sum_j \psi_{2j\alpha}^\dagger \tilde{\alpha} \tilde{f}_{j-\alpha}^\dagger B_2(j) + \text{h.c.} \end{aligned} \quad (43)$$

In order to keep the Hamiltonian extensive in N , we have rescaled the hybridization terms by $(N/2)^{-1/2}$, so that they recover the correct $N = 2$ form, (33). This rescaling implicitly assumes that the slave bosons fields B_l ($l = 0, 2$) will acquire a magnitude of order $O(\sqrt{N})$. Since there are only two flavors of bosons, for the bosons to play a role in the large N limit, they must condense.

Following the construction that led to the path integral description of the single-channel Anderson model (27) above, one can write down the Euclidean action that corresponds to this Hamiltonian:




FIG. 3. The six physical states in the Hilbert space of the $N = 2$ two channel Anderson model, representing the ground state and excited crystal field doublets, and the empty and doubly occupied singlets. Arrows show the operators that move between states in the Hilbert space.

$$\begin{aligned}
S_2[\tilde{\psi}, \tilde{f}, \mathcal{A}_0, \mathcal{A}_2] &= \int_0^\beta d\tau \sum_{\mathbf{k}, \alpha > 0} \tilde{\psi}_{\mathbf{k}\alpha}^\dagger (\partial_\tau + \epsilon_k \tau_3) \tilde{\psi}_{\mathbf{k}\alpha} \\
&+ \sum_j \left\{ \frac{1}{2} \text{Tr} \left[\tau_3 \mathcal{A}_{0j}^\dagger (\partial_\tau + E_0 + \vec{\lambda}_j \cdot \vec{\tau}) \mathcal{A}_{0j} \right] + \frac{1}{2} \text{Tr} \left[\tau_3 \mathcal{A}_{2j}^\dagger (\partial_\tau + E_2 + \vec{\lambda}_j \cdot \vec{\tau}) \mathcal{A}_{2j} \right] \right\} \\
&+ \sum_{\alpha > 0} \left\{ \tilde{f}_{j\alpha}^\dagger (\partial_\tau + \vec{\lambda}_j \cdot \vec{\tau}) \tilde{f}_{j\alpha} + \left(\frac{V_1}{\sqrt{N/2}} \tilde{\psi}_{1j\alpha}^\dagger \mathcal{A}_{0j}^\dagger \tilde{f}_{j\alpha} + \frac{V_2}{\sqrt{N/2}} \tilde{\psi}_{2j\alpha}^\dagger \mathcal{A}_{2j}^\dagger \tilde{f}_{j\alpha} + \text{h.c.} \right) \right\}, \quad (44)
\end{aligned}$$

where $\tilde{\psi}_{\Gamma j\alpha}^\dagger = (\psi_{\Gamma j\alpha}^\dagger, \text{sgn}(\alpha)\psi_{\Gamma j-\alpha})$ are Nambu spinors for the Wannier states in each channel. Above, we have collected the slave bosons into the $SU(2)$ matrices,

$$\mathcal{A}_0^\dagger = \begin{bmatrix} b_0^\dagger & a_0^\dagger \\ a_0 & -b_0 \end{bmatrix}, \quad \mathcal{A}_2^\dagger = \begin{bmatrix} a_2 & b_2 \\ b_2^\dagger & -a_2^\dagger \end{bmatrix}. \quad (45)$$

The action (44) remains manifestly invariant under the $SU(2)$ gauge symmetry $B_l \rightarrow \hat{g}_j B_l$, where \hat{g}_j is an $SU(2)$ matrix. The matrices $\mathcal{A}_0, \mathcal{A}_2$ transform under this gauge symmetry as $\mathcal{A}_l \rightarrow \hat{g}_j \mathcal{A}_l$, leaving the product

$$\mathcal{A}_2^\dagger \mathcal{A}_0 = \begin{bmatrix} b_0 a_2 + b_2 a_0 & a_0^\dagger a_2 - b_0^\dagger b_2 \\ b_2^\dagger b_0 - a_2^\dagger a_0 & b_2^\dagger a_0^\dagger + a_2^\dagger b_0^\dagger \end{bmatrix} \quad (46)$$

gauge invariant.

The off-diagonal components of the product $\mathcal{A}_2^\dagger \mathcal{A}_0$ have the physical meaning of composite pairing between conduction and f -electrons. Indeed, in the Kondo limit, $E_0, E_2 \gg \pi\rho V^2$, we can connect the two channel Anderson model results to those from the two channel Kondo model⁷. A Schrieffer-Wolff transformation maps $b_0 \rightarrow V_1$, $a_0 \rightarrow \Delta_1$, $b_2 \rightarrow \Delta_2$ and $a_2 \rightarrow V_2$, where V_Γ and

Δ_Γ are the particle-hole and particle-particle hybridizations, respectively. We can now identify the off-diagonal components of $\mathcal{A}_2^\dagger \mathcal{A}_0 \propto V_1 \Delta_2 - V_2 \Delta_1$ with composite pairing. More generally, the components of $\mathcal{A}_2^\dagger \mathcal{A}_0$ can be identified with the state mixing operators,

$$\mathcal{A}_2^\dagger \mathcal{A}_0 = \begin{bmatrix} X_{\Gamma_1 \Gamma_2} & -X_{02} \\ X_{20} & X_{\Gamma_2 \Gamma_1} \end{bmatrix}, \quad (47)$$

which confirms the identification of $\langle X_{02} \rangle$ with composite pairing, and implies that the composite pair state contains an admixture of the empty and doubly occupied states.

To write down a translationally invariant Hamiltonian, we assume that the expectation values of the slave bosons are uniform, which allows us to write down the Hamiltonian in momentum space. To simplify this step, we temporarily drop the spin-orbit dependence of the Wannier functions, treating the form factors as spin-diagonal, $\psi_{\Gamma j\alpha} = \sum_{\mathbf{k}} c_{\mathbf{k}\alpha} \phi_{\Gamma \mathbf{k}} e^{-i\mathbf{k} \cdot \mathbf{R}_j}$. This allows us to absorb the momentum dependence of the form-factors into the hybridizations by defining $V_{\Gamma \mathbf{k}} \equiv \frac{V_\Gamma}{\sqrt{N/2}} \phi_{\Gamma \mathbf{k}}$. To obtain the d -wave symmetry which arises naturally from the spin-

orbit form factors⁷, now we must explicitly make $V_{1k}V_{2k}$ d -wave. The full spin-orbit dependence can be restored in a similar manner to the two channel Kondo model⁷. The Hamiltonian is,

$$H = \sum_{\mathbf{k}\alpha} \left(\epsilon_k c_{\mathbf{k}\alpha}^\dagger c_{\mathbf{k}\alpha} + V_{1k} c_{\mathbf{k}\alpha}^\dagger B_0^\dagger \tilde{f}_{\mathbf{k}\alpha} + V_{2k} c_{\mathbf{k}\alpha}^\dagger \tilde{\alpha} \tilde{f}_{\mathbf{k}-\alpha}^\dagger B_2 + \text{h.c.} \right) + \mathcal{N}_s \left(E_0 B_0^\dagger B_0 + E_2 B_2^\dagger B_2 \right), \quad (48)$$

where \mathcal{N}_s is the number of lattice sites. As before, the $SU(2)$ constraint is implemented with a vector of Lagrange multipliers, $\vec{\lambda}$,

$$\vec{\lambda} \cdot \left(\sum_{\mathbf{k}} \tilde{f}_{\mathbf{k}\alpha}^\dagger \vec{\tau} \tilde{f}_{\mathbf{k}\alpha} + B_0^\dagger \vec{\tau} B_0 + B_2^\dagger \vec{\tau} B_2 \right), \quad (49)$$

where we have also assumed that $\vec{\lambda}$ is translationally invariant, enforcing the constraint on average. This approximation becomes exact in the large N limit.

The Hamiltonian can be re-written in the compact form with Nambu spinors,

$$H = \sum_{\mathbf{k}\alpha} \begin{pmatrix} \tilde{c}_{\mathbf{k}\alpha}^\dagger & \tilde{f}_{\mathbf{k}\alpha}^\dagger \end{pmatrix} \begin{bmatrix} \epsilon_k \tau_3 & V_{1k} \mathcal{A}_0^\dagger + V_{2k} \mathcal{A}_2^\dagger \\ V_{1k} \mathcal{A}_0 + V_{2k} \mathcal{A}_2 & \vec{\lambda} \cdot \vec{\tau} \end{bmatrix} \begin{pmatrix} \tilde{c}_{\mathbf{k}\alpha} \\ \tilde{f}_{\mathbf{k}\alpha} \end{pmatrix} + \left[E_0 B_0^\dagger B_0 + E_2 B_2^\dagger B_2 + \vec{\lambda} \cdot \left(B_0^\dagger \vec{\tau} B_0 + B_2^\dagger \vec{\tau} B_2 \right) \right], \quad (50)$$

We note that while in the one-channel infinite- U Anderson model (27), the spurious superconducting s -wave state was eliminated by fixing the $SU(2)$ gauge transformation, the two-channel model (44) generally possesses a composite superconducting ground state, which cannot be eliminated by a gauge fixing procedure. However we can always define a transformation \hat{g} such that a_0 vanishes, so that $B_0^\dagger \rightarrow (b_0^\dagger, 0)$. In this new basis, the composite pairing operator $X_{02} = B_0^\dagger B_2$ (42) takes on the simple form, $X_{02} = b_0^\dagger b_2'$.

A. The mean field solution

In order to study the effects of mixed valence on the superconductivity, we examine the mean field solution of the composite pair state in the symplectic- N limit. The bosons are replaced by their expectation values, $B_l \rightarrow \langle B_l \rangle \sim O(\sqrt{N})$, and the Hamiltonian (50) becomes quadratic in the fermions, which may be integrated out exactly, leading to the effective action $S_{eff}[B_0, B_2]$ in terms of the boson fields only. The mean-field solution is then obtained as a saddle-point of this action:

$$\frac{\delta S_{eff}[B_0, B_2]}{\delta B_l} = 0. \quad (51)$$

We use the $SU(2)$ gauge symmetry to eliminate the a_0 boson, and now the composite pair state is defined by the nonzero expectation value of $\langle X_{02} \rangle = \langle b_0^\dagger b_2 \rangle$. While the a_2 boson can in principle acquire an expectation value,

it would lead to a uniform composite density wave solution, which is generally unstable to the composite pair solution. Therefore in what follows, we shall set $\langle a_2 \rangle = 0$. The resulting free energy can be rewritten in terms of our mean field parameters, where we replace $\langle b_l \rangle / \sqrt{N/2}$ with b_l for clarity, (however keep in mind that these have lost their dynamics),

$$F = -NT \sum_{\mathbf{k}\pm} \log 2 \cosh \frac{\beta \omega_{k\pm}}{2} + \frac{N\mathcal{N}_s}{2} [b_0^2(E_0 + \lambda_3) + b_2^2(E_2 + \lambda_3)]. \quad (52)$$

\mathcal{N}_s is the number of sites, and the dispersion of the heavy electrons is given by four branches: $\omega_{k\pm}$ and $-\omega_{k\pm}$, where $\omega_{k\pm} = \sqrt{\alpha_k \pm \Gamma_k}$, and

$$\alpha_k = b_+^2 + \frac{1}{2}(\epsilon_{\mathbf{k}}^2 + \lambda_3^2 + \lambda_1^2), \quad \Gamma_{\mathbf{k}} = \sqrt{\alpha_k^2 - \gamma_k^2} \\ \gamma_k^2 = [\epsilon_{\mathbf{k}} \lambda_3 - b_-^2]^2 + [2V_{1k} b_0 V_{2k} b_2 - \epsilon_{\mathbf{k}} \lambda_1]^2. \quad (53)$$

We have also defined

$$b_{\pm}^2 = V_{1k}^2 b_0^2 \pm V_{2k}^2 b_2^2.$$

In a nodal composite pair superconductor, the $\vec{\lambda}$ constraint reduces to λ_3 , as the λ_1 constraint acts as a Coulomb pseudo-potential²¹ eliminating s -wave pairing, and it is thus unnecessary when we choose $V_{1k}V_{2k}$ such as to give nodal superconductivity. However, if we were to treat the finite U model, where $V_{1k} = V_{2k}$, this constraint is essential to eliminate the appearance of a false s -wave superconducting phase.

The mean field parameters are determined by minimizing the free energy with respect to b_0 , b_2 , λ_3 and λ_1 . To understand their implications, we first present the mean field equations in real space,

$$\langle b_{1j} \rangle = \frac{V_1^2}{E_0} \sum_{\alpha} \langle f_{j\alpha}^\dagger \psi_{1j\alpha} \rangle \\ \langle b_{2j} \rangle = \frac{V_2^2}{E_2} \sum_{\alpha} \langle \tilde{\alpha} f_{j-\alpha} \psi_{2j\alpha} \rangle \\ \sum_{\alpha} \langle f_{j\alpha}^\dagger f_{j\alpha} \rangle = N/2 - \langle b_{0j} \rangle^2 - \langle b_{2j} \rangle^2 \\ \sum_{\alpha} \langle \tilde{\alpha} f_{j\alpha}^\dagger f_{j-\alpha}^\dagger \rangle = 0. \quad (54)$$

These equations bear a strong resemblance to the two channel Kondo equations, where $\langle b_0 \rangle$ plays the role of the hybridization V_1 in channel one, while $\langle b_2 \rangle$ plays the role of the pairing field Δ_2 in channel two; here the hybridizations are explicitly identified as the magnitude of the valence fluctuations to the empty and doubly occupied states. The number of singly-occupied levels, $n_s = \sum_{\alpha} f_{\alpha}^\dagger f_{\alpha}$, is no longer fixed to $N/2$ and instead decreases as hybridization and pairing develop.

To calculate the phase diagram, we return to the momentum space picture, and derive the three equations relevant for composite pair superconductivity with a nodal

order parameter. The last two equations in (54) impose the constraint $\bar{Q} = 0$, fixing $n_s = N/2 - b_0^2 - b_2^2$ and annihilating any s -wave pairs, while the first two equations determine the magnitude of the valence fluctuations to the empty and doubly occupied states, respectively:

$$\sum_{\pm} \int_{\mathbf{k}} \frac{\tanh \frac{\beta \omega_{\mathbf{k}\pm}}{2}}{2\omega_{\mathbf{k}\pm}} \left\{ \begin{pmatrix} \lambda_3 \\ \lambda_1 \\ 2V_{1\mathbf{k}}^2 \\ 2V_{2\mathbf{k}}^2 \end{pmatrix} \pm \frac{A}{\Gamma_k} \right\} = \begin{pmatrix} b_0^2 + b_2^2 \\ 0 \\ 2(E_0 + \lambda) \\ 2(E_2 + \lambda) \end{pmatrix}, \quad (55)$$

where

$$A = \begin{pmatrix} \lambda_3 \alpha_k + \epsilon_{\mathbf{k}} [b_-^2 - \lambda_3 \epsilon_{\mathbf{k}}] \\ \lambda_1 \alpha_{\mathbf{k}} + \epsilon_{\mathbf{k}} [2V_{1\mathbf{k}} V_{2\mathbf{k}} b_0 b_2 - \epsilon_{\mathbf{k}} \lambda_1] \\ V_{1\mathbf{k}}^2 [(\epsilon_{\mathbf{k}} + \lambda_3)^2 + \lambda_1^2] + 2\lambda_1 V_{1\mathbf{k}} V_{2\mathbf{k}} \epsilon_{\mathbf{k}} b_2 \\ V_{2\mathbf{k}}^2 [(\epsilon_{\mathbf{k}} - \lambda_3)^2 + \lambda_1^2] + 2\lambda_1 V_{1\mathbf{k}} V_{2\mathbf{k}} \epsilon_{\mathbf{k}} b_0 \end{pmatrix}. \quad (56)$$

In addition to these four equations, we must also fix the total electromagnetic charge in the system by keeping the total number of conduction electrons plus physical f -electrons constant. Notice that the number of physical f -electrons, $n_f = N/2 - b_0^2 + b_2^2$ counts the electrons in both the singly and doubly occupied states, and differs from the occupation of the spin states, $n_s = N/2 - b_0^2 - b_2^2$ by $2b_2^2$.

These equations can be solved numerically for a simple two-dimensional model where we take an s -wave $V_{1\mathbf{k}} = V$ and a d -wave $V_{2\mathbf{k}} = V(\cos k_x - \cos k_y)$, and take the two-dimensional conduction electron dispersion, $\epsilon_{\mathbf{k}} = -2t(\cos k_x + \cos k_y) - \mu$, where μ is adjusted to fix the total charge, $n_f + n_c$. λ_1 can be set to zero here since by construction, we are not considering s -wave composite pairing. This model contains three non-trivial phases:

- For $E_0 \ll E_2$, a heavy Fermi liquid develops below the temperature T_1^* . In this phase, b_0 becomes nonzero and the hybridization has symmetry Γ_1 due to screening of f -spins by conduction electrons in this channel. The f -electron valence will be less than $N/2$, and these results will be identical to the infinite- U Anderson model discussed in the introduction.
- For $E_2 \ll E_0$, a heavy Fermi liquid develops at T_2^* , where b_2 becomes nonzero. This Fermi liquid will have the symmetry of the excited doublet, Γ_2 and the f -electron valence will be larger than $N/2$. Again, these results should be identical to the appropriate infinite- U Anderson model.
- Below the superconducting temperature, T_c , a phase with d -wave composite pairing develops out of the heavy Fermi liquid, where $b_0 b_2$ becomes nonzero. $T_c \leq \{T_1^*, T_2^*\}$ is maximal where $T_c = T_1^* = T_2^*$ and here the composite pair superconductor develops directly out of the high-temperature state of free spins, bypassing the heavy Fermi liquid. As superconductivity is driven by the Cooper channel in the heavy electron normal states, T_c is




FIG. 4. The superconducting transition temperature is plotted against the occupancy of the empty, n_0 and doubly occupied, n_2 states, showing that T_c typically increases with increasing mixed valency. The black line indicates the maximal T_c , where $T_1^* = T_2^*$, and its curve is due to the d -wave nature of the second channel. Two different physical paths are shown: (1) The cost of doubly occupancy, $U_{12} = E_2 - E_0 - 2|\epsilon_f|$ is tuned while fixing the f -level, ϵ_f (blue, solid path). Here, E_0 is fixed and E_2 increases from left to right. (2) Alternatively, the hybridization, V can be increased, as by pressure or by exchanging $4f$ for $5f$ ions (green, dashed path). T_c is scaled by $\Delta = \pi V_1^2$, and we have fixed $n_c = 1.8$ in units of $N/2$.

always finite and the ground state will always be superconducting. The f -electron valence will generally differ from $N/2$, with nonzero contributions of both f^0 and f^2 .

Note that in the full model, the Kondo temperatures T_1^* and T_2^* mark crossovers into the heavy Fermi liquids. The appearance of phase transitions associated with condensation of $\langle b_1 \rangle$ and $\langle b_2 \rangle$ here is a spurious consequence of the mean-field large- N treatment and is resolved with $1/N$ corrections¹⁷. However, the superconducting phase transition is *not* spurious and will survive to finite N .

In Figure 4, we plot the superconducting transition temperature versus the proportion of empty states, $n_0 = b_0^2$ and that of doubly occupied states, $n_2 = b_2^2$. Larger n_0 and n_2 indicate a greater degree of mixed valency, which may be obtained by varying V , E_0 and E_2 . We show two possible paths for tuning real materials: (1) By varying U_{12} , $E_2 = \epsilon_f + U_{12}$ will change, while E_0 remains fixed. This path is qualitatively identical to that of the two channel Kondo model when J_2/J_1 is varied: there is a superconducting dome with maximal T_c where $T_1^* = T_2^*$; (2) By changing the hybridization, V and keeping E_0/E_2 fixed, T_c can increase monotonically with increasingly mixed valency, as it does between CeCoIn₅ and PuCoGa₅. A similar increase slightly away from the maximal T_c can explain the non-monotonic change in T_c with increasing pressure in CeCoIn₅[31].

V. CHARGE REDISTRIBUTION

As the development of composite pairing mixes the empty and doubly occupied states, each develops a non-zero occupation, and the charge density changes. The link between the f -electron charge and the development of the Kondo effect in the one-channel Anderson model was explored by Gunnarsson and Schoenhammer²², who showed that the f -electron valence, n_f decreases gradually with temperature through the Kondo crossover, $n_f(T) = 1 - b_0^2(T)$. The mixing of the empty and doubly occupied states adds a new element to this relationship, and the consideration of real, non- s -wave hybridizations allows us to explore the higher angular momentum components of the charge distribution. The charge density can be written, $\hat{\rho}(\mathbf{x}) = \hat{\psi}_\alpha^\dagger(\mathbf{x})\hat{\psi}_\alpha(\mathbf{x})$, where $\hat{\psi}_\alpha^\dagger(\mathbf{x})$ creates a physical electron of spin α at \mathbf{x} . The electron field \mathbf{x} can be approximately decomposed as a superposition of two orbitals Γ_1 and Γ_2 at nearby lattice sites j ,

$$\hat{\psi}_\alpha(\mathbf{x}) = \sum_j [\Phi_1]_{\alpha\beta}(\mathbf{x} - \mathbf{R}_j)\hat{f}_{1j\beta} + [\Phi_2]_{\alpha\beta}(\mathbf{x} - \mathbf{R}_j)\hat{f}_{2j\beta}, \quad (57)$$

where we have reintroduced the spin-orbit form factor, $[\Phi_\Gamma]_{\alpha\beta}$ in order to model real materials. The charge density of an f -electron located at the origin in channel Γ is $\rho_\Gamma(\mathbf{x}) = \text{Tr}|\Phi_\Gamma(\mathbf{x})|^2 R(\mathbf{x})^2$, where $R(\mathbf{x})$ is the radial function for the f -electron, and $|\Phi_\Gamma(\mathbf{x})|^2$ is a diagonal matrix. If we assume that the overlap of electrons at neighboring sites is negligible, the total charge density has three different terms,

$$\hat{\rho}(\mathbf{x}) = \sum_j \rho_1(\mathbf{x} - \mathbf{R}_j)f_{1j\beta}^\dagger f_{1j\beta} + \rho_2(\mathbf{x} - \mathbf{R}_j)f_{2j\beta}^\dagger f_{2j\beta} + \left[\Phi_1^\dagger \Phi_2 \right]_{\alpha\beta}(\mathbf{x} - \mathbf{R}_j)f_{1j\alpha}^\dagger f_{2j\beta} + \text{h.c.}, \quad (58)$$

where we have kept the spin indices of $[\Phi_1^\dagger \Phi_2]_{\alpha\beta}$, as it may not be diagonal in spin space. In terms of the Hubbard operators, we can replace,

$$\begin{aligned} f_{1j\beta}^\dagger f_{1j\beta} &= X_{22}(j) + n_s(j) = B_{2j}^\dagger B_{2j} + n_s(j) \\ f_{2j\beta}^\dagger f_{2j\beta} &= X_{22}(j) + X_{\Gamma_2\beta\Gamma_2\beta}(j) = B_{2j}^\dagger B_{2j} + \gamma^\dagger \gamma \\ f_{1j\alpha}^\dagger f_{2j\beta} &= X_{\Gamma_1\alpha\Gamma_2\beta}(j), \end{aligned} \quad (59)$$

where as before, the number of singly occupied states on site j , $n_s(j) = N/2 - B_{0j}^\dagger B_{0j} - B_{2j}^\dagger B_{2j}$, and $\gamma^\dagger = B_0^\dagger(-i\sigma_2)[B_2^\dagger]^T = b_0^\dagger a_2^\dagger + b_2^\dagger a_0^\dagger$ is the operator from equation (41), so that $\gamma^\dagger f_\alpha^\dagger$ creates an electron in the excited single-electron crystal field state $|\Gamma_2\alpha\rangle$, see Fig. 3. The third term, $X_{\Gamma_1\alpha\Gamma_2\beta} = |\Gamma_1, \alpha\rangle\langle\Gamma_2, \beta|$ mixes the two crystal field states, shifting charge from Γ_1 to Γ_2 . In the large- N mean-field theory, this state corresponds to non-vanishing diagonal elements of the matrix $\langle\mathcal{A}_2^\dagger \mathcal{A}_0\rangle$ in Eq. (46), $\langle X_{\Gamma_1\alpha\Gamma_2\beta}\rangle \sim a_0 b_2 + a_2 b_0$. Since Γ_1 and Γ_2 are two different representations of the crystal point group, such mixing implies that the crystal symmetry is spontaneously broken: in Ce-115 materials it would correspond

to orthorhombic ‘‘nematic’’ density wave state, which has not been observed. We are primarily interested in superconducting instability, and therefore ignore such a state by setting $a_2 = 0$ in what follows, assuming we have already gauge fixed $a_0 = 0$. Any occupation of the excited crystal field state, $\langle X_{\Gamma_2\beta\Gamma_2\beta}\rangle$ is also eliminated by this Ansatz.

In the heavy Fermi liquid and superconducting states, we may use the constraint to rewrite $f_{1j\beta}^\dagger f_{1j\beta} = N/2 - X_{00}(j)$. The charge distribution becomes,

$$\hat{\rho}(\mathbf{x}) = \sum_j \rho_1(\mathbf{x} - \mathbf{R}_j) \left[\frac{N}{2} - X_{00}(j) \right] + \rho_2(\mathbf{x} - \mathbf{R}_j) X_{22}(j) \quad (60)$$

Integrating this charge density around a single site gives us the f -electron valence, $n_f = 1 - b_0^2 + b_2^2$, which we plot as a function of T in Figure 5 for two different E_2/E_0 . The phase transition at T^* is an artifact of the large N limit and becomes a crossover for any finite N , but the sharp kink in n_f at the superconducting transition temperature remains for all N . Experimentally determining the f -electron valence may be possible using core-level valence spectroscopy for Ce compounds or the Mössbauer isomer shift for NpPd₅Al₂, where current measurements do indicate a small, positive change in the isomer shift through T_c [6]. If Np is in the $5f^3$ valence state, with dominant fluctuations between $5f^3 \rightleftharpoons 5f^4$, then the isomer shift will increase with decreasing temperature down to T_c , where it will begin to decrease sharply as $5f^2$ states mix in, as the black curve in Figure 5 shows. Experimentally, the isomer shift was measured at 10K, well above T_c and then below T_c , so the observed positive shift could just be due to the increase above T_c , and further measurements are necessary. The clear observation of a sharp negative shift precisely at the superconducting transition temperature would indicate the presence of composite pairing.

As superconductivity develops, the occupation of the doubly occupied state acquires an expectation value, leading to an increase in the Γ_2 charge density. This redistribution of the f -electron charge results in a quadrupole moment associated with superconductivity. Again, since the development of superconductivity is a phase transition, the quadrupole moment changes sharply at T_c . The quadrupole charge component has an indirect effect on the superconducting transition temperature through its linear coupling to strain, leading to a linear dependence of T_c on the tetragonal strain, c/a . Such a linear increase of T_c with c/a has been observed in both the Ce and Pu 115s, although it is conventionally attributed to dimensionality effects²³. The quadrupole moment of the composite condensate provides an alternate explanation, and, in addition, leads to the development of electric field gradients around the f -lattice sites, which can also be measured directly as a shift in the nuclear quadrupole resonance frequency, $\Delta\nu_{NQR}$ at the nuclei of the nearby atoms.

To make contact with potential experiments, we examine CeCoIn₅ in more detail. ¹¹⁵In atoms have a nuclear




FIG. 5. The f -electron valence, n_f changes as the Kondo effect and composite pair superconductivity develop. Two examples are shown - the black curve has $T_2^* > T_1^*$, as expected for NpPd_5Al_2 , so that the valence increases below T_2^* , and then sharply decreases for $T < T_c$. For the dashed gray curve, $T_1^* > T_2^*$, as expected for CeMIn_5 and a sharp increase in the valence is seen at T_c . The sharp kinks at T_1^*, T_2^* are artifacts of the mean field calculation, becoming smooth crossovers in real materials, while the superconducting kinks should be observable in real materials.

moment $I = 9/2$, which results in a quadrupole moment, $Q = 8.3 \times 10^{-29} \text{m}^2$, making them NQR active²⁴. The symmetry of the ground state doublet is Γ_7^+ [25], whose angular dependence is given by,

$$|\Phi_{\Gamma_7^+}|^2(\theta, \phi) = \frac{3}{16} \sin^2 \theta \left[2\sqrt{5} \cos 4\phi \sin^2 \theta \sin 2\xi + 11 + 6 \cos 2\xi + 5 \cos 2\theta(1 + 2 \cos 2\xi) \right] \quad (61)$$

where ξ is a crystal-field parameter depending on the microscopic details that can be measured with inelastic neutron scattering, and we set $\xi \approx .25$ for CeCoIn_5 [25]. We take the symmetry of the second channel to be $\Gamma_2 = \Gamma_6$, whose angular dependence is,

$$|\Phi_{\Gamma_6}|^2(\theta, \phi) = \frac{3}{32} [12 \cos 2\theta + 5(3 + \cos 4\theta)]. \quad (62)$$

We can now use the real charge distributions of the two orbitals to estimate the magnitude of the electric field gradient, $V_{ab} = -\partial E_a / \partial x_b$, where

$$\rho_{\Gamma}(\mathbf{x}) = |\Phi_{\Gamma}|^2(\theta, \phi) R(r)^2. \quad (63)$$

$R(r)$ is the $4f$ radial function,

$$R(r) = \frac{1}{96\sqrt{35}} \left(\frac{Z^{3/2} r}{2a_B} \right)^3 \exp\left(-\frac{Zr}{4a_B}\right). \quad (64)$$

$a_B = .53 \text{\AA}$ is the Bohr radius, and $Z = 6\sqrt{10}a_B/r_{\text{Ce}}$ is adjusted so that the atomic radius is that of Ce^{3+} , $\langle r \rangle = r_{\text{Ce}} = 1.15 \text{\AA}$ [26].

CeCoIn_5	In(1) V_{zz}	In(2) V_{zz}
Γ_7^+	$-1.5q_{7+} \cdot 10^{20} \text{ V/m}^2$	$+5.0q_{7+} \cdot 10^{19} \text{ V/m}^2$
Γ_6	$+1.4q_6 \cdot 10^{20} \text{ V/m}^2$	$-3.6q_6 \cdot 10^{19} \text{ V/m}^2$

TABLE I. Estimated electronic field gradients at the two In sites in CeCoIn_5 due to eq_{Γ} charge in the f -electron orbital, $\Gamma = \Gamma_7^+, \Gamma_6$, where e is the charge of an electron.

The NQR frequency measures the electric field gradients at two different indium sites in the crystal: the in-plane, high symmetry In(1) sites, which sit in the center of a square of Ce atoms, and the lower symmetry out-of-plane In(2) sites, which are above and in-between two Ce atoms. The NQR frequency is given by²⁷,

$$\nu_{\text{NQR}} = \frac{3eV_{zz}Q}{2hI(2I-1)} \text{Hz}. \quad (65)$$

At the In(2) site, there is a nonzero asymmetric contribution, $\eta = |V_{xx} - V_{yy}|/V_{zz}$, which can be independently determined from experiment. Now that we have an accurate expression for the charge distribution of the two orbitals, we may calculate the electric field gradient at \mathbf{x} associated with a charge q in orbital Γ at \mathbf{R}_j :

$$V_{aa}^{\Gamma}(\mathbf{x}, \mathbf{R}_j) = \frac{q}{4\pi\epsilon_0} \int_{\mathbf{x}'} \rho_{\Gamma}(\mathbf{x}' - \mathbf{R}_j) \left[\frac{3(a-a')^2}{|\mathbf{x} - \mathbf{x}'|^5} - \frac{1}{|\mathbf{x} - \mathbf{x}'|^3} \right] \quad (66)$$

Summing over the eight neighboring Ce sites is sufficient to estimate the magnitude of the NQR shift, where we use the lattice constants of CeCoIn_5 , $a = 4.6 \text{\AA}$, and $c = 7.4 \text{\AA}$ [2]. The electric field gradients for a charge eq_{Γ} in channel Γ are shown in Table I.

For equal channel strengths, the total charge of the f -ion remains unity, and the increasing occupations of the empty and doubly occupied sites cause holes to build up with symmetry Γ_7^+ and electrons with symmetry Γ_6 , $q \equiv q_6 = -q_{7+}$. If we define $q(T)$ to be the temperature dependent occupation of the empty/doubly occupied states, in the mean field $q(T) = \langle b_0^2 \rangle = \langle b_2^2 \rangle$ will be proportional to $T_c - T$ just below T_c , and we can define,

$$q(T) = q_0 \frac{T_c - T}{T_c}, \quad (67)$$

where q_0 is the ground state occupation of the empty/doubly occupied states. In terms of q_0 , the superconducting NQR frequency shift will be,

$$\begin{aligned} \Delta\nu_{\text{NQR}}^1(T) &= -7.6q_0 \frac{(T_c - T)}{T_c} \text{kHz} \\ \Delta\nu_{\text{NQR}}^2(T) &= +11q_0 \frac{(T_c - T)}{T_c} \text{kHz} \end{aligned} \quad (68)$$

Even assuming a reasonably large 5% change in the single-occupancy ($q_0 = .05$) for CeCoIn_5 with $T_c = 2.3 \text{K}$ will lead to a small shift in $\nu_{\text{NQR}}^{1,2}$ with a slope of $\approx -.16, +.24 \text{ kHz/K}$, beginning precisely at T_c . We could also consider the case of unequal channel strengths, where the Ce exchanges charge with the conduction electrons,

sitting in the In p -orbitals, however this term will be similarly small in any clean sample. If this shift could be distinguished, it would be an unambiguous signal of composite pairing. As this shift is quite small, Mössbauer spectroscopy, which directly probes the f -ions may be a more likely technique to observe the development of a condensate quadrupole moment. Given that the crystal fields for NpPd_5Al_2 are unknown, we can only make a rough estimate of the magnitude of the quadrupolar splitting, following [28]. The f -ion contribution to the splitting will originate from a redistribution of charge eq within the f -orbitals, and can be as large as $0.2q$ mm/s. The lattice contribution to the quadrupole splitting, which originates from the change in f -valence redistributing charge within the lattice, will likely be a larger effect.

VI. CONCLUSIONS

Our two-channel Anderson model treatment has shown how composite pairing arises as the low energy consequence of valence fluctuations in two competing symmetry channels, which in turn manifests itself as a mixing of the empty and doubly occupied states,

$$\Delta_{SC} \propto \langle |0\rangle\langle 2| \rangle. \quad (69)$$

Composite pairing is primarily a local phenomena, where the pairing occurs within a single unit cell. The mixing is reminiscent of an *intra-atomic* antiferromagnetism, involving d-wave singlet formation between the $|\Gamma_1\rangle$ and $|\Gamma_2\rangle$ states. It is the atomic physics of the f -ions, tuned by their local chemical environment that drives the superconductivity. Such chemically driven d-wave pairing is a fascinating direction for exploring higher temperature superconductors in even more mixed valent $3d$ materials, as the strength of the composite pairing increases monotonically with increasing valence fluctuations, which accounts for the difference in transition temperatures between the cerium and the actinide 115 superconductors, and for the effects of pressure.

The local nature of composite pairing should make it less sensitive to disorder than more conventional anisotropic pairing mechanisms. Such insensitivity is observed in the doped Ce-115 materials, where superconductivity survives up to approximately 25% substitution

on the Ce site²⁹, while neither Ce-site nor In-site disorder behave according to Abrikosov-Gorkov, suggesting instead a percolative transition³⁰.

The redistribution of charge due to the mixing of empty and doubly occupied states provides a promising direction to experimentally test for composite pairing, which should appear as a sharp redistribution of charge associated with the superconducting transition. Both monopole (f -valence) and quadrupole (electric field gradients) charge effects should be observable, with core-level X-ray spectroscopy and the Mössbauer isomer shift or as a shift in the NQR frequency at surrounding nuclei, respectively. We predict a shift with slope of order $\pm 0.3\text{kHz/K}$ in the NQR frequency of In nuclei in CeCoIn_5 .

Deriving these results in an exact, controlled mean field theory required the introduction of symplectic Hubbard operators, which maintain the time-reversal properties of $SU(2)$ electrons in the large N limit. While our results are obtained in the large- N limit, it should also be possible to use these Hubbard operators to develop a dynamical mean field theory treatment of the two-channel Anderson lattice, enabling us to examine composite pairing for $N = 2$.

In addition to the two-channel Anderson model, the development of symplectic-Hubbard operators allows a controlled treatment of the finite- U Anderson model, which is potentially useful as an impurity solver for dynamical mean field theory. We identify the finite- U model as a special case of our two channel model when the electron and hole fluctuations occur in the same symmetry channel, $\Gamma_1 = \Gamma_2$. At first sight, this model appears to give s-wave superconductivity, however, the $SU(2)$ constraint, λ_1 forbids any on-site pairing and completely kills the superconductivity, leaving only the simple Fermi liquid solution. We expect $1/N$ corrections to this mean field limit will differ from the $SU(N)$ approach, and an interesting future direction is to use the Gaussian fluctuations to examine the charge fluctuation side peaks.

Acknowledgements. We should like to acknowledge discussions with Cigdem Capan, Maxim Dzero, Zachary Fisk, Pascoal Pagliuso and Ricardo Urbano. This work was supported by the National Science Foundation, Division of Materials Research grant DMR 0907179.

¹ N. D. Mathur, F. M. Grosche, S. R. Julian, I. R. Walker, D. M. Freye, R. K. W. Haselwimmer and G. G. Lonzarich, *Nature* **394** 39, (1998).
² C. Petrovic et al., *J. Phys.: Condens. Matter* **13**, L337(2001).
³ D. Aoki et al., *J. Phys. Soc. Jpn.*, **76**, 063701-063704 (2008).
⁴ J. L. Sarrao *et al.*, *Nature (London)* **420**, 297-299 (2002).
⁵ T. Willers, Z. Hu, N. Hollmann, P. O. Korner, J. Gegner, T. Burnus, H. Fujiwara, A. Tanaka, D. Schmitz, H. H.

Hsieh, H.-J. Lin, C. T. Chen, E.D. Bauer, J.L.Sarrao, E. Goremychkin, M. Koza, L. H. Tjeng and A. Severing, *Phys. Rev. B* **81**, 195114 (2010).
⁶ K Gofryk, J Griveau, E Colineau, J. P. Sanchez, J. Rebizant, and R. Caciuffo, *Physical Review B* **79**, 134525 (2009).
⁷ R. Flint, M. Dzero and P. Coleman, *Nat. Phys.* **4**, 643 (2008).
⁸ R. Flint and P. Coleman, *Phys. Rev. Lett.* **105**, 246404(2010).

- ⁹ E. Abrahams, A. Balatsky, D.J. Scalapino and J. R. Schrieffer, Phys. Rev. B **52**, 1271(1995).
- ¹⁰ P. G. Pagliuso et al.: Phys. Rev. B **64** (2001) 100503; P. G. Pagliuso et al.: Physica B 312 (2002) 129.
- ¹¹ H. Shishido et al., J. Phys. Soc. Jap. **7**, 162173(2002).
- ¹² P. Coleman, A. M. Tsvetlik, N. Andrei and H. Y. Kee, *Phys. Rev. B* **60**, 3608 - 3628 (1999).
- ¹³ J. Hubbard, Proc. Royal Soc. London A, 277 237 (1964).
- ¹⁴ C. J. Bolech and N. Andrei, Phys. Rev. Lett. **88**, 237206-237210, (2002).
- ¹⁵ I. Affleck, Z. Zou, T. Hsu and P. W. Anderson, Phys. Rev. B **38**, 745, (1988).
- ¹⁶ X.G. Wen and P.A. Lee, Phys. Rev. Lett. **76**, 503 (1996).
- ¹⁷ P. Coleman, Phys. Rev. B 28, 5255 (1983).
- ¹⁸ H. Keiter and J.C. Kimball, Int J. Magn. **1**, 233 (1971).
- ¹⁹ K. Haule and G. Kotliar, Nat. Phys. **5**, 796 - 799 (2009).
- ²⁰ P. W. Anderson, Phys. Rev. Lett. **34**, 953 (1975).
- ²¹ P. Morel and P.W. Anderson, Phys. Rev. **125**, 1263 (1962).
- ²² O. Gunnarsson & K. Schonhammer, Phys. Rev. B **28**, 4315(1983).
- ²³ Bauer, E.D., et al., Phys. Rev. Lett. **93**, 147005 (2004).
- ²⁴ R. Urbano (private communication).
- ²⁵ A. D. Christianson et al., PRB **70**, 134505(2004).
- ²⁶ A. Bringer, Solid State Comm. **46**, 591(1983).
- ²⁷ R.M. White and T. H. Geballe, "Long Range Order in Solids" p.193-194 (Academic Press, New York, 1979).
- ²⁸ W.Potzel, G.M. Kalvius, and J.Gal, in *Handbook on the Physics and Chemistry of Rare Earths*, edited by K.A. Gschneider, Jr., L. Eyring, G.H. Lander, and G.R. Chopin (Elsevier, Amsterdam, 1993), Vol. 17,p.539.
- ²⁹ J. P. Paglione, T. A. Sayles, P. C. Ho, J. R. Jeffries and M. B. Maple, Nature Physics **3**, 703 (2007).
- ³⁰ E. D. Bauer, Yi-feng Yang, C. Capan, R. R. Urbano, C. Miclea, H. Sakai, F. Ronning, M. J. Graf, A. V. Balatsky, R. Movshovich, A. D. Bianchi, A. P. Reyes, P. L. Kuhns, J. D. Thompson, and Z. Fisk, PNAS **108**, 6857 (2011).
- ³¹ V.A. Sidorov et al, Phys. Rev. Lett. **89**,157004 (2002).