

THERMODYNAMICS AND VISCOSITY ASPECTS IN MANGANESE NODULE RESIDUE SMELTING FOR SILICOMANGANESE PRODUCTION

N. S. RANDHAWA^{1*}, R. K. JANA¹ AND N. N. DAS²

¹MEF Division, CSIR-National Metallurgical Laboratory, Jamshedpur

²PG Department of Chemistry, North Orissa University, Baripada

Abstract:

Among several under trial processes for extraction of base metals (Cu, Co and Ni) from manganese nodules (MN), the reduction-roast ammoniacal leaching $\{NH_4OH/(NH_4)_2CO_3\}$ process is considered very attractive. After the leaching of base metals from roast-reduced MN, a substantial quantity of residue left behind (about 70 wt. %, by mass) as wastes for disposal or further use. Smelting studies showed that leached manganese nodules residue (WMNR) can be successfully utilized as raw material for silicomanganese production after maintaining proper metallurgical aspects like thermodynamics, viscosity etc. Literature survey on slag liquidus and viscosity aspects of silicomanganese smelting has been done. The slag liquidus has been found to be closely associated to slag basicity i.e. $(CaO+MgO/SiO_2)$ showing significant increase above 0.7 slag basicity. Charge mix basicity of 0.2 was found to give maximum Mn and Si recoveries. Increasing or decreasing charge basicity from 0.2 resulted in lower metallic yield and Mn and Si recoveries. This has been explained with liquidus calculations of final slags obtained at those charge mix basicities. Addition of CaF_2 during holding time i.e. time given after complete melting of charge mix was found to be beneficial. The optimum amount of CaF_2 was 4% of WMNR+Mn ore blend, which gave rise to maximum Mn and Si recoveries and metallic yield. Further addition of CaF_2 (>4%) produced a high basicity slag (basicity = 0.83) having very high liquidus leading to decrease in metallic yield and Mn and Si recoveries.

Keywords: Leached manganese nodules residue; Basicity; Smelting, Silicomanganese; Slag liquidus; Viscosity



1. INTRODUCTION

Wastes from mining and metallurgical industries are notorious for their hazardous impact on living beings. Hence, issues like processing of mining and metallurgical byproducts/wastes such as fines, lean grade ores, slags, dusts, sludges etc., their safe disposal and recovery of metallic values are considered critical from environmental, economic and social point of view [Richard, 1978]. The present work deal with the manganese nodules processing waste, generated after selective recovery of copper, nickel and cobalt by ammoniacal leaching of manganese nodules [Jana et al., 1999]. The leached residue of manganese nodules is a fine powdery oxide material. Several studies have been carried out to develop the technologies for complete utilization of waste manganese containing materials like high phosphorous manganese slag, high-carbon ferromanganese-byproduct metal etc [Voronov and Gavrilov, 1996; Zang et al., 1995; Eissa et al., 2004]. However, use of such complicated materials require detailed thermodynamic analysis and their

effect on partitioning of the main elements viz. Mn, Si etc., between the silicomanganese and slag in the industrial furnaces.

The thermodynamic equilibrium conditions between alloy and slag determine the yield and grade of alloy in silicomanganese smelting. The

MnO, SiO_2 , CaO, MgO and Al_2O_3 are the prevailing oxides taking part in silicomanganese smelting reactions in slag. The MnO and SiO_2 undergo reduction by 'carbon' either as graphite or in SiC [Olsen et al., 2007], which can be represented by Eqn (1) and Eqn. (2).



The oxides of CaO, MgO and Al_2O_3 remain entirely in the slag as they are thermodynamically stable in the operating conditions. Presence of these oxides in slag significantly affect the activity of the manganese oxide (a_{MnO}) and silicon oxides (a_{SiO_2}) [Swinbourne et al., 1995; Turkdogan, 1979; Kor, 1979] and hence, the extent of reaction 1 and 2.

This determines the distribution of Mn and Si between alloy and slag phase and hence the composition of alloy. Therefore, slag composition needs to be amply maintained to allow favorable distribution of Mn and Si across slag metal interface to recover metals in desired ratio. Slag composition is typically expressed by mass ratio different oxides in the slag [Olsen et al., 2007; Eissa et al., 2004; Nikolaev, 1974], as given in Eqn. (3) and Eqn. (4).

$$B(\text{Basicity}) = \frac{(\text{CaO} + \text{MgO})}{(\text{SiO}_2)} \quad (3)$$

$$R \text{ ratio} = \frac{(\text{CaO} + \text{MgO})}{(\text{Al}_2\text{O}_3)} \quad (4)$$

Silicomanganese smelting is generally done with excess silica i.e. acidic slag. Addition of alumina to acidic slag is also found to decrease the equilibrium MnO content in the slag [Swinbourne et al., 1995]. Several studies have reported that increase in basicity increases the a_{MnO} and decreases the a_{SiO_2} , resulting in decreased equilibrium MnO and increased SiO₂ [Swinbourne et al., 1995; Turkdogan, 1979; Kor, 1979; Eissa et al., 2004; Nikolaev, 1974]. The viscosity of slag significantly affect the partitioning of metals between alloy and slag phase [Tang and Tangstad, 2004]. A sufficiently fluid slag should always be maintained to avoid metal entrapment in slag so that proper slag-alloy separation can be achieved.

In present paper, some of the thermodynamic and viscosity aspects of leached manganese nodules residue smelting for silicomanganese production are described. Particularly, the dependence of charge mix preparation and Mn distribution on these two aspects is discussed in detail.

2. THERMODYNAMICS AND VISCOSITY ASPECTS IN SILICOMANGANESE SMELTING

As mentioned above, that reduction of MnO and SiO₂ mainly takes place from slag; and therefore maintaining a sufficiently liquid slag with minimum viscosity at operating temperature i.e. at 1600 ± 50 °C is a prerequisite for charge mix preparation. Additionally, the raw materials must be blended in such proportion that would produce slag with minimum MnO content and allow desired distribution of Mn and Si between alloy and slag phase.

In silicomanganese production, smelting is carried out in acidic slag i.e. slag basicity < 1. Several studies have been done to study the effect of slag basicity on Mn and Si distribution or Distribution Ratio i.e. [ratio of Wt. % metal in slag to that in

alloy]. Equilibrium studies on distribution of Mn between Mn-Si-Fe-C alloys and MnO-CaO-MgO-SiO₂-Al₂O₃ slag at 1500 °C under CO atmosphere revealed that an increase in basicity ratio of slag decreases the Mn distribution ratio [Cengizler et al., 2003]. In contrast, increase in silica concentration of the slag increases the Mn distribution ratio [Cengizler et al., 2003]. The optimum slag basicity B, reported by Chaichenko et al [1986] is in the range of 0.65-0.90. Addition of alumina to slag favours transfer of Mn to alloy leading to a low MnO slag [Cengizler et al., 1997]. Studies by Tang and Olsen [2006] and Ding and Olsen [2000] also reported that addition of alumina to acidic slag decreases the equilibrium MnO content in the slag. Whereas in another study by Cengizler et al [1997], activity data for Fe-Mn slags were modelled by applying neural nets at 1500°C for slag compositions lying in the range of MnO 5-40%, CaO 4-35%, MgO 0.3-38%, SiO₂ 25-60% and Al₂O₃ 2.5-7%. Their study concluded that activity coefficient of MnO in liquid slag region varies on both sides of unity. In acid slags the $\gamma_{\text{MnO}} < 1$, whereas in basic slags the $\gamma_{\text{MnO}} > 1$, where γ is activity coefficient.

The basicity of slag keeps on increasing up to the equilibrium value due to reduction of SiO₂ to Si. On the other hand, R ratio practically remains constant throughout the smelting and should be more influencing to slag-metal equilibrium. Nikolaev [1974] reported the optimum R value to be 2.5 whereas Emlin et al [1986] concluded optimum R value in the range of 1.2-2.2. Eissa et al [2004] studied the smelting of high Mn slag and observed the highest metallic yield and recoveries of manganese and silicon with initial R value of 1.8 by using dolomite as fluxing material.

They also concluded that slag basicity adjusted by addition of dolomite gave higher metallic yield, manganese and silicon recoveries comparing with that obtained by adding either limestone or dolomite and limestone together. Equilibrium studies done by Ding and Olsen [2000] concluded that the R ratio strongly influences the SiO₂ activity of the slag and thereby the Si content of the alloy. Iso-activity lines of SiO₂ in the system SiO₂-CaO-Al₂O₃ are shown in Fig 1 [Ding and Olsen, 2000]. The lines representing constant silica activities in the slag are at the same time lines of constant silicon activity in equilibrated metal alloy. From the top apex of Fig 1 are drawn straight lines having constant CaO/Al₂O₃ ratios called R ratios. Thus R ratio is found to be much more important in SiMn production (Eqn. 4) than the lime basicity ratio (Eqn. 3).

temperatures were 1680, 1580 and 1475 °C for slag containing 10%, 20% and 40% MnO.




Fig.3. Liquidus in the “MnO”-CaO-(Al₂O₃+SiO₂) system at Al₂O₃/SiO₂ weight ratio of 0.55 in equilibrium with Mn -Si alloy, as a function of CaO concentration for MnO = 5, 10, 20, and 40 wt pct. Presence of different compounds along the liquidus lines are also shown [Roghani et al., 2003]

Viscosity is one of the fundamental properties of the slag and key parameter for many smelting processes. Viscosity of slag is a complex function of slag composition, temperature and oxygen partial pressure. It is well accounted that the viscosity, being the viscous resistance of the melt in the flow process, prominently relies on the big complex anions (e.g., SiO₄⁴⁻, Si₂O₇⁶⁻, and Si₃O₁₀⁸⁻) of silica. Hence, the melts will have a high value of viscosity when there is a high SiO₂ content such as in the silicomanganese smelting. In absence of external flux i.e. dolomite, the Mn ore and HC-FeMn slag are the source of the CaO, MgO and Al₂O₃, which form slag upon melting. At this point, the Ca²⁺, Mg²⁺, and Mn²⁺ cations are at low concentrations and readily associate with larger ionic groups of silica and thus cause high viscosity. Likewise, a_{MnO} is low at this time due to lower free O²⁻ ions for they are associated by larger silica anions. As the basic oxides contents are increased by addition of dolomite, the Ca²⁺, Mg²⁺ are increased. The stronger interaction between Ca²⁺, Mg²⁺ and silicate ions than that between Mn²⁺ and silicate ions result in stable Ca- and Mg-silicates [Kubaschewsky et al., 1979; Barin, 1989]. This give rise to free Mn²⁺ ions which kinetically associate with free O²⁻ ions in the slag and increases a_{MnO} in the slag. The high a_{MnO} in the slag favours the transfer of Mn into metal [Turkdogan, 1983]. In the contrast, a_{SiO_2} in slag is diminished by addition of basic oxides and adversely affects the prime Si content of alloy. Therefore, it is of prime




Fig.1. Calculated (FACTSage) iso-activity lines of SiO₂ in SiO₂ - CaO - Al₂O₃ slags at 1600°C intersected by lines having constant R ratios (R=CaO/Al₂O₃) [Ding and Olsen, 2000].

Fig 2 shows equilibrium relations for ternary MnO-SiO₂-CaO slags in equilibrium with Mn-Si-Csat at P_{CO}=1 atm. As apparent from Fig 2, equilibrium temperature increase with decreasing MnO content. The liquidus temperature, at which slag is fully liquid, play important role to facilitate reduction reactions. Presence of oxides viz. CaO, MgO, Al₂O₃ and SiO₂ and their mass ratios influence liquidus of slag and thereby control the reduction of MnO and SiO₂.




Fig.2. Complete equilibrium relations for ternary MnO-SiO₂-CaO slags in equilibrium with Mn-Si-C_{sat} alloys at P_{CO}=1atm [Ding and Olsen, 2000]. Roghani et al. [2003] carried out the equilibrium studies between “MnO”-CaO-(Al₂O₃+SiO₂) slag (at Al₂O₃/SiO₂ weight ratio of 0.55) and Mn-Si alloy (Fig 3). Slag liquidus was found to be inversely related to MnO content of slag at certain CaO%. For example, at 20% CaO in slag, liquidus

importance to maintain appropriate concentrations of basic oxides as well as silica to yield desired grade of SiMn alloy.

It is always advantageous to simulate the viscosities of equilibrium slags, before proceeding to smelting, to predict slag-metal separation behaviour. A number of semi-empirical models have been developed to estimate the slag viscosities in the case of multicomponent slags [Setharaman et al., 2004]. Studies by Muller and Erwee [2011] on blast furnace type slags showed that viscosity increased with the basicity of slag at 1500 °C due to formation of solids at high basicities. Studies by Tang and Olsen [2007] on MnO-SiO₂-CaO-MgO-Al₂O₃ slag showed that viscosities of liquidus composition at liquidus temperature is of great practical importance.




Fig.4. Calculated viscosities along the liquidus with fixed A/S ratio and basicity (solid lines). The dotted lines represent the corresponding temperature in the solid lines [Tang and Olsen, 2007]

Fig 4 shows the viscosity as function of liquidus MnO content at different slag basicities. The calculated liquidus temperature vs. MnO content relations is shown as dotted lines in the figure. It is evident that an acid slag operation tends to increase the viscosity of “primary liquid slag”. This is primary due to the abundance of SiO₂ in more acidic slag. The viscosity of pure liquid SiO₂ is several orders of magnitudes higher than that of pure alumina and other oxides. Increasing MnO content, on one hand breaks the network and on the other hand increases liquidus temperature, results in the decrease in viscosity of liquid slag. This shows that the viscosity is not “sensitive” to the MnO content.

3. LEACHED MANGANESE NODULE RESIDUE SMELTING

Earlier paper by present authors [Randhawa et al., 2011] reported preparation of various charge mixes containing leached manganese nodules residue (WMNR), Mn ore (MO), quartzite, dolomite, coke etc. and smelting in 50 kVA electric arc furnace to produce standard grade silicomanganese (Si16Mn63, Table 1). The R ratio was fixed at 1.8, which has been reported to be optimum by Eissa et al [2004]. The liquidus for CaO-MgO-Al₂O₃-SiO₂-MnO slag system was calculated using FACTSage 6.1 slag database, shown as pseudo-ternary diagram in Fig 5. The fixed basicity lines for 0.16, 0.2 and 0.3 are also drawn. In Fig 5, the liquidus MnO content appears to decrease with the basicity of initial slag. It also appears that slag would contain higher liquidus MnO with increasing Mn/Si at fixed basicity (e.g. B = 0.2) line. From Fig 5, it is apparent that in the lower MnO region (10 wt.%), increase in slag basicity beyond 0.8 give rise to high slag liquidus changing from 1350 °C to 1850 °C.




Fig.5. Calculated (FACTSage) Slag-liquid projection at different temperatures for pseudo-ternary slag system (CaO+MgO+Al₂O₃)-SiO₂-MnO, also showing the basicity lines for 0.16, 0.2 and 0.3




Fig.6. Iso-viscosity line for (CaO+MgO)-(SiO₂+Al₂O₃)-MnO slag system with 12.5 mass % Al₂O₃ and 15 mass % MgO using Urbains [Setharaman et al., 2004] model.

3.1 Role of charge basicity in leached manganese nodule residue smelting

An increase in the basicity of the slag increases the a_{MnO} (basic oxide) decreases the a_{SiO_2} and hence, more MnO and less SiO₂ are reduced with increasing basicity of slag, which is also evident from a_{MnO} and a_{SiO_2} of initial slag calculated using Factsage 6.1, shown in Fig. 7. Thus, it is apparent that increasing basicity decreases equilibrium MnO and increases SiO₂ in slag [Turkdogan, 1983]. Therefore, optimum charge basicity is of utmost importance while smelting the MnO and SiO₂ together.




Fig.7. Calculated a_{MnO} and a_{SiO_2} in the initial slags using Factsage.

The optimum charge mix basicity has been found to be 0.2 [Randhawa et al., 2011], which produced maximum metallic yield and Mn & Si recovery, as shown in Table 1 and Fig.8 (a) & (b) respectively. The standard grade silicomanganese alloy has been produced from charge mix having basicity (B) of 0.2 and 0.3 but basicity of 0.16 produced off-grade with less manganese content (Table 1). The maximum metallic yield (Table 1) and Mn and Si recoveries were obtained at charge 0.2 basicity (Fig. 9 a and b). This can be attributed to the manganese distribution ratio (L_{Mn} i.e. ratio of mass of Mn in slag to that in alloy) on these charge basicities (Fig. 9), which shows sharp decrease with the increase of charge basicity from 0.16 to 0.2, which mean more Mn is transferred to alloy phase. Thereafter, nominal decrease in L_{Mn} was found with charge basicity of 0.3. Thus, charge mix basicity of 0.2 gave rise to better slag composition to yield maximum metallic yield and Mn & Si recovery.

Table-1: Comparison of alloy composition obtained from smelting of charge mixes at different basicity with target silicomanganese grade (Si16Mn63)

Sl no./ Grade	Initial Charge basicity	% Metallic yield	% , by mass					
			Mn	Si	C	S	P	Fe
Si16Mn63	----	----	60-65	14-17	2.5 _{max.}	0.03 _{max.}	0.3 _{max.}	balance
1	0.16	63.41	58.14	15.72	2.10	0.025	0.26	22.85
2	0.2	73.37	61.27	17.66	1.9	0.016	0.12	17.81
3	0.3	62.14	61.71	14.49	2.34	0.014	0.12	19.75

Table-2: Chemical composition of slags obtained from smelting of charge mix with different basicities

Initial Charge basicity	% , by mass						Final slag basicity
	CaO	MgO	Al ₂ O ₃	SiO ₂	MnO	FeO	
0.16	9.25	12.20	18.25	42.80	16.75	1.20	0.50
0.20	10.14	16.08	19.38	41.75	11.66	0.4	0.63
0.30	13.29	18.39	17.63	42.22	6.57	0.89	0.75




Fig.8. Effect of charge mix basicity on recovery of (a) Mn and (b) Si in alloy




Fig.9. Effect of charge mix basicity on Mn distribution between slag and alloy

The maximum metallic yield and Mn recovery at charge mix basicity of 0.2 can be explained by the final slag compositions given in Table 2. The slag composition obtained in the smelting of charge basicity 0.16, 2.0 and 3.0 give rise to final slag basicity of 0.50, 0.63 and 0.75, respectively as calculated from Table 2. Increasing charge basicity from 0.16 to 0.2 results in higher reduction of MnO and higher Mn and Si recoveries obtained (Fig. 9 a and b). Increasing charge basicity to 0.3 should have resulted in higher Mn and Si recovery. In contrast, lower metallic yield and manganese recovery with charge basicity 0.3 are obtained, which indicates possible role of insufficient slag fluidity causing less reduction and distribution of Mn and Si between alloy and slag. This is also evident from final slag basicity i.e. 0.75 falling in the higher liquidus region in Fig. 5. Thus, presence of solids in the final slag obtained from smelting of charge with basicity 0.3 produced lower recoveries and yield.

3.2 Effect of CaF_2 addition

The chemical composition of alloys obtained from CaF_2 addition smelting trails are given in Table 3. The acidic slag in silicomanganese smelting often poses difficulties in slag-alloy separation leading to lower yield and recovery. Therefore, CaF_2 is often added in the acidic slag to decrease the viscosity. The CaF_2 breaks the SiO_2 network in the slag and improves slag fluidity. On the other hand, dissolution of CaF_2 in the slag give rise to more CaO, which increases slag basicity as well as slag liquidus. Therefore, optimum amount of CaF_2 must be ascertained before proceeding to commercial smelting trials. The CaF_2 addition made in molten charge at initial charge mix basicity of 0.2, during holding time, found to be beneficial for smelting yield and recoveries. The Mn recovery (Fig. 10(a)) increased with addition of CaF_2 up to 4% of WMNR:MO blend but resulted in decreasing Mn recovery with 6% CaF_2 addition. The Si recovery (Fig. 10(b)) has also been found to increase with addition of 2% CaF_2 and thereafter decreased with further addition of CaF_2 . The decreasing manganese distribution ratio (L_{Mn}) has been obtained up to 4% of CaF_2 addition (Fig. 11), which depicts the proper slag metal separation. Addition of 6% CaF_2 showed increased manganese distribution ratio (L_{Mn}).

Table-3: Chemical compositions of alloys and metallic yield of smelting trials carried out with varying addition of CaF₂ during holding period.

Designation	CaF ₂ , grams	% Metallic yield	%, by mass					
			Mn	Si	C	S	P	Fe
Si16Mn63	----	----	60-65	14-17	2.5 _{max.}	0.03 _{max.}	0.3 _{max.}	balance
1	0	73.37	61.27	17.66	1.9	0.015	0.12	17.81
2	20	78.45	60.77	20.07	1.48	0.0043	0.14	16.6
3	40	81.86	61.88	17.44	2.08	0.021	0.12	17.39
4	60	79.67	59.8	18.64	2.07	0.0075	0.13	18.49

Table-4: Chemical composition of slags obtained from smelting of charge mix with different CaF₂ additions

CaF ₂ addition (% of WMNR+ MO)	%, by mass						Final slag basicity
	CaO	MgO	Al ₂ O ₃	SiO ₂	MnO	FeO	
2.0	14.29	15.19	17.07	39.94	13.45	0.97	0.73
4.0	16.10	13.25	15.19	38.49	12.97	0.72	0.76
6.0	20.04	12.56	14.88	39.97	9.38	0.43	0.82




Fig.10. Effect of CaF₂ addition on recovery of (a) Mn and (b) Si in alloy




Fig.11. Effect of CaF₂ addition on Mn distribution between slag and alloy

Though Mn distribution ratio (L_{Mn}) increased with CaF₂ addition, lower metallic yield and Mn and Si recoveries were obtained at 6% CaF₂ addition. This may be attributed to increase in final slag basicity due to increasing CaO content in slag, as shown in Table 4. Further addition of CaF₂ i.e. 6% increased the slag basicity to 0.82, which has very high liquidus (>1850 °C) as shown in Fig 5.

4. CONCLUSIONS

Smelting studies have shown that leached manganese nodule residue (WMNR) is a potential raw material for producing standard grade silicomanganese alloy (Si16Mn63). The thermodynamics and viscosity aspects of silicomanganese smelting have been evaluated and applied to WMNR smelting. The higher metallic yield and Mn recoveries at charge mix basicity of 0.2 were satisfactorily correlated to slag liquidus calculated using software Factsage. Addition of CaF₂ up to 4% of WMNR+Mn ore blend during holding time was found to be beneficial to metallic yield and Mn recovery. Further CaF₂ addition increased the slag liquidus resulting in lower metallic yield and Mn and Si recoveries. Thus thermodynamic and viscosity studies of WMNR

smelting has been found to be useful for charge mix optimisation and maximisation of metal recovery in the production silicomanganese from manganese nodules leached residue.

ACKNOWLEDGEMENT

The authors thankfully acknowledge the permission from Director, CSIR-NML, Jamshedpur to publish this paper.

REFERENCES

- Barin I. 1989, "Thermochemical data of pure substances". VCH Verlagsgesellschaft mbH, D-6940 Weinheim, Part 2.
- Cengizler H., Eric R.H. and Reuter M.A 1997, "Modelling of the activities and activity coefficients of Mn in ferromanganese slags". In Proc. 5th International Conference on Molten Slags, Fluxes and Salts'97, Australia, Iron and Steel Society, Warrendale, PA, pp. 75-90.
- Cengizler H. 2003, "The manganese distribution between the metal and slag at 1500 °C in ferromanganese and silicomanganese production. Ore Dressing/CEVHER HAZIRLAMA, 9, 1-5.
- Chaichenko A.A., Kashakashvili G.V., Arabuli I.A., Akhabadze T.V., Tskitashvili Yu.A., Veretennikov O.K., Murakhovskii V.V. and Sedov A.A., 1986, "Smelting of silicomanganese". Otkrytiya, Izobret, 44, 82.
- Ding W. and Olsen S. E. 2000, "Manganese and silicon distribution between slag and metal in silicomanganese production". ISIJ Int., 40(9), 850-856.
- Eissa M., Fathy A., Ahmed A., El-Mohammady A. and El-Fawakhary K. 2004, "Factors affecting silicomanganese production using manganese rich slag in the charge". In Proc. Conference of Tenth International Ferroalloys Congress, INFACON X (The South African Institute of Mining and Metallurgy: South Africa), pp 245-253.
- Emlin B.I., Pogrebnyak A.I., Vodin I.I., Matyashenko N.K., Belan V.D., Sarankin V.A., Chnpakhin Yu.M., Shaposhnik I.I. and Shchedrovitskii V.Ya. 1986, "Silicomanganese smelting", Otkrytiya Izobret, 30, 86-88.
- Jana R.K., Pandey B.D. and Premchand 1999, "Ammoniacal leaching of roast reduced deep-sea manganese nodules". Hydrometallurgy, 53, 45-56.
- Kor G.J.W. 1979, "Equilibria between liquid Mn-Si alloys and MnO-SiO₂-CaO-MgO slags". Metall. Mater. Trans. B, 10B, 367-364.
- Kubaschewsky O., Evans E.U. and Alcock C.B. 1979, "Metallurgical Thermochemistry". 5th ed., Pergamon Press, Oxford.
- Muller J. and Erwee M. 2011, "Blast furnace control using slag viscosities and liquidus temperature with phase equilibria calculations". In Proc. Southern African Pyrometallurgy 2011, ed. R.T. Jones & P. den Hoed, Southern African Institute of Mining and Metallurgy, pp. 309-326.
- Nikolaev V.I. 1974, "Selection of optimum slag basicity in ferromanganese production". Steel in USSR, 4, 299-302.
- Olsen S.E., Tangstad M. and Lingstad T. 2007, "Production of Manganese ferroalloys". Tapir Academic Press: Trondheim, Norway.
- Richard P.L. 1978, "Hazardous Solid Waste from Metallurgical Industries". Environmental Health Perspectives, 27, 251-260.
- Roghani G., Jak E. and Hayes P. 2003, "Phase-equilibrium data and liquidus for the system "MnO"-CaO-Al₂O₃-SiO₂ at Al₂O₃/SiO₂ of 0.55 and 0.65". Metall Mater Trans B, 34B, 173-182.
- Randhawa, N.S., Jana R. K. and Das N.N. 2011, "Manganese nodules residue: potential raw material for FeSiMn production", In Proc.15th Int. Conf. on Non-ferrous Metal, Kolkata, India, pp. Tech. 9/1-Tech.9/9
- Swinbourne D. R., Rankin W. J. and Eric R. H. 1995, "The effect of alumina in slag on manganese and silicon distribution in silicomanganese smelting". Metall Mater Trans B, 26B, 59-65.
- Seetharaman S., Mukai K. and Sichen Du 2004, "Viscosities of slags - An overview". In Proc. VII International Conference on Molten Slags Fluxes and Salts, The South African Institute of Mining and Metallurgy, pp. 31-42.
- Turkdogan E. T. 1983. "Physico-chemical properties of molten slags and glasses", The Metal Society, London.
- Tang K. and Olsen S.E. 2006, "Computer simulation of equilibrium relations in manganese ferroalloy production". Metall Mater Trans B, 37B, 599-606.
- Tang K. and Tangstad M. 2007, "Modelling viscosities of ferromanganese slags". in Proceedings Conference of Tenth International Ferroalloys Congress (INFACON XI), New Delhi, 344-357.
- Tang, K. And Olsen, S. E., 2007, "The effect of alumina in ferromanganese slag", in Proceedings Conference of Tenth International Ferroalloys Congress (INFACON XI) (New Delhi, India), pp 335-343.
- Voronov V. A. and Gavrilov V. A. 1996, "Efficiency of technology for smelting the silicomanganese during utilization of secondary resources". Publ: Russia, STAL' 1, 33-34.
- Zhang H. T., Liu Y.J., Zhao D.X., Wang S.M., Wang S.Z., Xi J.S. and Wu K.H. 1995, "Silicomanganese smelting using quartzite-coke as a reductant". IRON STEEL (CHINA) 30(1), 63-66.