



**UNIVERZITET CRNE GORE**  
**GRAĐEVINSKI FAKULTET**  
**U PODGORICI**

**PETI INTERNACIONALNI NAUČNO-STRUČNI SKUP**  
***GRAĐEVINARSTVO - NAUKA I PRAKSA***



**ZBORNİK RADOVA**

**ŽABLJAK, 17-21. FEBRUARA 2014.**

**ISBN 978-86-82707-23-3**

**ZBORNİK RADOVA GNP 2014**

*Izdavač*

**UNIVERZITET CRNE GORE  
GRAĐEVINSKI FAKULTET**

*Za izdavača*

**Prof.dr Miloš Knežević**

*Urednik*

**Prof.dr Miloš Knežević  
Doc.dr Biljana Šćepanović**

*Uređivački odbor*

**Prof.dr Miloš Knežević  
Doc.dr Biljana Šćepanović  
Mr Mladen Gogić  
Mr Strahinja Pavlović  
Goran Pavlović**

*Tehnički urednik*

**Goran Pavlović**

*Tiraž*

**400 primjeraka**

CIP - Каталогизacija y publikaciji  
Национална библиотека Црне Горе, Цетиње

ISBN 978-86-82707-23-3  
COBISS.CG-ID 24170256

*Sva prava zadržava izdavač i autori*



*Marina Četković<sup>1</sup>, Đorđe Vuksanović<sup>2</sup>*

## **TERMIČKA ANALIZA LAMINATNIH KOMPOZITNIH I SENDVIČ PLOČA PRIMENOM SLOJEVITOG KONAČNOG ELEMENTA**

### **Rezime**

U ovom radu analiziran je kvazi statički odgovor laminatnih kompozitnih i sendvič ploča ploča izloženih temperaturnom polju linearno promenljivom po debljini i sinusoidalno promenljivom u ravni. Matematički model, zasnovan na slojevitom polju pomeranja koje je predložio Reddy [15], formulisani je koristeći pretpostavke o geometrijskoj, materijalnoj i statičkoj linearnosti problema. Princip virtualnih pomeranja je primenjen za dobijanje slabe forme matematičkog modela. Slaba forma je diskretizovana koristeći izoparametarsku aproksimaciju konačnim elementom. Originalan MATLAB računski program je korišćen za analizu uticaja različitih debljina ploče na termo-elastičan odgovor laminatnih kompozitnih i sendvič ploča. Tačnost numeričkog modela je potvrđena poređenjem sa rešenjima iz literature.

### **Ključne reči**

Termička analiza, kompozitna ploča, slojeviti model, konačni element

## **THERMAL ANALYSIS OF LAMINATED COMPOSITE AND SANDWICH PLATE USING LAYERWISE FINITE ELEMENT**

### **Summary**

In this paper the quasi static response of laminated composite and sandwich plates subjected to lineary varaying through the thickness and sinusoidal distributed in plane temperature field, is analyzed. Mathematical model, based on layer-wise displacement field of Reddy [15], is formulated using small deflection linear-elasticity theory. The principle of virtual displacements (PVD) is used to obtain the weak form of the mathematical model. The weak form is discretized utilizing isoparametric finite element approximation. The originally coded MATLAB program is used to investigate the influence of plate thickness on thermo-elastic response of laminate composite and sandwich plates. The accuracy of the numerical model is verified by comparison with the available results from the literature.

### **Key words**

Thermal analysis, layer wise model, composite plates, finite element

---

<sup>1</sup> Docent, Dr Marina Četković, dipl. građ. inž., Građevinski fakultet u Beogradu, Srbija, [marina@grf.bg.ac.yu](mailto:marina@grf.bg.ac.yu)

<sup>2</sup> Profesor, Dr Đorđe Vuksanović, dipl. građ. inž., Građevinski fakultet u Beogradu, Srbija, [george@grf.bg.ac.yu](mailto:george@grf.bg.ac.yu)

## 1. INTRODUCTION

Multi layered composite structures are widely used in high-temperature environments such as aerospace applications, nuclear reactors and chemical plants, which attracted considerable investigations of researchers in order to meet an optimal design parameters.

In the presently published studies, generally two major problems are have appeared, when studying thermal problem in composite materials. The first is concerned with definition of realistic temperature distribution taking into account the material in use and second is formulating an appropriate material structural model. In other words, homogenization, have to be performed on two scales, the temperature and the structural scale.

On the temperature scale, it is well known that temperature distribution is three-dimensional and time dependent. This demand analyzing all three heat transfer mechanisms, i.e. heat conduction, radiation and convection. The heat conduction problem, described by second Fourier's law, results in solving nonlinear second order differential equation, in order to find actual nonlinear temperature distribution. Nonlinearity of temperature field comes from temperature dependent thermal conductivities of multi-layered structure.

On the structural scale, nonlinear temperature field results in geometrically and materially nonlinear response of composite structure. Namely, high temperature regime, accompanied by large deflections and large deformations may cause deviation from initial structural configuration and the change of its geometry. On the other hand, the thermal stresses accompanying the unsteady heating may cause thermal fatigue and considerable plastic strains may lead to complete or progressive destruction of the composite structures.

In order to find the appropriate mathematical model which will meet the requirement of two above mentioned scales, many papers have been reported to date. They generally attend to adjust present Laminated Plate Theories, initially formulated for mechanical loading, to meet the complex nature of temperature field. The key factor in understanding laminate plate deformation due to thermal load is the coefficients of thermal expansion. Namely, the coefficient of thermal expansions for selected orthotropic lamina in transverse direction is much larger than those in the in-plane direction. This implies that standard assumption of constant transverse deflection is acceptable in case of mechanical loading, but may become invalid if the load is thermal. On the stresses level, different thermal expansion coefficients will produce high transverse and normal stresses at the interfaces between adjacent layers, thus a realistic prediction of transverse normal stress and transverse shear stresses become a key issue, in obtaining response of composite plate to thermal load. Depending on how the two mentioned displacement and/or stress field are assumed, mathematical models for thermal analysis of composite laminates have been formulated using three dimensional theory of elasticity, Equivalent Single Layer Theories, Layer Wise Theories or Zig-Zag theories.

Tungikar and Rao [1] obtained 3D elasticity solution for temperature distribution and thermal stresses in simply supported rectangular laminates. The actual temperature distribution across the thickness of the laminate is evaluated by solving the ordinary differential equations (ODEs) of heat conduction without internal heat generation. Savoia and Reddy [2] also solved transient heat conduction equation for exact temperature

distribution across the thickness of laminates for 3D stress analysis of symmetric four-layered square laminate subjected to sudden uniform temperature change. Based on the three-dimensional elasticity solution described in the references of Pagano [3], Noor et al. [4] obtained the three-dimensional thermo elasticity solutions to compare with those of the two- and three-dimensional finite element models which considered only the effect of transverse shear stresses. In order to reduce computational cost of three-dimensional theories, and reach acceptable accuracy in the field of application, several solutions of thermal problems in composites have been proposed using Equivalent Single Layer, which are Classical Laminated Plate Theory (CLPT), First-order Shear Deformation Theory (FSDT) and Higher-order Shear Deformation Theory (HSDT).

Using the CLPT based on the Kirchhoff hypothesis, Wu and Tauchert [5] studied the thermal deformation and stress results in symmetric and antisymmetric laminates. However, this kind of approach is inaccurate for laminated plates with relatively soft transverse shear modulus. The inaccuracy is due to neglecting the transverse shear and normal strains in the composite laminates.

To take into account the effects of low ratio of transverse shear modulus to the in-plane modulus, the FSDT has been developed by Rolfes et al. [6]. Due to assumed displacement field, the transverse shear strains are constant through the plate thickness, obtained by the direct constitutive equation approach and the shear correction factors have to be adopted. However, the shear correction factors are not easy accurately to predict and a number of global higher-order shear deformation theories have been developed for thermal analysis.

Kant and Khare [7] developed a simple Co isoparametric finite element displacement model based on HSDT formulations for the analysis of symmetric and antisymmetric laminates subjected to thermal gradient. Rohwer et al. [8] removed the deficiencies in the FSDT by incorporating third and fifth order displacement approximations through the plate thickness. In order to study the effects of the higher-order displacement terms on thermal stresses Matsunaga [9] proposed a ninth-order theory for analysis of thermal behaviors of laminated composite and sandwich plates, in which the in-plane displacement field consists of a ninth-order polynomial in global thickness coordinate  $z$  whereas the transverse deflection is represented by an eighth-order polynomial of global coordinate  $z$ . Moreover, the ninth-order theory is extended to compute critical temperatures in cross-ply laminated composite plates and shells subjected to thermal loads.

Although results of the global ESL plate theories may be sufficiently accurate for predicting global responses, their results may exhibit considerable errors in predicting the local behavior. In such cases, layerwise plate theories have been proposed to overcome some of the shortcomings of the equivalent single layer theories [10]. The layer-wise theories assume separate field expansions within each layer, thus being able to more accurately predict plate behavior due to complex, generally nonlinear temperature field. However, as the number of layers in the laminates increase, layerwise models become computationally expensive for global laminate analysis.

In order to retain the benefits of less computational times of the equivalent single-layer theories and the accuracy of the layerwise theories, zigzag theories with linear or high-order layerwise zigzag functions were proposed. By imposing the continuity conditions of the transverse shear stresses, the number of unknowns in these models are independent on the number of the layers. Kapuria and Achary [11] presented a third-order zig-zag theory for the sandwich plates. Ganapathi et al. [12] investigated the nonlinear

dynamics behavior of the sandwich plates based on a zigzag theory. In addition to the contact conditions on the interlaminar shears, those on the transverse normal stress and stress gradient have been also fulfilled.

Since, there are so many papers on thermal analysis using layerwise plate theories, and limited 3D elasticity solutions are available, in this paper a layerwise finite element for thermo elastic analysis is formulated. The quasi static thermo elastic problem with linear through the thickness and sinusoidal in plane variation of the temperature field is studied. The temperature field is incorporated into the layerwise mechanical material model, which assumes layerwise variation of in-plane displacements and constant transverse displacement. With assumed displacement field, linear strain displacement relations and linear thermo mechanical materials properties, the governing equilibrium equations are formulated using principle of virtual displacements (PVD) and weak form is obtained. The weak form is discretized using isoparametric finite element approximation. The original MATLAB program is coded and used to investigate the influence of different side to thickness ratio on thermo elastic response of laminated composite and sandwich plates. The accuracy of the numerical model is verified by comparison with the available results from the literature.

## 2. THEORETICAL FORMULATION

### 2.1 DISPLACEMENT FIELD

In the LW theory of Reddy [15] in-plane displacements components ( $u, v$ ) are interpolated through the thickness using 1D linear Lagrangian interpolation function  $\Phi^I(z)$ , while transverse displacement component  $w$  is assumed to be constant through the plate thickness.

$$\begin{aligned} u_1(x, y, z) &= u(x, y) + \sum_{I=1}^{N+1} U^I(x, y) \cdot \Phi^I(z) \\ u_2(x, y, z) &= v(x, y) + \sum_{I=1}^{N+1} V^I(x, y) \cdot \Phi^I(z), \\ u_3(x, y, z) &= w(x, y) \end{aligned} \quad (1)$$

### 2.2 STRAIN-DISPLACEMENT RELATIONS

The Green Lagrange strain tensor associated with the displacement field Eq.(1) is computed using linear strain-displacement:

$$\begin{aligned} \varepsilon_{xx} &= \frac{\partial u_1}{\partial x} = \frac{\partial u}{\partial x} + \sum_{I=1}^{N+1} \frac{\partial U^I}{\partial x} \Phi^I, \\ \varepsilon_{yy} &= \frac{\partial u_2}{\partial y} = \frac{\partial v}{\partial y} + \sum_{I=1}^{N+1} \frac{\partial V^I}{\partial y} \Phi^I, \end{aligned}$$

$$\gamma_{xy} = \frac{\partial u_1}{\partial y} + \frac{\partial u_2}{\partial x} = \frac{\partial u}{\partial y} + \frac{\partial v}{\partial x} + \sum_{l=1}^{N+1} \left( \frac{\partial U^l}{\partial y} + \frac{\partial V^l}{\partial x} \right) \Phi^l, \quad (2)$$

$$\gamma_{xz} = \frac{\partial u_1}{\partial z} + \frac{\partial u_3}{\partial x} = \sum_{l=1}^{N+1} U^l \frac{d\Phi^l}{dz} + \frac{\partial w}{\partial x},$$

$$\gamma_{yz} = \frac{\partial u_2}{\partial z} + \frac{\partial u_3}{\partial y} = \sum_{l=1}^{N+1} V^l \frac{d\Phi^l}{dz} + \frac{\partial w}{\partial y}.$$

With linearly assumed strain displacement kinematics, an orthotropic linear Hook's material is assumed for each lamina, to formulate constitutive equations as:

$$\{\boldsymbol{\sigma}\}^{(k)} = [\mathbf{Q}]^{(k)} \cdot (\{\boldsymbol{\varepsilon}\}^{(k)} - \{\boldsymbol{\alpha}\}^{(k)} \Delta T). \quad (3)$$

where  $\boldsymbol{\sigma}^{(k)} = \{\sigma_{xx} \ \sigma_{yy} \ \tau_{xy} \ \tau_{xz} \ \tau_{yz}\}^{(k)T}$  and  $\boldsymbol{\varepsilon}^{(k)} = \{\varepsilon_{xx} \ \varepsilon_{yy} \ \gamma_{xy} \ \gamma_{xz} \ \gamma_{yz}\}^{(k)T}$  are stress and strain components respectively,  $\mathbf{Q}_{ij}^{(k)}$  and  $\boldsymbol{\alpha}^{(k)} = \{\alpha_{xx} \ \alpha_{yy} \ \alpha_{xy} \ 0 \ 0\}^{(k)T}$  are transformed reduced elastic stiffness [16] and coefficients of thermal expansion, of k-th lamina in global coordinates, while  $\Delta T$  is prescribed temperature field.

### 2.3 EQUILIBRIUM EQUATIONS

Using assumed displacement field, linear strain displacement relations and Hook's linear material, the principle of virtual displacements is employed to derive the governing equilibrium equations:

$$\delta\pi = \int_{\Omega} \left\{ N_{xx} \frac{\partial \delta u}{\partial x} + \sum_{l=1}^N N_{xx}^l \frac{\partial \delta U^l}{\partial x} + N_{yy} \frac{\partial \delta v}{\partial y} + \sum_{l=1}^N N_{yy}^l \frac{\partial \delta V^l}{\partial y} + N_{xy} \left( \frac{\partial \delta u}{\partial x} + \frac{\partial \delta v}{\partial y} \right) + \sum_{l=1}^N N_{xy}^l \left( \frac{\partial \delta U^l}{\partial y} + \frac{\partial \delta V^l}{\partial x} \right) + Q_x \frac{\partial \delta w}{\partial x} + \sum_{l=1}^N Q_x^l \delta U^l + Q_y \frac{\partial \delta w}{\partial y} + \sum_{l=1}^N Q_y^l \delta V^l \right\} dx dy = 0 \quad (4)$$

where internal force vectors are:

$$\begin{Bmatrix} N_{xx} \\ N_{yy} \\ N_{xy} \\ Q_x \\ Q_y \end{Bmatrix} = \sum_{k=1}^n \int_{z_k}^{z_{k+1}} \begin{Bmatrix} \sigma_{xx} \\ \sigma_{yy} \\ \tau_{xy} \\ \tau_{xz} \\ \tau_{yz} \end{Bmatrix} dz, \quad \begin{Bmatrix} N_{xx}^l \\ N_{yy}^l \\ N_{xy}^l \\ Q_x^l \\ Q_y^l \end{Bmatrix} = \sum_{k=1}^n \int_{z_k}^{z_{k+1}} \begin{Bmatrix} \sigma_{xx} \\ \sigma_{yy} \\ \tau_{xy} \\ \tau_{xz} \\ \tau_{yz} \end{Bmatrix} \left\{ \Phi^l \ \Phi^l \ \Phi^l \ \frac{d\Phi^l}{dz} \ \frac{d\Phi^l}{dz} \right\} dz \quad (5)$$

### 3. FINITE ELEMENT MODEL

The governing equations (4) are discretized using GLPT finite element [16]. Over each element, the displacements are expressed as linear combination of shape functions and primary nodal variables as:

$$\begin{Bmatrix} \mathbf{u} \\ \mathbf{v} \\ \mathbf{w} \end{Bmatrix}^e = \begin{Bmatrix} \sum_{j=1}^m \mathbf{u}_j \Psi_j \\ \sum_{j=1}^m \mathbf{v}_j \Psi_j \\ \sum_{j=1}^m \mathbf{w}_j \Psi_j \end{Bmatrix}^e = \sum_{j=1}^m [\Psi_j]^e \{\mathbf{d}_j\}^e \begin{Bmatrix} \mathbf{U}^I \\ \mathbf{V}^I \end{Bmatrix}^e = \begin{Bmatrix} \sum_{j=1}^m \mathbf{U}_j^I \Psi_j \\ \sum_{j=1}^m \mathbf{V}_j^I \Psi_j \end{Bmatrix}^e = \sum_{j=1}^m [\bar{\Psi}_j]^e \{\mathbf{d}_j^I\}^e \quad (6)$$

where  $\{\mathbf{d}_j\}^e = \{\mathbf{u}_j^e \ \mathbf{v}_j^e \ \mathbf{w}_j^e\}^T, \{\mathbf{d}_j^I\}^e = \{\mathbf{U}_j^I \ \mathbf{V}_j^I\}^T$  are displacement vectors, in the middle plane and I-th plane, respectively,  $\Psi_j^e$  are interpolation functions, while  $[\Psi_j]^e, [\bar{\Psi}_j]^e$  are interpolation function matrix for the  $j$ -th node of the element  $\Omega^e$ , given in [16].

Substituting element displacement field Eq.(6) in to governing equation (4), the following finite element equations are obtained:

$$[\mathbf{K}]^e \cdot \{\mathbf{d}\}^e = \{\mathbf{f}\}^e \quad (7)$$

where stiffness matrix is given in [16], while force vectors are:

$$\begin{aligned} \{\mathbf{f}^0\}^e &= \iint_{\Omega^e} [\mathbf{H}_i]^T \sum_{k=1}^n \int_{z_k}^{z_{k+1}} [\mathbf{Q}]^{(k)} \{\alpha\}^{(k)} \Delta T dz dx dy \\ \{\mathbf{f}^I\}^e &= \iint_{\Omega^e} [\bar{\mathbf{H}}_i]^T \sum_{k=1}^n \int_{z_k}^{z_{k+1}} [\mathbf{Q}]^{(k)} \{\alpha^I\}^{(k)} \Delta T dz dx dy \end{aligned} \quad (9)$$

where  $\{\alpha^I\}^{(k)} = \{\alpha_{xx} \ \Phi^I \ \alpha_{yy} \ \Phi^I \ \alpha_{xy} \ \Phi^I \ 0 \ 0\}^{(k)}$ .

### 4. EXAMPLE

To validate the results of the present theory the following material properties of laminated composite and sandwich plates have been used:

Material (1) laminated plate 0/90/0:

$$E_L / E_T = 25, G_{LT} / E_T = 0.5, G_{TT} / E_T = 0.2, \nu_{LT} = \nu_{TT} = 0.25, \alpha_T / \alpha_L = 1125 \quad (10)$$

Material (2) laminated plate 0/90:

$$E_L / E_T = 15, E_T = 10 \text{ GPa}, G_{LT} / E_T = 0.5, G_{TT} / E_T = 0.3356, \nu_{LT} = 0.30, \nu_{TT} = 0.49, \alpha_L / \alpha_0 = 0.015, \alpha_T / \alpha_0 = 0.015 \quad (11)$$

Material (3) sandwich plate 0/core/0:



(a) Face sheets ( $h/5 \times 2$ )

$$E_L = 200 \text{ GPa}, E_T = 8 \text{ GPa}, G_{LT} = 5 \text{ GPa}, G_{TT} = 2.2 \text{ GPa}, \nu_{LT} = 0.25, \nu_{TT} = 0.35, \alpha_L = -2 \times 10^{-6} / \text{K}, \alpha_T = 50 \times 10^{-6} / \text{K} \quad (12)$$

(b) Core material ( $3h/5$ )

$$E_L = 1 \text{ GPa}, E_T = 2 \text{ GPa}, G_{LT} = 0.8 \text{ GPa}, G_{TT} = 3.7 \text{ GPa}, \nu_{LT} = 0.25, \nu_{TT} = 0.35 \alpha_L = \alpha_T = 30 \times 10^{-6} / \text{K}$$

The plates with simply supported boundary conditions are studied subjected to temperature field:

$$\Delta T(x, y, z) = \frac{2T_0}{h} z \cdot \sin\left(\frac{\pi x}{a}\right) \cdot \sin\left(\frac{\pi y}{b}\right) \quad (13)$$

Transverse displacement is given in the following nondimensional form:

$$\bar{w} = \frac{w}{h\alpha_L T_0 (a/h)^2} \text{ for plate } 0/90/0, \text{ and } \bar{w} = \frac{w}{h\alpha_L T_0} \text{ for laminated plate } 0/90 \text{ and sandwich}$$

plate. Results of the present model are compared with available ones from the literature and are given in Table 1.

*Table 1. Normalized transverse displacement for laminated composite and sandwich plates subjected to thermal loading*

	$\bar{w}$			
	a/h	Present	3D <sup>[3]</sup>	HSDT
0/90 <sup>[13]</sup>	5	1.138	0.997	1.070
	10	4.317	4.120	4.171
	20	15.423	16.600	16.567
0/90/0 <sup>[14]</sup>	2	100.463	98.121	96.790
	4	44.608	42.020	42.690
	10	16.014	16.890	17.390
0/core/0 <sup>[9]</sup>	4	10.097	9.816	8.793
	8	18.050	19.870	18.780
	12	23.350	26.960	25.640

## 5. CONCLUSION

In this paper laminated layerwise finite element model for thermo elastic analysis of laminated composite and sandwich plates is presented. Finite element solution is incorporated into an original MATLAB computer program, which is used to analyze laminated composite and sandwich plates with different lamination schemes and different plate thickness. Results of the analysis have shown that the present layerwise model gives acceptable results for laminated composite plates, while the error is increased for sandwich

plates, when compared to three dimensional and higher order plate theories. The reason for this may be neglecting transverse normal strains, which become an important factor especially for highly anisotropic sandwich plates subjected to thermal environment. Finally, the presented results have shown the applicability and constrains of present layerwise finite element model for thermal load analysis, which may serve as a benchmark for future investigations.

**Acknowledgements** The authors are thankful for the financial support received by the Ministry of Education and Science of the Republic of Serbia, Project TP 36048.

## 6. REFERENCES

- [1] Tungikar V.B, Rao K.M, Three-dimensional exact solution of thermal stresses in rectangular composite laminate, *Compos Struct*, 1994, Vol. 27, pp. 419–30
- [2] Savoia M, Reddy J.N, Three-dimensional thermal analysis of laminated composite plates, *Int J Solids Struct*, 1995, Vol. 32, pp. 593–608
- [3] Pagano N.J, Exact solutions for rectangular bidirectional composites, *J Compos Mater*, 1970, Vol. 4, pp. 20–34
- [4] Noor A.K, Kim Y.H, Peters J.M, Transverse shear stresses and their sensitivity coefficients in multilayered composite panels, *AIAA J*, 1994, Vol. 32(6), pp. 1259–69
- [5] Wu CH, Tauchert TR, Thermoelastic analysis of laminated plates. 2: antisymmetric cross-ply and angle-ply laminates, *J Thermal Stresses*, 1980, Vol. 3, pp. 365–78
- [6] Rolfes R, Noor AK, Sparr H, Evaluation of transverse thermal stresses in composite plates based on first-order shear deformation theory, *Comput Methods Appl Mech Eng*, 1998, Vol. 167, pp.355–68
- [7] Kant T, Khare R.K, Finite element thermal stress analysis of composite laminates using a higher-order theory, *J Therm Stresses*, 1994, Vol. 17, pp. 229–55
- [8] Rohwer K, Rolfes R, Sparr, Higher-order theories for thermal stresses in layered plates, *Int J Solids Struct*, 2001, Vol. 38, pp. 3673–87
- [9] Matsunaga H. A comparison between 2-D single-layer and 3-D layerwise theories for computing interlaminar stresses of laminated composite and sandwich plates subjected to thermal loadings, *Compos Struct*, 2004, Vol. 64, pp. 161–77
- [10] Shariyat M, Thermal buckling analysis of rectangular composite plates with temperature dependent properties based on layerwise theory, *Thin-Walled Struct*, 2007, Vol. 45, 439-452
- [11] Kapuria S, Achary G.G.S, An efficient higher-order zigzag theory for laminated plates subjected to thermal loading, *Int J Solids Struct*, 2004, Vol. 41, pp. 4661–84
- [12] Ganapathi M, Patel B.P, Makhecha D.P, Nonlinear dynamic analysis of thick composite/sandwich laminates using an accurate higher-order theory, *Compos Part B*, 2004, Vol. 35, pp. 345–55
- [13] Zhen W, Wanji C, An efficient higher-order theory and finite element for laminated plates subjected to thermal loading, *Composite Structures*, 2005, Vol. 73, pp. 99-109
- [14] Kant T, Shiyekar S.M, An assessment of a higher order theory for composite laminates subjected to thermal gradient, *Compos Struct*, 2013, Vol. 96, pp. 698–707
- [15] Reddy J.N, Barbero E.J, Teply J.L, A plate bending element based on a generalized laminated plate theory, *International Journal for Numerical Methods in Engineering*, 1989, Vol. 28, pp. 2275-2299
- [16] Četković, M., Nonlinear behaviour of laminated composite plates, PhD Thesis, in serbian, Faculty of Civil Engineering in Belgrade, Serbia, 2011