



Official Journal of TESMA

# Regenerative Research

www.regres.tesma.org.my  
E-ISSN 2232-0822Tissue Engineering  
and Regenerative  
Medicine Society of  
Malaysia

Regenerative Research 3(2) 2014 65-66

## OSTEOGENIC POTENTIAL OF HUMAN ADIPOSE DERIVED STEM CELL CO-CULTURE WITH HUMAN OSTEOBLAST ON TITANIUM DIOXIDE NANOFIBROUS SURFACE

Rozila I<sup>1</sup>, Tan AW<sup>2</sup>, Pinguan-Murphy B<sup>2</sup>, Munirah S<sup>3</sup>, Chua KH<sup>1\*</sup><sup>1</sup>Department of Physiology, Faculty of Medicine, Universiti Kebangsaan Malaysia, Jalan Raja Muda Abdul Aziz, 50300 Kuala Lumpur, Malaysia<sup>2</sup>Department of Biomedical Engineering, University of Malaya, 50603 Kuala Lumpur, Malaysia<sup>3</sup>Department of Biomedical Science, Kulliyah of Allied Health Sciences, International Islamic University Malaysia, 25200 Kuantan, Pahang, Malaysia

### ARTICLE INFO

Published: 1<sup>st</sup> December, 2014\*Corresponding author  
email:  
ckienhui@hotmail.com

### KEYWORDS

TiO<sub>2</sub>  
Osteoblast  
Stem cell

### ABSTRACT

The study aims to evaluate the osteogenic potential of human adipose derived stem cell (HADSC) co-culture with human osteoblast (HOB) using selected HADSC/HOB ratio of 2:1, 1:1 and 1:2, respectively. The HADSC/HOB was seeded on Titanium dioxide (TiO<sub>2</sub>) coated with or without nanofibre substrate. The non-coated TiO<sub>2</sub> was used as control. The effects of TiO<sub>2</sub> based scaffolds on cell adhesion were characterized by scanning electron microscopy (SEM). Cell viability, differentiation and mineralization were assessed by Alamar Blue, alkaline phosphatase (ALP) and Alizarin Red assays, respectively. The combination of HADSC/HOB, 2:1 ratio, seeded on nanofibrous-coated TiO<sub>2</sub> showed better cell adhesion, viability, differentiation and mineralization than the other groups. This study offers opportunity to assess in vitro cellular development of HADSC through direct cell to cell contact with HOB. This study indicates that the co-cultured HADSC/HOB seeded on TiO<sub>2</sub> based scaffolds may serve as a promising approach to facilitate osteogenic differentiation activity.

### 1.0 Introduction

In tissue engineering principles, cell-cell interactions are considered to play an important role to regenerate a quality tissue (1). Human osteoblasts (HOB) are known as large bone cells that responsible for the synthesis and mineralization of bone. The processes occur during both initial bone formation and later bone remodelling (1). Human adipose derived stem cell (HADSC) is one of the most viable stem cell sources for skeletal tissue regeneration (2) and contributes to the understanding of stem cell biology. Numerous studies have employed HADSC or HOB as a single layer or monolayer culture (2). However, monolayer culture system cannot provide adequate evaluation on cell-cell interactions between HADSC and HOB. To overcome these inadequacies, many researches have now employed co-culture system to study cell-cell interactions in vitro (3). Hence in this study, co-

culture compositions of HADSC and HOB using various HADSC/HOB ratios were established to evaluate direct cell-cell interactions. The HADSC/HOB was also seeded on TiO<sub>2</sub> based scaffolds. The scaffolds were meant to provide three dimensional (3D) microenvironment and to direct cells growth. Results on cell adhesion, viability, differentiation and mineralization are presented in this paper.

### 2.0 Materials and Method

With the approval of the UKM Research and Ethical Committee, HADSC was co-cultured with HOB using selected HADSC/HOB ratios of 2:1, 1:1 and 1:2, respectively. They were cultured in an equal mixture of F12 Nutrient Mixture and Dulbecco's Modified Eagle Medium (F12/DMEM; Gibco) supplemented with 10% foetal bovine serum (FBS; Gibco), 1% antibiotic-antimycotic (Invitrogen,

Carlsbad, CA), 1% glutamax (Invitrogen) and 1% vitamin C (Sigma-Aldrich). The HADSC/HOB was then seeded on TiO<sub>2</sub> coated with or without nanofibre substrate. Cell adhesion were characterized by field emission SEM, cell viability using Alamar Blue assay, cell differentiation by alkaline phosphatase (ALP) assay and cell mineralization by Alizarin Red Assay. All evaluations were carried out at each time point of Day-1, -7 and -14.

### 3.0 Results

The HADSC/HOB (2:1) seeded on nanofibre-coated TiO<sub>2</sub> showed significantly higher cell viability (p=0.011) on day 14 and displayed significantly higher production of alkaline phosphatase activity (p= 0.014) and mineralization (p=0.000) compared to the other groups. Field emission SEM also showed better cell adhesion, migration and morphology of HADSC/HOB (2:1) seeded on nanofibre-coated TiO<sub>2</sub> when compared to other groups.

### 4.0 Discussion and Conclusion

Most of the previous studies assessing osteogenic differentiation of HADSCs into osteoblastic lineage have focused on modifying of osteogenic factors added to the media or the treatment with an osteogenic media (4,5) which are in contrast to this study. The outcome of this study suggested that the nanofibre-coated TiO<sub>2</sub> scaffold seeded with HADSC/HOB (2:1) serves as a better technique to promote osteogenic capacity. Other than holding the advantage of evaluating cell-cell interactions by having the co-culture system, the presence of the in vitro 3D microenvironment has facilitated cell growth and differentiation. Special emphases on this synthetic biology system are clearly necessary to understand various biological phenomenon as well as to develop its full potential for tissue engineering and regenerative applications. The method may be useful for generating osteoblasts or bone cells derived from other mesenchymal stem cells for skeletal tissue regeneration or repair.

### Acknowledgement

We thank the Department of Biomedical Engineering, University of Malaya for providing the TiO<sub>2</sub> based scaffolds (Ti-6Al-4V) and the Ministry of Higher Education, Malaysia for providing the High Impact Research Grant (UM.C/HIR/MOHE/END/44) to financially support the work.

### References

1. Lisa G, Paul F, and Karen MP. Co-culture systems and technologies: taking synthetic biology to the next level. *J.R. Soc. Interface*. 2014; 11:1-13.
2. Safwani WK, Makpol S, Sathapan S, Chua KH. Alteration of gene expression levels during osteogenic induction of human adipose derived stem cells in long-term culture. *Cell Tissue Bank*. 2013;14(2):289-301.
3. Tsai MT, Lin DJ, Huang S, Lin HT, Chang WH. Osteogenic differentiation is synergistically influenced by osteoinductive treatment and direct cell-cell contact between murine osteoblasts and mesenchymal stem cells. *International Orthopaedics (SICOT)*. 2012; 36:199-205.
4. Hou Y, Cai K, Li J, Chen X, Lai M, Hu Y, Luo Z, Ding X, Xu D. Effects of titanium nanoparticles on adhesion, migration, proliferation, and differentiation of mesenchymal stem cells. *International Journal of Nanomedicine*. 2013; 8:3619-3630.
5. Olivares-Navarrete R, Hyzy SL, Hutton DL, Erdman CP, Wieland M, Boyan BD, Schwartz Z. Direct and indirect effects of microstructured titanium substrates on the induction of mesenchymal stem cell differentiation towards the osteoblast lineage. *Biomaterials*. 2010; 31: 2728-2735.