
Articles

School of Electrical and Electronic Engineering

1999

The Dynamic Properties of 5Cb Filled with Aerosil Particles Investigated by Pcs

F.M. Aliev

M. Kreuzer

Yuri Panarin

Technological University Dublin, yuri.panarin@tudublin.ie

Follow this and additional works at: <https://arrow.tudublin.ie/engscheleart2>

 Part of the [Electrical and Computer Engineering Commons](#)

Recommended Citation

Aliev, F.M. et al. (1999). The dynamic properties of 5Cb filled with aerosil particles investigated by pcs. *MRS Online Proceedings Library Archive*, January, pg. 223-228. doi.org/10.1557/PROC-559-223

This Article is brought to you for free and open access by the School of Electrical and Electronic Engineering at ARROW@TU Dublin. It has been accepted for inclusion in Articles by an authorized administrator of ARROW@TU Dublin. For more information, please contact yvonne.desmond@tudublin.ie, arrow.admin@tudublin.ie, brian.widdis@tudublin.ie.



This work is licensed under a [Creative Commons Attribution-Noncommercial-Share Alike 3.0 License](#)

- January 1999, 223

The Dynamic Properties of 5Cb Filled with Aerosil Particles Investigated by PCS

- [F.M. Aliev](#) ^(a1), [M. Kreuzer](#) ^(a2) and [Yu.P. Panarin](#) ^(a1)
-
- DOI: <https://doi.org/10.1557/PROC-559-223>
 - Published online: 01 February 2011

Abstract

Nematic liquid crystal filled with Aerosil particles, a prospective composite material for optoelectronic application, has been investigated by static light scattering and Photon Correlation Spectroscopy (PCS). The Aerosil particles in filled nematic liquid crystals (FN) form a network structure with LC domains about 2500 Å in size with a random distribution of the director orientation of each domain.

We found that the properties of 5CB are considerably affected by the network. The N-I phase transition in filled 5CB was found to be smeared out and depressed. PCS experiments show that two new relaxation processes appear in filled 5CB in addition to the director fluctuation process in bulk. The slow relaxation process, with a broad spectrum of relaxation times, is somewhat similar to the slow decay, which is observed in confined nematic liquid crystal.

The middle frequency process was assigned to the director fluctuations in the surface layer formed at the particle-LC interface. The decay function describing this relaxation process is a stretched exponential ($\beta \approx 0.7$). The temperature dependence of the relaxation times of the middle frequency obeys the Vogel-Rilcher law. Such a temperature dependence, accompanied by a broad spectrum of relaxation times suggests that the dynamics of the director fluctuations near the Aerosil particle-LC interface is glass-like.

Copyright

COPYRIGHT: © Materials Research Society 1999

Linked references

This list contains references from the content that can be linked to their source. For a full set of references and notes please see the PDF or HTML where available.

- 1 P.S. Drzaic , *Liquid Crystal Dispersions*, (World Scientific, Singapore, 1995).
- [CrossRef](#) [Google Scholar](#)

3 D. Finotello and J. Iannacchione , *Int. Journ. Mod. Phys. B* 9, 109 (1995).

- [CrossRef](#)
- [Google Scholar](#)

4 G.P. Crawford and S. Zumer , *Int. Journ. Mod. Phys. B* 9, 331 (1995).

- [CrossRef](#) [Google Scholar](#)

6 X-l. Wu , W.I. Goldburg , M.X. Liu , and J.Z. Xue , *Phys. Rev. Lett.* 69, 470 (1992).

- [CrossRef](#)

7 T. Bellini , N.A. Clark , D.W. Schaefer , *Phys. Rev. Lett.* 74, 2740 (1995).

- [CrossRef](#) [Google Scholar](#)
8 A. Mertelj , L. Spindler , and M. Copic , *Phys. Rev. E* 56, 549 (1997).
- [CrossRef](#) [Google Scholar](#)
9 A. Mertelj and M. Copic , *Phys. Rev. E* 55, 504 (1997).
- [CrossRef](#) [Google Scholar](#)
10 F.M. Aliev and G.P. Sinha , *Mol. Cryst. Liq. Cryst.* 303, 325 (1997).
- [CrossRef](#) [Google Scholar](#)
11 M. Copic and A. Mertelj , *Phys. Rev. Lett.* 80, 1449 (1998).
- [CrossRef](#) [Google Scholar](#)
12 M. Kreuzer , T. Tschudi , W.H. de Jeu , and R. Eidenschink , *Appl. Phys. Lett.* 62, 1712 (1993).
- [CrossRef](#) [Google Scholar](#)
14 B. Zhou , G.S. Iannacchione , C.W. Garland , and T. Bellini , *Phys. Rev. E* 55, 2962 (1997).
- [CrossRef](#)
15 T. Bellini , N.A. Clark , V. Degiorgio , F. Mantegazza , and G. Natale , *Phys. Rev. E* 57, 2996 (1998).
- [CrossRef](#) [Google Scholar](#)
16 G.S. Iannacchione , C.W. Garland , J.T. Mang , and T.P. Rieker , *Phys. Rev. E* 58, 5966 (1998).
- [CrossRef](#)
17 F. Aliev , M. Kreuzer , N. Tabiryan , and B. Zel'dovich , *Mol. Cryst. Liq. Cryst.* 320, 173 (1998).
- [CrossRef](#) [Google Scholar](#)
19 *Disorder Effects on Relaxational Processes*, edited by R. Richert and A. Blumen (Springer Verlag, Berlin1994).
- [CrossRef](#) [Google Scholar](#)
20 A.L. Demirel and S. Granik , *Phys. Rev. Lett.* 77, 2261 (1996).
- [CrossRef](#) [Google Scholar](#)