



CHEMICAL AND MINERALOGICAL CHARACTERIZATION OF BOTTOM ASHES FROM A MUNICIPAL SOLID WASTE INCINERATOR IN NORTHERN ITALY, AIMED AT INERTIZATION AND REUSE

C. Caviglia¹, G. Confalonieri¹, E. Destefanis¹, G. Mandrone¹, L. Pastero¹, R. Boero², A. Pavese¹

¹Dipartimento di Scienze della Terra, Università degli Studi di Torino, via Valperga Caluso 35, 10125 Torino, Italy

²Trattamento Rifiuti Metropolitan - TRM SpA, Via Gorini 50, 10137, Torino

RECYCLING AND REUSE OF BOTTOM ASHES FROM MUNICIPAL SOLID WASTE THERMOVALORIZATION PLANT

Municipal solid waste after the treatment in the TRM plant are:



20% BOTTOM ASHES (BA)



2% FLY ASHES (FA)

Today

BA are taken by specialized Societies and converted mostly in secondary raw materials, available only if included in other matrices (problem of the release of chemical species in the environment)

MSWI PLANT OF TURIN

The plant is working since 2014 and burn about 500.000 t of waste per year, with three lines of combustion, and a total capacity of 67,5 tons/h, at a firing peak temperature of some 1000 °C.





1.SAMPLING+REDUCTION

2.TEXTURE ANALYSIS AND MORPHOMETRIC
DEFINITION

3.CHARACTERIZATION

1.SAMPLING+REDUCTION

Sampling of material in the TRM plant from a falling stream




Reduction by riffle splitter
(European normative CEN/ TR- 15310 - 3 for waste characterization)

Quartering to produce subsamples (3)



Cumulative % calculated as:
 $(Total\ weight - Retained\ weight) / Total\ weight \times 100$.

2. TEXTURE ANALYSIS AND MORPHOMETRIC DEFINITION



Grain size (mm)	Retained (%)
20	8,20%
16	2,73%
10	11,00%
8	9,30%
4	19,34%
2	14,90%
1	14,15%
0,5	7,18%
0,063	9,77%
<0,063	3,42%

The three subsamples, *QR*, *CL5* and *CL 10* show the same grain size distribution



3.CHARACTERIZATION

CHEMICAL COMPOSITION




CHEMICAL AND MINERALOGICAL DETERMINATION

- XRF
- ICP/OES+MW DISSOLUTION
 - SEM-EDS
- X-RAYS DIFFRACTION
- THERMOGRAVIMETRY

RELEASE TESTS


- LEACHING TESTS WITH CONDUCTIVITY LOGS
 - ICP-OES AND CHROMATOGRAPHY ANALYSIS OF LEACHATES

CRYSTALLINE PHASES: XRD ANALYSIS




X-RAYS DIFFRACTION, WITH GRAIN SIZE DIFFERENTIATION (BEFORE AND AFTER LEACHING)

X Ray Powder diffraction data was collected by means of a PANalyticalX'Pert Pro Bragg Brentano ($\theta/2\theta$) diffractometer





All the samples contain a large amount of an **amorphous phase** (> 50 wt%) with minority phases as quartz, calcite (except in QR 8 and 4) and feldspar (except in QR 16). **Cristobalite**, **Fe oxide** (hematite or magnetite), **melilite** and **halite** were found as **traces** in samples with grain size lower than QR 10. The presence of crystalline phases as **melilite** proved the reaching of high temperature during the firing process of the waste



All the samples present a **decreased amount of the amorphous phase**. Probably the leaching process mainly acts on the amorphous phase because this is not crystalline and then particularly reactive. This process has been proved to interest mainly the amorphous phase rather than the crystalline phases (except for the halite, which is dissolved


MOLAR COMPOSITION (WITH GRAIN SIZE DISCRIMINATION)

Chemical composition of BA was determined by combining data from μ -XRF, SEM-EDS and ICP-OES after microwave digestion in nitric acid. The observed chemical species are Si, Ca, Al, Fe, P, S, Cl, K, Ti, V, Cr, Mn, Ni, Cu, Zn, As, Sr and Pb, as reported in the figures, in terms of elemental molar percentages. Si, Ca, Al, Fe, Mg, Na and K (in order of abundance) are the major occurring species. The highest concentrations of heavy metals, save iron, are due to Cr, Ti, Zn and Cu. Si decreases upon decreasing grain size, while Ca increases




Si decreases upon decreasing grain size, while Ca increases

OVERALL MOLAR COMPOSITION (NO GRAIN SIZE DISCRIMINATION)




Overall composition (*XRF + microwave digestion values*) of bottom ashes. Average values calculated without grain size discrimination.

THERMOGRAVIMETRIC ANALYSIS




Thermogravimetric analyses (full sample) show there is a very low loss of material at about 100 °C (dehydration) and between 300 and 600 °C (probably "plastic" combustion) and a process of burning yielding a 5-6 % by weight loss that is completed at about 600 °C.




TG and DTG analyses in combination with IR-determination of volatile emissions, for bottom ashes > 1mm (black) and < 1mm (red).

OVERALL MOLAR COMPOSITION OF THE AMORPHOUS PHASE

Overall composition of the amorphous phase obtained by subtraction of the molar composition of the main crystalline phases from XRD analysis (quartz, calcite, plagioclase, Fe-oxides, gehlenite, halite) from the overall composition of bottom ashes (> 1 mm and < 1 mm grain sizes).





	Na+K	Mg+Ca+Fe	Si+Al	P+S	transition elements
20	21,5554	31,10051122	43,028	2,2852	2,030695353
16	17,6062	26,47212748	51,913	2,0567	1,951573644
10	15,3862	40,8876383	36,828	5,0398	1,858154686
8	18,9989	33,56211132	42,435	2,796	2,207594578
4	17,7828	39,52166724	35,89	4,9267	1,878781126
2	12,3006	41,40090291	39,272	4,1528	2,873886733
1	12,312	44,29781686	35,924	4,8672	2,598909153
0,5	12,6637	45,9979659	32,442	6,3328	2,563501701
0,063	13,5316	55,9979659	22,442	6,3328	2,207601201
<0,063	14,4789	60,9979659	13,442	6,3328	2,98648932



- The amorphous phase chemical composition depends on the particle size: Si+Al concentrate in large size particles, whilst Mg+Fe+Ca prefer to enter small size BA; P+S show an increase in the small particle size, especially over the range 0,063-1 mm.

LEACHING TEST AND LEACHATES ANALYSIS

European standards for the characterization of waste: EN-12457-2 (leaching test in deionized water L/S 10/1)



Cu lies above the legal threshold values, (0,05 mg/l), settled by the European Legislations 91/156/EEC and 91/698/EEC, and transposed into the Italian law about “*not dangerous waste reuse*”, D.M. 5/04/2006 n.186, (“Ministero dell’Ambiente e della Tutela del Territorio, 2006”). Pb, Cu, Ni and Zn decrease upon decreasing the grain size. Cr, Co, Cd, Ba and Zn turn out to lie below the legal threshold values.



LEACHING TEST AND LEACHATES ANALYSIS

≥ 1 mm

Low conductivity ($< 1000 \mu\text{S}/\text{cm}$)

pH 10-10.5

Low concentration of Cl^- ($< 800 \text{mg}/\text{l}$)

Na^+ ($< 800 \text{mg}/\text{l}$)

< 1 mm


High conductivity ($> 4000 \mu\text{S}/\text{cm}$)

pH 11.5

High concentration of Cl^- (up to $1800 \text{mg}/\text{l}$)

Na^+ (up to $950 \text{mg}/\text{l}$)

The sum of the heavy metals concentrations in the leachates of BA < 1 mm is more than three times larger than the one in the case of grain size ≥ 1 mm



CONCLUSIONS

Solid composition

- The average molar composition of the bottom ashes is represented by 52% Si, 17% Ca, 7% Al, 6% Fe, 4% Na and Mg.
- The highest concentrations of heavy metals (mol %) are represented by Ti (1,3%), Zn (0,3%), Cu (0,2%) and Cr (0,2%); concentrated in the finer grain sizes.
- The amorphous phase is > 65 wt%, with minority phases as quartz, calcite and feldspar. Cristobalite, Fe oxide (hematite or magnetite), melilite and halite were found as <5 %
- Unburnt/partially burnt materials occur as much as some 3-4 wt%. The amorphous phase chemical composition depends on the particle size: Si+Al concentrate in large size particles, whilst Mg+Fe+Ca prefer to enter small size BA; P+S show an increase in the small particle size, especially over the range 0,063-1 mm.
- The average molar composition of the amorphous phase and Ksp of heavy metals was determined: (Na + K) 16 mol%, (Mg + Ca + Fe) 42 mol%; (Si + Al) 35 mol %; (P + S) 5 mol %; transition elements 2 mol%.

CONCLUSIONS

Leachates composition

Leaching treatments lead to an average mass decrease of about 15-20 %wt of the solid, according to the trend that the larger the particle size, the smaller the weight loss.

Electrolytic conductivity observations in combination with chemical composition determination of BA suggest to split bottom ashes into two classes, *i.e.* ≥ 1 mm and <1 mm.

≥ 1 mm exhibits: electrolytic conductivity (<1000 $\mu\text{S}/\text{cm}$), pH ~ 10 - 10.5 , lower concentrations of Cl^- (<800 mg/l), Na^+ (<500 mg/l)

<1 mm : electrolytic conductivity up to 4000 $\mu\text{S}/\text{cm}$), pH ~ 11 - 11.5 , higher concentrations of Cl^- (up to 1800 mg/l), Na^+ (up to 950 mg/l).

Moreover the sum of the heavy metals concentrations in the leachates of BA <1 mm is more than three times larger than the one in the case of grain size ≥ 1 mm

CONCLUSIONS

- Exploiting the particle size dependence of bottom ashes is necessary to design possible inertization treatments or reuse.
- We suggest grain size separation at 1 mm, relying upon electrolytic and exchanging/release activities.
- Given that most chemical species exchanging activity is affected by the amorphous phase, it is necessary to engender its vitrification or decomposition into stable oxides.

