

Available online at www.sciencedirect.com

ScienceDirect

Energy Procedia 114 (2017) 6083 – 6086

Energy

Procedia

13th International Conference on Greenhouse Gas Control Technologies, GHGT-13, 14-18
November 2016, Lausanne, Switzerland

Passive mineral carbonation of Mg-rich mine wastes by atmospheric CO₂

Georges Beaudoin^{a*}, Ali Nowamooz^a, Gnouyaro Palla Assima^b, Karl Lechat^a, Antoine Gras^a, Ali Entezari^b, El Hadji Babacar Kandji^d, Akué-Sylvette Awoh^d, Micha Horswill^a, Sara Turcotte^a, Faïçal Larachi^a, Christian Dupuis^a, John Molson^a, Jean-Michel Lemieux^a, Xavier Maldague^c, Benoît Plante^d, Bruno Bussière^d, Marc Constantin^a, Josée Duchesne^a, René Therrien^a, Richard Fortier^a

^a Département de géologie et de génie géologique – Université Laval, Québec, Québec, G1V 0A6 Canada

^b Département de génie chimique – Université Laval, Québec, Québec, G1V 0A6 Canada

^c Département de génie électrique et de génie informatique – Université Laval, Québec, Québec, G1V 0A6 Canada

^d Université du Québec en Abitibi-Témiscamingue (UQAT), Rouyn-Noranda, Québec, J9X 5E4 Canada

Abstract

Mg-rich process tailings and waste rocks from mining operations can react spontaneously with atmospheric CO₂ to form stable carbonate minerals by exothermic reactions. Over the last decade, we have conducted a number of laboratory and field experiments and surveys on both mine waste rocks and different types of mine tailings from Ni-Cu, chrysotile, and diamond mines. The experiments and surveys cover a wide range of time (10³ to 10⁸ s) and mass (1-10⁸ g) scales. Mine waste rich in brucite or chrysotile enhances the mineral carbonation reactions. Water saturation, but more importantly, watering frequency, are highly important to optimize carbonation. Adjusting the chemical composition of the interstitial water to favour Mg dissolution and to prevent passivation of the reaction surfaces is crucial to ensure the progress of the carbonation reactions. Preservation of the permeability structure is also critical to facilitate water and CO₂ migration in the rock wastes and tailings. In field experiments, CO₂ supply controlled by diffusion in the mining waste is slower than the reaction rate which limits the capture of atmospheric CO₂. Industrial implementation of passive mineral carbonation of mine waste by atmospheric CO₂ can be optimized using the above parameters.

© 2017 The Authors. Published by Elsevier Ltd. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

Peer-review under responsibility of the organizing committee of GHGT-13.

* Corresponding author. Tel.: +1-418-656-3141; fax: +1-418-656-7339.
E-mail address: beaudoin@ggl.ulaval.ca

Keywords: mineral; carbonation; mining waste; atmosphere; CO₂; experimental;

1. Introduction

Passive mineral carbonation of Mg-rich mine wastes is an attractive process to capture atmospheric CO₂ from natural and anthropogenic sources, past or current. In particular, it is one of the few methods for scrubbing CO₂ from diffuse sources, such as transportation or housing, that are not amenable to capture at the emission point [1]. Passive mineral carbonation removes CO₂ from the atmosphere thereby directly addressing the goal to reduce warming caused by greenhouse gases. To this end, we have conducted experiments at various time (10³ to 10⁸ s) and mass (1-10⁸ g) scales, using benchtop laboratory experiments, field experimental cells, as well as within instrumented boreholes in a Mg-rich mine waste pile. The objective of these experiments has been aimed at identifying critical parameters that control reaction rates in order to optimize carbon sequestration and recovery of the geothermal energy associated with the exothermic mineral carbonation reactions.

2. Experimental results

2.1. Laboratory

Laboratory experiments have shown that brucite, followed by chrysotile, are the most reactive minerals for carbonation of Mg-rich mine waste and their proportions in mine waste are critical to assess the carbon capture potential [2, 3]. A supply of air with CO₂ and the degree of water saturation at the reaction sites are the limiting steps for the progress of the carbonation reactions [4]. Optimal water saturation of the mine waste or tailing residue (ca. 30-50 %) is a function of the physical properties of the mining waste. In addition, increased watering frequency near optimal water saturation increases the efficiency of the mineral carbonation reactions [3]. A water composition (pH, chelates) favouring dissolution of Mg from mining waste is also critical for the progress of mineral carbonation. The process involves dissolution of gaseous CO₂ from within the mining waste pore space into the interstitial water which precipitates hydrated magnesium carbonates. However, the mineral carbonation reactions are impeded by precipitation of amorphous silica, carbonates and Fe-hydroxides on the mineral and rock fragments of the mining waste [5]. Laboratory conditions of temperature and CO₂ partial pressures favor formation of metastable nesquehonite (MgCO₃·3H₂O). The morphology of the precipitated carbonate minerals evolves from a flaky and porous phase to less porous, elongated crystals of nesquehonite [6], that may be evidence of passivation control of the reactive surfaces. The neofomed carbonates cement together the rock and mineral fragments of the mine waste or tailing residue [6, 7]. However, the integrity of the carbonate layer may be manipulated over time rendering the unreacted cores accessible [8]. The development of a CO₂ consumption test enabled to quantify the CO₂ flux sequestered by mining wastes [9, 10].

2.2. Field experimental cells

Long-term monitoring (up to four years) of field experiments using four pilot-scale mine waste cells, located at Thetford Mines and Amos (Québec, Canada), allowed studying the carbonation reaction under atmospheric weathering conditions. The cells were constructed from mining or milling wastes (tailings) and instrumented with gas sampling ports to measure the interstitial gaseous composition as well as with probes to measure temperature and water saturation. At the bottom of the cells a drain allows collecting leachate water [11, 12, 13]. One of the cells at Thetford Mines has been dismantled to investigate the carbonation products. A fully instrumented weather station was also installed at each site in order to measure the ambient conditions and precipitation.

Within the cells, the CO₂ concentration was observed to decrease from local atmospheric levels (~400 ppmv), to values as low as 5 ppm inside the cell. The dominant CO₂ transport mechanism in the cell's porous medium is diffusion [11]. The carbon content in the mining residues increased over time, captured in neofomed carbonates (pyroaurite, nesquehonite, dypingite, hydromagnesite) [11, 12]. Over the same time period, the carbon isotopic composition of CO₂ in the interstitial air became heavier, from δ¹³C values of -8‰ at the surface, to values as high as 15‰ in the

center of the cells. This indicates kinetic carbon fractionation during CO₂ dissolution into the interstitial water, in cells where advection of CO₂ is limited [11]. The diffusion-controlled CO₂ supply in the cells is the rate-limiting step of the carbonation reaction [12].

2.3. Mining waste pile

We drilled a 90 meter-deep sonic borehole into a 300 Mt mine waste pile, at the Black Lake mine, Thetford Mines, Canada, in order to scale-up the laboratory and experimental cell results to the conditions of field implementation at the mine scale. The six-inch diameter well was instrumented with 22 thermistors and nine gas sampling ports for monitoring temperature, differential pressure and interstitial air composition, including the concentration and carbon isotope composition of CO₂, within the waste pile. A weather station, installed at the top of the mining waste pile, provides local environmental conditions in order to investigate correlations between the meteorological conditions and in-situ measurements. Measurements of gas composition show that air within the mine waste is depleted in CO₂ (<10-200 ppm) compared to the atmosphere (400 ppm). In situ temperatures measured in the borehole, show thermal anomalies as a result of the exothermic mineral reactions inside the mining waste pile. The lower 50 meters of the borehole show an average geothermal gradient of about 45 °C/km, twice the regional thermal gradient, whereas the upper 40 meters have a geothermal gradient of about 18 °C/km. The temperature profile is complex as a result of the internal structure of the waste pile that creates distinct hydrodynamic regimes of air and water advection. Snow cover and frozen ground at the surface of the mine waste pile during winter, as well as wind speed and direction, and the density of the air seems to be correlated with air and CO₂ migration into the mining waste pile.

3. Conclusions

Selecting mine waste rich in brucite or chrysotile enhances mineral carbonation reactions. Water saturation, but more importantly, watering frequency, are highly important to optimize the carbonation process. Adjusting the chemical composition of the interstitial water to favour Mg dissolution and prevent mineral precipitation which passivates the reaction surfaces is crucial to ensure the progress of the carbonation reactions. Preservation of the optimal permeability structure is also critical to facilitate water and CO₂ migration to the reaction sites. The CO₂ supply by diffusion into the mining waste appears slower than the reaction rate which limits the capture of atmospheric CO₂. Under the current natural conditions, the 300 Mt of chrysotile-rich mine wastes from the Black Lake mine at Thetford Mines are estimated to be passively capturing circa 0.002 tonnes CO₂/tonne mine waste per year, or 0.6 Mt CO₂/year. Injection of CO₂ and water to the reaction sites could significantly enhance mineral carbonation in, or on top of a mine waste pile, such as in heap leach mining operations.

Acknowledgements

We thank our research partners, Royal Nickel Corporation, Lab-Chrysotile, Mine Jeffery, Trans-Canada Corp, and the Natural Sciences and Engineering Research Council of Canada, and Fonds de recherche du Québec – Nature et Technologies for their long-term support of our research program.

References

- [1] K.S. Lackner, Capture of carbon dioxide from ambient air, *The European Physical Journal - Special Topics*, 176 (2009) 93-106.
- [2] J. Pronost, G. Beaudoin, J. Tremblay, F. Larachi, J. Duchesne, R. Hébert, M. Constantin, Carbon Sequestration Kinetic and Storage Capacity of Ultramafic Mining Waste, *Environmental Science & Technology*, 45 (2011) 9413-9420.
- [3] G.P. Assima, F. Larachi, G. Beaudoin, J. Molson, Dynamics of carbon dioxide uptake in chrysotile mining residues – Effect of mineralogy and liquid saturation, *International Journal of Greenhouse Gas Control*, 12 (2013) 124-135.
- [4] G.P. Assima, F. Larachi, J. Molson, G. Beaudoin, Emulation of ambient carbon dioxide diffusion and carbonation within nickel mining residues, *Minerals Engineering*, 59 (2014) 39-44.
- [5] G.P. Assima, F. Larachi, J. Molson, G. Beaudoin, New tools for stimulating dissolution and carbonation of ultramafic mining residues, *The Canadian Journal of Chemical Engineering*, 92 (2014) 2029-2038.
- [6] G. Beaudoin, R. Hébert, M. Constantin, J. Duchesne, E. Cecchi, F. Huot, S. Vigneau, R. Fiola (2008). Spontaneous carbonation of serpentine in milling and mining waste, southern Québec and Italy. *Accelerated Carbonation for Environmental and Materials Engineering (ACEME2008)*, Rome, Italy, p. 73-82

- [7] E.H.B. Kandji, B. Plante, B. Bussière, A.S. Awoh, B.A. Ibrahim Saïb, P.P. Dupont, Prediction of drainage water quality from mining waste with carbon sequestration potential. Proc. IMWA/ICARD, Santiago, Chile, April 21-24, 2015.
- [8] A. Entezari Zarándi, F. Larachi, G. Beaudoin, B. Plante, M. Sciortino, Multivariate study of the dynamics of CO₂ reaction with brucite-rich ultramafic mine tailings, *International Journal of Greenhouse Gas Control*, 52 (2016) 110-119.
- [9] A.S.Awoh, B. Plante, B. Bussière, M. Mbonimpa, CO₂ consumption test for the quantification of the mineral carbonation potential of mine wastes. Canadian Geotechnical Conference (GeoMontreal) proceedings, Montreal, Canada, 2013.
- [10] A.S.Awoh, B. Plante, B. Bussière, M. Mbonimpa, Measurement and prediction of the CO₂ effective diffusion coefficient in unsaturated media. Canadian Geotechnical Conference (GeoRegina) proceedings, Regina, Canada, 2014.
- [11] K. Lechat, J.-M. Lemieux, J. Molson, G. Beaudoin, R. Hébert, Field evidence of CO₂ sequestration by mineral carbonation in ultramafic milling wastes, Thetford Mines, Canada, *International Journal of Greenhouse Gas Control*, 47 (2016) 110-121.
- [12] A. Gras A, G. Beaudoin, J. Molson, B. Plante, J-M Lemieux, B. Kandji, 2015. Evidence for passive mineral carbonation from carbon isotope geochemistry in mine wastes from the Dumont Nickel Project (Abitibi, Quebec). 5th International Conference on Accelerated Carbonation for Environmental and Material Engineering, New York, 21-24 June 2015
- [13] B. Plante, E.H.B. Kandji, B. Bussière, A.S. Awoh, B.A. Ibrahim-Saib, G. Beaudoin, A. Gras, J. Molson, P.P. Dupont, P.P. Geochemical behavior of carbon-sequestering mine wastes: Dumont project, Royal Nickel Corporation. Tailings and mine waste Conference proceedings, Colorado, 5-8 October 2014.