



University of HUDDERSFIELD

University of Huddersfield Repository

Aiken, Stuart, Crossley, Daniel L., Gabbutt, Christopher D., Heron, B. Mark, Biver, Claudine, Archambeau, Samuel and Berit-Debat, Fabien

Electrochromic two-core viologen derivatives and optical articles containing them

Original Citation

Aiken, Stuart, Crossley, Daniel L., Gabbutt, Christopher D., Heron, B. Mark, Biver, Claudine, Archambeau, Samuel and Berit-Debat, Fabien (2015) Electrochromic two-core viologen derivatives and optical articles containing them. WO2015040031.

This version is available at <http://eprints.hud.ac.uk/25466/>

The University Repository is a digital collection of the research output of the University, available on Open Access. Copyright and Moral Rights for the items on this site are retained by the individual author and/or other copyright owners. Users may access full items free of charge; copies of full text items generally can be reproduced, displayed or performed and given to third parties in any format or medium for personal research or study, educational or not-for-profit purposes without prior permission or charge, provided:

- The authors, title and full bibliographic details is credited in any copy;
- A hyperlink and/or URL is included for the original metadata page; and
- The content is not changed in any way.

For more information, including our policy and submission procedure, please contact the Repository Team at: E.mailbox@hud.ac.uk.

<http://eprints.hud.ac.uk/>

(19)



(11)

EP 2 848 668 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

18.03.2015 Bulletin 2015/12

(51) Int Cl.:

C09K 9/02 ^(2006.01) **C07D 213/80** ^(2006.01)
C07D 213/06 ^(2006.01) **C07D 213/22** ^(2006.01)
C07D 213/26 ^(2006.01)

(21) Application number: **13184780.8**

(22) Date of filing: **17.09.2013**

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

Designated Extension States:

BA ME

(71) Applicant: **ESSILOR INTERNATIONAL**

(Compagnie Générale d'Optique)

94220 Charenton le Pont (FR)

(72) Inventors:

- **Aiken, Stuart**
York, North Yorkshire YO30 7AW (GB)
- **Crossley, Daniel Luke**
Normanton, West Yorkshire WF6 1PA (GB)

- **Gabbutt, Christopher David**
Preston, Lancashire PR3 2YS (GB)
- **Heron, Bernard Mark**
Brough, East Yorkshire HU15 1AB (GB)
- **Biver, Claudine**
94220 Charenton-le-Pont (FR)
- **Archambeau, Samuel**
94220 Charenton-le-Pont (FR)
- **Berit-Debat, Fabien**
94220 Charenton -le-Pont (FR)

(74) Representative: **Cabinet Plasseraud**

**52, rue de la Victoire
75440 Paris Cedex 09 (FR)**

(54) **Electrochromic two-core viologen derivatives and optical articles containing them**

(57) The present invention relates to a group of novel electrochromic materials. More specifically, it relates to electrochromic materials having two-core viologens and the use of these two-core viologens as a variable transmittance medium for the manufacture of an optical article, such as an ophthalmic lens.

EP 2 848 668 A1

Description

[0001] The present invention relates to a group of novel electrochromic materials. More specifically, it relates to electrochromic materials having two-core viologens and the use of these two-core viologens as a variable transmittance medium for the manufacture of an optical article, such as an ophthalmic lens.

[0002] Electrochromism is a well-known physical phenomenon which is observed with certain classes of chemical compounds that change reversibly colour when a voltage is applied to them. The material undergoes reversible changes in optical properties by oxidation and reduction. Usually the electrochromic material may be colourless when an electric field is not applied and may be coloured when an electric field is applied. An electrochromic device, i.e. a device containing electrochromic compounds, the visible light absorbance of which depends only on the presence of an electric field, can thus have two states, i.e. a coloured state (when electrically activated) and a bleached state (in the inactive state). The optical transmission properties of the device depend on the nature of the electrochromic compounds.

[0003] There remains a need for improving an electrochromic material in order to use them as transparent media for forming high quality optical articles, in particular high quality ophthalmic lenses, while keeping electrochromic properties and having a wide range of colours.

[0004] After conducting extensive research, the present inventors provide novel electrochromic compounds exhibiting not only good electrochromic properties such as high absorption of the visible light in the coloured state, fast colouring and fading rates, long-term stability but also can be incorporated easily in a cell to form for instance an electrochromic lens.


[0005] The applicants now have synthesized a group of novel electrochromic two-core viologens.

[0006] The present invention relates to electrochromic compounds of formula (I) as defined below.

[0007] The present invention also relates to an electrochromic composition comprising at least one compound of formula (I).

[0008] Finally, the present invention relates to an electrochromic device comprising said electrochromic composition, such as ophthalmic lens.

[0009] Thus, the present invention concerns electrochromic compounds represented by formula (I) :



(I)

wherein:

- Z is selected from:

- alkylene;
- cycloalkylene; and
- a bivalent group of formula -R⁵-Y-R⁶-, wherein

- R⁵ and R⁶ are each independently selected from single bond, alkylene and cycloalkylene, and
- Y is selected from arylene, cycloalkylene, heteroarylene, arylene-arylene or arylene-CR'R"-arylene wherein R' and R" form together with the carbon to which they are linked a carbocyclic group;

wherein said alkylene, cycloalkylene, arylene, heteroarylene, and carbocyclic groups may be substituted by one or more substituents selected from halogen, alkyl, alkoxy, alkylthio, hydroxyalkyl, acyloxy, cycloalkyl, aryl, substituted aryl, aryloxy, heteroaryl and substituted heteroaryl;

- A and B are respectively selected from nitrogen and -N⁺(R^{7a})-, and from nitrogen and -N⁺(R^{7b})-, wherein R^{7a} and R^{7b} are independently selected from:

- o alkyl which may be substituted by one or more groups independently selected from halogen, alkoxy, cycloalkyl,

vinyl, allyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl;

o aryl and heteroaryl which may be both substituted by one or more groups independently selected from:

- 5 • halogen, cyano, nitro, alkyl, haloalkyl, arylalkyl, cycloalkyl, cycloalkylalkyl and heterocycloalkylalkyl, alkenyl, alkynyl, allyl, vinyl, aryl, substituted aryl, heteroaryl, substituted heteroaryl, -N(aryl)₂, -N(aryl)CO(aryl), -CO-aryl and -CO-substituted aryl;
- -OR⁸, -SR⁸, -S(O)R⁸, -S(O₂)R⁸, -S(O₂)NR⁸R⁹, -NR⁸R⁹, -NR⁸COR⁹, -NR⁸CO(aryl), -NR⁸aryl, -CH₂OR⁸, -CH₂SR⁸, -CH₂R⁸, -CO-R⁸ and -CO₂R⁸ wherein R⁸ and R⁹ are independently selected from H, alkyl, haloalkyl, arylalkyl, cycloalkyl, cycloalkylalkyl and heterocycloalkylalkyl;
- 10 • -S(O₂)NR¹⁰R¹¹ and -NR¹⁰R¹¹, wherein R¹⁰ and R¹¹ form together with the nitrogen atom to which they are linked a saturated 5 to 7 membered heterocycloalkyl which may comprise in addition to the nitrogen atom one further heteroatom selected from oxygen, nitrogen and sulfur, and which may be optionally substituted by one or two groups independently selected from halogen, -R⁸, -OR⁹, and -NR⁸R⁹, wherein R⁸ and R⁹ are as defined above;
- 15 • -V-W-R¹² wherein:
 - V is selected from oxygen, -N(R⁸)-, sulfur, -S(O)- and -S(O₂)-wherein R⁸ is as defined above;
 - W is alkylene, which may be substituted by one or more groups independently selected from halogen and alkoxy; and
 - 20 ■ R¹² is selected from -OR⁸, -NR⁸(alkyl) and -SR⁸ wherein R⁸ is as defined above; and
- -OC(O)-R¹³ wherein R¹³ is selected from alkyl, haloalkyl, alkenyl, -W-R¹², and aryl group which may be substituted by 1 to 4 groups selected from halogen, -R⁸, -OR⁸, -SR⁸, -NR⁸R⁹, -NR¹⁰R¹¹, -CO-R⁸, -C(O)OR⁸ wherein R⁸, R⁹, R¹⁰, R¹¹, R¹² and W are as defined above.

- 25 - R¹_a, R¹_b, R¹_c, R¹_d, R²_a, R²_b, R²_c, R²_d, R³_a, R³_b, R³_c, R³_d, R⁴_a, R⁴_b, R⁴_c and R⁴_d are each independently selected from H, alkyl, alkoxy, alkylthio, haloalkyl, haloalkoxy, haloalkylthio, poly(alkylenoxy), alkoxy carbonyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl, wherein the alkyl group may be substituted by one or more substituents independently selected from alkoxy, cycloalkyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl;
- 30 wherein at least one of R¹_a, R¹_b, R¹_c, R¹_d, R²_a, R²_b, R²_c, R²_d, R³_a, R³_b, R³_c, R³_d, R⁴_a, R⁴_b, R⁴_c and R⁴_d is not H;
- X- is a counterion; and
- m is 2 if A and B are nitrogen, 3 if one of A and B is nitrogen and the other is not nitrogen, and 4 if both A and B are not nitrogen.

35 **[0010]** The expression "alkylene" represents any divalent radical of a linear or branched hydrocarbon chain comprising 1 to 12 carbon atoms. Examples of C₁-C₁₂ alkylene groups include C₁-C₄ alkylene groups such as -CH₂-, -(CH₂)₂-, -(CH₂)₃-, -(CH₂)₄-, -CH(CH₃)-, -CH(CH₃)-CH₂-, -CH₂-CH(CH₃)-, -(CH₂)₂-CH(CH₃)-, -CH₂-CH(CH₃)-CH₂- or -CH(CH₃)-(CH₂)₂-, as well as -(CH₂)₅-, -(CH₂)₆-, -(CH₂)₂-CH(CH₃)-(CH₂)₂-, -(CH₂)₃-CH(CH₃)-CH₂-, -(CH₂)₇-, -(CH₂)₈-, -(CH₂)₉-, -(CH₂)₁₀-, -(CH₂)₁₁-, -(CH₂)₁₂-.

40 **[0011]** The expression "cycloalkylene" represents any divalent radical of a monocyclic or bicyclic 3 to 12 membered carbocycle. Examples of C₃-C₁₂ alkylene groups include cyclopropylene, cyclopentylene, cyclohexylene, cycloheptylene, and decahydronaphthylene.

[0012] The expression "arylene" represents any divalent radical of an aromatic hydrocarbon comprising 6 to 18 carbon atoms. Examples of C₆-C₁₈ arylene groups include phenylene, naphthylene, anthracenylene and phenanthrenylene.

45 **[0013]** The expression "carbocyclic group" represents any monocyclic or fused polycyclic hydrocarbon rings comprising 3 to 20 carbon atoms and which may comprise one or more unsaturations. Examples of C₃-C₂₀ carbocyclic groups include C₁₀-C₂₀ fused hydrocarbon rings which may comprise one or more unsaturations, such as cyclohexenylene, indene, fluorene.

[0014] The expression "halogen" includes F, Cl, Br or I. Preferred halogens are F and Cl.

50 **[0015]** The expression "alkyl" represents any monovalent radical of a linear or branched hydrocarbon chain comprising 1 to 18 carbon atoms. Examples of C₁-C₁₈ alkyl groups include C₁-C₄ alkyl groups such as methyl, ethyl, *n*-propyl, *i*-propyl, *n*-butyl, *i*-butyl, *s*-butyl or *t*-butyl, C₆-C₈ alkyl groups such as *n*-hexyl, *n*-heptyl or *n*-octyl, as well as *n*-pentyl, 2-ethylhexyl, 3,5,5-trimethylhexyl, *n*-nonyl, *n*-decyl, *n*-undecyl, *n*-dodecyl or *n*-Octadecyl.

55 **[0016]** The expression "alkenyl" represents any monovalent radical of a linear or branched hydrocarbon chain from 2 to 18 carbon atoms and comprising one double bond. Examples of C₂-C₁₂ alkenyl groups include C₂-C₄ alkenyl groups such as ethenyl, *n*-propenyl, *i*-propenyl, *n*-butenyl or *i*-butenyl.

[0017] The expression "alkynyl" represents any monovalent radical of a linear or branched hydrocarbon chain from 2 to 12 carbon atoms and comprising one triple bond which may be either internal or terminal. Examples of C₂-C₁₂ alkynyl

groups include C₂-C₄ alkynyl groups such as ethynyl, *n*-propynyl, *n*-butynyl.

[0018] The expression "alkoxy" represents a radical of formula -OR wherein R is a C₁-C₁₂ alkyl. Examples of C₁-C₁₂ alkoxy groups include C₁-C₆ alkoxy groups such as -OCH₃, -OCH₂CH₃ or O(CH₂)₅CH₃.

[0019] The expression "cycloalkyl" represents any monovalent radical of a monocyclic or bicyclic 3 to 12 membered saturated carbocycle. Examples of C₃-C₁₂ cycloalkyl groups include cyclopropyl, cyclopentyl and cyclohexyl.

[0020] The expression "heterocycloalkyl" represents any monovalent radical of a monocyclic or bicyclic 3 to 12 membered saturated ring comprising one or two heteroatoms independently selected from oxygen, nitrogen and sulfur. Examples of C₃-C₁₂ heterocycloalkyl groups include for example tetrahydropyranyl or N-methylpiperidinyl.

[0021] The expression "cycloalkylalkyl" represents any (C₃-C₁₂ cycloalkyl)-substituted C₁-C₁₂ alkyl group. Examples of (C₃-C₁₂ cycloalkyl)-C₁-C₁₂ alkyl groups include (C₃-C₁₂ cycloalkyl)-C₁-C₄ such as cyclohexylmethyl or cyclohexylethyl.

[0022] The expression "heterocycloalkylalkyl" represents any (C₃-C₁₂ heterocycloalkyl)-substituted C₁-C₁₂ alkyl group. Examples of (C₃-C₁₂ heterocycloalkyl)-C₁-C₁₂ alkyl groups include (C₃-C₁₂ heterocycloalkyl)-C₁-C₄ such as tetrahydropyranylmethyl.

[0023] The expression "aryl" represents any monovalent radical of an aromatic hydrocarbon comprising 6 to 18 carbon atoms. Examples of C₆-C₁₈ aryl groups include phenyl and naphthyl, anthaceny, phenanthrenyl.

[0024] The expression "substituted aryl" represents any C₆-C₁₈ aryl group as defined above substituted by one or more substituents selected from halogen, alkyl, alkoxy, haloalkyl, haloalkoxy, alkoxy carbonyl, alkanoyl, aroyl, formyl, nitrile, nitro, amido, alkylthio, alkylsulfanyl, alkylsulfonyl, arylthio, arylsulfanyl, arylsulfonyl, amino, alkylamino, arylamino, dialkylamino and diarylamino. Preferably, the substituents are selected from bulky or electron withdrawing groups.

Examples of substituted C₆-C₁₈ aryl groups include substituted phenyl groups such as *p*-methylphenyl, *o*-*t*-butylphenyl, *p*-trifluoromethoxyphenyl, *o*-trifluoromethoxyphenyl, *m*-cyanophenyl, *o*-*i*-propylphenyl, 2,4-dinitrophenyl, 2,6-diisopropylphenyl or 3,5-dicyanophenyl.

[0025] The expression "aryloxy" represents a radical of formula -OR wherein R is a C₆-C₁₈ aryl. Examples of C₁-C₁₂ aryloxy groups include phenyloxy and naphthyloxy.

[0026] The expression "heteroaryl" represents any monovalent radical of a monocyclic or bicyclic 5 to 10 membered aromatic group comprising from 1 to 3 heteroatoms independently selected from oxygen, nitrogen and sulfur. Examples of C₅-C₁₀ heteroaryl groups include furyl, thienyl, pyrrolyl, pyrazolyl, imidazolyl, isoxazolyl, isothiazolyl, thiazolyl, oxazolyl, 1,2,3-triazolyl, 1,2,4-triazolyl, 1-benzofuryl, 1-benzothieryl, indolyl, benzimidazolyl, indazolyl, 1,2-benzisoxazolyl, 2,1-benzisoxazolyl, 1,2-benzisothiazolyl, 2,1-benzisothiazolyl, benzothiazolyl, benzoxazolyl, benzotriazolyl, pyridyl, quinolinyl, isoquinolinyl, pyridazinyl, cinnolyl, phthalazinyl, pyrimidinyl, quinazolyl, pyrazinyl and quinoxalinyl.

[0027] The expression "heteroarylene" represents any divalent radical of a monocyclic or bicyclic 5 to 10 membered aromatic group comprising from 1 to 3 heteroatoms independently selected from oxygen, nitrogen and sulfur. Examples of C₅-C₁₀ heteroarylene groups include furylene, thienylene, pyrrolylene, pyrazolylene, imidazolylene, isoxazolylene, isothiazolylene, thiazolylene, oxazolylene, 1,2,3-triazolylene, 1,2,4-triazolylene, 1-benzofurylene, 1-benzothierylene, indolylene, benzimidazolylene, indazolylene, 1,2-benzisoxazolylene, 2,1-benzisoxazolylene, 1,2-benzisothiazolylene, 2,1-benzisothiazolylene, benzothiazolylene, benzoxazolylene, benzotriazolylene, pyridylene, quinolinylene, isoquinolinylene, pyridazinylene, cinnolylene, phthalazinylene, pyrimidinylene, quinazolinylene, pyrazinylene and quinoxalinylene.

[0028] The expression "substituted heteroaryl" represents any C₅-C₁₀ heteroaryl group as defined above substituted by one or more substituents selected from alkyl, alkoxy, alkoxy carbonyl, alkanoyl, aroyl, formyl, nitrile, nitro, amido, alkylthio, alkylsulfanyl, alkylsulfonyl, arylthio, arylsulfanyl, arylsulfonyl, amino, alkylamino, arylamino, dialkylamino and diarylamino. Preferably, the substituents are selected from bulky or electron withdrawing groups. Examples of substituted C₅-C₁₀ heteroaryl groups include 4-methylthienyl, 5-methyl-2-thienyl, 6-methyl-2-pyridyl, N-methylpyrrol-2-yl and N-phenylindol-3-yl.

[0029] The expression "haloalkyl" represents any C₁-C₁₂ alkyl group substituted by one or more halogen atom such as F or Cl. Examples of C₁-C₁₂ haloalkyl groups include C₁-C₁₂ perhaloalkyl groups, in particular C₁-C₄ perhaloalkyl groups such as -CF₃, as well as C₁-C₁₂ (perhaloalkyl)alkyl groups, in particular (C₁-C₄ perhaloalkyl)-(C₁-C₄ alkyl) groups such as -CH₂CF₃.

[0030] The expression "haloalkoxy" represents a radical of formula -OR wherein R is a C₁-C₁₂ haloalkyl. Examples of C₁-C₁₂ haloalkoxy groups include C₁-C₁₂ perhaloalkoxy groups, in particular C₁-C₄ perhaloalkoxy groups such as -OCF₃, as well as C₁-C₁₂ (perhaloalkyl)alkoxy groups, in particular (C₁-C₄ perhaloalkyl)-(C₁-C₄ alkoxy) groups such as -OCH₂CF₃.

[0031] The expression "alkylthio" represents a radical of formula -SR wherein R is a C₁-C₁₂ alkyl. Examples of C₁-C₁₂ alkylthio groups include -SCH₃ and -SCH₂CH₃.

[0032] The expression "haloalkylthio" represents a radical of formula -SR wherein R is a C₁-C₁₂ haloalkyl. Examples of C₁-C₁₂ haloalkoxy groups include C₁-C₁₂ perhaloalkylthio groups, in particular C₁-C₄ perhaloalkylthio groups such as -SCF₃, as well as C₁-C₁₂ (perhaloalkyl)alkylthio groups, in particular (C₁-C₄ perhaloalkyl)-(C₁-C₄ alkylthio) groups such as -SCH₂CF₃.

[0033] The expression "hydroxyalkyl" represents any C₁-C₁₂ alkyl group substituted by one or more hydroxyl groups. Examples of C₁-C₁₂ hydroxyalkyl groups include -CH₂OH and -CH₂CH₂OH.


[0034] The expression "acyloxy" represents a radical of formula -OC(O)R wherein R is a C₁-C₁₂ alkyl. Examples of C₁-C₁₂ acyloxy groups include -OC(O)CH₃ and -OC(O)CH₂CH₃.


5 **[0035]** The expression "polyalkylenoxy" represents a radical of formula -O(R'O)_mR wherein R' is a C₁-C₁₂ alkylene, R is a C₁-C₁₂ alkyl and m is an integer from 1 to 12. Examples of poly(C₁-C₁₂ alkyleneoxy) groups include OCH₂CH₂OMe.

[0036] The expression "alkoxycarbonyl" represent a radical of formula -C(O)OR wherein R is a C₁-C₁₈ alkyl. Examples of C₁-C₁₈ alkoxycarbonyl groups include C₁-C₄ alkoxycarbonyl groups such as -C(O)OCH₃ and -C(O)OC₂H₅.

10 **[0037]** In formula (I), Z, called "the central core", is preferably selected from C₁-C₁₂ alkylene, C₃-C₇ cycloalkylene, C₃-C₁₄ arylene, C₅-C₁₀ heteroarylene, (C₁-C₄ alkylene)-(C₃-C₁₄ arylene), (C₁-C₄ alkylene)-(C₃-C₁₄ heteroarylene), (C₁-C₄ alkylene)-(C₃-C₁₄ arylene)-(C₁-C₄ alkylene), (C₁-C₄ alkylene)-(C₃-C₁₄ heteroarylene)-(C₁-C₄ alkylene), (C₃-C₁₄ arylene)-(C₃-C₁₄ arylene), (C₁-C₄ alkylene)-(C₃-C₁₄ arylene)-(C₃-C₁₄ arylene)-(C₁-C₄ alkylene) and (C₃-C₁₄ arylene)-(CR'R'')-(C₃-C₁₄ arylene) wherein R' and R'' form together with the carbon to which they are linked a C₃-C₂₀ carbocyclic group; wherein the arylene and cycloalkylene groups may be substituted by one or more substituents selected from halogen, C₁-C₄ alkyl, C₁-C₄ alkoxy and C₃-C₇ cycloalkyl, and the alkylene groups may be substituted by one or more substituents selected from halogen, C₃-C₁₄ alkyl, C₁-C₁₂ alkoxy, C₂-C₁₂ acyloxy, C₁-C₁₂ hydroxyalkyl, C₃-C₁₂ cycloalkyl, phenyl phenyloxy and substituted phenyl. In particular, substituted alkylene include -CH₂(CR^aR^b)CH₂- wherein R^a and R^b may be independently selected from H, C₃-C₁₄ alkyl, C₃-C₁₂ cycloalkyl, (cycloalkyl)methyl, aryl, substituted aryl, arylalkyl such as benzyl or phenyl(C₂-C₇ alkyl), phenyloxyethyl, substituted arylalkyl, C₁-C₁₂ alkoxy, C₂-C₁₂ acyloxy, C₁-C₁₂ hydroxyalkyl, and C₁-C₁₂ alkoxymethyl.

20 **[0038]** More preferably, Z is selected from C₁-C₁₂ alkylene, aryl substituted C₁-C₁₂ alkylene, phenylene, naphthylene, (C₁-C₄ alkylene)-phenylene-(C₁-C₄ alkylene), (C₁-C₄ alkylene)-naphthylene-(C₁-C₄ alkylene) such as naphthylene bis(methylene), quinoxaline-2,3-diyl, (C₁-C₄ alkylene)-quinoxaline-2,3-diyl-(C₁-C₄ alkylene) such as quinoxaline-2,3-diylbis(methylene), phenylene-phenylene, (C₁-C₄ alkylene)-phenylene-phenylene-(C₁-C₄ alkylene) and phenylene-fluorenylene-phenylene. For example, Z may be selected from -CH₂-, -(CH₂)₂-, -(CH₂)₃-, -(CH₂)₄-, -(CH₂)₅-, -CH₂-CH(CH₃)-CH₂-, -CH₂-CH(CH₂Phenyl)-CH₂-, -(CH₂)₂-CH(CH₃)-CH₂-, -(CH₂)₃-CH(CH₃)-CH₂-, -(CH₂)₂-CH(CH₃)-(CH₂)₂-,





20 **[0039]** A and B are preferably respectively selected from nitrogen and $-N^+(R^{7a})-$, and from nitrogen and $-N^+(R^{7b})-$, wherein R^{7a} and R^{7b} are independently selected from C_6-C_8 alkyl, in particular *n*-hexyl, and phenyl or naphthyl, wherein phenyl and naphthyl may be both substituted by one or more substituents independently selected from halogen, cyano, nitro, hydroxy, C_1-C_4 alkyl, C_1-C_4 haloalkyl, C_1-C_4 alkoxy, C_1-C_4 haloalkoxy, C_1-C_4 alkylthio, C_1-C_4 haloalkylthio, C_3-C_7 cycloalkyl, $(C_3-C_7$ cycloalkyl) C_1-C_4 alkyl.

25 **[0040]** In particular, A and B may be selected from $-N^+(C_6-C_8$ alkyl)-, preferably $-N^+(C_6H_{13})-$, more preferably $-N^+(n-C_6H_{13})-$, which have a good solubility in conventional solvents used in electrochromic compositions such as propylene carbonate while maintaining a fast fading rate to the bleached state. Indeed, C_1-C_5 alkyl substituted viologen compounds are more difficult to solubilise in some solvents used in electrochromic compositions like some ionic liquids. On the contrary, higher alkyl substituted two-core viologen compounds have good solubility. However, when two-core viologen compounds are substituted with long chain alkyls having more than 8 carbon atoms the fading rate tends to decrease, which prevents a fast reversibility to the bleached state.


30 **[0041]** Also, the inventors have observed that the presence of aryl substituents, in particular phenyl substituents, on the viologen cores of compounds of the present invention results in the stabilization of the compounds of the invention and, consequently, in a decrease of the activation potential, which corresponds to an increase in the reduction potential, of the viologen compounds. Therefore, in a preferred embodiment, A and B may be respectively selected from nitrogen and $-N^+(R^{7a})-$, and from nitrogen and $-N^+(R^{7b})-$, wherein R^{7a} and R^{7b} are independently selected from optionally substituted phenyl groups represented by formula (II):




45 wherein R_a , R_b , R_c , R_d and R_e are each independently selected from H, halogen, cyano, nitro, hydroxyl, alkyl, benzyl, haloalkyl, alkoxy, alkylthio, haloalkoxy, acyl, aroyl, alkoxy carbonyl, cycloalkyl, allyl, aryl and heteroaryl. In a particular embodiment, at least one of R_a , R_b , R_c , R_d and R_e is not H. Preferably, at least one of R_a , R_b , R_c , R_d and R_e is selected from halogen, cyano, nitro, hydroxyl, haloalkyl, haloalkoxy, alkoxy carbonyl, aryl and heteroaryl. Indeed, the applicant found that such electron-withdrawing substituents stabilize the cation which results in a decrease of the activation potential. In a preferred embodiment, R_e is H and at least one of R_a , R_b , R_c and R_d is not H.

50 **[0042]** For example, at least one of R_a , R_b , R_c , R_d and R_e may be selected from methyl, *i*-propyl, *t*-butyl, cyano, trifluoromethoxy preferably trifluoromethoxy. Thus, A and B may be respectively $-N^+(R^{7a})-$ and $-N^+(R^{7b})-$, wherein R^{7a} or R^{7b} are independently selected from:

55



15 **[0043]** In a preferred embodiment, A and B are respectively $-N^+(R^{7a})-$ and $-N^+(R^{7b})-$, wherein R^{7a} or R^{7b} are respectively selected from substituted phenyl groups of formula (II), wherein R_c , R_d and R_e are H and R_a and R_b are as defined above provided that at least one of R_a and R_b is not H. In particular, A and B are independently selected from $-N^+(R^{7a})-$ and $-N^+(R^{7b})-$ wherein R^{7a} or R^{7b} may be selected from:




25 **[0044]** Indeed, the Applicant has found that the presence of a substituent in the ortho position of the phenyl group results in a hypsochromic effect compared to the meta position, which provides itself a hypsochromic effect compared to the para position. Indeed the maximum wavelength λ_{max} in the absorption spectrum for a similar compound is higher when the substituent is in the para position of the phenyl group, than in the meta position, and a fortiori than in the ortho position. Consequently, the present invention provides new electrochromic compounds that can have a wide range of colours in their coloured state, in particular in the low visible wavelength - i.e. blue coloured state -, while presenting good stability and close oxydo-reduction potential values to each other.

30 **[0045]** The counterion X^- may be any anion that maintains electric neutrality of the viologen compounds of formula (I). X^- is preferably selected from halide, preferably fluoride and chloride, tetrafluoroborate, tetraphenylborate, perchlorate, hexafluorophosphate, nitrate, methanesulfonate, trifluoromethane sulfonate, toluene sulfonate, hexachloroantimonate, bis(trifluoromethanesulfonyl)imide, acetate and sulfate.

35 **[0046]** Preferably, R^1_a , R^1_b , R^1_c , R^1_d , R^2_a , R^2_b , R^2_c , R^2_d , R^3_a , R^3_b , R^3_c , R^3_d , R^4_a , R^4_b , R^4_c and R^4_d are each independently selected from hydrogen, aryl, substituted aryl, heteroaryl and substituted heteroaryl, preferably selected from optionally substituted phenyl, more preferably selected from phenyl, tolyl and cumyl.

40 **[0047]** In a first embodiment, the present invention relates to compounds of formula (I-1):




wherein Z, A, B, R^1_a , R^1_b , R^1_c , R^1_d , R^2_a , R^2_b , R^2_c , R^2_d , X^- and m are as defined above.

55 **[0048]** R^1_a , R^1_b , R^1_c , R^1_d , R^2_a , R^2_b , R^2_c and R^2_d are preferably selected from H, aryl, substituted aryl, heteroaryl and substituted heteroaryl provided that at least one of R^1_a , R^1_b , R^1_c , R^1_d , R^2_a , R^2_b , R^2_c and R^2_d is not H.

[0049] Indeed, aryl, heteroaryl, substituted aryl and substituted heteroaryl are particularly preferred, more particularly optionally substituted phenyl such as phenyl, tolyl and cumyl, because they induce a decrease of the activation potential of the compounds of the invention. Moreover, the steric hindrance provided by the presence of such substituents on the

viologen cores of the compounds of the invention is believed to prevent π - π interactions between the aromatic viologen cores which is the cause of the stacking phenomenon on or near the electrode surface. For example, R^1 , R^1_a , R^1_b , R^1_c , R^1_d , R^2 , R^2_a , R^2_b , R^2_c and R^2_d may be selected from H, aryl and heteroaryl, wherein the aryl and heteroaryl may be substituted by one or more substituents selected from C_1 - C_4 alkyl and C_1 - C_4 haloalkyl, wherein at least one of R^1 , R^1_b , R^1_c , R^1_d , R^2 , R^2_b , R^2_c and R^2_d is not H.


[0050] Particularly preferred compounds are compounds of formula (I-3):



(I-3)

wherein Z, A, B, X⁻ and m are as defined above and R^1 and R^2 are each independently selected from H, alkyl, alkoxy, alkylthio, haloalkyl, haloalkoxy, haloalkylthio, polyalkylenoxy, alkoxycarbonyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl, wherein the alkyl group may be substituted by one or more substituents independently selected from alkoxy, cycloalkyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl, provided that at least one of R^1 and R^2 is not H; preferably, none of R^1 and R^2 is H; more preferably, R^1 and R^2 are independently selected from aryl, heteroaryl, substituted aryl and substituted heteroaryl. For example, R^1 and R^2 , may be independently selected from phenyl, p-methylphenyl and p-trifluoromethylphenyl. In a particular embodiment, R^1 and R^2 are identical.

[0051] In a second embodiment, the present invention relates to compounds of formula (I-4):



(I-4)







wherein Z, A, B, R^3_a , R^3_b , R^3_c , R^3_d , R^4_a , R^4_b , R^4_c , R^4_d , X⁻ and m are as defined above.

[0052] R^3_a , R^3_b , R^3_c , R^3_d , R^4_a , R^4_b , R^4_c and R^4_d are preferably each independently selected from H, C_1 - C_4 alkyl and C_1 - C_4 alkoxycarbonyl, provided that at least one of R^3_a , R^3_b , R^3_c , R^3_d , R^4_a , R^4_b , R^4_c and R^4_d is not H. For example, R^3_a , R^3_b , R^3_c , R^3_d , R^4_a , R^4_b , R^4_c and R^4_d may be independently selected from methyl and ethoxycarbonyl. In a particular embodiment, none of R^3_a , R^3_b , R^3_c , R^3_d , R^4_a , R^4_b , R^4_c and R^4_d is H.

[0053] In a particularly preferred embodiment, the compounds of the present invention are selected from the group consisting of:






Compound	Formula
1-1	<p style="text-align: right;">2BF₄[⊖]</p>

(continued)

Compound	Formula
5 10 1-2	 <p style="text-align: center;">2BF_4^-</p>
15 1-3	 <p style="text-align: center;">4BF_4^-</p>
20 25 1-4	 <p style="text-align: center;">4BF_4^-</p>
30 1-5	 <p style="text-align: center;">2BF_4^-</p>
35 40 1-6	 <p style="text-align: center;">2BF_4^-</p>
45 50 1-7	 <p style="text-align: center;">2BF_4^-</p>

55

(continued)

Compound	Formula
5 10 1-8	
15 20 1-9	
25 1-10	
30 35 1-11	
40 45 50 1-12	


55

(continued)

Compound	Formula
5 10 15 1-13	
20 25 30 1-14	
35 40 2-1	
45 50 2-2	

Me represents methyl; *Ph* represents phenyl; *Tol* represents 4-methylphenyl

55 **[0054]** Compounds represented by formula (I) may be prepared according to various methods well known in the art. However, the Applicant has found a particularly advantageous method for preparing compounds of formula (I-3). According to this new method, which is illustrated hereafter, a wide variety of useful alkyl, aryl and heteroaryl substituents can be readily introduced onto the C-atoms of the pyridine rings.



Scheme A

[0057] Steps (i) and (ii) disclosed in scheme A may be achieved under heat, for example from 70 to 90°C, in an alcohol and in the presence of a base.

[0058] Compounds of formula (1-3) wherein A and/or B are respectively -N⁺(R^{7a})- and -N⁺(R^{7b})- as defined above can be obtained from the corresponding compounds (3) or (3') using suitable reaction step well known in the art. For example, compounds of formula (1-3) wherein A and/or B are -N⁺(alkyl)- can be obtained through an *N*-alkylation of the corresponding compound (3) or (3') with a suitable haloalkane.

[0059] The 2,6-disubstituted-4-[(1H)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate) (1) may be prepared according to various methods well known in the art. For example, 4-(4-pyridyl)-1,5-disubstituted-1,5-diketones can be obtained by the condensation of pyridine-4-carboxaldehyde and substituted acetophenones (see for example Aryl-substituted Derivatives of 4,4'-Bipyridylium Salts: their Spectroscopic Properties and Stereochemistry, J. E. Downes, J. Chem. Soc. (C), 1967, 1491 and Pyrylogens: Synthesis, Structural, Electrochemical, and Photophysical Characterization of a New Class of Electron Transfer Sensitizers, E. L. Clennan, C. Liao, E. Ayokosok, J. Am. Chem. Soc., 2008, 130, 7552). The cyclisation of the 4-(4-pyridyl)-1,5-disubstituted 1,5-diketones can be readily accomplished by, for example, heating in glacial acetic acid containing *trans*-chalcone and boron trifluoride etherate to give the 2,5-disubstituted 4-[(1H)-pyridinium-4-yl]pyrylium bis(tetrafluoroborates) (1).

[0060] Further specific examples of synthesis of compounds of the invention are illustrated below.

[0061] The present invention also relates to electrochromic compositions comprising at least one compound of formula (I) as defined above as an oxidizing electrochromic compound. One or more additional oxidizing electrochromic compounds can be added to the composition of the invention so as to adapt the colour or the intensity of the coloured state of the composition. Said additional compound can be another compound of formula (I) or a different compound such as compatible dyes or pigments. For Example, the additional oxidizing electrochromic compound can be selected from alkyviologens, arylviologens, alkylarylviologens, anthraquinone and their derivatives. Preferably, the additional compound has a redox potential close to the compound of formula (I). The composition also comprises a reducing compound.

The reducing compound can be also an electrochromic compound. Example of reducing compounds include 5,10-dihydrophenazine, phenazine, phenothiazine, N,N,N',N'-tetramethyl-p-phenylenediamine, thioanthrene, tetrathiafulvalene, ferrocene and their derivatives.

[0062] The composition of the invention may comprise a fluid, mesomorphous or gel host medium in which the electrochromic compounds are preferably dissolved. The fluid or mesomorphous host medium is preferably selected from the group consisting of organic solvents, liquid crystals, polymers or liquid crystal polymers and mixtures thereof.

[0063] Suitable solvents are redox-inert solvents which cannot react with the electrochromic compounds of the composition. Examples of suitable solvents are ethylene carbonate, propylene carbonate, γ -butyrolactone, γ -valerolactone, acetonitrile, propionitrile, benzonitrile, glutaronitrile, methylglutaronitrile, dimethylformamide, N-methylpyrrolidone, sulfolane, 3-methyl sulfolane, benzene, toluene, methyl ethyl ketone, acetone, ethanol, tetrahydrofurfuryl alcohol, 2-methoxyethyl ether, xylene, cyclohexane, 3-methylcyclohexanone, ethyl acetate, ethyl phenylacetate, tetrahydrofuran, methanol, methyl propionate, ethylene glycol ethylene carbonate, ionic liquids, and mixtures thereof. Preference is given to carbonate and particularly propylene carbonate.

[0064] The liquid crystal medium that may be used in the present invention includes, without being limited to, such materials as nematic or chiral nematic media.

[0065] The polymers that may be used in the present invention includes, without being limited to polymers which are soluble with the solvent, in particular PMMA or other acrylate polymers, polyurethane, polyethylene oxide, polypropylene oxide, polyvinyl acetate, poly(N-vinyl pyrrolidone), and polyvinylidene fluoride.

[0066] Alternatively a polymeric liquid crystal medium can be used as the host material. These liquid crystal, polymer polymeric liquid crystal media are generally used in combination with an organic solvent, for example one of the organic solvents mentioned above.

[0067] The present invention also relates to an electrochromic device comprising a compound of formula (I) or a composition according to the invention. Said device may be selected from an optical article, preferably an optical lens or an optical filter, a window, preferably an aircraft window, a visor, a mirror and a display, in particular a segmented or matrix display. Preferably, the electrochromic device of the invention is an optical article, more preferably an optical lens, and even more preferably an ophthalmic lens.

[0068] Non-limiting examples of ophthalmic lens include corrective and non-corrective lenses, including single vision or multi-vision lenses, which may be either segmented or non-segmented, as well as other elements used to correct, protect, or enhance vision, including without limitation contact lenses, intra-ocular lenses, magnifying lenses and protective lenses or visors. Non-limiting examples of display elements and devices include screens and monitors. Non-limiting examples of windows include automotive, marine and aircraft windows, filters, shutters, and optical switches.

[0069] A preferred device for holding the composition of the invention in a mechanically stable can comprise a pair of opposed substrates having a gap there between for receiving the mixture of the host medium and said compound or said composition of the present invention, and a frame for holding said pair of substrates adjacent one another.

[0070] Another device of the present invention comprises an optical component provided with at least one transparent cell juxtaposed in a parallel direction to the surface thereof, as disclosed in WO 2006/013250, each cell being tightly closed and containing said fluid, mesomorphous or gel host medium and said at least one compound of the present invention. Other devices according to the invention can be a device as described in FR 2937154 or FR2950710 comprising at least one compound of the invention.

EXAMPLES

[0071] This invention will be further illustrated by the following non-limiting examples which are given for illustrative purposes only and should not restrict the scope of the appended claims.

Example 1

Synthesis of compound 1-1: 4,4'-(1,4-phenylene)-bis[(4-pyridyl)-2,6-diphenylpyridinium] bis(tetrafluoroborate)

[0072] Boron trifluoride diethyl etherate (9 equiv.) was added dropwise to a solution of the 1,5-bis(phenyl)-3-(4-pyridyl)pentan-1,5-dione (1 equiv.) and *trans*-chalcone (1.15 equiv.) in hot glacial acetic acid (9 mL). The solution was heated under reflux for 6 hours. After cooling to room temperature diethyl ether (50 mL) was added and the resulting red precipitate was collected by filtration under reduced pressure. The foregoing solid was crystallised from glacial acetic acid to afford 2,6-diphenyl-4-[(1*H*)-pyridinium-4-yl]pyrylium bis(tetrafluoroborates) as a bright orange powder (71 %) after vacuum filtration and washing with anhydrous diethyl ether.

[0073] 2,6-diphenyl-4-[(1*H*)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate) (2.15 equiv.) and sodium acetate (8.5 equiv.) was added to a stirred solution of the 1,4-diaminobenzene (1.0 equiv.) in propan-2-ol (50 mL). The reaction mixture was then heated under reflux for 16 hours whereupon a pale cream/yellow precipitate had formed. Water (25

EP 2 848 668 A1

mL) was then added to the hot suspension and the reaction mixture was stirred at room temperature for 12 hours. The precipitate was collected by vacuum filtration and air dried and then dried at 20 °C under reduced pressure (1 mbar, Buchi Kugelrohr drying pistol) for 24 h to afford compound 1-1 as a yellow-beige powder (71 %), mp = >360 °C, ν_{\max} 3057, 1629, 1594, 1572, 1547, 1496, 1406, 1231, 1049, 1028, 816, 757, 701, 614, 557, 508 cm⁻¹, δ_{H} (300 MHz, d₆-DMSO) 7.25 (16H, m, Ar-H), 7.54 (8H, m, Ar-H), 8.23 (4H, d, J = 6.3 Hz, N-CH=CH), 8.58 (4H, s, PhC=CH), 8.84 (4H, d, J = 6.3 Hz, N-CH=CH).

Example 2

Synthesis of compound 1-4: 4,4'-(1,3-phenylene)-bis[(4-pyridyl)-2,6-diphenylpyridinium] bis(tetrafluoroborate)

[0074] Compound 1-2 was obtained through an equivalent synthesis to example 1 using 1,3-diaminobenzene instead of 1,4-diaminobenzene.

Example 3

Synthesis of compound 1-4: 4,4'-(1,3-phenylene)-bis[1'-*n*-hexyl-2,6-diphenylpyridinium] tetrakis(tetrafluoroborate)

[0075] A stirred solution of compound 1-2 (1 equiv.) and 1-iodohexane (4 equiv.) in acetonitrile (30 mL), protected from daylight, was heated under reflux for ca. 16 hours. The cooled solvent was evaporated to dryness and the residue dissolved in a minimum amount of methanol (ca. 15 mL) and added dropwise to a vigorously stirred solution of NaBF₄ (8-10 equiv.) in water (200 mL). The resulting yellow-orange precipitate was collected by vacuum filtration and washed thoroughly with cold water and dried at 20 °C under reduced pressure (1 mbar, Buchi Kugelrohr drying pistol) for 24 h. Compound 1-4 was obtained as a pale orange-fawn powder (77 %), mp = 212 °C softens, decomp. at 320 °C, ν_{\max} 3613, 3068, 2931, 2863, 1626, 1554, 1420, 1230, 1028, 849, 777, 764, 699, 519 cm⁻¹, δ_{H} (300 MHz, d₄-MeOH) 0.95 (6H, t, J = 7.2 Hz, [(CH₂)₅CH₃]₂), 1.40 (12H, bs, [(CH₂)₃]₂), 2.09 (4H, bm, (CH₂)₂), 4.73 (4H, t, J = 7.2 Hz, (NCH₂)₂), 7.05 (1H, app t, J = 8.1 Hz, NC=CH-CH), 7.15 (8H, m, Ar-H), 7.43 (8H, m, Ar-H), 7.57 (6H, m, Ar-H, NC=CH-CH), 7.74 (1H, app t, J = 1.8 Hz, NC-CH=CN), 8.60 (4H, s, ArC=CH), 8.69 (4H, d, J = 6.6 Hz, NCH=CH), 9.21 (4H, d, J = 6.6 Hz, NCH=CH), δ_{C} (75 MHz, d₄-MeOH) 14.27, 23.46, 26.88, 32.30, 32.51, 63.36, 128.76, 130.08, 130.29, 130.44, 130.55, 131.23, 132.18, 132.34, 133.75, 141.08, 146.87, 151.44, 152.43, 159.36. Found: [M - 3BF₄]³⁺ = 316.1678; C₆₂H₆₂B₄F₁₆N₄ requires [M - 3BF₄]³⁺ = 316.1675.

Example 4

Synthesis of compound 1-3: 4,4'-(1,4-phenylene)-bis[1'-*n*-hexyl-2,6-diphenylpyridinium] tetrakis(tetrafluoroborate)

[0076] Compound 1-3 was obtained through an equivalent synthesis starting from compound 1-1 instead of compound 1-2.

Example 5

Synthesis of compound 1-5: 1,1''-(2-methylpentan-1,5-diyl)bis(2,6-di(*p*-tolyl)-[4,4'-bipyridin]-1-ium) bis(tetrafluoroborate)

[0077] 2,6-di(*p*-tolyl)-4-[(1*H*)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate) was obtained from 1,5-di(*p*-tolyl)-3-(4-pyridyl)pentan-1,5-dione as a bright orange powder after crystallisation from glacial acetic acid (71 %), through an equivalent synthesis to 2,6-diphenyl-4-[(1*H*)-pyridinium-4-yl]pyrylium bis(tetrafluoroborates) of example 1.

[0078] A mixture of 2,6-di-*p*-tolyl-4-[(1*H*)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate) (2.10 g, 4.1 mmol), 2-methylpentan-1,5-diamine (0.21 g, 1.8 mmol) and NaOAc (1.34 g, 16.3 mmol) in isopropanol (30 mL) was heated at reflux for 16 h. After cooling, water (40 mL) was added and the resulting precipitate filtered, washed with water (2 × 20 mL) and air dried to give the compound 1-5 (1.10 g, 65 %) as a grey powder.

Example 6

Synthesis of compound 1-6: 4,4'-(1,5-naphthylene)-bis[2,6-di(*p*-tolyl)pyridinium] tetrakis(tetrafluoroborate)

[0079] 2,6-di-*p*-tolyl-4-[(1*H*)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate) (2.15 equiv.) and sodium acetate (8.5 equiv.), obtained from 1,5-di-*p*-tolyl-3-(4-pyridyl)pentan-1,5-dione, was added to a stirred solution of the 1,5-diaminonaphthalene (1.0 equiv.) in propan-2-ol (50 mL). The reaction mixture was then heated under reflux for ca. 16 hours

whereupon a pale cream/yellow precipitate had formed. Water (25 mL) was then added to the hot suspension and the reaction mixture was stirred at room temperature for ca. 12 hours. The precipitate was collected by vacuum filtration, washed with aqueous ethanol and air dried to give compound 1-6.

5 Example 7

Synthesis of compound 1-7: 1,1''-(2-methylpentan-1,5-diyl)bis(2,6-di(*p*-tolyl)-[4,4'-bipyridin]-1-ium) tetrakis(tetrafluoroborate)

10 **[0080]** A solution of compound 1-5 obtained in example 5 (1.10 g, 1.2 mmol) and 1-iodohexane (1 g, 4.7 mmol) in MeCN (20 mL) was heated at reflux for 16 h, cooled and the volume reduced (to ~10 mL) and Et₂O (60 mL) added. The mixture was stirred for 1 h and decanted. Fresh Et₂O was added and decanted and the residue was air dried, dissolved in MeOH (5 mL) and added dropwise to a solution of NaBF₄ (6.6 g, 60 mmol) in water (200 mL) with rapid stirring. The product was filtered, washed with water (3 × 20 mL) and air dried to give compound 1-7 (0.89 g, 56 %) as an orange powder, δ_H(400 MHz, CD₃OD) 9.07 - 9.13 (4H, m, NCH=CH), 8.58 (2H, d, *J* = 6.8 Hz, NCH=CH), 8.582 (2H, d, *J* = 6.8 Hz, NCH=CH), 8.37 (2H, s, NC(Tol)=CH), 8.34 (2H, s, NC(Tol)=CH), 7.60 - 7.50 (8H, m, Ar-H), 7.45 - 7.35 (8H, m, Ar-H), 4.70 - 4.10 (8H, m, NCH₂), 2.42 (6H, s, Ar-Me), 2.40 (6H, s, Ar-Me), 2.10 - 1.90 (7H, m, aliphatic-H), 1.40 - 0.70 (23H, m, aliphatic-H).

20 Example 8

Synthesis of compound 1-8: 4,4'-(1,4-phenylene)-bis[1'-*n*-hexyl-2,6-di(*p*-tolyl)pyridinium] tetrakis(tetrafluoroborate)

25 **[0081]** 4,4'-(1,4-phenylene)-bis[4-pyridyl]-2,6-di(*p*-tolyl)-pyridinium bis(tetrafluoroborate) was obtained through an equivalent synthesis to example 1 starting from 2,6-di(*p*-tolyl)-4-[(1*H*)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate), obtained from 1,5-di(*p*-tolyl)-3-(4-pyridyl)pentan-1,5-dione.

30 **[0082]** Compound 1-8 was obtained, through an equivalent synthesis to example 3 starting from 4,4'-(1,4-phenylene)-bis[4-pyridyl]-2,6-di(*p*-tolyl)-pyridinium bis(tetrafluoroborate) instead of compound 1-2, as a pale orange powder (63 %), mp = 223 °C softens, decomp. at 293 °C, ν_{max} 3617, 3066, 2929, 2863, 1626, 1552, 1514, 1229, 1027, 858, 814, 520 cm⁻¹, δ_H(300 MHz, d₄-MeOH) 0.94 (6H, t, *J* = 7.2 Hz, [(CH₂)₅CH₃]₂), 1.40 (12H, bs, [(CH₂)₃]₂), 2.09 (4H, bs, (CH₂)₂), 2.51 (12H, s, 4-CH₃C₆H₄), 4.73 (4H, t, *J* = 7.2 Hz, (NCH₂)₂), 7.24 (16H, m, 4-CH₃C₆H₄), 7.48 (4H, s, N-C₆H₄-N), 8.54 (4H, s, ArC=CH), 8.68 (4H, d, *J* = 6.6 Hz, NCH=CH), 9.20 (4H, d, *J* = 6.6 Hz, NCH=CH), δ_C(75 MHz, d₄-MeOH) 14.25, 21.69, 23.46, 26.88, 32.29, 32.50, 63.33, 128.66, 129.97, 130.68, 130.98, 131.07, 131.13, 141.74, 142.45, 146.87, 151.44, 151.79, 159.53. Found: [M - 3BF₄]³⁺ = 334.8549; C₆₆H₇₀B₄F₁₆N₄ requires [M - 3BF₄]³⁺ = 334.8550.

35

Example 9

Synthesis of compound 1-9: 4,4'-(1,3-phenylene)-bis[1'-*n*-hexyl-2,6-di(*p*-tolyl)pyridinium] tetrakis(tetrafluoroborate)

40 **[0083]** Compound 1-9 was obtained through an equivalent synthesis to example 8 using 1,3-diaminobenzene instead of 1,4-diaminobenzene.

Example 10

45 Synthesis of compound 1-10: 4,4'-(1,5-naphthylene)-bis[1'-*n*-hexyl-2,6-di(*p*-tolyl)pyridinium] tetrakis(tetrafluoroborate)

[0084] A stirred solution of compound 1-6 (1 equiv.), obtained in example 6, and 1-iodohexane (4 equiv.) in acetonitrile (30 mL), protected from daylight, was heated under reflux for ca. 16 hours. The cooled solvent was diluted with diethyl ether and the resulting precipitate was collected by vacuum filtration, washed with a minimum amount of diethyl ether and air dried. The foregoing precipitate was dissolved in a minimum amount of methanol (ca. 15 mL) and added dropwise to a vigorously stirred solution of NaBF₄ (8-10 equiv.) in water (200 mL). The resulting precipitate was collected by vacuum filtration and washed thoroughly with cold water and dried at 20 °C. Compound 1-10 was obtained as a pale orange powder (41 %), ν_{max} 3069, 2930, 2867, 1627, 1553, 1511, 1021, 822, 797, 520 cm⁻¹, δ_H(300 MHz, d₆-DMSO) 0.88 (6H, t, *J* = 7.6 Hz, [(CH₂)₅CH₃]₂), 1.33 (12H, bs, [(CH₂)₃]₂), 2.06 (4H, bs, (CH₂)₂), 2.33 (12H, s, 4-CH₃-C₆H₄), 4.71 (4H, t, *J* = 7.2 Hz, (NCH₂)₂), 7.01 (16H, m, Ar-H), 7.58 (4H, m, Ar-H), 8.05 (2H, d, *J* = 7.2 Hz, Ar-H), 8.91 (4H, s, Ar-C=CH), 9.02 (4H, d, *J* = 6.6 Hz, NCH=CH), 9.42 (4H, d, *J* = 6.6 Hz, NCH=CH), δ_C(75 MHz, d₆-DMSO) 13.8, 21.0, 21.8, 25.1, 30.5, 30.7, 61.0, 124.8, 127.0, 127.4, 128.0, 128.3, 128.5, 129.1, 129.2, 130.1, 134.9, 140.5, 145.8, 148.1, 149.8, 157.6. Found: [M - 3BF₄]³⁺ = 351.5269; C₇₀H₇₂BF₄N₄ requires [M - 3BF₄]³⁺ = 351.5279.

Example 11

Synthesis of compound 1-11: 4,4'-(2,2'-dimethyl-4,4'-biphenylene)-bis[1'-n-hexyl-2,6-di(4-methylphenyl)pyridinium] tetrakis(tetrafluoroborate)

5

[0085] 4,4'-(2,2'-dimethyl-4,4'-biphenylene)-bis[2,6-di(4-methylphenyl)pyridinium] tetrakis(tetrafluoroborate) was obtained, through an equivalent synthesis to examples 6 using 3,3'-dimethyl-biphenyl-4,4'-diamine instead of 1,5-diaminonaphthalene.

10

[0086] Compound 1-11 was obtained from 4,4'-(2,2'-dimethyl-4,4'-biphenylene)-bis[2,6-di(4-methylphenyl)pyridinium] tetrakis(tetrafluoroborate), through an equivalent synthesis to example 10, as a tan powder (85 %), ν_{\max} 3073, 2928, 2862, 1625, 1551, 1423, 1021, 853, 822, 519 cm^{-1} , δ_{H} (300 MHz, d_6 -DMSO) 0.87 (6H, t, $J = 7.6$ Hz, $[(\text{CH}_2)_5\text{CH}_3]_2$), 1.32 (12H, bs, $[(\text{CH}_2)_3]_2$), 1.91 (6H, s, (biphenyl- CH_3)₂), 2.01 (4H, bs, $(\text{CH}_2)_2$), 2.29 (12H, s, 4- CH_3 - C_6H_4), 4.71 (4H, t, $J = 7.2$ Hz, $(\text{NCH}_2)_2$), 7.22 (8H, m, Ar-H), 7.38 (8H, m, Ar-H), 7.51 (4H, m, Ar-H), 7.80 (2H, d, $J = 8.4$ Hz, Ar-H), 8.92 (4H, s, Ar-C=CH), 9.02 (4H, d, $J = 6.9$ Hz, $\text{NCH}=\text{CH}$), 9.43 (4H, d, $J = 6.9$ Hz, $\text{NCH}=\text{CH}$), δ_{C} (75 MHz, d_6 -DMSO) 13.8, 17.2, 20.8, 21.0, 25.1, 30.5, 30.7, 61.0, 124.0, 127.0, 128.1, 128.7, 128.9, 129.2, 129.6, 130.4, 133.8, 137.9, 138.8, 140.9, 145.7, 148.3, 149.4, 157.1. Found: $[\text{M} - 3\text{BF}_4]^{3+} = 369.5432$; $\text{C}_{74}\text{H}_{78}\text{BF}_4\text{N}_4$ requires $[\text{M} - 3\text{BF}_4]^{3+} = 369.5425$.

15

Example 12

20

Synthesis of compound 1-12: 4,4'-(9H-fluorene-9,9-diyl)-bis(1,4-phenylene)-bis[1'-n-hexyl-2,6-di(4-methylphenyl)pyridinium] tetrakis(tetrafluoroborate)

25

[0087] 4,4'-(9H-fluorene-9,9-diyl)-bis(1,4-phenylene)-bis[2,6-di(4-methylphenyl)pyridinium] tetrakis(tetrafluoroborate) was obtained, through an equivalent synthesis to examples 6 using 9H-fluorene-9,9-diamine instead of 1,5-diaminonaphthalene.

30

[0088] Compound 1-12 was obtained from 4,4'-(9H-fluorene-9,9-diyl)-bis(1,4-phenylene)-bis[2,6-di(4-methylphenyl)pyridinium] tetrakis(tetrafluoroborate), through an equivalent synthesis to example 10, as a pale yellow powder (96 %), δ_{H} (300 MHz, d_6 -DMSO) 0.88 (6H, t, $J = 7.2$ Hz, $[(\text{CH}_2)_5\text{CH}_3]_2$), 1.31 (12H, bs, $[(\text{CH}_2)_3]_2$), 1.99 (4H, bm, $(\text{CH}_2)_2$), 2.28 (12H, s, 4- CH_3 - C_6H_4), 4.70 (4H, t, $J = 7.5$ Hz, $(\text{NCH}_2)_2$), 6.62 (4H, d, $J = 8.7$ Hz, Ar-H), 7.08 (2H, d, $J = 7.5$ Hz, Ar-H), 7.16 (8H, m, Ar-H) 7.24 (12H, m, Ar-H), 7.33 (2H, app. t, Ar-H), 7.44 (2H, app. t, Ar-H), 7.89 (2H, d, $J = 7.2$ Hz, Ar-H), 8.88 (4H, s, Ar-C=CH), 9.02 (4H, d, $J = 6.9$ Hz, $\text{NCH}=\text{CH}$), 9.42 (4H, d, $J = 6.9$ Hz, $\text{NCH}=\text{CH}$).

Example 13

35

Synthesis of compound 1-13: 4,4'-(1,4-phenylene)-bis[1'-n-hexyl-2,6-di(4-trifluoromethylphenyl)pyridinium] tetrakis(tetrafluoroborate)

40

[0089] 4,4'-(1,4-phenylene)-bis[(4-pyridyl)-2,6-di(4-trifluoromethylphenyl)pyridinium] bis(tetrafluoroborate) was obtained through an equivalent synthesis to example 1 starting from 2,6-di(4-trifluoromethylphenyl)-4-[(1H)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate), obtained from 1,5-di(4-trifluoromethylphenyl)-3-(4-pyridyl)pentan-1,5-dione.

45

[0090] Compound 1-13 was obtained, through an equivalent synthesis to example 3 starting from 4,4'-(1,4-phenylene)-bis[(4-pyridyl)-2,6-di(4-trifluoromethylphenyl)pyridinium] bis(tetrafluoroborate) instead of compound 1-2, as a pale pink powder (50 %), mp = 275.7°C decomp., ν_{\max} 3072, 2935, 2867, 1632, 1619, 1558, 1322, 1111, 1031, 833, 666, 520 cm^{-1} , δ_{H} (300 MHz, d_4 -MeOH) 0.91 (6H, bs, $[(\text{CH}_2)_5\text{CH}_3]_2$), 1.38 (12H, bs, $[(\text{CH}_2)_3]_2$), 2.06 (4H, bs, $(\text{CH}_2)_2$), 4.70 (4H, bs, $(\text{NCH}_2)_2$), 7.61 (20H, m, 4- CF_3 - C_6H_4 , N- C_6H_4 -N), 8.66 (4H, bs, $\text{NCH}=\text{CH}$), 8.70 (4H, s, ArC=CH), 9.19 (4H, d, $J = 4.5$ Hz, $\text{NCH}=\text{CH}$), δ_{C} (75 MHz, d_6 -DMSO) 11.50, 20.71, 24.14, 29.54, 29.76, 60.69, 120.48, 124.08, 124.22, 126.02, 128.25, 128.65, 129.17, 130.56, 131.00, 134.74, 138.66, 144.25, 148.21, 150.24, 154.95. Found: $[\text{M} - 4\text{BF}_4]^{4+} = 283.6116$; $\text{C}_{66}\text{H}_{58}\text{B}_4\text{F}_{28}\text{N}_4$ requires $[\text{M} - 4\text{BF}_4]^{4+} = 283.6112$.

50

Example 14

Synthesis of compound 1-14: 1-{4-[1'-n-hexyl-2,6-di(4-methylphenyl)pyridinium]}-4-{4'-[1'-n-hexyl-2,6-di(4-trifluoromethylphenyl)pyridinium]}phenylene, tetrakis(tetrafluoroborate)

55

[0091] 2,6-Di(4-methylphenyl)-4-[(1H)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate), prepared as outlined in Example 5, (3.00 g, 5.8 mmol) was added portionwise to a warm (80 °C) stirred solution of 1,4-diaminobenzene (3.79 g, 35.0 mmol) and sodium acetate (0.96g, 11.7 mmol) in propan-2-ol (30 mL). Upon completion of the addition of the 2,6-di(4-methylphenyl)-4-[(1H)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate) the reaction mixture was stirred at 80 °C for 3 hours.

After cooling the precipitated solid was collected by vacuum filtration. The precipitate was then washed with propan-2-ol/water to give the 1-(4-aminophenyl)-2,6-di(4-methylphenyl)-4-(4-pyridyl)pyridinium tetrafluoroborate after drying as a pale brown powder (89 %), mp = 172 - 176 °C, ν_{\max} 3488, 3392, 3034, 1621, 1597, 1513, 1402, 1312, 1235, 1094, 1050, 988, 893, 814, 539, 517 cm^{-1} , δ_{H} (300 MHz, d_4 -MeOH) 2.35 (6H, s, $\text{CH}_3\text{C}_6\text{H}_4$), 6.40 (2H, m, $\text{H}_2\text{NC}-\text{CH}$), 6.89 (2H, m, $\text{H}_2\text{NC}-\text{C}=\text{CH}$), 7.10 (4H, m, $\text{CH}_3\text{C}-\text{CH}=\text{CH}$), 7.32 (4H, m, $\text{CH}_3\text{C}-\text{CH}=\text{CH}$), 8.09 (2H, dd, $J = 4.5, 1.8$ Hz, $\text{N}-\text{CH}=\text{CH}$), 8.49 (2H, s, $\text{ArC}=\text{CH}$), 8.83 (2H, dd, $J = 4.5, 1.8$ Hz, $\text{N}-\text{CH}=\text{CH}$), NH_2 signal absent in d_4 -MeOH due to exchange but resonates as a broadened singlet at δ 3.87 in CDCl_3 , δ_{C} (75 MHz, d_4 -MeOH) 21.34, 114.63, 118.49, 123.89, 127.68, 129.74, 130.11, 130.34, 130.92, 131.96, 141.94, 144.16, 151.15, 151.68, 154.69, 159.73. Found: $[\text{M} - \text{BF}_4]^{+} = 428.2115$; $\text{C}_{30}\text{H}_{26}\text{BF}_4\text{N}_3$ requires $[\text{M} - \text{BF}_4]^{+} = 428.2121$.

[0092] 2,6-Di(4-trifluoromethylphenyl)-4-[(1*H*)-pyridinium-4-yl]pyrylium bis(tetrafluoroborate) (1.1 equiv.) and sodium acetate (5 equiv.) was added to a stirred solution of the foregoing 1-(4-aminophenyl)-2,6-di(4-methylphenyl)-4-(4-pyridyl)pyridinium tetrafluoroborate (1.0 equiv.) in propan-2-ol (50 mL). The reaction mixture was then heated under reflux for 15 hours whereupon a pale cream coloured precipitate had formed. Water (30 mL) was then added to the hot suspension and the reaction mixture was stirred at room temperature for 12 hours. The precipitate, 1-{4-[(4-pyridyl)-2,6-di(4-methylphenyl)pyridinium]}-4-[4'-[(4-pyridyl)-2,6-di(4-trifluoro-methylphenyl)pyridinium]]phenylene bis(tetrafluoroborate), was collected by vacuum filtration and air dried and then dried at 20 °C under reduced pressure (1 mbar, Buchi Kugelrohr drying pistol) for 24 h. A stirred solution of the foregoing dried 1-{4-[(4-pyridyl)-2,6-di(4-methylphenyl)pyridinium]}-4-[4'-[(4-pyridyl)-2,6-di(4-trifluoromethylphenyl)pyridinium]]phenylene bis(tetrafluoroborate) (1 equiv.) and 1-iodohexane (4 equiv.) in acetonitrile (35 mL), protected from daylight, was heated under reflux for 20 hours. The cooled solvent was evaporated to dryness and the residue dissolved in a minimum amount of methanol (10 mL) and added dropwise to a vigorously stirred solution of NaBF_4 (8 equiv.) in water (200 mL). The resulting yellow-orange precipitate was collected by vacuum filtration and washed thoroughly with cold water and dried at 20 °C under reduced pressure (1 mbar, Buchi Kugelrohr drying pistol) for 24 h to afford compound 1-14 as a pale brown powder 91 %, mp = 295 - 297 °C, δ_{H} (300 MHz, d_4 -MeOH) 0.94 (6H, t, $J = 7.2$ Hz, $[(\text{CH}_2)_5\text{CH}_3]_2$), 1.42 (12H, bm, $[(\text{CH}_2)_3]_2$), 2.09 (4H, bm, $(\text{CH}_2)_2$), 2.49 (6H, s, 4- $\text{CH}_3\text{C}_6\text{H}_4$), 4.73 (4H, t, $J = 7.2$ Hz, $(\text{NCH}_2)_2$), 7.25 (8H, m, 4- $\text{CH}_3\text{C}_6\text{H}_4$), 7.53 (4H, s, $\text{N}-\text{C}_6\text{H}_4-\text{N}$), 7.60 (4H, m, $\text{F}_3\text{C}-\text{C}-\text{CH}=\text{CH}$), 7.69 (4H, m, $\text{F}_3\text{C}-\text{C}-\text{CH}=\text{CH}$), 8.64 (2H, s, $\text{ToI}-\text{C}=\text{CH}$), 8.69 (4H, m, $\text{NCH}=\text{CH}$), 8.75 (2H, s, 4- $\text{CF}_3\text{C}_6\text{H}_4-\text{C}=\text{CH}$), 9.21 (4H, m, $\text{NCH}=\text{CH}$), δ_{C} (75 MHz, d_6 -DMSO) 13.77, 20.68, 21.82, 25.08, 30.51, 30.68, 61.06, 121.89, 125.51, 126.93, 128.10, 128.85, 128.95, 129.22, 129.60, 129.70, 129.81, 130.24, 130.69, 136.21, 139.06, 140.18, 140.49, 145.75, 145.91, 147.37, 147.88, 148.90, 149.38, 155.60, 157.08. Found: $[\text{M} - 2\text{BF}_4]^{2+} = 599.2575$; $\text{C}_{66}\text{H}_{64}\text{B}_4\text{F}_{22}\text{N}_4$ requires $[\text{M} - 2\text{BF}_4]^{2+} = 599.2578$.

Example 15

Synthesis of compound 2-1: 1,1''-(1,3-phenylenebis(methylene))bis(3',5'-bis(ethoxycarbonyl)-2',6'-dimethyl-[4,4'-bipyridin]-1-ium) bis-tetrafluoroborate)

[0093] *m*-Xylene dibromide (0.66 g, 2.5 mmol) and diethyl 2,6-dimethyl-4,4'-bipyridine-3,5-dicarboxylate (3.28 g, 10 mmol) were refluxed in MeCN (50 mL). After 2 days the solvent was removed under reduced pressure and residue was crystallised from DCM-hexane by slow evaporation to give the dibromide salt (2.17 g, 94 %) as a cream powder. The foregoing dibromide salt (1 g, 1.1 mmol) was dissolved in water (10 mL) and added dropwise to a solution of sodium tetrafluoroborate (1.43 g, 13 mmol) in water (10 mL) with stirring. After 0.5 h the precipitate was filtered off and dried to give compound 2-1 (0.82 g, 81 %) as tan needles, δ_{H} (400 MHz, d_6 -DMSO) 9.32 (4H, d, $J = 6.8$ Hz, $\text{NCH}=\text{CH}$), 8.22 (4H, d, $J = 6.8$ Hz, $\text{NCH}=\text{CH}$), 7.91 (1H, s, Ar-H), 7.70 - 7.50 (3H, m, Ar-H), 5.94 (4H, s, NCH_2), 3.98 (8H, q, $J = 7.2$ Hz, OCH_2CH_3), 2.62 (12H, s, CH_3), 0.768 (12H, t, $J = 7.2$ Hz, OCH_2CH_3).

Example 16

Synthesis of compound 2-2: 1,1''-(1,4-phenylenebis(methylene))bis(3',5'-bis(ethoxycarbonyl)-2',6'-dimethyl-[4,4'-bipyridin]-1-ium) bis-tetrafluoroborate)

[0094] *p*-Xylene dibromide (0.5 g, 1.9 mmol) and diethyl 2,6-dimethyl-4,4'-bipyridine-3,5-dicarboxylate (1.86 g, 5.7 mmol) was refluxed in MeCN (50 mL). After 16 h, the mixture was cooled, filtered and washed with acetone (30 mL) and Et_2O (30 mL) and air dried to give the dibromide salt (1.6 g, 92 %) as a colourless powder. The foregoing dibromide salt (1 g, 1.1 mmol) was dissolved in MeOH-water (100 mL, 1:4) and added dropwise to sodium tetrafluoroborate (7.2 g, 65 mmol) in water (350 mL) to give, in the same manner as described for example 15, compound 2-2 (0.87 g, 96 %) as tan needles, δ_{H} (400 MHz, d_6 -DMSO) 9.32 (4H, d, $J = 6.8$ Hz, $\text{NCH}=\text{CH}$), 8.20 (4H, d, $J = 6.8$ Hz, $\text{NCH}=\text{CH}$), 7.69 (4H, s, Ar-H), 5.92 (4H, s, NCH_2), 3.97 (8H, q, $J = 7.2$ Hz, OCH_2CH_3), 2.61 (12H, s, CH_3), 0.76 (12H, t, $J = 7.2$ Hz, OCH_2CH_3).

Example 17

Evaluation of oxido-reduction potential and of the absorption spectrum of the compounds of the invention

5 **[0095]** The oxido-reduction potentials of the compounds are measured by a method of cyclic voltammetry with 3 electrodes.

[0096] The 3 electrodes used are:

- 1 Platinum working electrode
- 10 - 1 Platinum auxiliary or counter electrode
- 1 Platinum reference electrode which is immersed into a solution consisting of 0.01M AgNO₃ + 0.1M TBAP (tetrabutylammonium perchlorate) in acetonitrile.

15 **[0097]** The potential values indicated are the first oxidative potential for the compounds, with regards to the standard hydrogen reference electrode (SHE).

[0098] The analyzed solution comprises 0.01M of the compound to be analyzed and 1M of TBAP salt.

[0099] The scan rate of the potential is fixed to 100mV/s.

20 **[0100]** The absorption spectra of the compounds are measured with a solution comprising 0.01M of the compound to be analyzed, 0.02M Phenothiazine (Phtz) or 10-Methylphenothiazine (Mephtz) and 1M of TBAP salt in propylene carbonate as solvent.

[0101] This solution is introduced into a quartz tank where at least one glass electrode coated with Indium Tin Oxide (ITO) is placed in order to colour the analyzed compound on this electrode. The absorption spectrum of the compound in the time domain is measured by a spectrophotometer.

25 **[0102]** The reductive agent (phenothiazine for all compounds except compounds 1-6 and 1-7 using 10-methylphenothiazine) is colouring on another glass electrode coated with Indium Tin Oxide (ITO).

[0103] The potential applied between both electrodes, for activating the compounds, is equal to the addition, in absolute value, of E_{red}^1 of the compound + E_{ox}^1 of phenothiazine (which is $E_{ox}^1 = 0.36V$) or methylphenothiazine (which is $E_{ox}^1 = 0.45V$).

30 **[0104]** The absorption spectrum is read after 3 min of activation, in particular the λ_{max} value, which corresponds to the maximum absorption peak within the visible spectrum (between 400 and 800 nm).

[0105] The results for each of the synthesized compounds are indicated in Table 1 below. E_{red}^1 corresponds to the first oxidative potential. The colour indicated in Table 1 is the visual colour perceived by emmetropic eyes under the day light. It should be noted that the λ_{max} value is just orienting the colour of the molecule, but the whole absorption spectrum has to be taken into account in order to understand the final perceived colour of one compound.

35

40

45

50

55

5

10

15

20

25

30






35

40

45

50

Table 1

Compound	Formula	E ¹ _{red} (V)	λ_{max} (nm)	Colour
1-1		-0.73	544	red
1-2		-0.70	420	Yellow
1-3		-0.76	629	green
1-4		-0.76	630	green
1-5		-0.79	721	green

55

5

10

15

20

25

30

35






40

45

50

55

(continued)

Compound	Formula	E ¹ _{red} (V)	λ _{max} (nm)	Colour
1-6		-0.75	547	red
1-7		-0.8	741	green
1-8		-0.78	643	green
1-9		-0.78	628	green
1-10		-0.77	628	green

5

10

15

20

25

30

35

40

45

50

(continued)

Compound	Formula	E ¹ _{red} (V)	λ _{max} (nm)	Colour
1-11		-0.79	643	green
1-12		-0.81	632	green
1-13		-0.65	642	green

55

5

10

15

20

25

30

35

40

45

50

55

(continued)


Compound	Formula	E ¹ _{red} (V)	λ_{max} (nm)	Colour
1-14		/	/	/
2-1		-1.35	/	/
2-2		-1.34	/	/

Claims

1. Compound of formula (I) :

5

10



15

(I)

wherein:

- Z is selected from:

20

- alkylene;
- cycloalkylene; and
- a bivalent group of formula -R⁵-Y-R⁶-, wherein

25

- R⁵ and R⁶ are each independently selected from single bond, alkylene and cycloalkylene, and
- Y is selected from arylene, cycloalkylene, heteroarylene, arylene-arylene or arylene-CR^RR^R-arylene wherein R and R form together with the carbon to which they are linked a carbocyclic group;

30

wherein said alkylene, cycloalkylene, arylene, heteroarylene, and carbocyclic groups may be substituted by one or more substituents selected from halogen, alkyl, alkoxy, alkylthio, hydroxyalkyl, acyloxy, cycloalkyl, aryl, substituted aryl, aryloxy, heteroaryl and substituted heteroaryl;

35

- A and B are respectively selected from nitrogen and -N⁺(R^{7a})-, and from nitrogen and -N⁺(R^{7b})-, wherein R^{7a} and R^{7b} are independently selected from:

40

- alkyl which may be substituted by one or more groups independently selected from halogen, alkoxy, cycloalkyl, vinyl, allyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl;
- aryl and heteroaryl which may be both substituted by one or more groups independently selected from:

45

- halogen, cyano, nitro, alkyl, haloalkyl, arylalkyl, cycloalkyl, cycloalkylalkyl and heterocycloalkylalkyl, alkenyl, alkynyl, allyl, vinyl, aryl, substituted aryl, heteroaryl, substituted heteroaryl, -N(aryl)₂, -N(aryl)CO(aryl), -CO-aryl and -CO-substituted aryl;
- -OR⁸, -SR⁸, -S(O)R⁸, -S(O₂)R⁸, -S(O₂)NR⁸R⁹, -NR⁸R⁹, -NR⁸COR⁹, -NR⁸CO(aryl), -NR⁸aryl, -CH₂OR⁸, -CH₂SR⁸, -CH₂R⁸, -CO-R⁸ and -CO₂R⁸ wherein R⁸ and R⁹ are independently selected from H, alkyl, haloalkyl, arylalkyl, cycloalkyl, cycloalkylalkyl and heterocycloalkylalkyl;
- -S(O₂)NR¹⁰R¹¹ and -NR¹⁰R¹¹ wherein R¹⁰ and R¹¹ form together with the nitrogen atom to which they are linked a saturated 5 to 7 membered heterocycloalkyl which may comprise in addition to the nitrogen atom one further heteroatom selected from oxygen, nitrogen and sulfur, and which may be optionally substituted by one or two groups independently selected from halogen, -R⁸, -OR⁹, and -NR⁸R⁹, wherein R⁸ and R⁹ are as defined above;
- -V-W-R¹² wherein:

50

- V is selected from oxygen, -N(R⁸)-, sulfur, -S(O)- and -S(O₂)-wherein R⁸ is as defined above;
- W is alkylene, which may be substituted by one or more groups independently selected from halogen and alkoxy; and
- R¹² is selected from -OR⁸, -NR⁸(alkyl) and -SR⁸ wherein R⁸ is as defined above; and

55

- -OC(O)-R¹³ wherein R¹³ is selected from alkyl, haloalkyl, alkenyl, -W-R¹², and aryl group which may

be substituted by 1 to 4 groups selected from halogen, $-R^8$, $-OR^8$, $-SR^8$, $-NR^8R^9$, $-NR^{10}R^{11}$, $-CO-R^8$, $-C(O)OR^8$ wherein R^8 , R^9 , R^{10} , R^{11} , R^2 and W are as defined above.




$-R^1_a, R^1_b, R^1_c, R^1_d, R^2_a, R^2_b, R^2_c, R^2_d, R^3_a, R^3_b, R^3_c, R^3_d, R^4_a, R^4_b, R^4_c$ and R^4_d are each independently selected from H, alkyl, alkoxy, alkylthio, haloalkyl, haloalkoxy, haloalkylthio, poly(alkylenoxy), alkoxycarbonyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl, wherein the alkyl group may be substituted by one or more substituents independently selected from alkoxy, cycloalkyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl;


wherein at least one of $R^1_a, R^1_b, R^1_c, R^1_d, R^2_a, R^2_b, R^2_c, R^2_d, R^3_a, R^3_b, R^3_c, R^3_d, R^4_a, R^4_b, R^4_c$ and R^4_d is not H;

- X- is a counterion; and


- m is 2 if A and B are nitrogen, 3 if one of A and B is nitrogen and the other is not nitrogen, and 4 if both A and B are not nitrogen.

2. The compound according to claim 1, wherein Z is selected from C_1 - C_{12} alkylene, aryl substituted C_1 - C_{12} alkylene, phenylene, naphthylene, $(C_1$ - C_4 alkylene)-phenylene- $(C_1$ - C_4 alkylene), $(C_1$ - C_4 alkylene)-naphthylene- $(C_1$ - C_4 alkylene), quinoxaline-2,3-diyl, $(C_1$ - C_4 alkylene)-quinoxaline-2,3-diyl- $(C_1$ - C_4 alkylene), phenylene-phenylene, $(C_1$ - C_4 alkylene)-phenylene-phenylene- $(C_1$ - C_4 alkylene) and phenylene-fluorenylene-phenylene, preferably Z is selected from $-CH_2-$, $-(CH_2)_2-$, $-(CH_2)_3-$, $-(CH_2)_4-$, $-(CH_2)_5-$, $-CH_2-CH(CH_3)-CH_2-$, $-CH_2-CH(CH_2Phenyl)-CH_2-$, $-(CH_2)_2-CH(CH_3)-CH_2-$, $-(CH_2)_3-CH(CH_3)-CH_2-$, $-(CH_2)_2-CH(CH_3)-(CH_2)_2-$,





- 20
3. The compound according to claim 1 or 2, wherein A and B are respectively selected from nitrogen and $-N^+(R^{7a})-$, and from nitrogen and $-N^+(R^{7b})-$, wherein R^{7a} and R^{7b} are independently selected from C_6-C_8 alkyl, phenyl and naphthyl which may be both substituted by one or more substituents selected from halogen, cyano, nitro, hydroxy, C_1-C_4 alkyl, C_1-C_4 haloalkyl, C_1-C_4 alkoxy, C_1-C_4 haloalkoxy, C_1-C_4 alkylthio, C_1-C_4 haloalkylthio, C_3-C_7 cycloalkyl, $(C_3-C_7$ cycloalkyl) C_1-C_4 alkyl.
- 25
4. The compound according to any one of claims 1 to 3, wherein the counterion X^- is selected from halide, tetrafluoroborate, tetraphenylborate, hexafluorophosphate, nitrate, methanesulfonate, trifluoromethane sulfonate, toluene sulfonate, hexachloroantimonate, bis(trifluoromethanesulfonyl)imide, perchlorate, acetate and sulfate.
- 30
5. The compound according to any one of claims 1 to 4, wherein $R^1_a, R^1_b, R^1_c, R^1_d, R^2_a, R^2_b, R^2_c, R^2_d, R^3_a, R^3_b, R^3_c, R^3_d, R^4_a, R^4_b, R^4_c$ and R^4_d are each independently selected from hydrogen, aryl, substituted aryl, heteroaryl and substituted heteroaryl, preferably selected from optionally substituted phenyl, more preferably selected from phenyl, tolyl and cumyl.
- 35
6. The compound according to any one of claims 1 to 5, wherein said compound is represented by formula (I-1):




(I-1)

50

wherein Z, A, B, $R^1_a, R^1_b, R^1_c, R^1_d, R^2_a, R^2_b, R^2_c, R^2_d, X^-$ and m are as defined in claims 1 to 5.

- 55
7. The compound according to any one of claims 1 to 5, wherein said compound is represented by formula (I-3):

5



$m X^-$

10

(I-3)


15

wherein Z, A, B, X^- and m are as defined in claims 1 to 5, and R^1 and R^2 are each independently selected from H, alkyl, alkoxy, alkylthio, haloalkyl, haloalkoxy, haloalkylthio, polyalkylenoxy, alkoxy carbonyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl, wherein the alkyl group may be substituted by one or more substituents independently selected from alkoxy, cycloalkyl, aryl, substituted aryl, heteroaryl and substituted heteroaryl, provided that at least one of R^1 and R^2 is not H.

20

8. The compound according to any one of claims 1 to 5, wherein said compounds are represented by formula (I-4):

25



$m X^-$

30


(I-4)

wherein Z, A, B, R^3_a , R^3_b , R^3_c , R^3_d , R^4_a , R^4_b , R^4_c , R^4_d , X^- and m are as defined in claims 1 to 5.

35


9. The compound according to any one of claims 1 to 5, wherein said compound is selected from:

40




45

50




55

5




10




15

20




25

30




35

40







45





50



55


5
10
15
20
25
30
35
40
45
50
55





10. Method for preparing the compound (I-3) as defined in claim 7, comprising the step of reacting a 2,6-disubstituted-4-[(1H)-pyridinium-4-yl]pyridinium bis(tetrafluoroborate) (1) with a diamine (2):

55



11. Electrochromic composition comprising at least one compound as defined in claims 1 to 9.
- 15 12. The electrochromic composition according to claim 10, wherein said composition comprises a fluid, mesomorphous or gel host medium.
13. The electrochromic composition according to claim 12, wherein the fluid or mesomorphous host medium is selected from the group consisting of organic solvents, liquid crystals, polymers, liquid crystal polymers and mixtures thereof.
- 20 14. Electrochromic device comprising a compound according to any one of claims 1 to 9, or a composition according to any one of claims 11 to 13.
- 15 15. The electrochromic device according to claim 14, wherein said device comprises a mechanism for holding said compound or said composition in a mechanically stable environment.
16. The electrochromic device according to claim 15, wherein said device comprises a pair of opposed substrates having a gap there between for receiving said compound or said composition, and a frame for holding said pair of substrates adjacent one another.
- 30 17. The electrochromic device according to claim 15, wherein said device comprises an optical component provided with at least one transparent cell juxtaposed in a parallel direction to the surface thereof, each cell being tightly closed and containing said compound or said composition.
- 35 18. The electrochromic device according to any one of claims 12 to 17, wherein said electrochromic device is selected from an optical article, preferably an optical lens or an optical filter, a window, notably an aircraft window, a visor, a mirror and a display, more preferably an optical article selected from optical lenses, and most preferably an optical article selected from ophthalmic lenses.

40

45

50

55



EUROPEAN SEARCH REPORT

Application Number
EP 13 18 4780

5

10

15

20

25

30

35

40

45

50

55

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
X A	US 7 106 489 B2 (BERNETH HORST [DE] ET AL) 12 September 2006 (2006-09-12) * pages 14-17; claims *	1-8, 11-18 9,10	INV. C09K9/02 C07D213/80 C07D213/06
X A	EP 1 156 098 A2 (BAYER AG [DE]) 21 November 2001 (2001-11-21) * paragraphs [0015], [0028], [0029]; claim 4; figure 1 *	1-8, 11-18 9,10	C07D213/22 C07D213/26
X A	US 4 116 535 A (PONJEE JOHANNES JACOBUS ET AL) 26 September 1978 (1978-09-26) * column 1, lines 45-56; tables A,E * * column 2, lines 16-55 * * column 5, lines 1-18 *	1,2,4-8, 11-18 3,9,10	
X	US 2005/231784 A1 (SHINOHARA RYUJI [JP] ET AL) 20 October 2005 (2005-10-20) * page 13; figures *	1,2,4-8, 11-18	
X	WO 2011/082354 A2 (OREGON STATE; STRONGIN ROBERT M; SIBRIAN-VAZQUEZ MARTHA OREGON STATE []) 7 July 2011 (2011-07-07) * claim 1 *	1-8	TECHNICAL FIELDS SEARCHED (IPC) C09K C07D
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 20 February 2014	Examiner Baldé, Kaisa
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPC FORM 1503 03.02 (P/C/C01)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 13 18 4780

5

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

20-02-2014

10

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 7106489 B2	12-09-2006	AT 316129 T	15-02-2006
		AU 6390701 A	26-11-2001
		DE 10023765 A1	22-11-2001
		EP 1285040 A1	26-02-2003
		ES 2256245 T3	16-07-2006
		JP 2003533583 A	11-11-2003
		KR 20030007614 A	23-01-2003
		US 2003206326 A1	06-11-2003
		WO 0188060 A1	22-11-2001
EP 1156098 A2	21-11-2001	DE 10023744 A1	13-12-2001
		EP 1156098 A2	21-11-2001
		JP 2002049061 A	15-02-2002
		US 2002027700 A1	07-03-2002
US 4116535 A	26-09-1978	AU 512745 B2	23-10-1980
		AU 2496277 A	09-11-1978
		CA 1099091 A1	14-04-1981
		DE 2718910 A1	17-11-1977
		FR 2351463 A1	09-12-1977
		GB 1564266 A	02-04-1980
		JP S612710 B2	27-01-1986
		JP S52135884 A	14-11-1977
		US 4116535 A	26-09-1978
		US 2005231784 A1	20-10-2005
WO 2011082354 A2	07-07-2011	CN 102781934 A	14-11-2012
		EP 2574193 A2	03-04-2013
		JP 2013516430 A	13-05-2013
		RU 2012132313 A	10-02-2014
		US 2012276649 A1	01-11-2012
		WO 2011082354 A2	07-07-2011

15

20

25

30

35

40

45

50

55

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 20090082570 A1 [0055]
- WO 2006013250 A [0070]
- FR 2937154 [0070]
- FR 2950710 [0070]

Non-patent literature cited in the description

- **J. E. DOWNES.** Aryl-substituted Derivatives of 4,4'-Bipyridylium Salts: their Spectroscopic Properties and Stereochemistry. *J. Chem. Soc. (C)*, 1967, 1491 [0059]
- **E. L. CLENNAN ; C. LIAO ; E. AYOKOSOK.** Perylene: Synthesis, Structural, Electrochemical, and Photophysical Characterization of a New Class of Electron Transfer Sensitizers. *J. Am. Chem. Soc.*, 2008, vol. 130, 7552 [0059]