

We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

4,800

Open access books available

122,000

International authors and editors

135M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.

For more information visit www.intechopen.com



Silver nanoparticles: sensing and imaging applications

Carlos Caro¹, Paula M. Castillo¹, Rebecca Klippstein²,
David Pozo² and Ana P. Zaderenko¹

¹*Department of Physical, Chemical and Natural Systems, Pablo de Olavide University*

²*CABIMER-Andalusian Center for Molecular Biology and Regenerative Medicine CSIC-
University of Seville-UPO-Junta de Andalucía
Spain*

1. Introduction

Recent advances in nanotechnology have allowed the development of robust, and highly sensitive and selective detection methods that are expected to address some deficiencies of conventional detection technologies. Within this context gold and silver nanoparticles have emerged as a powerful tool in sensing and imaging applications due to their surprising optical properties.

Although silver exhibits many advantages over gold, such as higher extinction coefficients, sharper extinction bands, higher ratio of scattering to extinction, and extremely high field enhancements, it has been employed far less in the development of sensors, with the exception of sensors based on surface enhanced spectroscopies. The reason for this is the lower chemical stability of silver nanoparticles when compared to gold. Nevertheless, recent developments include means of protecting efficiently silver nanoparticles that offer far improved chemical stabilities. As a consequence, silver nanoparticles are rapidly gaining in popularity and several research groups have begun to explore alternative strategies for the development of optical sensors and imaging labels based on the extraordinary optical properties of these metal nanoparticles.

In the present chapter, we will focus on recent developments regarding silver nanoparticles and their emerging sensing applications.

2. Surface plasmon

Noble metal nanoparticles display unique optical properties that differentiate them from their bulk counterparts. Probably the most fascinating finding, regarding this peculiar optical performance, is that they often exhibit strong extinction bands in the visible spectrum, and therefore bright and gaudy colours, that are not present in the spectrum of the bulk metal. Although these colours are reminiscent of molecular dyes, it is important to

emphasize that their fundamentals are different. While the spectra of molecular dyes can be understood only in terms of quantum mechanics, the extinction spectra of metal nanoparticles can be treated in terms of classical electromagnetism. Moreover, metal nanoparticles also scatter light with high efficiency and, unlike molecular dyes, their extinction spectra are really a combination of both absorption and scattering (Kelly et al., 2002). The interaction of the oscillating electromagnetic field of the light with metal nanoparticles, results in the collective coherent oscillation of the metal conduction electrons with respect to the nanoparticle positive lattice. At a particular frequency of the light this process is resonant, receiving the name of *Localized Surface Plasmon Resonance*, LSPR (Figure 1), and is the responsible of the strong extinction band exhibited by the nanoparticle. Additionally to the extremely high molar extinction coefficients and resonant Rayleigh scattering, LSPR also results in enhanced local electromagnetic fields near the surface of the nanoparticle (Novotny & Hecht, 2006).




Fig. 1. Schematic representation of surface plasmon (electronic cloud) oscillation under the effect of an electromagnetic field

The first theoretical approach for modelling the optical properties of nanoparticles proposed by Mie, within classical electromagnetic formalisms, is still in common use today. According to the Mie theory, the resonance condition is achieved when the real part of the dielectric function of the metal equals the dielectric function of the surrounding medium (Mie, 1908). Therefore, the LSPR frequency depends both on the nanoparticle itself and on the medium where it is dispersed. Two important consequences arise from this dependency, on the one hand, the LSPR is tunable, i.e., its frequency can be modified through changes in the nanoparticle composition, size and shape (Kelly et al., 2003). On the other hand, metal nanoparticles are sensitive to their local environment, i.e., changes in the dielectric properties of their surroundings results in LSPR shifts that can be measured. Both tunability and sensitivity of LSPR convert metal nanoparticles in materials of choice for optical sensing and imaging applications. The most suitable metals are silver and gold, since the localized plasmon resonance condition mentioned above is satisfied at visible light frequencies. Additional advantages of these metal nanoparticles include simple preparation methods for a wide range of sizes and shapes and easy surface conjugation to a variety of ligands.

Over the last decade, several types of sensors have been developed on the basis of the plasmonic properties of noble metal nanoparticles i.e., extremely high molar extinction coefficients and resonant Rayleigh scattering on one side, and enhanced local electromagnetic fields near the surface of the nanoparticle on the other. These properties are inherent to a given detection mechanism and a given detection technique, enabling the classification of sensors in two main groups depending on the type of interaction involved, and therefore measured, between the metal nanoparticle and the analyte molecule. The first group encompasses sensors involving LSPR frequency shift, due to the interaction between nanoparticle and target molecule. Within this group, two different sensors may be distinguished, depending on the origin of LSPR changes: aggregation sensors and refractive index sensors. In aggregation sensors the LSPR shift is due to the plasmon coupling of nanoparticles in close proximity, in refractive index sensors the LSPR shift is due to changes in the local refractive index of the medium. The second main group of sensors is based on the enormous electromagnetic field enhancement in the vicinity of noble metal nanoparticles, which results in the so called surface enhanced spectroscopies, such as Surface Enhanced Raman Spectroscopy (SERS) and Metal Enhanced Fluorescence (MEF). This simple classification scheme is resumed in Table 1 that collects also the associated measurement techniques.

Sensor	Mechanism		Measurement/technique
Aggregation	LSPR-shift origin:	near-field electromagnetic coupling	Extinction/UV-Vis spectroscopy
Refractive Index		local refractive index changes	Extinction/UV-Vis spectroscopy Elastic Scattering/Dark-field microscopy
SERS	local electric field enhancement		Inelastic Scattering/Raman spectroscopy
MEF			Fluorescence

Table 1. Optical plasmonic sensors

In the following sections of this chapter, the principles of these sensors will be introduced and recent application examples for silver nanoparticles will be given.

3. Chemical sensing based on silver nanoparticles LSPR shift

3.1. Chemical sensing based on interparticle plasmon coupling: Aggregation sensors

The enhancement of electric fields on the nanoparticle surface, owing to plasmon resonance, decays over a distance on the order of the nanoparticle size. This means that when nanoparticles aggregate, i.e., approach each other within this distance, their fields interact leading to interparticle plasmon coupling and, consequently, to coupling-induced LSPR shift (Kreibig & Vollmer, 1995).

Generally, naked silver nanoparticles are stabilized against aggregation by means of anions (e.g., Cl⁻ or citrate³⁻) or polymers (e.g., polyvinylpyrrolidone) absorbed on their surfaces. However, changes in dispersant media such as pH and ionic strength can cause nanoparticle destabilization and aggregation. When the nanoparticle aggregates, its LSPR is red-shifted and broadened (Figure 2). This effect has been exploited in the design of so-called

aggregation sensors that form the basis of simple, highly sensitive and low cost colorimetric assays, which have been applied to the detection of small molecules, DNA, proteins, toxic metal ions and pollutants.




Fig. 2. Absorbance spectra of silver nanoparticles in aqueous solution before (black line) and after aggregation due to increasing salt concentrations (coloured lines). The suspension colour changes from yellow to blue.

In some cases, the proper analyte of interest is able to promote nanoparticle aggregation. An interesting example of this type of analyte-induced detection system has been recently described by Huang and co-workers. The authors have established a colorimetric analytical method for the detection of an anti-inflammatory drug, berberine hydrochloride, by means of citrate stabilized silver nanoparticles. Citrate stabilized silver nanoparticles exhibit a negatively charged surface rendering yellow stable dispersions in water due to the electrostatic repulsion between nanoparticles. In the presence of positively charged berberine hydrochloride, nanoparticles aggregate and suspension colour changes from yellow to green or blue, depending on the aggregation degree. By adjusting pH and ionic strength values of the medium, a good correlation between the absorbance change at the plasmon wavelength of the nanoparticle, and the berberine concentration was achieved, with detection limits of 1.3×10^{-8} M. Assay reliability was validated in berberine contained in commercially available drugs (Ling et al, 2008).

However, this method is restricted to cases where the analyte of interest is able to induce nanoparticle aggregation and no other substance present in the sample interferes by aggregating the nanoparticle. To overcome these limitations, it is necessary to endow aggregation sensors with selectivity. For this purpose, molecular recognition events have been employed to achieve selective colorimetric assays. The general strategy consists in functionalizing the silver nanoparticle surface with a monolayer of molecular recognition ligands. Aggregation is induced by specific recognition and binding to the target (Figure 3). The plasmon band is broadened and red-shifted as a function of the aggregation degree; therefore the change in absorbance is related to the target concentration.




Fig. 3. Schematic representation of silver nanoparticles aggregation induced by molecular recognition events.

The hybridization properties of DNA make this biomolecule an especially suitable candidate in aggregation sensing applications. Silver nanoparticles conjugated to oligonucleotides have recently emerged as powerful tools for the detection of target DNA sequences, and have been used in the design of colorimetric assays based on aggregation induced by sequence-specific hybridization. Different conjugates nanoparticle-oligonucleotide have been proposed to this end (Chen et al., 2004; Liu et al., 2005; Lee et al., 2007).

Additionally, when gold (Jin et al., 2003) and silver (Thompson et al., 2008) nanoparticles are conjugated to oligonucleotides, sharper melting transitions are observed as compared to free oligonucleotides, allowing the differentiation between complementary strands and strands with one or more mismatches by both colorimetric and melting curve analysis. Taking advantage of this property, Mirkin and co-workers developed a “dual” detection method for single-nucleotide-polymorphisms. The authors employed two different types of probe systems, Au and Ag/Au core shell nanoparticles, which offer two different colour signatures for target DNA-directed colorimetric detection. The metal nanoparticles were conjugated to oligonucleotide probe strands, wild-type and single nucleotide mutant, and hybridized to the corresponding DNA targets. After hybridization, nanoparticles aggregated, and these aggregates could be dispersed again by heating them above the melting temperature of the duplex DNA interconnects. Mismatched hybridization, e.g. wild type strand functionalized nanoparticle-mutant DNA target, displayed lower melting points than their matching counterparts, and could be easily differentiated. As in this approach two different colour pairs are available, the method provides a cross-check, enhancing the reliability of the determination (Cao et al., 2005). Further improvement using silver nanoparticles offered higher sensitivity, due to the greater extinction coefficient of silver nanoparticles when compared to their gold analogues (Thompson et al., 2008). Anyway, with the achieved sensitivity, a PCR amplification step is still compulsory.

A completely different strategy, where the molecular recognition is performed away from the nanoparticle enabling the use of naked nanoparticles without loss of selectivity, has been very recently reported (Kanjawarut & Su, 2009). In this strategy, charge neutral peptide nucleic acids (PNA) are used both as hybridization probe and to induce aggregation of citrate stabilized metal nanoparticles. In the absence of a complementary target DNA, PNA molecules, which remain free in solution, are able to coat nanoparticles inducing aggregation and, consequently, the colour changes in the colloidal solution. When a complementary DNA is present, PNA–DNA complexes are formed and nanoparticles do not aggregate, due to the stabilizing effect of the negative charges of the DNA strands in the

PNA–DNA complexes adsorbed on the nanoparticle surface. Nanoparticle behaviour could be easily followed by UV-Vis spectroscopy. This strategy enabled even single-base mismatch discrimination by means of adding NaCl to accelerate the aggregation process of the nanoparticles. Although both silver and gold citrate capped nanoparticles were employed to carry out the assay, silver rendered higher sensitivity.

Silver aggregation sensors are not restricted to DNA detection, and protein recognition has also been demonstrated. For example, carbohydrate binding proteins have been detected with carbohydrate stabilized nanoparticles. The tetrameric lectin concanavalin A (Con A) was detected by means of silver nanoparticles functionalized with mannose. Each Con A subunit contains a carbohydrate binding site that binds to a mannose ligand on the nanoparticle surface inducing nanoparticle aggregation (Schofield et al., 2006). Conversely, Con A can be utilized to detect a carbohydrate. Silver nanoparticles functionalized with dextran undergo aggregation in the presence of Con A, owing to the interaction of dextran with Con A. Competitive binding of glucose to Con A, is able to restore nanoparticles to solution, permitting the colorimetric detection of glucose. Although the detection limit obtained was below the physiological level of glucose, the specificity of this approach is not nearly sufficient for a diagnostic assay (Zhang et al., 2004a).

Aggregation based chemical sensing has also been used to monitor enzymatic reactions. Unmodified Ag nanoparticles have recently been used to develop a colorimetric assay to detect enzymatic reactions where adenosine triphosphate (ATP) is consumed, such as ATP dephosphorylation by calf intestine alkaline phosphatase and peptide phosphorylation by protein kinase. The assay relies on the capacity of ATP to protect the Ag nanoparticles against salt-induced aggregation. As ATP is consumed in the enzymatic process, nanoparticles begin to aggregate (Wei et al., 2008).

Other applications of protein functionalized silver nanoparticles that have been proposed include a colorimetric pH sensor based on the principle of pH dependent denaturation of proteins. Conformational changes in cytochrome c in response to pH changes could be measured over a wide range of pH values, as a result of plasmon shift in a system formed by silver nanoplates functionalized with the protein (Park et al., 2009).

A different approach to the molecular recognition events consists in functionalizing silver nanoparticles with complexing agents. Aggregation is achieved by formation of inclusion complexes between the functionalized nanoparticle and the guest molecule. Highly sensitive and selective colorimetric assays have thus been accomplished for the detection of histidine (Xiong et al., 2008; Li et al., 2009), pesticides (Xiong & Li, 2008) and Yb³⁺ ions (Han et al., 2009).

A very promising application of silver nanoparticles has been recently described. By means of the interdependency between the extent of nanoparticle coupling-induced LSPR shift and the distance between the interacting nanoparticles, Alivisatos and co-workers have developed a new class of molecular rulers based on plasmon coupling of single gold and silver nanoparticles (Sonnichsen et al., 2005). These “plasmon rulers” were used to study the dynamics of DNA hybridization on the single molecule level, with notorious advantages

when compared to conventional rulers based on Fluorescent Resonance Energy Transfer technique (FRET), e.g., scattering measurements offers better sensitivity and lower background signal than FRET, unlike reporter dyes used in FRET, the plasmon ruler neither blinks nor bleaches and affords upper distance limits of 70 nm as compared to approximately 10 nm for FRET.

3.2. Chemical sensing based on plasmon shifts with local refractive index

The silver nanoparticle LSPR is extremely sensitive to changes in local refractive index induced by analyte binding at or near the nanoparticle surface. The nanoparticle response to these changes can be measured as a LSPR shift in the UV-Vis extinction spectrum. This overall LSPR shift depends on surface coverage, i.e., on analyte concentration, allowing the development of refractive index sensors for quantitative determinations. Although other noble metals, such as gold, also exhibit high sensitivity to the local refractive index, the narrower plasmon bandwidth found in silver nanoparticles permits more accurate measurements of the LSPR shift (Lee et al., 2006).

As mentioned above, the extinction spectra of silver nanoparticles are really a combination of both absorption and scattering, and therefore the response of the LSPR to changes in local refractive index can also be measured by means of elastically scattered light. The Rayleigh scattering efficiency of a silver nanoparticle is 10^6 times higher than the fluorescence efficiency of a fluorescent dye molecule (Yguerabide et al., 1998), with the additional advantages that, unlike fluorescent probes, silver nanoparticles neither blink nor bleach. This extremely high scattering quantum yield of silver nanoparticles enables their use in highly sensitive imaging applications using dark-field optical microscopy, e.g. for imaging single living cells (Xu et al., 2004) as well as single receptor molecules on single living cells (Huang et al., 2007).

Apart from high sensitivity, selectivity for the analyte is also required to enable the use of silver nanoparticles in a detection system. For this purpose, the silver nanoparticle surface has to be tailored in such a way that only the target of interest binds to it. As in the previously described aggregation sensors, this can be achieved by functionalizing the nanoparticle surface with ligands capable of specifically binding the target molecule therefore eliminating non-specific surface adsorption (Haes & Van Duyne, 2003; Malinsky et al., 2001). Over the last decade, many functionalization protocols have been developed, nevertheless the most popular is the one based on using a thiolated intermediate linker or directly a thiolated derivative of the ligand. Such a popularity of thiolated compounds is mainly due to their capacity to form stable metal-sulphur bonds with the nanoparticle surface atoms under mild conditions. Moreover, silver nanoparticles modified with alkanethiol self-assembled monolayers exhibit extremely high short-range refractive index sensitivities (Malinsky et al., 2001; Sherry et al., 2006). The incorporation of different functionalities into the terminal position of the alkanethiol provides an easy way to tailor the chemical properties of the nanoparticle surface. These tailored silver nanoparticles have emerged as a powerful tool in the study of adsorption and binding events in biological systems (Ostuni et al., 1999), and have been extensively used in the design of refractive index sensors.

Basically, a refractive index sensor is any device that operates by transducing small changes in local refractive index in the silver nanoparticle surroundings into a measurable

wavelength shift response. A widely used configuration for refractive index sensors consists in a surface covered with silver nanoparticles that are coated with a recognition layer designed to bind a specific target molecule.

As first demonstrated by Van Duyne and co-worker, surface-confined triangular silver nanoparticles fabricated by nanosphere lithography on a glass substrate, render highly sensitive refractive index sensors. The recognition layer was constituted by a self-assembled mixed monolayer of alkanethiol molecules, comprising a thiolated compound with a terminal carboxylic acid group that could be used to attach biotin by common coupling chemistry. As a proof of concept, the biotinilated affinity sensor was assayed with streptavidin. Biotin-streptavidin binding induced a plasmon band shift, which was dependent on the streptavidin concentration. Exposure to 100 nM streptavidin, for example, rendered a LSPR red shift of 27 nm. After validation, its use was extended to the more realistic biotin-anti-biotin system with lower binding affinity typical of immunoassays. Limits of detection of 1 pM (streptavidin) and 100pM (anti-biotin) were obtained (Haes & Duyne, 2002). By using distinct ligand modified self-assembled monolayers to functionalize the triangular silver nanoparticles, this affinity sensor scheme has been extended to the optical detection of carbohydrate binding proteins (Yonzon et al., 2004), anti-amyloid-derived diffusible ligands focussed on the diagnosis of Alzheimer's disease (Haes et al., 2004) and small protein toxins (Zhu et al., 2009).

Interestingly, it has been reported that when chromophores are used as ligands, amplified spectral response to target binding can be achieved. For this to happen, the LSPR frequency of the silver nanoparticles has to be close to the molecular resonance of the chromophore, so that they couple (Haes et al., 2006; Zhao et al., 2007). This enhanced sensitivity has been recently applied to detect the binding of low molecular weight substrates and inhibitors (Zhao et al., 2008) as well as different drugs (Das et al., 2009) to human cytochrome P450.

Although the previous examples in this section were based on triangular nanoparticles, many other nanoparticle shapes are usable in refractive index sensors, such as rhombic silver nanoparticles (Zhu et al., 2008), and spherical silver nanoparticles (Gish et al., 2007). Groves and co-workers have recently developed a label-free LSPR sensor constituted by silver nanocubes covered with a self-assembled alkanethiol monolayer and interfaced with a glass-supported model membrane. This sensor was used to monitor and quantify static and dynamic protein binding to the membrane (Galush et al., 2009).

Refractive index sensors are also highly interesting for pollutant detection, for example, very recently a sensor based on silver colloidal nanoparticles has been reported for the detection of volatile organic compounds (Chen & Lu, 2009).

Further exploration of the potential of silver nanoparticles in refractive index sensors showed that a single silver nanoparticle monitored by dark-field microscopy can be used to sense local refractive index changes (McFarland & Van Duyne, 2003). Moreover, single silver nanoparticles functionalized with a single ligand molecule have demonstrated their capacity to constitute an optical sensor by themselves. These "single nanoparticle sensors" permit the target detection at the single molecule resolution and opens the door to studying single

molecular interactions of chemical functional groups on the surface of nanoparticles. Sensing and imaging of a single human cytokine molecule, tumor necrosis factor- α (TNF α), have been recently achieved by employing small silver nanoparticles (2.6 nm) functionalized with a single antibody molecule. Such as small nanoparticle size provides intrinsic single molecule detection volumes per nanoparticle, affording high sensitivity and a notably wide dynamic range (0-200 ng/mL) suitable for diagnostic purposes in diseases inducing increased TNF α levels (Huang et al., 2008).

Other examples involving silver nanoparticles in sensing and imaging applications associated to dark field microscopy include the development of a microarray-based DNA hybridization assay to screen for a given polymorphic site in the breast cancer gene BRCA1 (Oldenburg et al., 2002), the study of the action of antibiotics upon the cell membrane of living bacterial cells (Kyriacou et al., 2004; Xu et al., 2004) and imaging nanoparticle binding to fungi (Weinkauff & Brehm-Stecher, 2009).

4. Chemical sensing based on inelastic light scattering: SERS

Raman scattering is an extremely inefficient process. When a molecule interacts with visible light, most of the light is absorbed and only a small fraction is inelastically scattered to render the Raman spectrum of the molecule. As a consequence, Raman cross sections are extremely small, less than $10^{-29}\text{cm}^2\text{sr}^{-1}$, i.e., about 10 orders of magnitude smaller than that of infrared absorption, and 14 orders of magnitude smaller than that of fluorescent dye molecules. This means that the detection sensitivity of Raman spectroscopy is intrinsically low and, in order to achieve the high sensitivity required in biological or pollutant samples, the scattering intensity should be greatly increased.

Nevertheless, when the Raman spectrum is registered for a molecule located in the vicinity of a metal nanoparticle, or a metallic surface with nanometric roughness, the Raman cross section can be amplified dramatically. This enhancement effect is known as *Surface Enhanced Raman Scattering* or Surface Enhanced Raman Spectroscopy (SERS). SERS is probably one of the most powerful techniques currently available for sensing applications since, additionally to an extremely high sensitivity, it provides valuable structural information on the analyzed molecule.

Although SERS effect has not been completely elucidated, two enhancement mechanisms are generally recognized to contribute to SERS effect, the electromagnetic mechanism and the chemical mechanism. In the electromagnetic mechanism, local electric fields in the surroundings of the metal nanoparticle are enhanced due to the surface plasmon excitation, leading to more intense electronic transitions in molecules located near the nanoparticle, and enhanced Raman scattering (Schatz et al, 2006). The chemical mechanism consists in changes in the polarizability of the molecule, owing to charge transfer interaction between electronic states of the molecule and the metal nanoparticle surface, which results in increased Raman signals (Otto & Futamata, 2006). Even though these two mechanisms contribute to the enhancement, the electromagnetic one plays a major role when compared to the chemical one which is much smaller. Moreover, whereas the chemical mechanism depends on the properties of the analyte molecule, the electromagnetic mechanism only depends on tunable

optical properties of the metal nanoparticles that can be optimized in order to obtain higher SERS enhancements. In this sense, electromagnetic mechanism plays a key role in the development of improved SERS substrates, and current efforts directed to optimize nanostructures will be further discussed within this section.

The most active metal in SERS is silver, followed by gold and copper, in that order. SERS enhancement factors as high as 10^{14} - 10^{15} have been described for silver nanoparticles (Kneipp et al., 1997; Xu et al., 1999; Futamata et al., 2002), enabling detection limits as low as a single molecule (Nie & Emory, 1997; Kneipp et al., 1997; Le Ru et al., 2006). The enormous sensitivity achieved in SERS permits the ultrasensitive and ultraspecific detection of biomolecules (Ji et al., 2005; Fabris et al., 2008) as well as pollutants (Guerrini et al., 2009a; Abalde-Cela et al., 2009).

The IR signals of molecules nearby silver nanoparticles are also enhanced, giving rise to *Surface Enhanced Infrared Absorption Spectroscopy* (SEIRAS). However, SERS presents the considerable advantage over SEIRAS that aqueous samples may be examined, due to the very weak Raman scattering of water as compared to strong IR absorption. This is extremely significant for biological samples.

The largest Raman scattering enhancements have been described for molecules residing in gaps of a few nanometers between aggregated colloidal silver nanoparticles, the so called "Hot Spots" (Jiang et al., 2003; Michaels et al., 2000). This is attributed to plasmon-coupling between nanoparticles in close proximity (Su et al., 2003; Atay et al., 2004; Fromm et al., 2004; Jana & Pal, 2007). Other factors concerning the nanostructure have also been claimed to influence the enhancement effect, such as the presence of sharp edges and the LSPR coupling to Raman excitation source. On the basis of these considerations, a great deal of the current research effort in SERS focuses on the development of improved SERS active substrates for analytical purposes, by means of controlling composition, size, shape, and interparticle spacing of nanoparticles and their assemblies (Lin et al., 2009).

From the numerous methods actually available to fabricate SERS substrates, aggregation of colloidal nanoparticles is still preferred in applications requiring extremely high sensitivity. Indeed, silver nanoparticle aggregates have been found to be responsible for single-molecule detection in SERS, due to their high content in hot spots (Nie & Emory, 1997; Kneipp et al., 1997).

Aggregation can be achieved by increasing the ionic strength of the medium, (Jana & Pal, 2007). In this salt-induced aggregation strategy, attention has to be paid to salt election, as far as some ions have been claimed to enhance SERS effect, by means of surface activation, while others can even quench it (Doering & Nie, 2002). In fact, the SERS spectra of DNA and RNA mononucleotides may be obtained with high sensitivity when the silver colloid is aggregated with $MgSO_4$ instead of the more commonly used halide ions. (Bell & Sirimuthu, 2006)

Despite being widely utilized, owing to its simplicity and sensitivity, the aggregation method has several drawbacks such as low reproducibility and the lack of stability of the substrates. Very recently Mejías and co-workers have developed a new method for the obtention of highly reproducible films of silver nanoparticle aggregates that are strongly attached to the substrate and exhibit a high hot spots content (Figure 4). Due to the high stability of this SERS substrate, it can even be reused. Moreover, this substrate has shown its potential in quantitative SERS applications (Caro et al., 2008).




Fig. 4. Schematic representation of the sensor (left). Scanning electron microscopy image of silver nanoparticle aggregates on the sensor surface (right).

Although SERS is a selective technique, given that it provides a vibrational fingerprint of the analyte, distinguishing between closely-related species in complex samples, for example peptides that differ only slightly in sequence, is beyond the Raman discrimination capacity. Furthermore, a necessary condition for obtaining SERS activity is that the analyte molecule possesses affinity for the metal surface to ensure that it will approach the SERS substrate surface. If, to the contrary, the analyte of interest has no affinity for the surface at all, it does not matter how active the substrate is, it will not display SERS effect. These drawbacks have been overcome by coating the nanoparticle surface with a substance that promotes the adsorption or binds specifically to the target molecule. Such surface coated SERS sensors have made possible, for example, the detection of molecules with no affinity for uncoated surfaces, such as polycyclic aromatic hydrocarbons (Guerrini et al., 2009b), and the quantitative *in vivo* glucose measurement (Stuart et al., 2006).

Another interesting example of these modified SERS substrates, consist in a novel and fast method for the qualitative detection of protein kinase activity. To constitute the sensor, silver nanoparticles were deposited on a glass substrate and covalently linked to a target kinase-recognition peptide through a thiol group in the amine terminus of the peptide. After kinase reaction, the covalent attachment of the phosphate group to the peptide tyrosine residue resulted in a prominent change in the Raman spectra, exhibiting a collapse of the 848/828 cm^{-1} doublet to a single peak around 830 cm^{-1} . The reported method proved to be selective even in crude cell lysates (Yue et al., 2009).

In addition to the SERS active substrates, another attractive sensor arrangement has been described, the fiber-optic SERS sensor. In this type of sensor, the substrate is simultaneously part of the excitation and detection mechanism. For example, glass fiber tips coated by silver nanoparticles enabled the recording of spectra of biological samples, such as plant tissues or microbiological cells, with a high spatial resolution and avoiding sample photoinduced destruction due to the considerably reduced laser power required with this sensor (Gessner et al., 2002). In another example, crystal violet molecules, a contaminant in aquaculture, were detected in water far below the ppb detection limit (Lucotti & Zerbi, 2007).

Over the last years a new SERS sensor architecture has emerged as a powerful tool in biological assays, the SERS tags. Briefly, a SERS tag is a chemically encoded labeling agent. The basic structure of the SERS tag is formed by a SERS reporter molecule as labeling agent, i.e., a molecule with a high Raman cross-section, adsorbed on the surface of a silver nanoparticle that can be optionally further encapsulated in a protective shell. Once the basic structure is assembled, it may be conjugated to a recognition element, such as an antibody. In a detection process, the Raman signature of the SERS reporter molecule will reveal whether the labeling agent is present or not. SERS tags represent an excellent alternative to fluorescence-based encoding methods due to the advantages that they present when compared with traditional fluorescence labels, such as narrower emission peaks, increased number of optical signatures, high-level multiplexing, single laser excitation for detection of multiple labels and higher stability.

As mentioned above, a SERS tag can be obtained by simply adsorbing a SERS reporter molecule on the nanoparticle surface, this simple yet effective approach has been employed, for example, to develop a sandwich type immunosensor to detect hepatitis B surface antigen (Ji et al., 2005).

A wide variety of SERS tags have been reported, the most popular being the encapsulated ones, given that encapsulation prevents desorption of the SERS reporter molecule and increases the chemical stability of metal nanoparticles. As encapsulating agent, polymers (Stokes et al., 2006) and silica (Jun et al., 2007) are generally employed. Indeed, silica encapsulated SERS tags are being commercialized.

Exploiting the fact that the SERS effect is stronger in nanoparticle aggregates, Su and co-workers have developed an induced-aggregation method to obtain SERS tags. In this approximation, silver seed nanoparticles are grown, in the presence of appropriate SERS reporters, which are able to induce aggregation. Once the silver clusters reach the desired size, they are stabilized by the addition of bovine serum albumin (BSA). These SERS BSA-coated tags can be easily conjugated to antibodies by direct adsorption, for their use in immunoassays (Su et al., 2005). Covalent binding to antibodies is also possible by employing a cross-linked organic encapsulation with BSA and glutaraldehyde. These SERS tags have been used to map prostate specific antigen in tissue samples (Sun et al., 2007).

A different aggregation strategy has been recently reported by Fabris and co-workers who prepared silver nanoparticle dimers and small aggregates via a dithiol linker, which acts both as a "bridge" between the nanoparticles and as SERS reporter molecule. Further functionalization of these SERS tags with aptamers allowed highly sensitive protein detection (Fabris et al., 2008).

In a complex variation of the SERS tag scheme, Lee and co-workers have conjugated the optical properties of silver nanoparticles with the magnetic properties of iron oxide nanoparticles to obtain SERS encoded multiplex beads that afford both protein separation and identification (Jun et al., 2009). For this purpose sulfonated polystyrene-divinylbenzene beads were successively functionalized with magnetic iron oxide nanoparticles, silver nanoparticles, SERS reporter molecules and, finally, encapsulated with a silica shell. These

multiplex beads were tested as separation vehicles on the model system biotin–streptavidin. Multiplex beads retain both magnetic and SERS properties after silica coating and biotin functionalization, offering a wide range of applications in drug screening and combinatorial chemical synthesis. This combination of SERS detection and magnetic separation capacities by means of silver and magnetic nanoparticles, have also been used in a sandwich type immunoassay. In this assay, monoclonal antibody modified silica-coated magnetic nanoparticles, as separation tool, and polyclonal antibody Ag/SiO₂ core-shell nanoparticles embedded with a SERS tag, were employed to bind to target antigen, affording separation and detection. Using this strategy, concentration of human tumor marker α -fetoprotein up to 0.12 μ g/ml was detected with a detection limit of 11.5 pg/ml (Gong et al., 2007).

Silver nanoparticles functionalized with SERS reporter molecules exceed the simple molecule detection frontier, and applications such as SERS cellular imaging (Kim et al., 2006; Hu et al., 2007), or intracellular pH sensing (Talley et al., 2004; Wang et al., 2008) are also feasible.

5. Chemical sensing based on metal enhanced fluorescence: MEF

Fluorescence detection still plays a major role in most of the biological assays currently used. Nevertheless, fluorescence detection at the single molecule level has several limitations arising from the use of organic fluorophores, such as low signal to background ratio, poor photostability, and strong photoblinking.

Metal nanoparticles are known to interact with nearby fluorophores affecting their emission intensity. When this interaction results in a fluorescence enhancement, the effect is known as *Metal Enhanced Fluorescence* (MEF). This effect can be understood as arising from two contributions. On the one hand the enhanced emission intensity from the fluorophore can be attributed to the enhanced local fields associated with the metal nanoparticle, as in the case of SERS. On the other hand, the interaction with the nanoparticle LSPR results in increased radiative and nonradiative decay rates and, consequently, increased quantum yield and decreased lifetime (Lakowicz et al., 2002a; Lakowicz, 2005; Cade et al., 2009). Additionally, and as a consequence of the decreased lifetimes, the photostability of the fluorophore increases (Lakowicz et al., 2002b). Considering the potential of MEF, it could therefore improve current fluorescence based techniques.

In contrast to other metals, which typically quench nearby fluorophores (Huang & Murray, 2002), silver nanoparticles enhance the luminescence of fluorophores when they are localized at a distance of 4-10 nm from the silver nanoparticle surface. For example, silver nanoparticles deposited on a glass substrate increase the emission intensity of the common biological label fluorescein by an average of at least three fold (Pugh et al., 2003) and, what is more, fluorescein self-quenching decreases even in highly labeled proteins, permitting the use of ultrabright over-labeled protein as labels (Lakowicz et al., 2003; Lukomska et al., 2004).

Generally, MEF leads to 10-1000 fold intensity enhancements. Some factors affecting the enhancement degree have been described, such as the distance between the silver nanoparticle and the dye (Kühn et al., 2006; Anger et al., 2006), silver nanoparticle

aggregation (Zhang et al, 2004b; Zhang et al, 2007a) and the spectral overlap between the LSPR band of the silver nanoparticle and the emission band of the attached fluorophore (Chen et al., 2007).

The detection of DNA hybridization is of interest in numerous biological applications such as microarrays and PCR. To this end, Lakowicz and co-workers have studied in depth the MEF effect applied to DNA. They have found that silver nanoparticles enhance the intrinsic fluorescence of DNA (Lakowicz et al., 2001). Further research demonstrated that when DNA was labeled with a fluorescent probe, silver nanoparticles improved the fluorophore photostability (Malicka et al., 2002). The increased brightness of the fluorophore near silver islands enabled the measurement of the DNA hybridization kinetics as well as the development of the first MEF-based DNA hybridization assay (Malicka et al., 2003). Taking into account that silver nanoparticle LSPR also permits the detection of hybridization events, a further refinement was made and a dual detection method was developed. In this new approach, DNA hybridization was monitored through both nanoparticle absorbance and fluorophore emission spectral changes (Zhang et al., 2006). In these studies, the authors have made use of tiopronin monolayer-protected silver nanoparticles with the additional advantage that these nanoparticles are not cytotoxic (Castillo et al., 2008).

As fluorescent labeling is widely employed in immunoassays, efforts have been made to implement this technique by means of MEF, for example to detect insulin (Lochner et al., 2003) and myoglobin (Barnett et al., 2007).

Biological recognition events, such as antigen-antibody interaction or DNA hybridization, are often kinetically slow, requiring long incubation times. Recently, low-power microwave heating has been employed to accelerate these processes in MEF based assays. The thermal gradient created between the bulk aqueous medium and the metal nanoparticles during microwave heating has been claimed to play a major role in the observed faster biorecognition kinetics in such a microwave-accelerated MEF-based bioassay. This principle has been applied to immunoassays and DNA hybridization assays that could be completed within a few seconds with the benefits of increased sensitivity associated to MEF (Aslan & Geddes, 2008).

Silver nanoparticles have also demonstrated their potential in applications such as the development of solid substrate-based RNA capture assays (Aslan et al., 2006), label-free bioassays by means of enhancement of tryptophan fluorescence in proteins (Szymanski et al., 2009), the detection of glucose (Aslan et al., 2004) and the development of a MEF ratiometric pH sensor, using a pH-sensitive fluorophore (Aslan et al., 2005).

The development of molecular imaging agents for fluorescent imaging of cells is of great interest in disease diagnosis and elucidation of signalling pathways. Silver nanoparticles, conjugated to target molecules and fluorophores, have emerged as promising tools for cell imaging applications (Zhang et al., 2007b). Advantages of their use as cell imaging agents owing to their increased brightness and decreased lifetimes have been recently reported. Single molecule detection in cells by means of fluorescence requires the utilization of intense laser beams, which cause cell damage. This undesirable effect can be reduced by means of

MEF, which permits the use of weaker laser beams. Furthermore, owing to shorter lifetimes afforded by MEF, which reduces the time that a fluorophore spends in the excited state when it is vulnerable to oxygen attack, photobleaching is also decreased (Borejdo et al., 2008). Moreover, lifetime images generally lack interest given that the lifetimes of most organic fluorophores are close to the value of cell autofluorescence resulting in background interference. However, useful lifetime images can be obtained thanks to the decreased lifetimes obtained in MEF (Zhang et al., 2008).

6. Conclusions

Silver nanoparticles possess many valuable optical properties that have opened the door to new approaches in sensing and imaging applications, offering a wide range of detection modes such as colorimetric, scattering, SERS, and MEF techniques, at extremely low detection limits. Moreover, nanoparticles have made possible the use of scattering imaging techniques and have brought valuable improvements to standard imaging techniques. Silver nanoparticles may be introduced explicitly as labels, or may already be required in the application design to perform other functionalities, such as drug delivery, and simply provide this extremely useful added benefit.

Although LSPR sensing offers many promising features, detection thresholds must be improved for most practical applications. A great deal of current research effort is directed towards the optimization of nanoparticle tunable properties to improve their response in LSPR sensors.

One of the most promising contributions of silver nanoparticles to sensing and imaging applications is SERS. In this highly active research field, hundreds of papers are published each year on both fundamental aspects and applications. SERS has risen to its potential in the ultrasensitive detection of a wide variety of compounds, ranging from chemical pollutants to biomolecules, with detection thresholds as low as a single molecule, and the added advantage to provide structural information on the target molecule. It is to be expected that future improvements in this technique will be directed towards the development of more robust and reproducible sensors with a maximum coverage of hot spots. Additionally to SERS sensors, encapsulated SERS tags have emerged as an alternative to traditional fluorescent labeling offering advantages such as improved stabilities and multiplexing capability. On the other hand, MEF has also shown a great potential to address the deficiencies of traditional fluorescent labeling.

Summarizing, although further research is required, future perspectives of silver nanoparticles include applications in multiplexing assays, massively parallel bioassays for high throughput screening of drugs, diagnostic level sensing for clinical assays, the study of biological interactions at the molecular level and the measurement of intermolecular distances of tens of nm with plasmon rulers.

7. References

- Lochner, N.; Lobmaier, C.; Wirth, M.; Leitner, A.; Pittner, F. & F. Gabor. (2003) Silver nanoparticle enhanced immunoassays: one step real time kinetic assay for insulin in serum. *Eur. J. Pharm. Biopharm.*, 56:469-477, ISSN: 0939-6411.
- Abalde-Cela, S.; Ho, S.; Rodríguez-González, B.; Correa-Duarte, M. A.; Álvarez-Puebla, R. A.; Liz-Marzán, L. M. & Kotov, N. A. (2009) Loading of Exponentially Grown LBL Films with Silver Nanoparticles and Their Application to Generalized SERS Detection. *Angew. Chem. Int. Ed.*, 48:5326–5329, ISSN: 1521-3773.
- Anger, P.; Bharadwaj, P.; Novotny, L. (2006) Enhancement and quenching of single-molecule fluorescence. *Phys. Rev. Lett.*, 96:113002-11300.
- Aslan, K.; Zhang, J.; Lakowicz, J. R. & Geddes, C. D. (2004) Saccharide Sensing Using Gold and Silver Nanoparticles-A Review. *J Fluores.*, 14(4):391-400, ISSN 1573-4994.
- Aslan, K.; Lakowicz, J.R.; Szmackinski, H. & Geddes, C.D. (2005) Enhanced ratiometric pH sensing using SNAFL-2 on silver island films: metal enhanced fluorescence sensing. *J Fluores.*, 15(1):37–40, ISSN 1573-4994.
- Aslan, K.; Huang, J.; Wilson, G. M. & Geddes, C. D. (2006) Metal-Enhanced Fluorescence-Based RNA Sensing. *J. Am. Chem. Soc.*, 128 (13):4206–4207, ISSN: 1520-5126.
- Aslan, K. & Geddes, C. D. (2008) A Review of an Ultrafast and Sensitive Bioassay Platform Technology: Microwave-accelerated Metal-enhanced Fluorescence. *Plasmonics*, 3:89–101, ISSN: 1557-1963.
- Atay, T.; Song, J. H. & Murmikko, A. V. (2004) Strongly Interacting Plasmon Nanoparticle Pairs: From Dipole–Dipole Interaction to Conductively Coupled Regime. *Nano Lett.*, 4:1627-1631, ISSN: 1530-6992.
- Barnett, A.; Matveeva, E. G.; Gryczynski, I.; Gryczynski, Z. & Goldys, E. M. (2007) Coupled plasmon effects for the enhancement of fluorescent immunoassays. *Physica B* 394:297–300, ISSN: 0921-4526.
- Bell, S. E. J. & Sirimuthu, N. M. S. (2006) Surface-Enhanced Raman Spectroscopy (SERS) for Sub-Micromolar Detection of DNA/RNA Mononucleotides. *J. Am. Chem. Soc.*, 128:15580-15581, ISSN: 1520-5126.
- Borejdo, J., Muthu, P., Talent, J., Gryczynski, Z., Calander, N., Akopova, I., Shtoyko, T., Gryczynski, I. (2008) Reduction of photobleaching and photodamage in single molecule detection: observing single actin monomer in skeletal myofibrils. *J. Biomed. Opt.*, 13:034021-034032, ISSN: 1083-3668.
- Cade, N. I.; Ritman-Meer, T.; Kwakwa K. A. & Richards, D. (2009) The plasmonic engineering of metal nanoparticles for enhanced fluorescence and Raman scattering. *Nanotechnology*, 20 285201-285206, ISSN 1361-6528.
- Cao, Y. C.; Jin, R.; Thaxton, C. S. & Mirkin, C. A. (2005) A two-color-change, nanoparticle-based method for DNA detection. *Talanta* 67:449–455, ISSN: 0039-9140.
- Caro, C.; López-Cartes, C.; Zaderenko A.P. & Mejías J. A. (2008) Thiol-immobilized silver nanoparticle aggregate films for surface enhanced Raman scattering. *J. Raman Spectrosc.*, 39 (9):1162-1169, ISSN 1097-4555.
- Castillo, P. M.; Herrera, J. L.; Fernandez-Montesinos, R.; Caro, C.; Zaderenko, A. P.; Mejias, J. A. & Pozo, D. (2008). Tiopronin monolayer-protected silver nanoparticles modulate IL-6 secretion mediated by Toll-like receptor ligands. *Nanomed*, 3(5):627-635, ISSN 1743-5889.

- Chen, Y.; Aveyard, J. & Wilson, R. (2004) Gold and silver nanoparticles functionalized with known numbers of oligonucleotides per particle for DNA detection. *Chem. Commun.*, 24:2804–2805, ISSN 1359-7345.
- Chen, Y.; Munechika, K. & Ginger, D. S. (2007) Dependence of Fluorescence Intensity on the Spectral Overlap between Fluorophores and Plasmon Resonant Single Silver Nanoparticles. *Nano Lett.*, 7(3):690–696, ISSN: 1530-6992.
- Chen, Y. & Lu, C. (2009) Surface modification on silver nanoparticles for enhancing vapor selectivity of localized surface plasmon resonance sensors. *Sens. Act. B*, 135:492–498, ISSN: 0925-4005.
- Das, A.; Zhao, J.; Schatz, G. C.; Sligar, S. G. & Van Duyne, R. P. (2009) Screening of Type I and II Drug Binding to Human Cytochrome P450-3A4 in Nanodiscs by Localized Surface Plasmon Resonance Spectroscopy. *Anal. Chem.*, 81:3754–3759, ISSN: 1520-6882.
- Doering, W. E. & Nie, S. (2002) Single-Molecule and Single-Nanoparticle SERS: Examining the Roles of Surface Active Sites and Chemical Enhancement. *J. Phys. Chem. B*, 106:311–317, ISSN 1520-5207.
- Fabris, L.; Dante, M.; Nguyen, T.; Tok, J. B.H. & Bazan, G. C. (2008) SERS Aptatags: New Responsive Metallic Nanostructures for Heterogeneous Protein Detection by Surface Enhanced Raman Spectroscopy. *Adv. Funct. Mater.*, 18:2518–2525, ISSN: 1616-3028.
- Fromm, D. P.; Sundaramurthy, A.; Schuck, P. J.; Kino, G. & Moerner, W. E. (2004) Gap-Dependent Optical Coupling of Single “Bowtie” Nanoantennas Resonant in the Visible *Nano Lett.*, 4:957–961. ISSN: 1530-6992.
- Futamata, M.; Maruyama, Y. & Ishikawa, M. (2002) Microscopic morphology and SERS activity of Ag colloidal particles *Vib. Spectrosc.*, 30:17–23, ISSN: 0924-2031.
- Galush, W. J.; Shelby, S. A.; Mulvihill, M. J.; Tao, A.; Yang, P. & Groves, J. T. (2009) A Nanocube Plasmonic Sensor for Molecular Binding on Membrane Surfaces. *Nano Lett.*, 9 (5):2077–2082, ISSN: 1530-6992.
- Gessner, R.; Rösch, P.; Kiefer, W. & Popp, J. (2002) Raman Spectroscopy Investigation of Biological Materials by Use of Etched and Silver Coated Glass Fiber Tips. *Biopolymers (Biospectroscopy)*, 67:327–330, ISSN 1520-6343.
- Gish, D. A.; Nsiah, F.; McDermott, M. T. & Brett, M. J. (2007) Localized Surface Plasmon Resonance Biosensor Using Silver Nanostructures Fabricated by Glancing Angle Deposition. *Anal. Chem.*, 79:4228–4232, ISSN: 1520-6882.
- Gong, J.; Liang, Y.; Huang, Y.; Chen, J.; Jiang, J.; Shen, G. & Yu, R. (2007) Ag/SiO₂ core-shell nanoparticle-based surface-enhanced Raman probes for immunoassay of cancer marker using silica-coated magnetic nanoparticles as separation tools. *Biosensors and Bioelectronics*, 22:1501–1507, ISSN: 0956-5663.
- Guerrini, L.; Garcia-Ramos, J. V.; Domingo, C. & Sanchez-Cortes, S. (2009a) Nanosensors Based on Viologen Functionalized Silver Nanoparticles: Few Molecules Surface-Enhanced Raman Spectroscopy Detection of Polycyclic Aromatic Hydrocarbons in Interparticle Hot Spots. *Anal. Chem.*, 81, 1418–1425, ISSN: 1520-6882.
- Guerrini, L.; Garcia-Ramos, J. V.; Domingo, C. & Sanchez-Cortes, S. (2009b) Sensing Polycyclic Aromatic Hydrocarbons with Dithiocarbamate-Functionalized Ag Nanoparticles by Surface-Enhanced Raman Scattering. *Anal. Chem.*, 81:953–960, ISSN: 1520-6882.

- Haes, A.J. & Van Duyne, R.P. (2002) A Nanoscale Optical Biosensor: Sensitivity and Selectivity of an Approach Based on the Localized Surface Plasmon Resonance Spectroscopy of Triangular Silver Nanoparticles. *J. Am. Chem. Soc.*, 124:10596-10604, ISSN: 1520-5126.
- Haes, A.J. & Van Duyne, R.P. (2003) Nanosensors Enable Portable Detectors for Environmental and Medical Applications. *Laser Focus World*, 39:53-156, ISSN: 1043-8092.
- Haes, A. J.; Hall, W. P.; Chang, L.; Klein, W. L. & Van Duyne, R. P. (2004) A Localized Surface Plasmon Resonance Biosensor: First Steps toward an Assay for Alzheimer's Disease. *Nano Lett.*, 4 (6):1029-1034, ISSN: 1530-6992.
- Haes, A. J.; Zou, S.; Zhao, J.; Schatz, G. C. & Van Duyne, R. P. (2006) Localized surface plasmon resonance spectroscopy near molecular resonances. *J. Am. Chem. Soc.*, 128:10905-10914, ISSN: 1520-5126.
- Han, C.; Zhang, L. & Li, H. (2009) Highly selective and sensitive colorimetric probes for Yb³⁺ ions based on supramolecular aggregates assembled from β -cyclodextrin-4,4'-dipyridine inclusion complex modified silver nanoparticles. *Chem. Commun.*, 24:3545-3547, ISSN 1359-7345.
- Hu, Q. Y.; Tay, L. L.; Noestheden, M. & Pezacki, J. P. (2007) Mammalian Cell Surface Imaging with Nitrile-Functionalized Nanoprobes: Biophysical Characterization of Aggregation and Polarization Anisotropy in SERS Imaging. *J. Am. Chem. Soc.*, 129:14-15, ISSN: 1520-5126.
- Huang, T. & Murray, R.W. (2002) Quenching of [Ru(bpy)₃]²⁺ fluorescence by binding to Au nanoparticles, *Langmuir* 18:7077-7081, ISSN: 1520-5827.
- Huang, T.; Nallathamby, P. D.; Gillet, D. & Xu, X. N. (2007) Design and Synthesis of Single-Nanoparticle Optical Biosensors for Imaging and Characterization of Single Receptor Molecules on Single Living Cells. *Anal. Chem.*, 79 (20):7708-7718, ISSN: 1520-6882.
- Huang, T.; Nallathamby, P. D. & Xu, X. N. (2008) Photostable Single-Molecule Nanoparticle Optical Biosensors for Real-Time Sensing of Single Cytokine Molecules and Their Binding Reactions. *J. Am. Chem. Soc.*, 130:17095-17105, ISSN: 1520-5126.
- Jana, N. R. & Pal, T. (2007) Anisotropic Metal Nanoparticles for Use as Surface-Enhanced Raman Substrates. *Adv. Mater.* 19:1761-1765, ISSN: 1521-4095
- Ji, X.; Xu, S.; Wang, L.; Liu, M.; Pan, K.; Yuan, H.; Ma, L.; Xu, W.; Li, J.; Bai, Y. & Li, T. (2005) Immunoassay using the probe-labeled Au/Ag core-shell nanoparticles based on surface-enhanced Raman scattering. *Colloids Surf. A: Physicochem. Eng. Aspects* 257-258, ISSN: 0927-7757.
- Jiang, J.; Bosnick, N.; Maillard, M. & Brus, L. (2003) Single molecule Raman spectroscopy at the junctions of large Ag nanocrystals *J. Phys. Chem. B*, 107:9964-9972, ISSN 1520-5207.
- Jin, R.; Wu, G.; Li, Z.; Mirkin, C.A. & Schatz, G.C. What controls the melting properties of DNA-linked gold nanoparticle assemblies? (2003) *J. Am. Chem. Soc.*, 125 (6), 1643-1654, ISSN: 1520-5126.
- Jun, B.; Kim, J.; Park, H.; Kim, J.; Yu, K.; Lee, S.; Choi, H.; Kwak, S.; Kim, Y.; Jeong, D. H.; Cho, M. & Lee, Y. (2007) Surface-Enhanced Raman Spectroscopic-Encoded Beads for Multiplex Immunoassay. *J. Comb. Chem.*, 9:237-244, ISSN: 1520-4774.

- Jun, B.; Noh, M. S.; Kim, G.; Kang, H.; Kim, J.; Chung, W.; Kim, M.; Kim, Y.; Cho, M.; Jeong, D. H. & Lee, Y. (2009) Protein separation and identification using magnetic beads encoded with surface-enhanced Raman spectroscopy. *Analytical Biochem.*, 391:24–30, ISSN 0003-2697.
- Kanjanawarut, R. & Su, X. (2009) Colorimetric Detection of DNA Using Unmodified Metallic Nanoparticles and Peptide Nucleic Acid Probes. *Anal. Chem.*, 81 (15):6122–6129, ISSN: 1520-6882.
- Kelly, K. L.; Jensen, T. R.; Lazarides A. A. & Schatz G. C. (2002). Modeling metal nanoparticle optical properties, In *Metal Nanoparticles: Synthesis, Characterization, and Applications*, D. L. Feldheim and C. A. Foss, Jr., 89-118, Marcel Dekker, New York, ISBN 0-8247-0604-8.
- Kelly, K. L.; Coronado, E.; Zhao, L. L. & Schatz, G. C. (2003) The Optical Properties of Metal Nanoparticles: The Influence of Size, Shape, and Dielectric Environment. *J. Phys. Chem. B*, 107, 668–677, ISSN 1520-5207.
- Kim, J.; Kim, J.; Choi, H.; Lee, S.; Jun, B.; Yu, K.; Kuk, E.; Kim, Y.; Jeong, D. H.; Cho, M. & Lee, Y. (2006) Nanoparticle Probes with Surface Enhanced Raman Spectroscopic Tags for Cellular Cancer Targeting. *Anal. Chem.*, 78 (19): 6967–6973, ISSN: 1520-6882.
- Kneipp, K.; Wang, Y.; Kneipp, H.; Perelman, L. T.; Itzkan, I.; Dasari, R. R. & Feld, M. S. (1997) Single Molecule Detection Using Surface-Enhanced Raman Scattering (SERS). *Phys. Rev. Lett.*, 78:1667-1670, ISSN 1079-7114.
- Kneipp, K.; Wang, Y.; Kneipp, H.; Perelman, L.T. & Itzkan, I. (1997) Single molecule detection using surface-enhanced Raman scattering (SERS). *Phys. Rev. Lett.*, 78:1667–1670, ISSN 1079-7114.
- Kreibig, U. & Vollmer, M. (1995) *Optical properties of metal clusters* Vol. 25 (Springer-Verlag, Berlin), ISBN: 978-3-540-57836-9.
- Kühn, S.; Håkanson, U.; Rogobete, L. & Sandoghdar, V. (2006) Enhancement of single-molecule fluorescence using a gold nanoparticle as an optical *Phys. Rev. Lett.*, 97:017402-017405, ISSN 1079-7114.
- Kyriacou, S. V.; Brownlow, W. J. & Xu, X. N. (2004) Using Nanoparticle Optics Assay for Direct Observation of the Function of Antimicrobial Agents in Single Live Bacterial Cells. *Biochem.*, 43:140-147, ISSN: 1520-4995.
- Lakowicz, J.R.; Shen, Y.; Gryczynski, Z.; D'Auria, S. & Gryczynski, I. (2001) Intrinsic fluorescence from DNA can be enhanced by metallic particles. *Biochem. Biophys. Res. Com.*, 286:875-879, ISSN: 0006-291X.
- Lakowicz, J.R.; Gryczynski, I.; Malicka, J.; Gryczynski, Z. & Geddes, C.D. (2002a) Enhanced and localized multiphoton excited fluorescence near metallic silver islands: metallic islands can increase probe photostability. *J Fluores.*, 12:299-302, ISSN 1573-4994.
- Lakowicz, J.R.; Shen, Y.; D'Auria, S.; Malicka, J. Fang, J.; Gryczynski, Z.; Gryczynski, I. (2002b) Radiative decay engineering 2. Effects of silver island films on fluorescence intensity, lifetimes, and resonance energy transfer. *Analytical Biochem.*, 301:261-277, ISSN 0003-2697.
- Lakowicz, J.R.; Malicka, J.; D'Auria, S. & Gryczynski, I. (2003) Release of the self-quenching of fluorescence near silver metallic surface. *Analytical Biochem.*, 320:13-20, ISSN 0003-2697.
- Lakowicz, J. R. (2005b) Radiative Decay Engineering 5: Metal-Enhanced Fluorescence and Plasmon Emission. *Analytical Biochem.*, 337:171-194, ISSN 0003-2697.

- Le Ru, E. C.; Meyer, M. & Etchegoin, P. G. (2006) Proof of Single-Molecule Sensitivity in Surface Enhanced Raman Scattering (SERS) by Means of a Two-Analyte Technique. *J. Phys. Chem. B*, 110:1944-1948, ISSN 1520-5207.
- Lee, J.; Lytton-Jean, A. K. R.; Hurst, S. J. & Mirkin, C. A. (2007) Silver Nanoparticle-Oligonucleotide Conjugates Based on DNA with Triple Cyclic Disulfide Moieties. *Nano Lett.*, 7 (7):2112-2115, ISSN: 1530-6992.
- Lee, K.S. & El-Sayed, M.A. (2006) Gold and Silver Nanoparticles in Sensing and Imaging: Sensitivity of Plasmon Response to Size, Shape, and Metal Composition. *J. Phys. Chem. B*, 110:19220-19225, ISSN 1520-5207.
- Li, H. & Bian, Y. (2009) Selective colorimetric sensing of histidine in aqueous solutions using cysteine modified silver nanoparticles in the presence of Hg²⁺. *Nanotechnology*, 20:145502-145507, ISSN 1361-6528.
- Lin, X.; Cui, Y.; Xu, Y.; Ren, B. & Tian, Z. (2009) Surface-enhanced Raman spectroscopy: substrate-related issues. *Anal. Bioanal. Chem.* 394:1729-1745, ISSN: 1618-2650.
- Ling, J.; Sang, Y. & Huang, C. Z. (2008). Visual colorimetric detection of berberine hydrochloride with silver nanoparticles. *J. Pharm. Biomed. Anal.*, 47:860-864, ISSN: 0731-7085.
- Liu, S.; Zhang, Z. & Han, M. (2005) Gram-Scale Synthesis and Biofunctionalization of Silica-Coated Silver Nanoparticles for Fast Colorimetric DNA Detection. *Anal. Chem.*, 77 (8):2595-2600, ISSN: 1520-6882.
- Lucotti, A. & Zerbi, G. (2007) Fiber-optic SERS sensor with optimized geometry. *Sens. Act. B*, 121:356-364, ISSN: 0925-4005.
- Lukomska, J.; Malicka, J.; Gryczynski, I. & Lakowicz, J. R. (2004) Fluorescence Enhancements on Silver Colloid Coated Surfaces. *J Fluores.*, 14:417-423, ISSN 1573-4994.
- Malicka, J.; Gryczynski, I.; Fang, J. & Lakowicz, J.R. (2002) Photostability of Cy3 and Cy5-labeled DNA in the presence of metallic silver particles. *J Fluores.*, 12:439-447, ISSN 1573-4994.
- Malicka, J.; Gryczynski, I. & Lakowicz, J. R. (2003) DNA hybridization assays using metal-enhanced fluorescence. *Biochem. Biophys. Res. Com.*, 306:213-218, ISSN: 0006-291X.
- Malinsky, M.D.; Kelly, K.L.; Schatz, G.C. & Van Duyne, R.P. (2001) Chain Length Dependence and Sensing Capabilities of the Localized Surface Plasmon Resonance of Silver Nanoparticles Chemically Modified with Alkanethiol Self-Assembled Monolayers. *J. Am. Chem. Soc.*, 123:1471-1482, ISSN: 1520-5126.
- McFarland, A. D. & Van Duyne, R. P. (2003) Single Silver Nanoparticles as Real-Time Optical Sensors with Zeptomole Sensitivity. *Nano Lett.*, 3 (8):1057-1062, ISSN: 1530-6992.
- Michaels, A. M.; Jiang, J. & Brus, L. (2000) Ag Nanocrystal Junctions as the Site for Surface-Enhanced Raman Scattering of Single Rhodamine 6G Molecules *J. Phys. Chem. B*, 104:11965-11971, ISSN 1520-5207.
- Mie G. (1908). Contributions to the optics of turbid media, especially colloidal metal solutions. *Ann. Phys.* 25:377-445, ISSN 0003-4916.
- Nie, S. & Emory, S.R. (1997) Probing single molecules and single nanoparticles by surface enhanced Raman scattering. *Science*, 275:1102-1106, ISSN: 1095-9203.
- Novotny, L. & Hecht, B. (2006). *Principles of nano-optics*, 378-414, Cambridge University Press, United Kingdom, ISBN-13 968-0-521-83224-3.

- Oldenburg, S. J.; Genick, C. C.; Clark, K. A. & Schultz, D. A. (2002) Base pair mismatch recognition using plasmon resonant particle labels. *Analytical Biochem.*, 309:109-116, ISSN 0003-2697.
- Ostuni, E.; Yan, L. & Whitesides, G. M. The interaction of proteins and cells with self-assembled monolayers of alkanethiolates on gold and silver. *Colloids Surf.B: Biointerfaces* 15:3-30, ISSN: 0927-7765.
- Otto, A. & Futamata. (2006). Electronic Mechanisms of SERS, In: Surface-enhanced Raman scattering physics and applications. *Topics in applied Physics* Vol. 103, Kneipp, K.; Moskovits, M. & Kneipp, H., 147-182, Springer-Verlag, Berlin Heidelberg, ISBN-10 3-540-33566-8.
- Park, J.; Yoon, D. & Kim, Y. (2009) Applications of silver nanoplates as colorimetric indicators of pH-induced conformational changes in cytochrome c. *Korean J. Chem. Eng.*, 26(1):258-260, ISSN: 1975-7220.
- Pugh, V. J.; Szmecinski, H.; Moore, W.E.; Geddes, C.D. & Lakowicz, J.R. (2003) Submicrometer spatial resolution of metal-enhanced fluorescence. *Applied Spectroscopy* 57:1592-1598, ISSN: 0003-7028.
- Schatz, G.C., Young, M. A. & Van Duyne R. P. (2006). Electromagnetic theory of SERS, In: Surface-enhanced Raman scattering physics and applications. *Topics in applied Physics* Vol. 103, Kneipp, K.; Moskovits, M. & Kneipp, H., 47-65, Springer-Verlag, Berlin Heidelberg, ISBN-10 3-540-33566-8.
- Schofield, C. L.; Haines, A. H.; Field, R. A. & Russell, D. A. (2006) Silver and Gold Glyconanoparticles for Colorimetric Bioassays. *Langmuir*, 22:6707-6711, ISSN: 1520-5827.
- Sherry, L. J.; Jin, R.; Mirkin, C. A.; Schatz, G. C. & Van Duyne, R. P. (2006) Localized Surface Plasmon Resonance Spectroscopy of Single Silver Triangular Nanoprisms. *Nano Lett.*, 6 (9):2060-2065, ISSN: 1530-6992.
- Sonnichsen, C.; Reinhard, B.M.; Liphardt, J. & Alivisatos, A.P. (2005) A molecular ruler based on plasmon coupling of single gold and silver nanoparticles. *Nat Biotechnol* 23:741-745, ISSN 1087-0156.
- Stokes R. J.; Hernandez-Santana, A.; Macaskill, A.; Cormack, P. A. G.; Smith, W. E. & Graham, D. (2006) SERRS-active nanoparticle-polymer beads for ultra-sensitive biodiagnostic applications. *Micro & Nano Lett.*, 1:57-61, ISSN: 1750-0443
- Stuart, D. A.; Yuen, J. M.; Shah, N.; Lyandres, O.; Yonzon, C. R.; Glucksberg, M. R.; Walsh J. T. & Van Duyne R. P. (2006) In Vivo Glucose Measurement by Surface-Enhanced Raman Spectroscopy. *Anal. Chem.*, 78 (20):7211-7215, ISSN: 1520-6882.
- Su, K. H.; Wei, Q. H.; Zhang, X.; Mock, J. J.; Smith, D. R. & Schultz, S. (2003) Interparticle Coupling Effects on Plasmon Resonances of Nanogold Particles *Nano Lett.*, 3:1087-1090, ISSN: 1530-6992.
- Su, X.; Zhang, J.; Sun, L.; Koo, T.; Chan, S.; Sundararajan, N.; Yamakawa, M. & Berlin, A. A. (2005) Composite Organic-Inorganic Nanoparticles (COINs) with Chemically Encoded Optical Signatures. *Nano Lett.*, 5(1):49-54, ISSN: 1530-6992.
- Sun, L.; Sung, K. B.; Dentinger, C.; Lutz, B.; Nguyen, L.; Zhang, J. W.; Qin, H. Y.; Yamakawa, M.; Cao, M. Q.; Lu, Y.; Chmura, A. J.; Zhu, J.; Su, X.; Berlin, A. A.; S. Chan, & Knudsen, B. (2007) Composite Organic-Inorganic Nanoparticles as Raman Labels for Tissue Analysis. *Nano Lett.*, 7:351-356, ISSN: 1530-6992.

- Szmacinski, H.; Ray, K. & Lakowicz, J. R. (2009) Metal-enhanced fluorescence of tryptophan residues in proteins: Application toward label-free bioassays. *Analytical Biochem.*, 385:358–364, ISSN 0003-2697.
- Talley, C. E.; Jusinski, L.; Hollars, C. W.; Lane, S. M. & Huser, T. (2004) Intracellular pH Sensors Based on Surface-Enhanced Raman Scattering. *Anal. Chem.*, 76 (23):7064–7068, ISSN: 1520-6882.
- Thompson, D. G.; Enright, A.; Faulds, K.; Smith, W. E. & Graham, D. (2008) Ultrasensitive DNA Detection Using Oligonucleotide–Silver Nanoparticle Conjugates. *Anal. Chem.* 80 (8), 2805–2810, ISSN: 1520-6882.
- Wang, Z.; Bonoiu, A.; Samoc, M.; Cui, Y. & Prasad, P. N. (2008) Biological pH sensing based on surface enhanced Raman scattering through a 2-aminothiophenol-silver probe. *Biosensors and Bioelectronics*, 23:886–891, ISSN: 0956-5663.
- Wei, H.; Chen, C.; Han, B. & Wang, E. (2008) Enzyme Colorimetric Assay Using Unmodified Silver Nanoparticles. *Anal. Chem.* 80:7051–7055, ISSN: 1520-6882.
- Weinkauff, H. & Brehm-Stecher, B. F. (2009) Enhanced dark field microscopy for rapid artifact-free detection of nanoparticle binding to *Candida albicans* cells and hyphae. *Biotechnol. J.*, 4:871–879, ISSN: 0168-1656.
- Xiong, D. & Li, H. (2008) Colorimetric detection of pesticides based on calixarene modified silver nanoparticles in water. *Nanotechnology*, 19:465502–465507, ISSN 1361-6528.
- Xiong, D.; Chen, M. & Li, H. (2008) Synthesis of para-sulfonatocalix[4]arene-modified silver nanoparticles as colorimetric histidine probes. *Chem. Commun.* 7:880–882, ISSN 1359-7345.
- Xu, H.; Bjerneld, E. J.; Käll, M. & Börjesson, L. (1999) Spectroscopy of Single Hemoglobin Molecules by Surface Enhanced Raman Scattering *Phys. Rev. Lett.*, 83:4357-4360, ISSN 1079-7114.
- Xu, X. N.; Brownlow, W. J.; Kyriacou, S. V.; Wan, Q. & Viola, J. J. (2004) Real-Time Probing of Membrane Transport in Living Microbial Cells Using Single Nanoparticle Optics and Living Cell Imaging. *Biochem.*, 43 (32):10400–10413, ISSN: 1520-4995.
- Yguerabide, J. & E. E. Yguerabide, E. E. (1998) Light-Scattering Submicroscopic Particles as Highly Fluorescent Analogs and Their Use as Tracer Labels in Clinical and Biological Applications. *Anal. Biochem.* 262:157–176, ISSN 0003-2697.
- Yonzon, C. R.; Jeoung, E.; Zou, S. & Schatz, G. C. (2004) Milan Mrksich and Richard P. Van Duyne. A Comparative Analysis of Localized and Propagating Surface Plasmon Resonance Sensors: The Binding of Concanavalin A to a Monosaccharide Functionalized Self-Assembled Monolayer. *J. Am. Chem. Soc.*, 126:12669-12676 ISSN: 1520-5126.
- Yue, Z.; Zhuang, F.; Kumar, R.; Wang, I.; Cronin, S. B. & Liu, Y. (2009) Cell kinase activity assay based on surface enhanced Raman spectroscopy. *Spec. Acta Part A*, 73:226–230, ISSN: 1386-1425.
- Zhang, J.; Roll, D.; Geddes, C. D. & Lakowicz, J. R. (2004a) Aggregation of Silver Nanoparticle-Dextran Adducts with Concanavalin A and Competitive Complexation with Glucose. *J. Phys. Chem. B*, 108:12210-12214, ISSN 1520-5207.
- Zhang, J.; Malicka, J.; Gryczynski, I. & Lakowicz, J. R. (2004b) Oligonucleotide displaced organic monolayer-protected silver nanoparticles and enhanced luminescence of their salted aggregates. *Analytical Biochem.*, 330:81-86, ISSN 0003-2697.

- Zhang, J. & Lakowicz, J. R. (2006) A Model for DNA Detection by Metal-Enhanced Fluorescence from Immobilized Silver Nanoparticles on Solid Substrate. *J. Phys. Chem. B*, 110:2387-2392, ISSN 1520-5207.
- Zhang, J.; Fu, Y.; Chowdhury, M. H. & Lakowicz, J. R. (2007a) Metal-Enhanced Single-Molecule Fluorescence on Silver Particle Monomer and Dimer: Coupling Effect between Metal Particles. *Nano Lett.*, 7(7):2101-2107, ISSN: 1530-6992.
- Zhang, J.; Fu, Y. & Lakowicz, J. R. (2007b) Single Cell Fluorescence Imaging Using Metal Plasmon-Coupled Probe. *Bioconjugate Chem.*, 18:800-805, ISSN: 1520-4812.
- Zhang, J.; Fu, Y.; Liang, D.; Nowaczyk, K.; Zhao, R. Y. & Lakowicz, J. R. (2008) Single-Cell Fluorescence Imaging Using Metal Plasmon-Coupled Probe 2: Single-Molecule Counting on Lifetime Image. *Nano Lett.*, 8(4):1179-1186, ISSN: 1530-6992.
- Zhao, J.; Das, A.; Schatz, G. C.; Sligar, S. G. & Van Duyne, R. P. (2008) Resonance Localized Surface Plasmon Spectroscopy: Sensing Substrate and Inhibitor Binding to Cytochrome P450. *J. Phys. Chem. C*, 112:13084-13088, ISSN: 1520-5126.
- Zhao, J.; Jensen, L.; Sung, J.; Zou, S.; Schatz, G. C. & Van Duyne, R. P. (2007) Interaction of plasmon and molecular resonances for rhodamine 6G adsorbed on silver nanoparticles. *J. Am. Chem. Soc.*, 129:7647-7656, ISSN: 1520-5126.
- Zhu, S.; Du, C. & Fu, Y. (2009) Localized surface plasmon resonance-based hybrid Au-Ag nanoparticles for detection of Staphylococcus aureus enterotoxin B. *Opt. Mat.*, 31:1608-1613, ISSN: 0925-3467.
- Zhu, S.; Li, F.; Du, C. & Fu, Y. (2008) A localized surface plasmon resonance nanosensor based on rhombic Ag nanoparticle array. *Sens. Act. B*, 134:193-198, ISSN: 0925-4005.

IntechOpen

IntechOpen

IntechOpen



Silver Nanoparticles

Edited by David Pozo Perez

ISBN 978-953-307-028-5

Hard cover, 334 pages

Publisher InTech

Published online 01, March, 2010

Published in print edition March, 2010

Nanotechnology will be soon required in most engineering and science curricula. It cannot be questioned that cutting-edge applications based on nanoscience are having a considerable impact in nearly all fields of research, from basic to more problem-solving scientific enterprises. In this sense, books like “Silver Nanoparticles” aim at filling the gaps for comprehensive information to help both newcomers and experts, in a particular fast-growing area of research. Besides, one of the key features of this book is that it could serve both academia and industry. “Silver nanoparticles” is a collection of eighteen chapters written by experts in their respective fields. These reviews are representative of the current research areas within silver nanoparticle nanoscience and nanotechnology.

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Carlos Caro, Paula M. Castillo, Rebecca Klippstein, David Pozo and Ana P. Zaderenko (2010). Silver Nanoparticles: Sensing and Imaging Applications, Silver Nanoparticles, David Pozo Perez (Ed.), ISBN: 978-953-307-028-5, InTech, Available from: <http://www.intechopen.com/books/silver-nanoparticles/silver-nanoparticles-sensing-and-imaging-applications>

INTECH

open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447
Fax: +385 (51) 686 166
www.intechopen.com

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820
Fax: +86-21-62489821

© 2010 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the [Creative Commons Attribution-NonCommercial-ShareAlike-3.0 License](#), which permits use, distribution and reproduction for non-commercial purposes, provided the original is properly cited and derivative works building on this content are distributed under the same license.

IntechOpen

IntechOpen