

# 5<sup>TH</sup> REGIONAL SYMPOSIUM ON ELECTROCHEMISTRY SOUTH EAST EUROPE

PROGRAM  
BOOK OF ABSTRACTS

5<sup>TH</sup> REGIONAL  
SYMPOSIUM ON ELECTROCHEMISTRY  
SOUTH-EAST EUROPE

PROGRAM & BOOK OF ABSTRACTS

PUBLISHED BY

Academician Evgeni Budevski Institute of Electrochemistry and Energy Systems  
Bulgarian Academy of Sciences  
10 Acad. G. Bonchev Str.  
1113 Sofia, Bulgaria  
Tel: (+359 2) 872 25 45  
Fax: (+359 2) 872 25 44  
[www.bas.bg/cleps](http://www.bas.bg/cleps)

PRINTED BY

Es Print  
49 Kliment Ohridski Blvd.  
1756 Sofia, Bulgaria

EDITORS

Daria Vladikova  
Gergana Raikova

DESIGN

Evgenia Ilkova

Sofia, Bulgaria  
June 2015

ISBN 978-954-92483-4-0

5<sup>TH</sup> REGIONAL  
SYMPOSIUM ON  
ELECTROCHEMISTRY  
SOUTH EAST EUROPE

June 7-11, 2015  
RIU Pravets | Pravets, Bulgaria

PROGRAM  
BOOK OF ABSTRACTS

Sofia € 2015

## Microwave Synthesis of Crystalline RuO<sub>2</sub> Supercapacitor Materials

Gavrilo Šekularac\*, Aleksandar Dekanski, Milica Košević and Vladimir Panić  
*Institute of Chemistry, Technology and Metallurgy - Department of Electrochemistry ,  
University of Belgrade, Njegoševa 12, 11001 Belgrade, Serbia*  
\*gavrilo@ihtm.bg.ac.rs

One-step simple temperature-controlled microwave synthesis was applied to prepare nanocrystalline RuO<sub>2</sub> dispersion from aqueous RuCl<sub>3</sub>. RuO<sub>2</sub> samples were synthesized at temperature 120, 150, 200, 220 and 250 °C in closed vessel. Reaction time was 5 min. Capacitive properties of RuO<sub>2</sub> was investigated by cyclic voltammetry and electrochemical impedance spectroscopy in 1 M H<sub>2</sub>SO<sub>4</sub> and standard three-electrode cell, with ink-type working electrode on glassy carbon substrate. The specific capacitance of 320, 550, 750, 750 F/g was obtained for samples synthesized at temperature 150, 200, 220 and 250 °C respectively, cyclic voltammetry curves are shown in (Fig.1). The best capacitive performance was obtained for sample synthesized at temperature of 200 °C, specific capacitance of 750 F/g which negligibly depend on sweep rate in 5–500 mV/s range. RuO<sub>2</sub> dispersion was subjected to dynamic light scattering in order to analyze the synthesized particles, whereas structural and morphological properties of the solid phase are investigated by AFM, SEM, EDAX and XRD techniques. The ordered unusual shape of ca. 100 nm native particles, as well as highly-ordered prismatic agglomerate sheets are observed for sample synthesized at temperature 200 °C. These findings are quite unusual for this kind of material consisted of rather large particles [1], and makes it excellent candidate for both low and high power applications.




Fig.1. Cyclic voltammograms of RuO<sub>2</sub> synthesized in microwave at temperature 150, 200, 220, 250 °C in 1 M H<sub>2</sub>SO<sub>4</sub>, scan rate 50 mV/s.

### References

- [1] J. P. Zheng, P. J. Cygan, T.R. Jow, J. Electrochem. Soc. 142 (1995) 2699