



Aberystwyth University

The rheology and processing of "edge sheared" colloidal polymer opals

Wong, H.; Mackley, Malcolm; Butler, Simon; Baumberg, J. J.; Snoswell, David R. E.; Finlayson, Christopher E.; Zhao, Qibin

Published in:

Journal of Rheology

DOI:

[10.1122/1.4862920](https://doi.org/10.1122/1.4862920)

Publication date:

2014

Citation for published version (APA):

Wong, H., Mackley, M., Butler, S., Baumberg, J. J., Snoswell, D. R. E., Finlayson, C. E., & Zhao, Q. (2014). The rheology and processing of "edge sheared" colloidal polymer opals. *Journal of Rheology*, 58(2), 397-409. <https://doi.org/10.1122/1.4862920>

General rights

Copyright and moral rights for the publications made accessible in the Aberystwyth Research Portal (the Institutional Repository) are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the Aberystwyth Research Portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the Aberystwyth Research Portal

Take down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

tel: +44 1970 62 2400
email: is@aber.ac.uk

The rheology and processing of “edge sheared” colloidal polymer opals

By

Hon Sum Wong, Malcolm Mackley and Simon Butler,

Department of Chemical Engineering and Biotechnology
University of Cambridge
CB2 3RA
UK

Jeremy Baumberg, David Snoswell*, Chris Finlayson and Qibin Zhao**

NanoPhotonics Centre
Cavendish Laboratory
University of Cambridge
CB3 0HE
UK

*

Current address
Schlumberger Gould Research
Cambridge, CB3 0EL
UK

**

Current address
Institute of Mathematics, Physics and Computer Science (IMPACS),
Prifysgol Aberystwyth University,
SY23 3BZ
Wales

Abstract.

This paper is concerned with the rheology and processing of solvent-free core shell “polymer opals” that consist of a soft outer shell grafted to hard colloidal polymer core particles. Strong iridescent colours can be produced by shearing the material in a certain way that causes the initially disordered spheres to rearrange into ordered crystalline structures and produce colours by diffraction and interference of multiple light scattering, similar to gemstone opals. The basic linear viscoelastic rheology of a polymer opal sample was determined as a function of temperature and the material was found to be highly viscoelastic at all tested temperatures. A Cambridge Multipass Rheometer (MPR) was specifically modified in order to make controlled mechanical measurements of initially disordered polymer opal tapes that were sandwiched between protective PET sheets. Axial extension, simple shear and a novel “edge shearing” geometry were all evaluated and multiple successive experiments of the edge shearing test were carried out at different temperatures. The optical development of colloidal ordering, measured as optical opalescence, was quantified by spectroscopy using visible backscattered light. The development of opalescence was found to be sensitive to the geometry of deformation and a number of process variables suggesting a complex interaction of parameters that caused the opalescence. In order to identify aspects of the deformation mechanism of the edge shearing experiment, a separate series of in situ optical experiments were carried out and this helped indicate the extent of simple shear generated with each edge shear deformation. The results show that strong ordering can be induced by successive edge shearing deformation. The results are relevant to polymer opal rheology, processing and mechanisms relating to ordering within complex viscoelastic fluids.

1. Introduction

Polymer Opals are a relatively new and exciting class of materials that have unusual rheology, processing and optical properties (see for example Pursiainen et al 2005, Snoswell et al 2010, Finlayson et al 2013). Following the development of monodisperse colloidal polymer particle suspensions in the 1950s (Alfrey et al 1954), it became clear that they could have interesting optical properties if ordered (see for example Hachisu et al 1973). Subsequently Solvent-free polymer particle spheres have been developed of the type shown schematically in figure 1, where polymer chains are grafted to the outside of the particles in a manner that creates a solvent-free concentrated dispersion of monodisperse spheres within a highly viscoelastic matrix (See for example Ruhl et al 2003, Viel et al 2007). Because the spheres were of a diameter similar to the wavelength of light there is potential for these solvent-free materials to exhibit interesting photonic optical effects, particularly if the colloidal particles become ordered (see for example Ruhl et al 2004, Pursiainen et al 2007).

A breakthrough was achieved with the development of an edge-induced rotational shearing (EIRS) process (Finlayson et al 2011a) shown schematically in figure 2. Repeated shearing at elevated temperature around a sharp edge can produce samples with improved reproducibly and uniformity of bulk-ordering, greatly enhancing both the intensity and chromaticity of the observed structural colour. The application of shear ordering techniques to these solvent-free systems allow formation of permanent, mechanically robust composites in the solid-state. An attractive feature of elastomeric polymer opals is the tunability of their perceived colour by the bending or stretch modification of the (111) plane spacing. As such, these “polymer opals” present opportunities for a step-change away from the monolithic architectures which are currently relied upon in the field of photonic structures, and are a promising platform for next generation bulk-scale photonics materials, coatings, fibres and sensors (Sussman et al 2009, Finlayson et al 2011b Finlayson et al 2013).

The effect of shear on the ordering and rheology of colloidal suspensions in a low viscosity matrix has been reported before and in general it has been found that simple shear is capable of creating order in concentrated colloidal systems (see for example Ackerson et al 1988, Chen et al 1992, Liu et al 1993) with an associated rheological general trend of shear thinning (Mewis et al 1989). A number of authors, (see for example, Ackerson (1990), Haw et al (1998), Koumakis et al (2008), McMullan (2009)) have reported the ordering of colloidal suspensions using oscillatory shear and a review on low viscosity base fluid ordering in steady and oscillatory simple shear is given by Vermant et al (2005). As the

concentration of suspension increases, complications such as jamming (see for example Trappe et al 2001, Kramb et al 2011) and high shear disorder (Catherall et al 2000) can also occur which makes generalisation of microstructural behaviour difficult.

The melt rheology and theory of commercial processible polymer melts is well documented and now understood (See for example Dealy and Wang 2013), however, as polymer melts become more intractable and rubber-like, both their rheology and process behaviour become more difficult to characterise and understand (see for example White et al 2008).

In this paper a polymer opal sample is considered where the rheology is in a transition region between that of a polymer melt and a rubber. The material is difficult to process at all available temperatures and depending on process history the material may be ordered or not. The ability to directly visualise the ordering and hence shear history in the polymer opals through colour changes aids understanding of flow induced ordering mechanisms and may give insight into the rheological behaviour of the material. In addition to reporting temperature dependant rheological measurements of a polymer opal sample, this paper builds on the discovery by Finlayson et al (2011a) that showed successive hand edge shearing can induce ordering of an initially disordered sample. A new way of carrying out machine controlled experiments has been developed by modifying a Cambridge Multipass Rheometer (MPR) (Mackley et al 1995) in order that systematic deformation experiments could be carried out as a function of a number of different variables that influence ordering. The test materials were then subsequently evaluated for their optical spectra response thereby enabling optimum process conditions for opalescence to be established.

2. Opal Material.

The polymeric opal material described in this paper was based on ensembles of core-interlayer-shell (CIS) particles, synthesized at Deutsches Kunststoff Institut (DKI), Germany using a multi-stage emulsion polymerisation process (Ruhl et al 2003, Viel et al 2007). As illustrated in figure 1, the core-shell particle precursors are approximately 250nm in diameter, and consist of a hard crosslinked polystyrene (PS) core, coated with a thin polymer layer containing PMMA as a grafting agent, and a soft polyethylacrylate (PEA) outer-shell (Spahn et al 2011). In this configuration, the net refractive index contrast between core and shell material is $\Delta n/n \approx 0.11$. The volume fraction of PS core particles in the samples used was about 50% as determined from the initial reaction mix composition and the material recovered from the reactor had a rubbery consistency. The material also contained the

addition of 0.05%wt carbon black which has been found to enhance optical contrast when opalescence occurs (Pursiainen 2007). A mini-extruder (Thermo Scientific, MiniLab) consisting of two counter rotating metallic screws with adjustable speed in the range 1-150 (rpm) and adjustable temperature 25-250°C was used to compound the material. Typical compounding temperatures were ~150°C and up to 6g of the opal precursor material was manually fed into the extruder, where a melt was formed and homogenized under the extreme shear conditions provided by the screws. The generated overpressure then forced the material through a narrow-bore stainless steel die, producing rectangular section extrudates of a few mm thickness. At this stage of processing the polymer sample had a dull green colour due to limited particle ordering but was not strongly opalescent.

3. Viscoelastic response

The viscoelasticity of the polymer opal was studied using an Ares rheometer. This involved applying an oscillatory deformation to the polymer opal sample and measuring the torque response. Two oscillatory rheometric measurements were made, namely a strain sweep test and a frequency sweep test. The strain sweep test was performed at a fixed angular frequency of 10rad/s while the frequency sweep test was performed at a fixed strain amplitude of 0.01. Between 3-5g of the polymer opal sample was heated to 150 °C and pressed into a circular aluminium template to form a polymer opal disk with a diameter of 25 mm and a uniform thickness of 3 mm. The polymer opal disk was subsequently loaded into the test region of a parallel plate flat disc rheometer. Strain sweep and frequency sweep tests were then carried out at 25 °C, 100 °C and 150 °C to measure the viscoelastic response at the different temperatures. At all the test temperatures the shell (PEA) material was above its glass transition temperature (-15 °C) and because the PS core was crosslinked the core structure remained intact. These tests captured the viscoelastic properties of the polymer opal by providing information on the G' (storage modulus), G'' (loss modulus), and η^* (complex viscosity). Additional steady shearing experiments were attempted but the material would not deform uniformly at any temperature for large strains within the parallel plate geometry.

The rheological data is shown in figure 3 for temperatures of 25, 100 and 125 °C. The 0.01 strain frequency sweeps show that at all temperatures the material is highly viscoelastic with G' dominance at all measured frequencies. The values of both G' and G'' decrease with temperature, however the G' dominance at all temperatures is a clear indication of the processing difficulty that this material exhibits. The strain sweeps for the material carried out

at 10 rads/s show a very strong strain sensitivity with the linear behaviour limited up to an approximate strain level of 0.1. The dramatic strain softening resembles that observed by Kramb et al (2011) and Koumakis et al (2008) for a dense suspension of mono disperse spheres and or could be due to a number of factors with slip at the boundary walls a strong possibility. Previous attempts at melt processing this material had meet with only partial success, (Snoswell et al 2010) and the rheological data presented here supports the view that the material is closer to a rubber than a commercial polymer melt at all test temperatures.

4. Experimental configuration of Multipass Rheometer (MPR) testing.

The Multipass rheometer (MPR) was originally designed as a capillary melt processing device (Mackley et al 1995) and subsequently has been modified to perform a wide range of different rheometric deformations (Mackley et al 2011). A further modification was carried out in order to test the deformation behaviour of polymer opal samples. In this new configuration the two servo hydraulic pistons of the MPR were used to deform polymer opal samples in tension, simple shear, and edge shearing. Figure 4 a, b, and c shows schematically the form of a) tension, b) simple shear and c) edge shearing applied deformations and the figure also shows a photograph of the apparatus. Because the opal material was difficult to process it was necessary to sandwich the material between PET tapes. The extruded opal ribbons were positioned between 2 metre-long, 4 cm wide PET tapes and the tapes were then fed under a quartz roller, which had a compressive downwards pressure of order 3 bar. The sample was then positioned on a heated glass plate, with the cartridge and plate being pre-heated to 150°C. The translation stage was moved horizontally at 1 mm s⁻¹ relative to the roller, which was free to rotate, pressing the sample into uniform thin films in a squeeze/shear mechanism. The roller was typically set to produce thicknesses of order 100 µm and films could be of length from a few centimetres up to several metres. The processing resulted in a certain level of mechanical bonding between the PET tape and opal sample, however for simple shear and pure extension mechanical tests there were difficulties.

Samples were prepared in the way indicated in figure 4 in order that tensile, simple shear or edge shearing tests could be carried out. This meant that some of the protective PET tape had to be removed and this in turn resulted in a test sample that was more difficult to manipulate. Heating of the sample was provided either by bringing a purpose built heated flat face up to the surface of the tape/opal assembly or by using the heated knife edge. This 90⁰ knife edge was mounted on a horizontal traverse that enabled different levels of knife edge

penetration to be explored. Three different radii of curvature at the edge of 1, 2 and 5 mm radius were available for testing. Samples were clamped and by movement of one piston the samples could be pre tensioned. Subsequently the pistons were then programmed to move in a synchronous fashion. Surface temperatures were measured using both an IR thermal probe and a thermocouple.

5. MPR Results and optical interrogation

MPR experiments were carried out under different boundary conditions and samples were subsequently optically interrogated at room temperature in order to establish their photonic response. Figure 5 shows representative photographs of the processed tapes. Figure 5a is the starting tape where most of the colour contrast comes from the PET outer tapes. Figure 5b shows the tape after tensile testing. In this case the outer PET tapes are only present in the clamped region. A deformation velocity of 0.5 mm/s was applied for a period of fifteen seconds and the central area of the tape was maintained at 100⁰C using a flat faced heater block. A weak colour change can be seen in figure 5b. Slippage of the sample within the mechanical clamps resulted in only a limited range of strains being able to be achieved and in addition the opal material had limited extensibility before mechanical failure. Difficulties were also experienced with the simple shearing test where, as shown in Figure 4b the sample was gripped with PET sheet on opposite sides. Slip within the clamps and at the opal/PET interface was problematic and levels of deformation again were very limited, however Figure 5c shows a successfully sheared sample with a deformation velocity of 0.5mm/s applied for 15s at 100⁰C. The photograph shows some enhanced colour contrast and the development of an opalescent appearance. In both the cases of pure extension and simple shear it was not possible to carry out repeat experiments on the same sample.

The edge shearing, knife edge tests proved to be by far the easiest to perform as the opal sample was protected on each face by the PET tape and the type of deformation shown schematically in figure 4c resulted in a compressive load acting between the sample and the tape thereby enhancing adhesion between the two surface. Figure 5d shows a representative photograph of a knife edge test where the central region of the tape had been successively oscillated around the knife edge. There are a number of process variables that can be systematically explored and this photograph was taken a piston velocity $V=1\text{mm/s}$, $T=100^0\text{C}$, Number of oscillations $N=10$ and knife edge penetration distance beyond the centre line of 8mm. The initial tensile load on the sample is another variable but little change was observed over the range of 5 -50N tested. Figure 5d shows there is a strong opalescent optical

contrast in the region of the processed tape that has passed successively across the knife edge and this experiment proved to give very reproducible results.

In order to make a more quantitative measure of the optical changes, optical reflectivity spectra was obtained for both faces of the processed opal sample. Measurements were taken using an adapted Olympus BX51 microscope, using a focused spot diameter of about 20 μ m, with the light signal collected using suitable focusing optics and a fibre-coupled CCD spectrometer (Finlayson et al 2011a). The spectra were normalised using a highly-reflective aluminium mirror (bright-field reflectance). Figure 6 shows representative spectra for the tapes photographed in figure 5 and from the observed spectra, it is possible to establish more clearly the changes due to the processing.

Figure 6 shows the spectral reflectivity intensity as a function of wavelength for the different samples. The intensity profile as a function of wavelength for the starting material increases with wavelength and shows a mild shoulder. The tensile test sample shows a small change in reflectivity with an enhancement of signal above 600nm. The simple shear sample shows the beginning of a peak in the region of 600nm and the knife edge, edge sheared sample shows a clear opalescent peak. Previous modelling of polymer opal spectra as a consequence of progressive crystallisation (Snoswell et al 2010) has linked the peak height with the number of ordered layers within the sample, the peak breadth with the level of ordering and peak wavelength position with the “Bragg spacing” of the ordered structure. The data show that edge shearing is the most effective of the deformation processes and that tensile deformation alone does not appear to induce ordering that produces opalescence.

When edge shearing experiments were carried out it was discovered that there were differences in optical properties between the “outer surface” that was furthest away from the knife edge and the “inner” surface which was closest and in figure 7 the optical spectra for both the inner and outer surface are given for different process conditions. Experiments were carried out as a systematic function of the following variables.

- a) Temperature $T = 25, 50, 100$ and 150 °C
- b) Number of passes $N = 1, 10, 100, 200$ and 300
- c) Knife edge penetration $X = 6, 8, 10, 12, 14$ and 16 mm
- d) Piston velocity $V = 0.1, 0.5, 1, 5, 10, 20$ and 30 mm/s

The complete process conditions for each of the experiments are given in the figure 7

Additional experiments were carried out at different initial loads but this was found to have little effect on the results and all those reported here were carried out at a 5N initial load. Knife edge curvature was also explored and this again was found to have little effect.

Figure 7a and b show the strong effect that temperature has on the development of opalescence. For all cases considered the outer surface effects were stronger than the inner surface, although the trends for both surfaces were similar. Both at 25 and 150 °C there was very little development of opalescence, however between these two temperatures there was a strong effect, with 100 °C experiment showing the largest opalescent peak. Whilst it was not necessarily surprising that an opalescent peak did not develop at 25 °C, it was surprising that there was no opalescence at 150 °C. Higher temperatures do promote thermal motion and so it is possible that shear-ordered crystalline regions are dissolved at the higher temperatures once shearing has ceased. The corresponding rheology changes as a function of temperature that were shown in figure 3 did not indicate any significant change in rheological profile other than a general reduction in modulus with temperature suggesting that the change in opalescence could not be directly detected by a rheology change.

The number of passes also had a significant effect on the observed level of opalescence and this is shown in figure 7c and d. One pass produces a small effect and maximum peak height is achieved at 100 passes. After that, the peak height signal decreases with a further 200 and 300 passes. Again the results are surprising with a clear maximum developing followed by an unexpected decrease. Colloidal crystallisation is known to be strongly induced by wall effects (see for example van Blaaderen et al (1997)) and in the polymer opal case, surface growth is believed to develop from the surface into the interior of the sample with each shear pass. A possible explanation of the decrease from the maximum may be that the crystallised phase of the opals is stationary with respect to the outer foils and it is only the disordered inner part of the phase that flows. As crystal planes develop, growing in from the wall, the ratio of ordered stationary phase and disordered "flowing" phase changes. This in effect increases the local shear at the boundary between the disordered and ordered phases throughout crystal growth, despite the fact the bulk shear conditions are constant. When the stationary crystal phase occupies a large proportion of the sample thickness, local shear at the growing crystal boundary becomes very large and starts to break up multiple crystal layers causing degradation of the colour.

Figure 7e and f show the effect of knife edge penetration and once again a maximum was detected within the experimental range. As knife edge penetration increased from 6 to 12 mm the opalescent peak height increased. Then for penetration of 14 and 16mm there was a

progressive decrease. Conceptually a disordered arrangement of spheres requires individual sphere to move by up to 0.5 of its diameter relative to its neighbour to find a location in an ordered lattice. Therefore it might be expected for shear strain magnitudes of 0.5 to be optimal for crystallisation. Since shear magnitude is controlled by knife edge penetration, this may account for the optimum positions observed.

Finally the effect of piston velocity is shown in figure 7g and h. These graphs too show a peak effect at 1mm/s with a progressive increase and then decrease in peak height with increasing piston velocity. The effect of velocity can be interpreted as changing the shear rate. This impacts on the ordering process by changing the proportion of viscous and elastic deformation during shear, with only viscous shear producing sphere-sphere movement and alignment into the ordered crystal state.

For any set of process conditions the results were essentially reproducible when repeated and taken as a whole the data shows a complex, but reproducible sensitivity to the process variables tested. This in turn suggests that the mechanisms controlling the development of ordering is also complex and not directly related to the materials rheology which for example showed a weak but monotonic effect to temperature.

6. Deformation of model material

The edge shearing, knife edge deformation of the polymer opal sample sandwiched between plastic sheets is both an unusual and a complicated deformation and so in an attempt to help understand the type of deformation that had occurred, a model deformation was carried out using a thicker foamed material.

An initial 3mm thick polyethylene foam strip was fixed with double sided adhesive tape to the PET tape. The assembly was then in turn fixed to the pistons of the MPR in the edge shearing mode and then tensioned. It was possible to draw lines on the edge of the compressed foamed material as shown in the photographs of figure 8 and from this determine the strain deformation experienced during the edge shearing experiment. From photographs of the type shown in figure 8 it can be seen that the deformation is dominantly simple shear as initially conjectured by Finlayson et al (2011a) and the maximum level of shear strain achieved for the compressed foam sample was of order 0.5. The results indicate that the model knife - edge shearing was predominantly simple shear and it is possible that this is also true for the opal sample which unfortunately could not be tested in this way because the thickness of the sample was too thin and side view optical observation was not possible. Because the geometry of the model system is similar for the opal samples we believe the dominant type and level of shear strain is similar in both cases and this would correspond for

the opal tests to an approximate applied shear rate of 0.05 s^{-1} at the lowest piston speed and 15 s^{-1} at the highest piston speed.

7. Discussion and conclusions

The linear viscoelastic rheology of the tested polymer opal samples had rubbery like properties, and the material was on the edge of processibility. Both aspects result in a rheologically complex material with a high level of elasticity. Normally the polystyrene colloidal particles in the solvent-free core shell material would be expected to be disordered, however shear induced ordering occurs under certain processing conditions.

The ordering of colloidal suspensions in low viscosity matrix fluids has been reported before (see for example Liu et al 1993); however the transition, even in this relatively simple fluid, from low shear disorder to intermediate shear order and then potentially high shear disorder has not been extensively studied, mapped or modelled. In the case of polymer opals the situation is even more complex. The high level of elasticity as reported in this paper resulted in material that was both strain and strain rate dependant. The structure of the solvent-free rubbery material is also complex as the mobile shell phase of the material is grafted to the core particle. The MPR experimental results indicate that simple tension did not induce ordering within the material; however the direct application of a single pass simple shear did induce some ordering. Both these experiments suffered from experiment difficulties and so only very limited experiments were possible Multiple edge shearing around a knife edge did induce significant ordering. As with low viscosity matrix suspensions, (see for example Vermant et al (2005), the application of repeated simple shear oscillations enhances ordering kinetics.

Successive edge shearing proved to be the only effective experimental way of inducing ordering and this was investigated as a function of a number of process variables. When each process variable was scanned an optimum range for opal formation was discovered; namely a process temperature of 100°C , 100 oscillations, a knife edge penetration of 12mm and a piston velocity of 1mm/s. In addition the outer surface of the opal sample always showed a stronger opalescence to the inner surface. These results indicate that ordering kinetics are influenced by a complex series of variables with nucleation and growth of ordering being controlled by many different factors.

The MPR model edge shearing experiments demonstrated that the main deformation for edge shearing was simple shear; however the difference in opalescence for the polymer opal

sample between the outer and inner surfaces suggest that the opal deformation is more complex than the model deformation. The polymer opal edge shear deformation will have additional factors including compressive squeeze flow deformation and almost certainly wall slip between the PET and Opal interfaces. The fact that the opalescence on the top and bottom faces was different for any one set of experiments also highlights potential differences between the apparently homogeneous simple shear deformation of the model experiments and a more complex deformation for the opal sample.

Clearly many uncertainties remain in relation to both the Polymer Opal material and the fact that the unusual edge shearing around a knife edge can be so effective at inducing opalescent ordering of particles. There is therefore a need for further experiments and in particular there is scope for a rich vein of modelling that can help to understand the deformation, rheology, ordering and resulting opalescence of this remarkable material.

Acknowledgements

We would like to thank Strata Technology Ltd and in particular Trevor Hesketh for the manufacture of the MPR mechanical testing facility and we are also grateful to DKI for supply of base material. We acknowledge EPSRC grants EP/G060649/1, EP/H027130/1, EP/E040241 and EU LINASS 320503.

References

B. J. Ackerson and P. N. Pusey
Shear-Induced Order in Suspensions of Hard Spheres
Phys Rev letters 61, 8, 1033-1036 (1988)

B.J. Ackerson
Shear induced order and shear processing of model hard sphere suspensions
Journal of Rheology. 34(4) 553 (1990)

T Alfrey, E.B.Bradford, J.W.Vanderhoff and G. Oyster
Optical Properties of Uniform Particle-Size Latexes,
J. Opt. Soc. Am. **44**, 603-607 (1954)

A.van Blaaderen, R. Ruel, and P. Wiltzius
Template directed colloidal crystallisation
Nature 385, 321-324 (1997)

- A. A. Catherall, J. R. Melrose and R. C. Ball
 Shear thickening and order–disorder effects in concentrated colloids at high shear rates
 Journal of Rheology 44,1, 1-25 (2000)
- L. B. Chen, C. F. Zukoski, B. J. Ackerson, H. J. M. Hanley, G. C. Straty, J. Barker and C. J. Glinka
 Structural Changes and Orientational Order in a Sheared Colloidal Suspension
 Physical Review letters 69, 4 688-703 (1992)
- J. M. Dealy and J. Wang
 Melt Rheology and its Applications in the Plastics Industry
 Springer, Munich, 2013.
- C. E. Finlayson, P. Spahn, D. R. E. Snoswell, G. Yates, A. Kontogeorgos, A. I. Haines, G. P. Hellmann, and J. J. Baumberg
 3D Bulk Ordering in Macroscopic Solid Opaline Films by Edge-Induced Rotational Shearing
 Adv. Mater. 23, 1540-1544 (2011a)
- C.E Finlayson, C Goddard, E. Papachristodoulou, D.R.E Snoswell, A. Kontogeorgos, P.Spahn, G.P. Hellmann, O. Hess, J.J Baumberg
 Ordering in stretch tunable polymeric opal fibers
 Opt. Express 19, 3144-3154 (2011b)
- C.E. Finlayson and J.J. Baumberg,
 Polymer opals as novel photonic materials
 Polym. Int. 62,10 1403-1407(2013)
- M. D. Haw, W. C. K. Poon, and P. N. Pusey
 Direct observation of oscillatory-shear-induced order in colloidal suspensions
 Phys Rev E 57, 6 6859- 6864 (1998)
- S. Hachisu, Y. Kobayashi, A.D. Kose
 Phase separation in monodisperse latexes
 Journal of Colloid and Interface Science 42 (2), 342 (1973)
- AND
 ¥OKO KOBAYASHI AI-D AKIRA KOSE
 N. Koumakis, A. B. Schofieldc and G. Petekidis
 Effects of shear induced crystallization on the rheology and ageing of hard sphere glasses
 Soft Matter, 4, 2008–2018 (2008)
- R. C. Kramb and C. F. Zukoskia
 Nonlinear rheology and yielding in dense suspensions of hard anisotropic colloids
 Journal of Rheology 55(5), 1069-1084 (2011)
- J. Liu, D. A. Weitz and B.J. Ackerson
 Coherent crystallography of shear-aligned crystals of hard-sphere colloids
 Phys RevE 48, 2, 1106-1104 (1993)
- A.J. Liu, and S.R. Nagel,
 Granular and jammed materials
 Soft Matter, 6, 2869-2870 (2010).

M.R.Mackley, R.T.J.Marshall and J.B.A.F. Smeulders.
The multipass rheometer.
Journal of Rheology. 39(6), 1293- 1309 (1995).

M.R.Mackley and D.G.Hassell
The Multipass Rheometer; a review
Journal of Non Newtonian Fluid Mechanics, 166, 9-10, 421-456 (2011)

J.M. McMullan and N.J. Wagner,
Directed self-assembly of suspensions by large amplitude oscillatory shear flow
Journal of Rheology. 53(3) 575-588 2009,

J. Mewis, W.J. Frith, T.A. Strivens and W.B. Russel
The rheology of suspensions containing polymerically stabilized particles
AIChE Journal 35, 3, 415-422 (1989)

O.L.J. Pursiainen, J.J.Baumberg, H.Winkler, B.Viel and T.Ruhl
Compact strain-sensitive flexible photonic crystals for sensors
Appl. Phys. Lett. 87, 10, 1902 (2005)

O. L. J. Pursiainen, J. J. Baumberg, H. Winkler, B. Viel, P. Spahn, and T. Ruhl,
Nanoparticle-tuned structural colour from polymer opals,
Opt. Express 15, 9552-9561 (2007)

T. Ruhl, P. Spahn, G. P. Hellmann.
Artificial opals prepared by melt compression
Polymer 44, 7625-7634 (2003)

T. Ruhl, P. Spahn, H. Winkler, G. P. Hellmann,
Large Area Monodomain Order in Colloidal Crystals,
Macromol. Chem. Phys. 205, 1385-1393 (2004)

D.R.E.Snoswell, A. Kontogeorgos, J.J.Baumberg, T.D.Lord M.R.Mackley, P.Spahn and G.P.
Hellmann
Shear ordering in polymer photonic crystals
Phys. Rev. E 81, 020401 (2010).

P. Spahn, C.E. Finlayson, W.Mbi Etah, D.R.E.Snoswell, J.J.Baumberg and G.P.Hellmann
Modification of the Refractive-Index Contrast in Polymer Opal Films
J. Mater. Chem. 21, 8893-8897 (2011)

J. Sussman, D.R.E.Snoswell, A. Kontogeorgos, J.J. Baumberg and P Spahn
Thermochromic polymer opals
Appl. Phys. Lett. 95, 17, 3116 (2009)

V. Trappe, V. Prasad, L Cipelletti, P. N. Segre & D. A. Weitz
Jamming phase diagram for attractive particles
Nature 411, 14 772-775 (2001)

J. Vermant and M. J. Solomon
Flow-induced structure in colloidal suspensions
J. Phys.: Condens. Matter 17, 187–216 (2005)

B. Viel, T. Ruhl and G. P. Hellmann,
Reversible Deformation of Opal Elastomer.
Chemistry of Materials. 19, 5673-5679 (2007)

J.L.White and K.J Kim
Thermoplastic and Rubber Compounds
Hanser (2008)




Figure 1. Schematic diagram of polymer opal microstructure. a) Core interlayer shell structure b)-c) Ordering of particles from disordered state to opalescent ordered state (Cambridge NanoPhotonic Centre, 2009)







Figure 2. Schematic diagram of the edge shearing process showing geometry of opal film sandwiched between PET films.




(a)




(b)




(c)



(d)




(e)




(f)


Figure 3. Linear viscoelastic frequency and strain plots for Polymer Opal sample: (a) $T = 25^\circ\text{C}$, strain = 1%, (b) $T = 25^\circ\text{C}$, frequency = 10 rad/s , (c) $T = 100^\circ\text{C}$, strain = 1%, (d) $T = 100^\circ\text{C}$, frequency = 10 rad/s , (e) $T = 150^\circ\text{C}$, strain = 1% and (f) $T = 150^\circ\text{C}$, frequency = 10 rad/s .




(a)



(b)




(c)



Strata Technology “edge shearing” MPR fitting

Figure 4. Schematic diagrams and photograph of MPR. a) Tensile deformation. b) Simple shear deformation. c) Edge shearing deformation geometry and photograph of Strata Technology “edge shearing” attachment.



a

b

c

d

Figure 5. Representative photographs showing optical appearance of polymer opal samples. a) Initial tape. b) Tape after MPR tensile deformation. c) Tape after MPR simple shear deformation. d) Tape after successive MPR edge-shearing deformation.







Figure 6, Representative spectra on the variation of polymer opal outer surface spectral reflectivity as a function of wavelength for different types of deformation applied to the tape for; MPR unprocessed tape, MPR simple shear $V=0.5\text{mm/s}$, MPR tensile test $V=0.5\text{mm/s}$ and MPR edge shearing. MPR processed , $V= 1\text{mm/s}$. $T=100\text{ }^{\circ}\text{C}$ for all experiments




(a)




(b)




(c)




(d)




(e)



(f)



(g)



(h)

Figure 7. The effect of processing conditions on the polymer opal spectra: (a) and (b) temperature, $N=100$, $V=1\text{mm/s}$, $P=8\text{mm}$, $L=5N$. (c) and (d) number of passes over the knife edge, $T=100^\circ\text{C}$, $V=1\text{mm/s}$, $P=8\text{mm}$, $L=5N$. (e) and (f) penetration of the knife edge, $T=100^\circ\text{C}$, $N=10$, $V=1\text{mm/s}$, $L=5N$. (g) and (h) linear velocity of the film. $T=100^\circ\text{C}$, $P=8\text{mm}$, $N=10$, $L=5N$.




Figure 8. Side view photographic sequence of Polymer Opal sample being edge sheared from right to left, (a)-(c). $T=25^{\circ}\text{C}$. Piston tape translation velocity= 1mm/s. Approximate thickness of sample = 0.5mm
The photograph shows the V metal edge and the foam, sandwiched between a top and bottom PET tape. The vertical marker line shown in 7a is seen to shear as the sample progressively moves from right to left over the edge as shown in figures 7b and 7c