



You have downloaded a document from  
**RE-BUS**  
repository of the University of Silesia in Katowice

**Title:** Dielectric and electrostrictive properties of ferroelectric relaxors

**Author:** Zygmunt Surowiak, E. G. Fesenko, Ryszard Skulski

**Citation style:** Surowiak Zygmunt, Fesenko E. G., Skulski Ryszard. (1999). Dielectric and electrostrictive properties of ferroelectric relaxors. "Archives of Acoustics" (Vol. 24, no. 3 (1999) s. 391-399).



Uznanie autorstwa - Na tych samych warunkach - Licencja ta pozwala na kopiowanie, zmienianie, rozprowadzanie, przedstawianie i wykonywanie utworu tak długo, jak tylko na utwory zależne będzie udzielana taka sama licencja.



## DIELECTRIC AND ELECTROSTRICTIVE PROPERTIES OF FERROELECTRIC RELAXORS

Z. SUROWIAK, E.G. FESENKO\* and R. SKULSKI

University of Silesia, Faculty of Engineering  
Department of Materials Science  
(41-200 Sosnowiec, 2, Śnieżna St., Poland)  
e-mail: surowiak@us.edu.pl

\* Rostov State University,  
PIEZOPRIBOR  
(344-104 Rostov-on-Don, 10, Milchakova St., Russia)

On the basis of ferroelectric relaxors electrostrictive ceramics has been obtained. Searching for electrostrictive ceramic transducers with optimal electromechanical parameters include the following: 1) investigation of different types of complex oxides with the perovskite structure (OPS): ferroelectric, antiferroelectric, non-polar; 2) investigation of OPS with different degree of the cation order; 3) measurements of the electrostrictive coefficient ( $Q$ ), Curie-Weiss constant ( $C$ ), coefficient of linear thermal expansion ( $\lambda$ ), polarization ( $P$ ) and permittivity ( $\epsilon$ ); 4) X-ray structure analysis. The following rules have been stated out during the experimental investigations: 1) values of the electrostrictive coefficients ( $Q_{ijkl}$ ) depend not only on the chemical constitution of OPS but, first of all, on the degree of cation order (i.e. the coefficients increase with an increase in the degree of cation order: non-ordered state — simple state — ordered state); 2) products of the hydrostatic electrostrictive coefficient ( $Q_h$ ) and the Curie-Weiss ( $C$ ) constant of all ferroelectric and antiferroelectric OPS are nearly equal; 3) value of the hydrostatic electrostrictive coefficient ( $Q_h$ ) is nearly proportional to the linear thermal expansion coefficient square ( $\lambda^2$ ). Taking into account the above mentioned rules the detailed and systematic investigations of OPS with non-ordered cations and high value of the Curie-Weiss constant ( $C$ ) and permittivity ( $\epsilon$ ) were carried out. In such OPS high value of induced polarization leads to considerable electrostrictive deformation described by the  $M_{ijkl}$  tensor ( $M_{ijkl} \approx Q_{ijkl}\epsilon_r^2$ ). One can mention  $\text{PbNb}_{2/3}\text{Mg}_{1/3}\text{O}_3$  and solid solution prepared on the basis of  $\text{PbNb}_{2/3}\text{Mg}_{1/3}\text{O}_3$  as an example. Devices fabricated on the basis of electrostrictive ceramics provide a relative displacement of about  $10^{-3}$  what is few times more than the one provided by devices on the basis of piezoelectric ceramics.

### 1. Introduction

Among ferroelectrics, *relaxors* are mainly characterized by:

- 1) a very broad permittivity ( $\epsilon$ ) vs. temperature peak;
- 2) hysteresis loops above the temperature  $T_m$  (the temperature at which the permittivity is a maximum, i.e.,  $\epsilon_m$ );

- 3) a frequency dependence of permittivity maximum ( $\varepsilon_m(\omega)$ ) and of  $T_m(\omega)$ ;
- 4) a depolarization temperature  $T_d$  (as defined in reference [1]) lower than the temperature  $T_m$  (for  $\nu = 10^1 - 10^6$  Hz);
- 5) no evidence for any symmetry transformation;
- 6) when the temperature is higher than  $T_m$ ,  $\varepsilon(T)$  does not obey the Curie-Weiss law:

$$\varepsilon = \varepsilon_0 + \frac{C}{T - T_0} \approx \frac{C}{T - T_0}, \quad (1)$$

where  $C$  — the Curie-Weiss constant;  $T_0$  — the Curie-Weiss temperature ( $T > T_0$ ,  $T_0$  is different from the Curie point  $T_c$ ; in the case of the first-order phase transition,  $T_0 < T_c$ , while for the second-order phase transition  $T_0 = T_c$ );  $\varepsilon_0$  — the temperature-independent term  $\varepsilon_0$  can be neglected, because it is much smaller than the term  $C/(T - T_0)$  when  $T$  is near  $T_0$ .

In fact,  $\varepsilon(T)$  of the relaxors changes with  $T$  in the following manner:

$$\frac{1}{\varepsilon} - \frac{1}{\varepsilon_m} = C'(T - T_m)^n, \quad (2)$$

where  $C'$  — a constant,  $n$  — a constant ( $1 < n < 2$ ).

It has been shown that the largest relative strains ( $\eta$ ) of the electrostrictive nature take place in the case of the *ferroelectric relaxors* and of the *ferroelectrics with a diffuse phase transition*. The value of such strains ( $\sim 10^{-3}$ ) may exceed relative strains of magnetostrictive or piezoelectric nature ( $10^{-4} - 10^{-5}$ ).

When the electric field is applied to a dielectric material, it produces a strain proportional to the square of the field ( $\eta \sim E^2$ ). This effect is called the *electrostrictive effect*. Electrostrictive effect is a quadratic effect and the electrostrictive strain is not related to the sign of the applied field. In fact, *electrostriction is a result of the polarization  $P$  induced by the applied field* and the electrostrictive strain is directly proportional to the square of the polarization ( $\eta \sim P^2$ ). Unlike the piezoelectric effect, electrostriction may occur in all crystals whether or not the crystals have polarity.

In the case of ferroelectric crystal (e.g.  $\text{BaTiO}_3$  in  $T < T_c$ ) the electromechanical effect has a complex nature ( $\eta(E)$  effect must be a function of the domain structure, the spontaneous ( $P_s$ ) and induced ( $P_{\text{ind}}$ ) polarizations, etc.).

In the case of a *centrosymmetric crystal* (e.g., barium titanate in its paraelectric state), the electrostrictive effect has rather simple form. In this case, the equations of state for stress ( $\sigma_{ij}$ ) and for strain ( $\eta_{ij}$ ) components can be written as:

$$\sigma_{ij} = c_{ijkl}^P \eta_{ij} + q_{ijkl} P_k P_l, \quad (3)$$

$$\sigma_{ij} = c_{ijkl}^E \eta_{ij} + m_{ijkl} E_k E_l, \quad (4)$$

$$\eta_{ij} = s_{ijkl}^P \sigma_{kl} + Q_{ijkl} P_k P_l, \quad (5)$$

$$\eta_{ij} = s_{ijkl}^E \sigma_{kl} + M_{ijkl} E_k E_l, \quad (6)$$

where  $c_{ijkl}^{P(E)}$  — the elastic stiffness constants at constant electric field (the superscript  $E$ ) or polarization (the superscript  $P$ ),  $s_{ijkl}^{P(E)}$  — the elastic compliance constants at constant  $E$  or  $P$ .

Equations (3) - (6) are called *electrostriction equations*. In each of these equations, the first term on the right-hand side corresponds to Hooke's law and the second term to the electrostrictive effect. These equations define the electrostrictive coefficients  $Q$ ,  $q$ ,  $M$  and  $m$ . Each of the four electrostrictive coefficients is a fourth-rank tensor. Among these four coefficients,  $Q$  and  $M$  are most useful and its unit are  $\text{m}^4/\text{C}^2$  and  $\text{C}^2/\text{N}^2$  respectively. The relationship between  $Q_{ijkl}$  and  $M_{ijkl}$  is:

$$M_{ijkl} = \varepsilon_0^2 (\varepsilon_r^\sigma - 1)^2 Q_{ijkl}, \quad (7)$$

where  $\varepsilon_0$  — the permittivity of free space ( $\varepsilon_0 = 8.854 \cdot 10^{-12} \text{ F/m}$ ),  $\varepsilon_r^\sigma$  — the relative permittivity at stress  $\sigma = \text{const.}$ , or  $\sigma = 0$  (the superscript  $\sigma$ ).

The aim of the present work was to obtain different types of complex oxides with the *perovskite* type structure (OSP) and with the *tetragonal tungsten bronze* type structure, to investigate of these ceramic materials (ferroelectric, antiferroelectric, non-polar) with different degree of the cation order and to search for electrostrictive ceramic transducers with optimal electromechanical parameters.

## 2. Methods for measuring the electrostrictive coefficients

Using the Voigt notation (with two subscripts to replace the four subscripts), Eq. (5) can be written as:

$$\eta_i = s_{ij}^P \sigma_j + Q_{ijkl} P_k P_l \quad (i, j = 1, 2, \dots, 6; \quad k, l = 1, 2, 3). \quad (8)$$

Furthermore, upon stipulating that

$$Q_{i\mu} = Q_{ikl} \quad (\text{for } k = l), \quad (9)$$

and

$$Q_{i\mu} = 2Q_{ikl} \quad (\text{for } k \neq l), \quad (10)$$

$Q_{ikl}$  becomes  $Q_{i\mu}$  (with two subscripts). Thus, 81 components of the fourthrank tensor are reduced to 36 components. Due to the crystal's macroscopic symmetry, the number of independent components  $Q_{i\mu}$  can further be reduced. For centrosymmetric crystals (such as  $\bar{4}3m$ ,  $432$ ,  $m3m$ , etc) as well as unpoled ceramics, the  $Q_{i\mu}$  tensor is

	$P_1^2$	$P_2^2$	$P_3^2$	$P_2 P_3$	$P_1 P_3$	$P_1 P_2$
$\eta_1$	$Q_{11}$	$Q_{12}$	$Q_{12}$	0	0	0
$\eta_2$	$Q_{12}$	$Q_{11}$	$Q_{12}$	0	0	0
$\eta_3$	$Q_{12}$	$Q_{11}$	$Q_{11}$	0	0	0
$\eta_4$	0	0	0	$Q_{44}$	0	0
$\eta_5$	0	0	0	0	$Q_{44}$	0
$\eta_6$	0	0	0	0	0	$Q_{44}$

(11)

In the present experiment with a sample in the zero-stress state ( $\sigma_j = 0$ ), we obtain from Eqs. (8) and (11) relationships between components of strain ( $\eta_i$ ) and components

of polarization ( $P$ ) as follows:

$$\begin{aligned}
 \eta_1 &= Q_{11}P_1^2 + Q_{12}P_2^2 + Q_{12}P_3^2, \\
 \eta_2 &= Q_{12}P_1^2 + Q_{11}P_2^2 + Q_{12}P_3^2, \\
 \eta_3 &= Q_{12}P_1^2 + Q_{12}P_2^2 + Q_{11}P_3^2, \\
 \eta_4 &= Q_{44}P_2P_3, \\
 \eta_5 &= Q_{44}P_3P_1, \\
 \eta_6 &= Q_{44}P_1P_2.
 \end{aligned}
 \tag{12}$$

These formulae are essential in the measurement of electrostrictive coefficients. Most of the practical electrostrictive materials are used in their paraelectric state, because in this state the remanent strain is avoidable. For studying the electrostrictive effect, direct and indirect methods have been designed.

In general, electrostrictive coefficients ( $Q_{\lambda\mu}$ ) are obtained by measuring the electrostrictive strain directly. For example, if an electric field is applied in the direction 2 on a dielectric material with cubic symmetry (paraelectric phase), a transverse electrostrictive effect occurs, i.e., a strain develops along the direction 1. In this case the electrostriction equations (12) can be simplified to the form (transverse electrostrictive effect;  $\eta_1 \perp P_2$ ):

$$\eta_1 = Q_{12}P_2^2, \tag{13}$$

where  $\eta_1 = (\Delta l_1/l_1)$  — the strain in direction 1.

By applying an electric field on a sample, we can measure the strain  $\eta_1$  and the polarization  $P_2$  as a function of the applied field  $E$ . A plot of  $\eta_1$  as a function of  $P_2^2$  is a straight line with slope  $Q_{12}$ . The extension  $\Delta l_1$  as a function of the applied field is measured by a micro-displace meter with an X-Y recorder, while the polarization  $P_2$  as a function of the applied field is measured by a Sawyer-Tower circuit. If the strain is measured in the direction of the field, one obtains the longitudinal electrostrictive coefficient  $Q_{11}$  ( $\eta_2 \parallel P_2$ ):

$$\eta_2 = Q_{11}P_2^2. \tag{14}$$

A plot of  $\eta_2$  as a function of  $P_2^2$  is a straight line with slope  $Q_{11}$ . The schematic diagram of a typical experimental set-up for direct measurement of the electrostrictive coefficients  $Q_{\lambda\mu}$  has been shown in the book [2].

Block diagram of a set-up for indirect measurement of the electrostrictive coefficients has been shown in the paper [3].

According to thermodynamics, in the case of an isotropic material

$$(\partial\beta/\partial p_h)_T = 2Q_{11} + 4Q_{12} = 2Q_h, \tag{15}$$

where  $\beta$  — the impermeability,  $p_h$  — the hydrostatic pressure,  $Q_h$  — is defined as the electrostrictive coefficient under hydrostatic pressure.

As sample is inserted into a high-pressure container where it is subjected to a hydrostatic pressure  $p_h$  ( $0 - 10^3$  MPa). The variation of  $\beta$  is measured as a function of  $p_h$

under isothermal conditions.  $\beta$  is usually calculated from the dielectric permittivity  $\epsilon$  using the following equations:

$$\beta_{mn} = (-1)^{m+n} \Delta_{mn}^\epsilon / \Delta^\epsilon, \quad (16)$$

$$\epsilon_{mn} = (-1)^{m+n} \Delta_{mn}^\beta / \Delta^\beta, \quad (17)$$

where  $\Delta^\epsilon$  (or  $\Delta^\beta$ ) — an algebraic determinat of  $\epsilon_{mn}$  or  $\beta_{mn}$  tensor,  $\Delta_{mn}^\epsilon$  (or  $\Delta_{mn}^\beta$ ) — represents a remanent subdeterminant in which the term  $\epsilon_{mn}$  (or  $\beta_{mn}$ ) is removed.

$Q_h$  is then obtained from the slope of the  $\beta$  versus  $p_h$  curve. In practice, the hydrostatic pressure is raised to a maximum value in the beginning of the experiment and then allowed to drop gradually in steps. At each pressure step  $p_h$ , after the sample temperature becomes stable the sample capacity is measured by an *a.c.* bridge.

The method of indirect measurement has also been applied to a system under a uniaxial pressure. Thus, each independent component of the electrostrictive coefficient may be obtained separately. For example, if a stress  $\sigma_1$  is applied in the direction 1, we obtain

$$2Q_{11} = -(\partial\beta_1/\partial\sigma_1). \quad (18)$$

For studying high-frequency piezoelectric and electrostrictive strains, a double-beam laser interferometr has been designed. This system is capable of resolving a displacement of  $10^{-1}$  nm with the lock-in detection device and measuring strains up to the piezoelectric resonance frequencies using a digital oscilloscope. The interference of the sample bending in signal detection is effectively avoided. The schematic diagram of the double-beam laser interferometer along with the electronic accessories is shown in the paper [4].

### 3. Results of investigations and their interpretation

The following parameters are used for estimation of electric field induced electrostrictive deformations of dielectric and for practical estimation of usefulness of electrostrictive transducer:

1. Coefficients of electrostriction ( $M_{ij}$ ,  $Q_{ij}$ ):

$$M_{ij} = Q_{ij} \epsilon_0^2 (\epsilon_r^\sigma - 1)^2, \quad (19)$$

where

$$M_{ij} = \left( \frac{\partial^2 \eta_i}{\partial E_k \partial E_l} \right)_{\sigma, T}, \quad (20)$$

$$Q_{ij} = \left( \frac{\partial^2 \eta_i}{\partial P_k \partial P_l} \right)_{\sigma, T}, \quad (21)$$

$$\epsilon_r^\sigma = \frac{\epsilon^\sigma}{\epsilon_0}. \quad (22)$$

2. Hydrostatic coefficient of electrostriction:

$$Q_h = Q_{11} + 2Q_{12}. \quad (23)$$

## 3. Temperature coefficient of electrostriction

$$k_e = \frac{\Delta Q_{ij}}{\Delta T Q_{ij}} 100 \quad [\%K^{-1}], \quad (24)$$

where

$$\Delta T = T_2 - T_1, \quad \Delta Q_{ij} = |Q_{ij}(T_2) - Q_{ij}(T_1)|, \quad Q_{ij} = Q_{ij}(T_{1/2}). \quad (25)$$

## 4. Linear expansion coefficient:

$$\lambda = \frac{\Delta x}{x_0 \Delta T} \quad [K^{-1}]. \quad (26)$$

## 5. Curie-Weiss constant (C):

$$\varepsilon = \frac{C}{T - T_0}. \quad (27)$$

The values of  $M_{ij}$ ,  $Q_{ij}$ ,  $Q_h$ ,  $\varepsilon_r^\sigma$  of electrostrictive materials used for production of electromechanical transducers (micromotors, micromanipulators etc.) should be as high as possible while values of  $\lambda$  and  $k_e$  should be as small as possible.

Ceramic compounds and ferroelectric solid solutions ( $BaTiO_3$  (BT),  $PbTiO_3$  (PT),  $Pb(Mg_{1/3}Nb_{2/3})O_3$  (PMN),  $Pb(Zn_{1/3}Nb_{2/3})O_3$  (PZN),  $Pb(Sc_{1/2}Nb_{1/2})O_3$  (PSN), (x)PT-(1-x)PMN,  $(Pb_{1-x}La_x)(Zr_yTi_{1-y})O_3$  (PLZT),  $Sr_{5-x}Ba_xNb_{10}O_{30}$  (SBN)), anti-ferroelectric ( $PbZrO_3$  (PZ),  $Pb(Co_{1/2}W_{1/2})O_3$ , (PCW),  $Pb(Fe_{2/3}U_{1/3})O_3$  (PFU)) and non polar ( $BaZrO_3$  (BZ),  $(K_{3/4}Bi_{1/4})(Zn_{1/6}Nb_{5/6})O_3$  (KBiZnN)), of perovskite type structure (BT, PT, PMN, PZN, PSN, PLZT, PZ, PLW, PFU, BZ, KBiZnN) and of tetragonal bronze type structure (SBN), ordered, partially ordered and disordered of  $(A'A'')(B''B'')O_3$ ,  $A(B''B'')O_3$  and another were the material of investigations.

Samples for investigations have been obtained by classic ceramic technology and by hot pressing method in conditions presented in our previous papers [e.g. 2]. Technological conditions substantially influence on the density of ceramics: from  $\rho = (0.90 \div 0.93)\rho_{rtg}$  (for classic technology) to  $\rho > 0.96\rho_{rtg}$  (for hot pressed ceramics). The increase of density influence on the value of dielectric permittivity at room temperature ( $T_r = 293$  K) well as at  $T_m$  temperature. The degree of the diffusion of the phase transition ( $\delta$ ) in ferroelectric and antiferroelectric solid solutions decreases with increasing density (up to  $\rho = 0.92\rho_{rtg}$ ). For samples with  $\rho > 0.92\rho_{rtg}$  the degree of diffusion does not depends neither on conditions of deposition or on the method of sintering. In temperature range  $T > T_m$  dielectric permittivity changes according to equation

$$1 - \varepsilon = \frac{1}{\varepsilon_m} + \frac{(T - T_m)^2}{2\varepsilon_m \delta}. \quad (28)$$

With increasing dielectric permittivity caused by increasing density of samples increase also the values of electrostriction coefficients  $M_{ij}$ .

**Furthermore during the experimental investigations there were stated the following relations:**

1) The values of electrostriction coefficients ( $Q_{ijkl}$ ,  $Q_h$ ) depend not only on the chemical composition of perovskite type oxides but first of all on the degree of ordering of

cations in solid solutions  $A(B'B'')O_3$  (i.e. increase after transition from disordered state through simple  $(ABO_3)$  to ordered state):

- simple compound (for example  $BaTiO_3$ )  $:Q_h \approx 0.02 \text{ m}^4/\text{C}^2$ ;
- ordered solid solution (for example  $Pb(Co_{1/2}W_{1/2})O_3$ )  $:Q_h \approx 0.027 \text{ m}^4/\text{C}^2$ ;
- partially ordered solid solution (for example  $Pb(Sc_{1/2}Nb_{1/2})O_3$ )  $:Q_h \approx 0.008 \text{ m}^4/\text{C}^2$ ;
- disordered solid solution (for example  $Pb(Mg_{1/3}Nb_{2/3})O_3$ )  $:Q_h \approx 0.006 \text{ m}^4/\text{C}^2$ .

2) With increasing degree of ordering of cations in perovskite type oxides increases  $Q_h$ , while in ferroelectrics and antiferroelectrics decreases Curie-Weiss constant ( $C$ ). The product of Curie-Weiss constant ( $C$ ) and hydrostatic coefficient of electrostriction ( $Q_h$ ) is approximately constant for all ferroelectric and antiferroelectrics perovskite type oxides:

$$Q_h \cdot C = (3.1 \pm 0.6) \cdot 10^3 \text{ m}^4 \text{C}^{-2} \text{K}. \quad (29)$$

This relation allows to estimate the value of  $Q_h$  for ferroelectrics and antiferroelectrics if the value of Curie-Weiss constant ( $C$ ) is known (for example from the dependency  $\varepsilon^{-1}(T)$  in temperatures higher than  $T_c$  (or  $T_m$ ):

- simple compound (for example  $BaTiO_3$ )  $:C = 1.5 \cdot 10^5 \text{ K}$ ,
- ordered solid solution (for example  $Pb(Co_{1/2}W_{1/2})O_3$ )  $:C = 1.2 \cdot 10^5 \text{ K}$ ,
- partially ordered solid solution (for example  $Pb(Sc_{1/2}Nb_{1/2})O_3$ )  $:C = 3.5 \cdot 10^5 \text{ K}$ ,
- disordered solid solution (for example  $Pb(Mg_{1/3}Nb_{2/3})O_3$ )  $:C = 4.7 \cdot 10^5 \text{ K}$ .

3) The value of hydrostatic electrostriction coefficient is approximately proportional to square of linear expansion coefficient:

$$Q_h \sim \lambda^2, \quad (30)$$

$$\lambda = (3.8 \pm 0.4) \cdot 10^{-5} Q_h^{0.5} \text{ [K}^{-1}\text{]}.$$

In perovskite solid solution the value of  $\lambda$  decreases with increasing degree of disorder of cations:

- simple compound  $: \lambda \approx 5.88 \cdot 10^{-6} \text{ K}^{-1}$ ,
- ordered solid solution  $: \lambda \approx 6.72 \cdot 10^{-6} \text{ K}^{-1}$ ,
- partially ordered solid solution  $: \lambda \approx 3.78 \cdot 10^{-6} \text{ K}^{-1}$ ,
- disordered solid solution  $: \lambda \approx 3.36 \cdot 10^{-6} \text{ K}^{-1}$ .

Very small value of  $\lambda$  in wide temperature range is typical for ferroelectric perovskite structure relaxors with low degree of ordering of cations. For such materials low value of hydrostatic electrostriction coefficient ( $Q_h$ ) is also characteristic, independent on temperature. It means that it is not possible to obtain materials with high  $Q_h$  and low  $\lambda$ .

4) The highest stability of hydrostatic electrostriction coefficient ( $Q_h$ ) is characteristic for ferroelectrics with diffused phase transition and ferroelectric relaxors. Estimated from Eq. (24) values  $k_e$  oscillated in the range from  $0.4\% \text{ K}^{-1}$  for three component solid solution PMN-PT-BZN ( $M_{13} \approx 12 \cdot 10^{-16} \text{ m}^2/\text{V}^2$ ), to  $3.5\% \text{ K}^{-1}$  for two component solid solution PMN-PT ( $M_{13} \approx 0.2 \cdot 10^{-16} \text{ m}^2/\text{V}^2$ ). In order to decrease the temperature coefficient of electrostriction ( $k_e$ ) we should take into account that the increase of degree of diffusion of the phase transition leads to decrease of  $\varepsilon_r^0$  and as a consequence to



decrease of the electrostriction coefficient  $M_{ij}$ . It means that it is not possible to obtain electrostrictive ceramics with high  $M_{ij}$  and simultaneously with low temperature coefficient  $k_e$ .

5) The value of the product  $Q_{ij}\varepsilon_0^2(\varepsilon_r^\sigma - 1)^2 = M_{ij}$  used for estimation of the electrostrictive deformation is very high for ferroelectric relaxors i.e. solid solution with disordered structure. Such materials are obviously used as electrostrictive materials because in spite of their low  $Q_{ij}$  value their dielectric permittivity  $\varepsilon_r^\sigma$  in the surrounding of  $T_m$  temperature is very high (where  $T_m$  temperature in which dielectric permittivity reaches their maximal value). For example in pure PMN  $\varepsilon_m = 16470$ ;  $Q_{11} = 0.006 \text{ m}^4/\text{C}^2$ ,  $\varepsilon_0 = 8.854 \cdot 10^{-12} \text{ F/m}$ , and as a result  $M_{11} = 1.31 \cdot 10^{-16} \text{ m}^2/\text{V}^2$ , however for solid solution 0.975 PMN - 0.025 PT:  $\varepsilon_m = 19390$ ,  $Q_{11} = 0.011 \text{ m}^4/\text{C}^2$ , and  $M_{11} = 3.5 \cdot 10^{-16} \text{ m}^2/\text{V}^2$ .

High values of  $M_{ij}$  electrostriction coefficients allows to obtain relative deformation of order  $\eta \approx 10^{-3}$  in low electric fields.

The regularities in  $\varepsilon_r^\sigma$ ,  $Q_{ij}$ ,  $M_{ij}$ ,  $k_e$ ,  $\lambda$  and  $C$  related with different degree of cations ordering may be explained on the base of *ordered and disordered crystal structures model* for complex  $A(\text{B}'_{1/2}\text{B}''_{1/2})\text{O}_3$  oxides. According to this model in ordered structure small B ions surrounded by bigger A and O ions have relatively small free space than in disordered structure. It leads to higher polarization related to the unit of electric field tension, and as a consequence to higher values of dielectric permittivity and Curie-Weiss constant. As a result the deformation related to the unit of polarization is smaller what gives smaller value of electrostriction coefficient  $Q_{ij}$ .

Regularities typical for ferroelectric relaxors presented in this work are in good agreement with results of investigations presented by another authors for example [5].

#### 4. Conclusions

- In relaxor ferroelectrics and ferroelectrics with diffused phase transition (at  $T > T_m$ ) the effect of electrostriction (deformation of the mechanically free sample ( $\sigma_{\text{ext}} = 0$ ) in external electric field ( $\eta \sim E^2$ ) or appearance stresses proportional to the square of electric field ( $\sigma \sim E^2$ ) in mechanically short circuited sample ( $\eta = 0$ )) are very high. The main cause of observed electromechanical effects is arising in investigated samples strong field induced polarization and as a result we can write that  $\eta \sim P_{\text{ind}}^2$  (for  $\sigma_{\text{ext}} = 0$ ) and  $\sigma \sim P_{\text{ind}}^2$  (for  $\eta = 0$ )).

- Strong electrostrictive effect in ferroelectric relaxors and in ferroelectrics with diffused phase transition has wide practical applications.

- The electromechanical transducers based on electrostrictive ceramics can be applied in microengines, microactuators, micromanipulators, etc. One can mention the following unique advantage of electrostrictive ceramics namely:

- 1) high value of dielectric constant ( $\varepsilon \approx 10^4$ );
- 2) small coefficient of linear thermal expansion ( $\lambda$ );
- 3) independence of the deformation sign on direction of the external electric field intensity (simplified control of the deformation by electric field);
- 4) ability of reaching high tensile stresses ( $< 4 \cdot 10^3 \text{ N/cm}^2$ );

- 5) high value of the relative strain ( $\eta \approx 10^{-3}$ );
- 6) low inertia (short turn on- and off-time:  $\sim 10 \mu\text{s}$ );
- 7) small driving power;
- 8) absence of the remanent strain;
- 9) absence of the electromechanical hysteresis.

### Acknowledgement

The authors would like to thank Committee for Scientific Research (KBN), Poland, for financial support under grant No 7 TO 8D 005 17.

### References

- [1] Z. SUROWIAK, R. SKULSKI and J. DUDEK, *The properties of the electromechanical transducers on the basis of electrostrictive ceramics*, [in:] Proc. of The XLIV Open Seminar on Acoustics, OSA'97, Gdańsk - Jastrzębia Góra (Poland), 15-18.09.1997. Ed. PTA Gdańsk. Vol. II, 1997, pp. 621-627.
- [2] Y. XU, *Ferroelectric materials and their applications*, North-Holland, New York 1991, pp. 64-68.
- [3] Z. SUROWIAK, *The electrostrictive properties of the ferroelectric ceramics* [in Polish], Molecular and Quantum Acoustics (Poland), **8**, 267-295 (1997).
- [4] Z. SUROWIAK, J. RANACHOWSKI and A.E. PANICH, *Ceramic electrostrictive materials obtained on the basis of ferroelectrics* [in Polish], [in:] Advanced ceramics, technology and research methods, J. RANACHOWSKI [Ed.], IPPT PAN, Warszawa 1998, pp. 361-391.
- [5] T.G. LUPEIKO *et al.*, *Electrostrictive properties of the  $(1-x)\text{PbMg}_{1/3}\text{Nb}_{2/3}\text{O}_3 - x\text{PbTiO}_3$  ceramic materials* [in Russian], [in:] Piezoactive materials, A.E. PANICH [Ed.], RGU, Rostov-on-Don 1991, pp. 52-64.