

MECHANICAL AND WATER ABSORPTION PROPERTIES OF HYBRID
KENAF AND PINEAPPLE COMPOSITE ADDED WITH EPOXIDIZED
NATURAL RUBBER

NORAZIMAH BINTI HARUN

A dissertation submitted in partial fulfillment of
the requirements for the award of the degree of
Master in Science (Polymer Technology)

Faculty of Chemical and Energy Engineering
Universiti Teknologi Malaysia

JANUARY 2017

Thank you God for blessing me with the presence of loving person around me.

*To my husband... your love and your support along this journey have helped me
faced the challenges that spread ahead,*

To my children... thank you for standing by Umi and be very understanding,

*This dedication also goes to my sisters, brothers, my mother...
... and my late father who always live in my memory... you brought me up and made
me the person I am today.*

ACKNOWLEDGEMENT

I am so fortunate to be able to be awarded with a scholarship that enabled me to pursue my dream in achieving a master degree. The precious experience and knowledge gained during completing my study had boost my competency and confident level in the field of my chemistry study. I am also excited to share such feeling and experienced I obtained with my students back at the college.

A high gratitude for my supervisor, Professor Madya Dr. Wan Aizan binti Wan Abdul Rahman for your kindness and brilliant idea in facilitating the progress of my experiment. My deep thankful also goes to the program coordinator of Polymer Technology who had ease the administration process during my study and had inspired me to stay focus on my research. Also not forgotten to all laboratory staff, where without them I could never be able to complete my laboratory task. Your professionalism and dedication, in lending me your helping hand are very much appreciated especially to Mr. Nordin of Biopolymer Research laboratory.

My heartfelt gratitude goes to all lecturers, staffs, friends who had assist me during the study. I'm very grateful to God for everything that happened in my life. Pursuing this study was more than just a strive to get a master degree but also a process of educating my soft skills and given me a wider perspective in seeing life. For my husband, children and my family, your support and your understanding had kept me strong during this journey.

ABSTRACT

Wood polymer composites, WPC, is a competitive material which ranging from consumer products to engineering parts in various of application field. In this research, mechanical properties and water absorption were investigated on the hybrid WPC made from kenaf fibre and pineapple leaf fibres, PALF, as fillers at three level of total fibre loading of 30 %, 40 % and 50 % by weight, mixed in high density polyethylene, HDPE. The fibres hybrid ratio was kept constant at 60% kenaf to 40% PALF and the composite was compounded in a melt mixer and fabricated by compression moulding. The effect of different total fibres loading and addition 3% by weight epoxidized natural rubber, ENR, into the composite formulation was evaluated. For both with and without addition of ENR into kenaf-PALF/HDPE composite, tensile strength, tensile modulus, flexural modulus, impact strength and water absorption increased with an increase in total fibres loading, but the elongation at break of the composite decreased with increasing total fibres loading. Flexural strength only increased at lower fibre loading but decreased at highest fibre loading of this experiment. Meanwhile, overall effect of ENR addition was that it enhanced the tensile strength, impact strength and water absorption of the composite but only improved flexural strength and flexural modulus at lower fibre loadings of 30 and 40 %. On the other hand, ENR decreased the tensile modulus and elongation at break of the composites. At highest fibres loading from this study and with 3 % ENR-50 added, the composite, KP50PE2 is deformable and experienced a slight decreased in tensile strength. However, its enhanced impact property and higher toughness enabled the composite to withstand impact loading.

ABSTRAK

Komposit Polimer Kayu, WPC, adalah bahan yang kompetitif yang digunakan di dalam produk pengguna sehinggalah ke barangan kejuruteraan di dalam pelbagai lapangan aplikasi. Di dalam kajian ini, sifat-sifat mekanikal dan penyerapan air adalah dikaji ke atas hibrid WPC yang dibina dari hibrid di antara gentian kenaf dan gentian daun nanas, PALF yang berperanan sebagai pengisi pada tiga paras jumlah pengisian gentian iaitu 30 %, 40 % and 50 % mengikut berat, yang dicampur dengan polietilena berketumpatan tinggi, HDPE. Nisbah hibrid gentian adalah ditetapkan pada 60% kenaf kepada 40% PALF dan komposit dibancuh di dalam pencampur dan difabrikasi menggunakan pengacuan mampatan. Kesan jumlah pengisian gentian yang berbeza dan penambahann 3% mengikut berat getah asli terepoksidakan, ENR, ke dalam formulasi komposit dinilai. Bagi kedua-dua formulasi dengan dan tanpa penambahan ENR ke dalam komposit kenaf-PALF/HDPE, kekuatan regangan, modulus regangan, modulus lenturan, kekuatan hentaman dan penyerapan air bertambah dengan penambahan di dalam jumlah pengisian gentian, tetapi peratus pemanjangan komposit ketika putus berkurang dengan penambahan di dalam jumlah pengisian gentian. Kekuatan lenturan hanya bertambah pada jumlah pengisian gentian yang rendah tetapi berkurang pada pengisian gentian yang tinggi. Manakala kesan keseluruhan apabila ENR ditambahkan, adalah ia telah meningkatkan kekuatan regangan, kekuatan hentaman dan penyerapan air oleh komposit tetapi hanya memperbaiki kekuatan lenturan dan modulus lenturan pada pengisian gentian yang rendah iaitu pada 30 and 40 % pengisian gentian. Sebaliknya, ENR mengurangkan modulus regangan komposit dan mengurangkan peratus pemanjangan komposit ketika putus. Pada pengisian gentian tertinggi dari kajian ini dan dengan penambahan 3 % ENR-50, komposit dengan formula KP50PE2 menunjukkan ciri mudah berubah dan hanya melalui perubahan yang sedikit sahaja dalam kekuatan regangan. Walau bagaimanapun peningkatan dalam ciri hentamannya dan pertambahan ketahanan membolehkan komposit tersebut menghadapi kekuatan hentaman.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	x
	LIST OF FIGURES	xi
	LIST OF ABBREVIATIONS	xiv
	LIST OF SYMBOLS	xvi
	LIST OF APPENDICES	xviii
1	INTRODUCTION	1
	1.1 Road safety barriers	1
	1.2 Wood polymer composite	2
	1.3 Hybrid wood polymer composite	3
	1.4 Problem statement	4
	1.5 Objective of the study	6
	1.6 Scope of the study	7
	1.7 Significance of study	8
2	LITERATURE REVIEW	9
	2.1 Material's substitution for guardrails	10
	2.2 Wood polymer composite as material for outdoor application	11
	2.3 Wood polymer composite	11
	2.4 Natural fibre	13
	2.4.1 Natural fibres sources	13
	2.4.2 Natural fibres as reinforcement and fillers	13

2.4.3	Disadvantages of lignocellulosic fibres and its improvisation	15
2.4.4	Kenaf fibre	16
2.4.5	Pineapple leaf fibre (PALF)	20
2.5	Hybrid wood polymer composite	23
2.6	Synergistic effect of kenaf fibres and pineapple leaf fibres	24
2.6.1	Tensile properties	25
2.6.2	Flexural properties	26
2.6.3	Impact properties	26
2.6.4	Water absorption property	27
2.7	High density of polyethylene, HDPE as polymer matrix in composite	28
2.8	Epoxidized natural rubber, ENR	29
2.8.1	Application of ENR	32
2.8.2	ENR as toughening agent of composite	33
2.8.3	ENR as interfacial modifier	35
2.8.4	ENR and autonomic self-healing property	37
2.9	Alkalization Pre-treatment of fibres	38
3	METHODOLOGY	41
3.1	Materials and reagents	41
3.1.1	Kenaf (<i>Hibiscus cannabinus</i>)	42
3.1.2	Pineapple leaf (<i>Ananas Comosus</i>) fibre	42
3.1.3	High density polyethylene (HDPE)	43
3.1.4	Epoxidized natural rubber of 50 % mol epoxidation (ENR-50)	43
3.2	Experimental procedure	44
3.2.1	Alkalization pre-treatment of fibres	44
3.2.2	PALF extraction and fillers preparation	46
3.2.3	Sample preparation	49
3.2.4	Formulation of WPC	51
3.3	Mechanical Testing	52
3.3.1	Tensile test	52
3.3.2	Flexural test	53
3.3.3	Impact test	54
3.4	Water Absorption Test	55

4	RESULT AND DISCUSSION	58
4.1	Mechanical properties of hybrid WPC of kenaf-PALF in HDPE matrix	61
4.1.1	Tensile properties	62
4.1.1.1	Tensile strength	63
4.1.1.2	Tensile modulus	67
4.1.1.3	Elongation at break	69
4.1.2	Flexural Property	70
4.1.2.1	Flexural strength	71
4.1.2.2	Flexural modulus	78
4.1.3	Impact strength	80
4.2	Water absorption property	86
4.3	WPC for guardrail	92
5	CONCLUSION	94
	REFERENCES	96
	Appendices A-B	105-108

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Tensile properties of kenaf fibre	18
2.2	Comparison of mechanical properties of PP and kenaf reinforced PP composite with other synthetic fibres reinforced PP	18
2.3	Tensile strength and Young's Modulus of PALF, carbon and E-glass	22
2.4	Mechanical properties of HDPE	28
3.1	The WPC formulation table	52
4.1	Tensile properties of kenaf-PALF/HDPE composite with and without addition of ENR-50	62
4.2	Flexural properties of kenaf-PALF/HDPE composite	71
4.3	Impact properties of kenaf-PALF/HDPE composite	80
4.4	Percentage of water absorption for every 24 hours immersion	87

LIST OF FIGURES

FIGURE NO.	TITTLE	PAGE
2.1	Schematic representation of structure and material of roadside safety material	10
2.2	Structure of fibres showing the helical arrangement of cellulose and its microfibrils angle	21
2.3	Structure of ENR	30
2.4	Schematic reaction of the production of ENR via an in situ proxy formic acid route	30
2.5	The ring opening reaction between epoxy ring in ENR and Si-OH on silica surface in NR/Si composite	35
2.6	SEM analysis of NR/Si composite without ENR-25 and with different content of ENR-25	36
2.7	Optical image of ENR-50 with no presence of holes at the impact zone and optical image of ENR-25	38
2.8	A schematic representation of untreated and treated fibres	39
3.1	Kenaf fibre	42
3.2	PALF	42

3.3	ENR-50	44
3.4	Illustration of NaOH preparation and an immersion process of kenaf fibre in the colourless NaOH solution.	45
3.5	Alkalization pretreatment of PALF by immersing the fibres in 5 % NaOH	46
3.6	Machine used in decortication process of PALF	47
3.7	PALF preparation	47
3.8	Grinding process	48
3.9	The kenaf filler and the PALF filler	48
3.10	Mixture of raw materials and the compounded WPC	49
3.11	Tensile specimens	53
3.12	Flexural specimens	54
3.13	Notching process of the impact test specimens and the notched specimen test bar.	55
4.1	Difference in physical appearance between treated and untreated fibres.	57
4.2	Infra-red spectra of the untreated and treated kenaf fibres and PALF	58
4.3	SEM of treated and untreated kenaf fibres	59

4.4	SEM of treated and untreated PALF	60
4.5	Aggregation of fibres during the fabrication process and within on the surface of a tensile sheet specimen.	64
4.6	A wetting mechanism by compatibilizer creating a chemical link of interfacial bonding between hydrophilic fibre and hydrophobic polymer	66
4.7	Schematic of an ester linkage formation with anhydride group attached to hydroxyl group of the cellulose	75
4.8	A reaction scheme of alkali catalyzed reaction on hydroxyl group of fibres during pre-treatment	75
4.9	A ring opening reaction of the epoxy group in ENR with treated cellulose	76
4.10	A schematic diagram showing of impact property in a composite with ENR	84
4.11	Graph of water absorption of kenaf-PALF in HDPE	91

LIST OF ABBREVIATIONS

ASN	-	Atlas Automatic Sample Notcher
ASTM	-	American Society for Testing and Materials
BS	-	British standard
CaCO ₃	-	Calcium carbonate
DCP	-	Dicumyl peroxide
E-GMA	-	Ethylene-glycidil methacrylate
EN	-	European standard
ENR	-	Epoxidized natural rubber
ENR-25	-	Epoxidized natural rubber at 25 % mol of epoxidation level
ENR-50	-	Epoxidized natural rubber at 50 % mol of epoxidation level
FTIR	-	Fourier-transform infrared spectroscopy
HDPE	-	High density of polyethylene
LENR	-	Liquid epoxidized natural rubber
LNR	-	Liquid natural rubber
MAPE	-	Maleated polyethylene
MAPP	-	Maleic anhydride-grafted polypropylene
NaOH	-	Sodium hydroxide
NBR	-	Nitrile rubber
NR	-	Natural rubber
NFM	-	Non-fibrous material
OH	-	Hydroxyl group
PALF	-	Pineapple leaf fibre
PA6	-	Nylon 6
PBAT	-	Poly(butylene adipate-co-terephthalate)

PE	-	Polyethylene
PE-g-MA	-	Maleated polyethylene
PET	-	Polyethylene terephthalate
PHBV	-	Poly(3-hydroxybutyrate-co-3-hydroxyvalerate)
PLA	-	Poly(lactic acid)
PP	-	Polypropylene
PVC	-	Poly(vinyl chloride)
RNP	-	Recycled newspaper
SEM	-	Scanning electron microscopy
Si	-	Silica
TPU	-	Thermoplastic polyurethane
UHMWPE	-	Ultra high molecular weight of polyethylene
UPR	-	Unsaturated polyester resin
WGL	-	Whole ground pineapple leaf
WPC	-	Wood polymer composite

LIST OF SYMBOLS

ρ_c	-	Density of composite
ρ_{HDPE}	-	Density of HDPE
ρ_{kenaf}	-	Density of kenaf
ρ_{PALF}	-	Density of PALF
g/10 min	-	grams in 10 minutes
g/cm ³ (gcm ⁻³)	-	grams per centimeter cubic
kJ/m ²	-	Kilojoule per meter square
kN	-	KiloNewton
MPa	-	Megapascal
m_c	-	Mass of composite
m_{HDPE}	-	Mass of HDPE
m_{kenaf}	-	Mass of kenaf
m_{PALF}	-	Mass of PALF
mm ³	-	Milimeter cubic
mm/min	-	Milimeter per minute
Nm	-	Newton meter
T_g	-	Glass transition temperature
V_c	-	Volume of composite
V_{HDPE}	-	Volume of HDPE
V_{kenaf}	-	Volume of kenaf
V_{PALF}	-	Volume of PALF
w_1	-	Initial weight at day 1
w_2	-	Final weight after 24 hours immersion

W_{uptake}	-	Weight gained by the composite
w/v	-	Weight per volume

LIST OF APPENDICES

APPENDIX	TITLE	PAGE
A	Accidental death caused by guardrail reported in local newspaper (Mokhtar, 2015)	107
B	The WPC's density and weight determination	105-108

CHAPTER 1

INTRODUCTION

1.1 Road safety barriers

Guardrails are road barriers of a safety devices fixed at the roadside or at highway (Xiao and Shang, 2011; Tabatebaei et al., 2012), that is meant to ensure the safety on the public roads (Borovinsek, 2013).

“Guardrail is longitudinally placed elements which are connected by bolts to guardrail connector where guardrail connector is an element for the connection of the neighbouring guardrails using bolt connection. Guardrail are deformable and reduce the severity of an impact but should be strong enough not to rupture during vehicle impact” (Borovinsek, 2013).

Among the material that are suitable for use in road safety application are plastics, fibreglass, rubber, wood fibres and they were used either alone or in various combination (Bligh et. al., 1995). In this study, wood polymer composite, WPC synthesised by using hybridised fibre based on pineapple leaf fibre (PALF) and kenaf

fibre in high density of polyethylene (HDPE) matrix was suggested as an alternative material for guardrail and the material is expected to be able to experience deformation easily but sufficiently tough to withstand an impact.

1.2 Wood polymer composite

Wood polymer composite (WPC) is gaining much attention from the industry and becomes a dynamic sector in plastic industry (Amir and Ashori, 2010). The trend in WPC's product is developing product range that is having an enhancement in terms of its mechanical properties and durability. *“Major growth in the technology is coming from equipment design, process formulation and durability”* (Niska and Sain, 2008).

WPC has two main constituents, polymer and wood (Amir and Ashori, 2010). Wood are usually in the form of chips, flour or special wood fibres; whereas the plastics usually consumed are polyethylene (PE), polypropylene (PP), polyvinyl chloride (PVC), polystyrene as a matrix in a virgin or recycled form (Carus and Gahle, 2008; Cai et al., 2012). *“WPC are thermoplastically processible composite that consist of varying contents of woods, plastics and additives, and are processed by thermoplastic shape-forming techniques such as extrusion, injection moulding, rotomoulding or pressing”* (Carus and Gahle, 2008).

The natural fibre from wood as composite material in WPC have advantages in terms of its specific properties such as high specific strength and modulus, low density property, non-abrasiveness or low friction during processing (Amir and

Ashori, 2010; Kim and Pal, 2010), and in addition, they are also a low-cost material for replacing synthetic fibres, non-toxic, renewable and are environmental friendly (Amir and Ashori, 2010; Perez-Fonseca, 2014; Gouda, 2014). Natural fibres are used in many fields, for example, a natural fibre reinforced composite for automotive application such as door panels, seat backs, armrests, consoles and other part shifting form using steel and aluminium material (Zampaloni, 2007; Akil, 2015), sisal fibre reinforcement epoxy resin composite for orthopaedic implants (Gouda, 2014),

1.3 Hybrid wood polymer composite

When two or more different types of reinforcement applied in a matrix, hybrid composites is produced. Hybrid composites composed with two different fibres nowadays is harbouring interest scientifically and industrially (Beauson, 2013). Hybrid composites are developed for synergism effect that are able to display by the chosen fillers and matrix (Ashori and Sheshmani, 2010). Each fibres used must have different mechanical properties and different interaction with matrix, thereby some advantages of properties can be gained from both fibres utilized (Perez-Fonseca et al., 2014; Beauson et al., 2013; McDonough et al., 2004). Therefore, with appropriate combination of two natural fibres will result in properties improvement of composite material and at the same time maintain the environment natural appeal (Perez-Fonseca et al., 2014; Beauson et al., 2013).

1.4 Problem statement

Safety barriers or guardrails is a method for roadside immunization where the deviated vehicles will be redirect onto right path, preventing overturning that might cause collision with dangerous obstacle along the road sides, hence, reduce fatality and injury. However, there were also studies that showed that most death accidents involving collision with safety barriers especially guardrails are due to technical and structural faults, improper instalment place and improper design (Tabatebaei et al., 2012). Such casualty and fatal could be avoided if some investment and effort is made in providing new design in terms of material used in constructing a safer guardrail. Diagrams showing a fatal accident between vehicles and guardrail where guardrail had penetrated into the vehicles and cause injuries to the passenger are shown in Appendix A.

According to the British standard BS EN 1317-2:1998 and also a study reported by Atahan et al., 2014 on road restraint system, safety barrier should behave as the following:

“The safety barrier shall contain and redirect the vehicle without complete breakage of the principal longitudinal elements of the system.

No major part of the safety barrier shall become totally detached or present an undue hazard to other traffic, pedestrians or personnel in a work zone.

Elements of the safety barrier shall not penetrate the passenger compartment of the vehicle.

Deformations of, or intrusion into the passenger compartment that can cause serious injuries are not permitted.

Ground anchorages and fixings shall perform according to the design of the safety barrier system”.

Interaction between drivers, vehicles, road and environment determines the highway design safety, and the comfort operating of the highway, where ensuring these safety and comfort for the user has become a growing concern (Wei, 2012). In 1995, Bligh et. al. had reported that products design to serve as direct substitute to currently used wood and steel in guardrails are lacking. Nowadays, some study had been conducted in finding new material of roadside barrier system which in present is using conventional metal, concrete or based on steel w-beam guardrail in order to withstand without failure the load coming from the impact of the crashing vehicles (Xiao and Shang, 2011; Viderkers et al., 2013; Borovinsek, 2013).

If car manufacturers are nailing interest in part components made from natural fibres composite (El Messiry, 2013), the road safety devices could also take the same action in contributing to safer and healthier environment by considering an alternative material for guardrail. Concrete barrier of road safety devices for instance, leaves more damages for being very rigid (Tabatebaei et al., 2012).

Wood polymer composite made from hybridized fibres of kenaf-pineapple leaf fibres in high density polyethylene, were considered in this study for alternative material of guardrail or road barrier system. The kenaf fibre has the ability to toughen and improve impact property of the guardrail due to its high aspect ratio (Aji et al., 2012; Akil et al., 2015) that gives an advantage in spreading the matrix throughout the composite, therefore yields in a better stress transfer from the matrix to fibre (Aji et al., 2012). On the other hand, high tensile strength of PALF will increase flexibility where it is achieved because PALF's cellulose has lower microfibrillar angle with ribbon like orientation that provides spring-like extension in tension and compression (Aji et al., 2012). In addition, kenaf fibre reduced water

absorbance in the hybrid composite since it has lower cellulose content (Aji et al., 2012; Akil et al., 2015).

Appropriate blending and correct intermingling of bast (stem) of kenaf and leaf fibre of PALF are expected to give an optimum performance that has stiffness-toughness balance meant for composite to be used for structural application. Aji et al, (2012) reported that at equal ratio of kenaf and PALF, hybridisation effect had optimized tensile and flexural properties of the composite with HDPE matrix. At 60 % kenaf loading, impact strength was optimised. The hybridized fibres are able to give synergistic relationship in the composite without their properties being deteriorated when combined with the matrix, and at certain hybrid formulation between kenaf and PALF, interfacial bonding of fibres to the matrix was improved, thus yielded a hybrid composite with effective mechanical properties.

In this study, the composite is using thermoplastic resin of HDPE which allows the potential of being remoulding and recycle. Epoxidized natural rubber at 50 % epoxidation level, ENR-50 was added to the composite formulation to act as additional absorbent of energy and prolong the elastic deformation, thus is expected to contribute in improving shock-absorbent capacity. The fabricated composites were then be investigated for its deformable property and toughening effect.

1.5 Objective of the study

1. To investigate the mechanical properties and water absorption of kenaf/PALF fibres filled HDPE composite at different fibres loading.

2. To evaluate the mechanical properties and water absorption of the composite after mixing with 3 % ENR-50.

1.6 Scope of the study

The kenaf fibres and PALF were randomly oriented, mixed, and used as fillers in high density polyethylene. Toughening agent of epoxidized natural rubber at 50 % mol of epoxidation level (ENR-50) was incorporated in the composite. The hybridized formula of kenaf and PALF as fillers, was kept constant at ratio 60 % kenaf: 40 % PALF and the WPC was formulated at specific fibre loading. HDPE is the matrix in this preparation of WPC.

The main parameters investigated was how different percentage weight of filler content in mixing ratio of fibrous composite formulation; and the effect of addition 3 % by weight ENR-50 in the composite formula will affect the properties of the hybrid WPC produced. The mechanical properties studied are tensile, flexural and impact properties. Composite's water uptake behaviour after 24 hours immersion in water for 11 days were also investigated. ENR ability in enhancing WPC's mechanical properties and its ability to resist water uptake were evaluated.

1.7 Significance of study

The development of incorporating lignocellulosic material in thermoplastic matrix are favourable (Talavera et al., 2007) and are giving a great impact on environmental and social issues (Monteiro, 2011). The material has high strength to weight ratio property, low deformation character, highly energy-absorbent and is cost saving (Xiao and Shang, 2011; El Messiry, 2013). The composite with lignocellulosic material in its formula is renewable, thus supporting an effort of recycling an agriculture waste (El Messiry, 2013; Talavera et al., 2007). In addition, the ability of the recyclability of plastic lead to positive eco-environmental impact (Talavera et al., 2007).

Mechanical properties of fibre reinforced composite materials can be tailored to serve the application outlined for the end products by changing the orientation or placement of the fibre. (Zampaloni, 2007). Therefore, kenaf-PALF in HDPE WPC is offering new materials for guardrails, where HDPE consumption is offering a cost reduction compared to the use of ultra high molecular weight polyethylene, UHMWPE, suggested by Xiao J. and Shang X. (2011) for guardrail material's substitution. The materials designed for road safety devices should be able to move or deviate at "working width" during the impact. In this study, ENR-50 was added into the composite for toughening reason. The capacity to be able to absorb impact energy through deformation of the guardrails will reduce the severity of the crash of collision (Tabatebaei et al., 2012). Hence, by adding ENR, the complete interlayer interfacial of ENR towards the fibres is expected to improve fracture toughness of the composites (Tanjung et al., 2015).

REFERENCES

- Abbot A. P. et al. (2012). *Starch as Replacement for Urea-formaldehyde in Medium Density fibreboard*. Green Chemistry. 14. 3067-3070. The Royal Society of Chemistry.
- Adhikary K. B., Pang S. and Staiger M. P. (2008). *Dimension Stability and Mechanical Behaviour of Wood-plastic Composites Based on Recycled and Virgin High-density Polyethylene (HDPE)*. Composite Part B: engineering. 39. 807-815. Elsevier.
- Aji I. S. et al. (2013). Mechanical Properties and Water Absorption Behavior of Hybridized Kenaf/Pineapple Leaf Fibre-reinforced High-density Polyethylene Composite. *Journal of Composite Materials*. 47(8). 979–990. Sage.
- Akil H., Zamri H. and Osman M. R. (2015). *The Use of Kenaf Fibres as Reinforcements in Composites*. Biofibre Reinforcement in Composite Material. 138-161. Woodhead Publishing.
- Amir N. and Ashori A. (2010). *Wood Plastic Composite from Agro-waste Material: Analysis of Mechanical Properties*. Bioresource Technology. 101. 2525-2528. Elsevier.
- Araujo M. A. M. et al. (2014). *Curaua Leaf Fiber (Ananas comosus var. erectifolius) Reinforcing Poly(lactic acid) Bio composites: Formulation and Performances*. Society of Plastic Engineers. 1520-1530. Wiley Online Library.
- Ashori A. (2008). *Wood-plastic composites as promising green-composites for automotive industries!*. Bioresource technology. 99. 4661-4667. Elsevier.

- Ashori A. and Sheshmani S. (2010). *Hybrid Composites Made from Recycled Materials: Moisture Absorption and Thickness Swelling Behaviour*. Bioresource technology. 101. 4717-4720. Elsevier.
- Atahan A. O. et al. (2014). *Crash Testing and Evaluation of a New Generation L1 Containment Level Guardrail*. Engineering Failure Analysis. 38. 25-37. Elsevier.
- Ayrilmis N. and Jarusombuti S. (2011). Flat-pressed Wood Plastic Composite as an Alternative to Conventional Wood-based Panels. *Journal of composite materials*.45. 103-112. Sage.
- Aziz N. Z. A. et al. (2015). Effect of Kenaf and Rice Husk on Water Absorption and Flexural Properties of Kenaf/CaCO₃/HDPE and Rice Husk/CaCO₃/HDPE Hybrid Composite. *International journal of environmental, chemical, ecological, geological and geophysical engineering*. 9(4). 354-358. World academy of science, engineering and technology (waset).
- Beauson J., Markussen C. M. and Madsen B. (2013). Analysis of Composition and Microstructural Uniformity of Hybrid Glass/Carbon Fibre Composites. Madsen B., Liholt H., Kusano Y., Faester S. and Ralph B. *Proceedings of the 34th Risø International Symposium on Material Science: Processing of Fibre Composites - Challenges for Maximum Materials Performance*. 177-191. Department of Wind Energy, Risø Campus, Technical University of Denmark.
- Bligh R. P. et. al. (1995). Application of Recycled Materials in Roadside Safety Devices. *Research report 1458-1. Grant No. 0-1458*. Texas Transportation Institute, The Texas A&M University System College Station, Texas.
- Borovinsek M., Vesenjsek M. and Ren Z. (2013). *Improving the Crashworthiness of Reinforced Wooden Road Safety Barrier Using Simulations of Pre-Stressed Bolt Connections With Failure*. Engineering Failure Analysis. 35. 625-635. Elsevier.
- British Standard Institution. (2009). *BS EN 1317-2:1998*. London: British Standard Institution.

- Brown W. H., Foote C. S. and Iverson B. L. (2005). *Organic chemistry*. (4th ed.) Belmont, USA. Thomson Brooks/Cole.
- Bruice P. Y. (2001). *Organic chemistry*. (3rd ed.) New Jersey. Prentice-Hall Inc. Pearson education.
- Cai Z. et al. (2012). Integrated technology for biobased composite. Christopher L. *Integrated forest biorefineries: Challenges and opportunities*. Page 276-289. The royal society of chemistry.
- Cao X. V. et al. (2014). Effect of Filler Surface Treatment on The Properties of Recycled High-Density Polyethylene/(Natural Rubber)/(Kenaf Powder) Biocomposite. *Journal of Vinyl & Additive Technology*. 20. 218-224. Society of Plastic Engineers. Wiley Online Library.
- Carus M. and Gahle C. (2008). Market and future trends for wood-polymer composites in Europe: the example of Germany. Niska K. O. and Sain M. *Wood-Polymer Composite- A Volume in Woodhead Publishing Series in Composites Science and Engineering*. 300–330. Woodhead Publishing Limited. ScienceDirect.
- Chapman A. V. (2007). Natural rubber and NR-based polymers: renewable materials with unique properties. *24th International H.F. Mark-Symposium, 'Advances in the Field of Elastomers & Thermoplastic Elastomers'*. 15-16 November 2007. Vienna.
- Chen R. S. et al. (2015a). Mechanical, water absorption and morphology of recycled polymer blend rice husk flour biocomposite. *Journal of applied polymer science*. 41494. Wiley Periodical Inc.
- Chen R. S. et al. (2015b). Rice husk flour biocomposites based on recycled high-density polyethylene/polyethylene terephthalate blend: effect of high filler loading on physical, mechanical, and thermal properties. *Journal of Composite Materials*. 49(10). 1241-1253. Sage.
- Clemons C. (2008). Raw materials for wood-polymer composites. Niska K. O. and Sain M. *Wood-Polymer Composite- A Volume in Woodhead Publishing Series in Composites Science and Engineering*. 1–22. Woodhead Publishing Limited. ScienceDirect.

- Costa Junior A. E. et al. (2015). Thermal and Mechanical Properties of Biocomposite Based on a Cashew Nut Shell Liquid Matrix Reinforced With Bamboo Fibres. *Journal of Composite Materials*. 49(18). 2203-2015. Sage.
- El Messiry M. (2013). Theoretical Analysis of Natural Fiber Volume fraction of Reinforced Composites. *Alexandria Engineering Journal*. 52. 310-306. Elsevier.
- Furtado S. C. R. et al. (2012). Natural fibre composite: Automotive application. John M. J. and Sabu T. *Natural Polymers : Volume 1 : Composites*. 118-139. The Royal Society of Chemistry
- Gouda A. T. et al. (2014). Characterization and Investigation of Mechanical Properties of Hybrid Natural Fibre Polymer Composite Materials Used as Orthopaedic Implants for Femur Bone Prosthesis. *Journal of Mechanical and Civil Engineering*. 11. 40-52. IOSR Journal.
- Hamel S. C. et al. (2015). Mechanical and time-dependant behaviour of wood-plastic composites subjected to bending. *Journal of Thermoplastic Composite Materials*. 28(5). 630-642. Sage.
- Jiang C. et al. (2015). In Situ Dispersion and Compatibilization of Lignin/Epoxidized Natural Rubber composites: Reactivity, Morphology and Property. *Journal of Applied Polymer Science*. 132. 42044. Wiley Periodicals Inc.
- Kargarzadeh H. et al. (2015). *Functionalized Liquid Natural Rubber and Liquid Epoxidized Natural Rubber: A Promising Green Toughening Agent for Polyester*. 132. 41292. Wiley Periodicals Inc.
- Kengkhetkit N. and Amornsakchai T. (2014). *A New Approach to "Greening" Plastic Composites Using Pineapple Leaf Waste for Performance and Cost Effectiveness*. *Material and design*. 55. 292-299. Elsevier.
- Kim J. K. and Pal K. (2010). Surface modification in WPC with pre-treatment methods. Kim J. K. and Pal K. *Recent Advances in the Processing of Wood-plastic Composites*. *Engineering materials*. 32. 23-57. Springer-Verlag Berlin Heidelberg.

- Lake G. J. and Thomas A. G. (1967). The strength of highly elastic materials. *Proceeding of the Royal Society of London. Series A, Mathematical and Physical Sciences*. August 22, 1967. 300. 108-119. Royal Society.
- Lei Y. and Wu Q. (2010). *Wood Plastic Composites Based on Moco-fibrillar Blends of High Density of Polyethylene/Poly(ethylene terephtalate)*. Bioresource technology. 101. 3665-3671. Elsevier.
- Mahmood W. A. K. and Azarian M. H. (2015). *Thermal, Surface, Nanomechanical and Electrical Properties of Epoxidized Natural Rubber (ENR-50)/ Polyaniline Composite Films*. Current Applied Physics. 15. 599-607. Elsevier.
- McDonough W. G. et al. (2004). A Test to Determine the Fiber and Voids Content of Carbon/Glass Hybrid Composites. *Journal of ASTM International*. 1(3). 1-15. ASTM International.
- Mison M. I. et al. (2014). *Potentially of Utilising Natural Textile Materials for Engineering Composite Applications*. Materials and Design. Volume 59. 359-368. Elsevier.
- Mokhtar N. A. (2015, 15 June). Dua Maut Kereta Terbabas. *Berita Harian*. 24.
- Monteiro S. N. et al. (2011). *Natural Lignocellulosic Fibers as Engineering Materials-A Overview*. Metallurgical and Materials Transactions A. ISSN: 1073-5623 (Print) 1543-1940 (Online). Volume 42A. 2963-2974. Springer US.
- Neagu R. C. (2008). Micromechanical modelling of wood-polymer composites. Niska K. O. and Sain M. *Wood-Polymer Composite- A Volume in Woodhead Publishing Series in Composites Science and Engineering*. 118–141. Woodhead Publishing Limited. ScienceDirect.
- Neto A. R. S et al. (2013). *Characterization and Comparative Evaluation of Thermal, Structural, Chemical, Mechanical and Properties of Six Pineapple Leaf Fibre Varieties for Use in Composites*. Industrial crops and products. Volume 43. 529-537. Elsevier.
- Niska K. O. and Sain M. (2008). *Wood-Polymer Composite- A Volume in Woodhead Publishing Series in Composites Science and Engineering*. Woodhead Publishing Limited. ScienceDirect.

- Niska K. O and Sanadi A. R. (2008). Interaction Between Wood and Synthetic Polymers. Niska K. O. and Sain M. *Wood-Polymer Composite-A Volume in Woodhead Publishing Series in Composites Science and Engineering*. 41-71. Woodhead Publishing Limited. ScienceDirect.
- Ochi S. (2008). *Mechanical Properties of Kenaf Fibers and Kenaf/PLA composites*. Mechanics of Materials. 40. 446-452. Elsevier.
- Osman H. et al. (2010). Effects of maleic anhydride polypropylene on tensile, water absorption, and morphological properties of recycled newspaper filled polypropylene/ natural rubber composite. *Journal of Composite Material*. 44. 1477-1491. Sage.
- Perez-Fonseca A. A. et al. (2014). *Effect of hybridization on The Physical and Mechanical Properties of High Density Polyethylene-(Pine/Agave) Composites*. Material and Design. 64. 35-43. Elsevier.
- Perhac D. G. et al. (2007). Exploring reliability of wood-plastic composites: Stiffness and Flexural Strength. *International Journal of Reliability and Applications*. 8. 153-173. Korean Reliability Society.
- Pickering K. L., Efendy M. G. A. and Le T. M. (2016). *A Review of Recent Developments in Natural Fibre Composites and Their Mechanical Performance*. Composite: Part A. 83. 98-112. Elsevier.
- Rahman M. A. et al. (2011). *Self-Repairing Systems Based on Epoxidized Natural Rubber Blends*. Applied material and interfaces. 3. 4865-4874. American Chemical Society.
- Rahman M. A. et al. (2013). *Autonomic Self-healing in Epoxidized Natural Rubber*. Applied material and interfaces. 5. 1494-1502. American Chemical Society.
- Ramadevi et al. (2012). *Effect of Alkali Treatment on Water Absorption of Single Cellulosic Abaca Fibre*. Bioresources 7(3). 3515-3524. Peer-reviewed article.
- Sain M. and Pervaiz M. (2008). Mechanical properties of wood-polymer composites. Niska K. O. and Sain M. *Wood-Polymer Composite- A Volume in Woodhead Publishing Series in Composites Science and Engineering*. 101–117. Woodhead Publishing Limited. ScienceDirect.

- Salit M. S. (2014). *Tropical Natural Fibre Composites*. Engineering Materials. Singapore: Springer Science+Business Media.
- Smith J. G. (2006). *Organic Chemistry*. Unites States. McGraw-Hill.
- Siregar J. P. et al. (2010). The Effect of Alkali Treatment on The Mechanical Properties of Short Pineapple Leaf Fibre (PALF) Reinforced High Impact Polystyrene (HIPS) Composite. *Journal of Food Agriculture & Environment*. 8. Issue 2. 1103-1108. WFL PUBL
- Tabatabaei S. A., Rahman A. and Khourani H. (2012). Assessment of Road Safety Barriers and Their Effects on The Fatal Injuries Reduction in Iran. *Advanced Material Research*. 472-475. 1469-1472. Trans Tech Publication, Switzerland.
- Talavera F. J. F et al. (2007). Effect of production variables on bending properties, water absorption and thickness swelling of bagasse/plastic composite boards. *Industrial Crops and Product- An International Journal*. 26. 1-7. Elsevier.
- Tanjung F. A., Hassan A. and Hasan M. (2015). Use of Epoxidized Natural Rubber as a Toughening Agent in Plastic. *Journal of Applied Polymer Science*. 132, 42270. Wiley Periodicals, Inc.
- Tanrattanakul V., Sungthong N. and Raksa P. (2008). *Rubber Toughening of Nylon 6 with Epoxidized Natural Rubber*. *Polymer Testing*. 27. 794-800. Elsevier.
- Thamae T. and Baillie C. (2008). Life-cycle assessment (LCA) of wood-polymer composites: a case study. Niska K. O. and Sain M. *Wood-Polymer Composite- A Volume in Woodhead Publishing Series in Composites Science and Engineering*. 273–299. Woodhead Publishing Limited. ScienceDirect.
- Venkatesh R. P., Ramanathan K. and Raman V. S. (2016). *Tensile, Flexural, Impact and Water Absorption Properties of Natural Fibre Reinforced Polyester Hybrid Composite*. *Fibre and textile in Eastern Europe*. DOI: 10.5604/12303666.1196617. 90-94.
- Viderkers N. et al. (2013). Development of Glass-Fibre-Reinforced Polyethylene Roadside Restraints. *9th International Conference On Composite Science And Technology: 2020 - Scientific And Industrial Challenges*. April 24-26, 2013. Naples, Italy. 584-591.

- Wade L. G., Jr. (2003). *Organic Chemistry*. (5th edition). Pearson Education Inc, New Jersey. Prentice Hall.
- Wei Y., Zhao L. and Yang H. (2012). *Study on Highway Safety Simulation Evaluation Model and Method*. Applied Mechanics And Materials. 170-173. 3677-3682. Trans Tech Publication, Switzerland.
- Wichian A. N. (2013). Preparation and mechanical property of the epoxidized natural rubber from field latex. *Rubber Thai Journal* 2. 1-8. Rubber research Institute of Thailand.
- Wisittanawat U. et al. (2014). *Mechanical Properties of Highly Aligned Short Pineapple Leaf Reinforced - Nitrile Rubber Composite: Effect of Fibre Content and Bonding Agent*. Polymer testing. 35. 20-27. Elsevier.
- Xia X. et. al. (2015). Study on flax fibre toughened poly(lactic) acid composite. *Journal of Applied Polymer Science*. 132, 42573. Wiley Periodicals, Inc.
- Xiao J., Shang X. (2011). *Study on Shock-absorbing Capacity of Roadside Safety Devices Made by Porous Ultra-high Molecular Weight Polyethylene*. Applied Mechanics and Materials. 55-57. 1403-1406. Trans Tech Publications, Switzerland.
- Xu T. et al. (2015). *Interfacial Interaction Between the Epoxidized Natural Rubber and Silica in Natural Rubber/Silica Composite*. Applied Surface Science. 328. 306-313. Elsevier.
- Zampaloni M. et al. (2007). *Kenaf Natural Fibre Reinforced Polypropylene Composites: A discussion on Manufacturing Problems and Solutions*. Composite Part A: applied science and manufacturing. 38. 1569-1580. Elsevier.
- Zhang K. et al. (2014). *Toughened Sustainable Green Composites from Poly(3-hydroxybutyrate-co-hydroxyvalerate) Based Ternary Blends and Miscanthus Biofibre*. Sustainable chemistry engineering. 2. 2345-2354. American Chemical Society.

Zhu et al. (2013). Effect of fibre treatments on water absorption and tensile properties of flax/Tannin composite. *The 19th International Conference on Composite Materials*. 28 July - 2 August 2013. Montreal, Canada.