



***EFFECTS OF LIGNIN IN NANOCRYSTALLINE CELLULOSE ON  
MECHANICAL, MORPHOLOGICAL AND THERMAL PROPERTIES OF  
KENAF CORE-REINFORCED POLYPROPYLENE COMPOSITES***

**FATIMAH ATHIYAH BINTI SABARUDDIN**

**IPTPH 2019 10**



**EFFECTS OF LIGNIN IN NANOCRYSTALLINE CELLULOSE ON  
MECHANICAL, MORPHOLOGICAL AND THERMAL PROPERTIES OF  
KENAF CORE-REINFORCED POLYPROPYLENE COMPOSITES**

By

**FATIMAH ATHIYAH BINTI SABARUDDIN**

**Thesis Submitted to the School of Graduate Studies,  
Universiti Putra Malaysia, in Fulfilment of the Requirement for the Degree of  
Doctor of Philosophy**

**April 2019**

All material contained within the thesis, including without limitation text, logos, icons, photographs and all other artwork, is copyright material of Universiti Putra Malaysia unless otherwise stated. Use may be made of any material contained within the thesis for non-commercial purposes from the copyright holder. Commercial use of material may only be made with the express, prior, written permission of Universiti Putra Malaysia.

Copyright © Universiti Putra Malaysia





*Bismillahirrahmanirrahim*

*To my beloved parent, family, teachers and friends*

© COPYRIGHT UPM

Abstract of the thesis to Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Doctor of Philosophy

**EFFECTS OF LIGNIN IN NANOCRYSTALLINE CELLULOSE ON MECHANICAL, MORPHOLOGICAL AND THERMAL PROPERTIES OF KENAF CORE-REINFORCED POLYPROPYLENE COMPOSITES**

By

**FATIMAH ATHIYAH BINTI SABARUDDIN**

**April 2019**

**Chairman : Professor Paridah Md Tahir, PhD**  
**Institute : Tropical Forestry and Forest Products**

The excessive application of chemicals during the NCC production led to harmful chemical discharge that can damage the environment. The process of NCC production can be shortened by excluding the bleaching process and retain partial of lignin within NCC. Lignin was found to be high in thermal stability as it was able to withstand high temperature up to 900 °C. Lignin also possess polar and non-polar groups in its chain network which make lignin as good compatibilizer. The implication of lignin in NCC surface has been reported, however its effect on the nanocomposites has not been discussed yet. Hence, if lignin can be retained in NCC and posing no significant adverse effect on the composites, it would give a new perspective in the NCC application. Therefore, in this study, NCC from KC was produced through the soda-AQ pulping process and the lignin content in NCC were varied via different sequence of bleaching. Four different pulps were produced from the bleaching process denoted as UB (unbleached pulps), B1 (bleached up to stage D1), B2 (bleached up to stage D2), and B3 (bleached up to stage D3). All pulps were proceeded with acid hydrolysis treatment to produce the NCCs. All NCCs were analysed having different lignin content which confirmed via chemical analysis and kappa number test. The thermal analysis shows that, the NCC of high lignin content was not able to resist early thermal degradation temperature but was able to withstand a temperature up to 700 °C with highest amount of residual char. The NCCs (0.5 and 1 wt. %) then were incorporated within kenaf core reinforced polypropylene (PP/KC) composites with addition of 1 wt % of maleic anhydride grafted polypropylene (MAPP) and its effect on physical, chemical, mechanical, and thermal properties were determined. Overall, the presence of lignin in NCC help to improve the thermal stability of the nanocomposites with marginal effect on the mechanical properties. Furthermore, post alkaline treatment were done upon NCC having different bleaching condition to remove the remaining sulphates as by-product of acid hydrolysis process. However, post alkaline treatment were analysed to be unnecessary for unbleached NCC as it did not give any significant effect to the properties of the NCC and the nanocomposites.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**KESAN KANDUNGAN LIGNIN DALAM SELULOSA NANOKRISTAL  
TERHADAP SIFAT-SIFAT MEKANIKAL, MORFOLOGI DAN HABA  
TERHADAP TERAS KENAF DIPERKUAT KOMPOSIT POLIPROPALINA**

Oleh

**FATIMAH ATHIYAH BINTI SABARUDDIN**

**April 2019**

**Pengerusi : Profesor Paridah Md Tahir, PhD**  
**Institut : Perhutanan Tropika dan Produk Hutan**

Penggunaan bahan kimia yang berlebihan semasa pembuatan NCC menyebabkan penghasilan bahan kimia berbahaya yang boleh merosakkan alam sekitar. Proses pembuatan NCC dapat dipendekkan dengan pengecualian proses pelunturan dan mengekalkan sebahagian daripada lignin didalam NCC. Lignin didapati mempunyai kestabilan terma yang tinggi kerana dapat menahan suhu tinggi sehingga 900 °C. Lignin juga mempunyai kumpulan kutub dan bukan kutub dalam rangkaian rantaianya yang menjadikan lignin sebagai penserasi yang baik. Kesan lignin di permukaan NCC telah pun dibentangkan tetapi kesannya terhadap nano-komposit masih belum dibincangkan. Oleh itu, jika lignin dapat dikekalkan di permukaan NCC dan tidak memeberikan kesan yang tidak baik terhadap komposit, ia dapat memberi perspektif baru terhadap penggunaan NCC. Oleh itu, dalam kajian ini, NCC dari teras kenaf dihasilkan melalui proses pulpupaan soda-AQ dan kandungan lignin dalam NCC divariasikan melalui urutan proses pelunturan. Empat pulpa berlainan dihasilkan dari proses pelunturan yang dikenali sebagai UB (pulpa yang tidak diluntur), B1 (diluntur hingga ke tahap D1), B2 (diluntur hingga ke tahap D2), dan B3 (diluntur hingga tahap D3). Semua pulpa kemudiannya diteruskan dengan proses hidrolisis asid untuk menghasilkan NCC. Semua NCC dianalisis mempunyai kandungan lignin yang berbeza dan disahkan melalui analisis kimia dan ujian nombor kappa. Analisis terma menunjukkan bahawa NCC dengan kandungan lignin tinggi tidak dapat menahan degradasi pada suhu awal tetapi dapat bertahan sehingga suhu 700 °C. NCC (0.5 dan 1 wt.%) kemudiannya dimasukkan dalam komposit teras kenaf diperkuat polipropilena (PP / KC) dengan penambahan 1% berat maleik anhidrida dicantum polipropilena (MAPP) dan kesannya terhadap fizikal, kimia, mekanikal dan terma ditentukan. Secara keseluruhannya, kehadiran lignin di dalam NCC membantu meningkatkan kestabilan haba nanokomposit dengan memberi kesan kecil pada sifat-sifat mekanik. Tambahan pula, rawatan pasca-alkali telah dilakukan apabila NCC dengan sifat kelunturan yang berbeza untuk mengeluarkan sisa sulfat kesan hasil sampingan proses hidrolisis asid. Walau bagaimanapun, rawatan pasca-alkali telah dianalisis untuk tidak diperlukan untuk NCC yang tidak diluntur kerana ia tidak memberi kesan kepada sifat-sifat NCC dan nanokomposit.

## ACKNOWLEDGEMENTS

In the name of Allah, Most Gracious, Most Merciful and Praise be to Allah, the Cherisher and Sustainer of the worlds for giving me chance to complete this work. I would also like to convey my sincere salam to His messenger and our prophet, Nabi Muhammad (SAW). I wish to express my sincere appreciation and gratitude to my supervisor Prof Dr Paridah Md Tahir, for her extremely helpful guidance, generous support and continuous encouragement with her wisdom, knowledge and experience. I would also thanks my co-supervisor, Dr Khalina Abdan, Dr Norkhairunnisa and Dr Adlin Sabrina for their kind support and meaningful contribution.

My appreciations also extends to all staffs of Institute of Tropical Forestry and Forest Products (INTROP) who have help me a lot in accomplishing my study. My gratitude also goes to my research mates, Naziratul Asikin, Zakiah Sobri, Nur Liyana Mohd Hafiz, Lee Chuan Li, Mohd Hizami, Norwahyuni, Redzuan and Aisyah Humairah for their help, encouragement and support throughout this research. My further appreciation goes to my post doctorate and fellow researcher; Dr Mohammad Asim Khan and Dr Lee Seng Hua for their help in contributing and accomplishing my research.

Finally, I would particularly like to thanks and acknowledge my parents, siblings and nephews for their countless help on giving me their affection and moral support. I will always be in their debt.

Thank you very much, only Allah can repay everything.

I certify that a Thesis Examination Committee has met on 25 April 2019 to conduct the final examination of Fatimah Athiyah binti Sabaruddin on her thesis entitled "Effects of Lignin in Nanocrystalline Cellulose on Mechanical, Morphological and Thermal Properties of Kenaf Core-Reinforced Polypropylene Composites" in accordance with the Universities and University Colleges Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The Committee recommends that the student be awarded the Doctor of Philosophy.

Members of the Thesis Examination Committee were as follows:

**Edi Suhaimi Bakar, PhD**

Associate Professor  
Faculty of Forestry  
Universiti Putra Malaysia  
(Chairman)

**Edi Syams bin Zainudin, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Zulkiflle bin Leman, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Sami Boufi, PhD**

Professor  
Faculty of Sciences of Sfax  
University of Sfax  
Tunisia  
(External Examiner)



**RUSLI HAJI ABDULLAH, PhD**  
Professor and Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 26 June 2019



This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

**Paridah Binti Md Tahir, PhD**

Professor and Director  
Institute of Tropical Forestry and Forest Product,  
Universiti Putra Malaysia  
(Chairman)

**Khalina Binti Abdan, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)

**Norkhairunnisa Binti Mazlan, PhD**

Senior Lecturer  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)

**Adlin Sabrina Binti Muhammad Roseley, PhD**

Senior Lecturer  
Faculty of Forestry  
Universiti Putra Malaysia  
(Member)

---

**ROBIAH BINTI YUNUS, PhD**

Professor and Dean  
School of Graduates Studies  
Universiti Putra Malaysia

Date:

## Declaration by graduate student

I hereby confirm that:

- This thesis is my original work;
- Quotations, illustration and citations have been duly referenced;
- This thesis has not been submitted previously or concurrently for any other degree at any other institutions;
- Intellectual property from the thesis and copyright of thesis are fully-owned by Universiti Putra Malaysia, as according to the Universiti Putra Malaysia (Research) rules 2012;
- Written permission must be obtained from supervisor and the office of Deputy Vice-Chancellor (Research and Innovation) before thesis is published (in the form of written, printed, or in electronic form) including books, journals, modules, proceedings, popular writings, seminar papers, manuscripts, posters, reports, lecture notes, learning modules or any other materials as stated in the Universiti Putra Malaysia (Research) Rules 2012;
- There is no plagiarism or data falsification / fabrication in the thesis, and scholarly integrity is upheld as according to the Universiti Putra Malaysia (Graduate Studies) Rules 2003 (Revision 2012-2013) and the Universiti Putra Malaysia (Research) Rules 2012. The thesis has undergone plagiarism detection software.

Signature: \_\_\_\_\_ Date: \_\_\_\_\_

Name and Matric No.: Fatimah Athiyah Binti Sabaruddin (GS43926)

## Declaration by Members of Supervisory Committee

This is to confirm that

- The research conducted as stated in the Universiti Putra Malaysia was under our supervision;
- Supervision responsibilities as stated in the Universiti Putra Malaysia (Graduated Studies) Rules 2003 (Revision 2012-2013) are adhered to.

Signature : \_\_\_\_\_  
Name of Chairman  
of Supervisory Committee : Prof Dr. Paridah Binti Md Tahir

Signature : \_\_\_\_\_  
Name of Member of  
Supervisory Committee : Assoc. Prof. Dr. Khalina Binti Abdan

Signature : \_\_\_\_\_  
Name of Member of  
Supervisory Committee : Dr. Norkhairunnisa Binti Mazlan

Signature : \_\_\_\_\_  
Name of Member of  
Supervisory Committee : Dr. Adlin Sabrina Binti Muhammad Roseley

## TABLE OF CONTENTS

		Page
<b>ABSTRACT</b>		i
<b>ABSTRAK</b>		ii
<b>ACKNOWLEDGEMENT</b>		iii
<b>APPROVAL</b>		iv
<b>DECLARATION</b>		vi
<b>LIST OF TABLES</b>		xi
<b>LIST OF FIGURES</b>		xiii
<b>LIST OF ABBREVIATIONS</b>		xvi
<b>CHAPTER</b>		
<b>1</b>	<b>INTRODUCTION</b>	1
	1.1 Overview	1
	1.1.1 Advantages in Using NFRPC	1
	1.1.2 Nanocellulose as New Source of Reinforcement in NFRPC	2
	1.2 Problem Statement and Justification	3
	1.3 Research Objective	3
	1.4 Scope of Study	4
	1.4.1 Development of NCC with Different Lignin Percentage from Kenaf Core	4
	1.4.2 Study on NCC Loading in PP/Kenaf Core Composites	4
	1.4.3 Evaluation on the Effects of NCC loading on PP/KC/Composites	5
	1.4.4 Production of Post Alkaline Treated NCC and its Effect on PP/KC Composites	5
	1.5 Research Novelty	5
	1.6 Summary	5
<b>2</b>	<b>LITERATURE REVIEW</b>	6
	2.1 Introduction	6
	2.2 Kenaf	7
	2.2.1 Physical, Chemical, Mechanical and Thermal Properties of Kenaf Fibres.	7
	2.2.2 Products and Application of Kenaf	12
	2.3 Nanocellulose	13
	2.4 Lignin	18
	2.4.1 Utilization of Lignin as Additives in Biocomposites	19
	2.4.2 Separation of Lignin during Production	20
	2.4.3 Production of NCC without Lignin Removal	20

2.5	Natural Fibre Reinforced Polymer Composites (NFRPC)	24
2.5.1	Interfacial Bonding Strength	24
2.5.2	Properties of NFRPC	25
2.6	Addition of NCC in NFRPC	26
2.7	Summary	30
<b>3</b>	<b>PRODUCTION OF NANOCRYSTALLINE CELLULOSE PREPARED KENAF CORE PULPS OF DIFFERENT LIGNIN CONTENT</b>	<b>31</b>
3.1	Introduction	31
3.2	Materials	32
3.2.1	Kenaf Core	32
3.2.2	Chemicals for Chemical Treatment Process	32
3.3	Methodology	33
3.3.1	Process Flow for NCC Production	33
3.3.2	Nanocrystalline Cellulose (NCC) Preparation	34
3.3.3	Experimental Characterization	37
3.4	Results and Discussion	45
3.4.1	Chemical Analysis	45
3.4.2	Kappa Number of Pulps	46
3.4.3	Colour Comparison	47
3.4.4	Particle Size Distribution and Zeta Potential	48
3.4.5	Fourier Transform Infrared (FTIR) Analysis	50
3.4.6	X-ray Diffraction (XRD) Analysis	51
3.4.7	Thermal Analysis	53
3.4.8	Morphological Analysis	57
3.5	Conclusion	59
<b>4</b>	<b>PRODUCTION OF PP/KC/MAPP COMPOSITES REINFORCED WITH NCC OF DIFFERENT LIGNIN CONTENT AND ITS EFFECT ON MECHANICAL, MORPHOLOGICAL AND PHYSIO-CHEMICAL PROPERTIES</b>	<b>61</b>
4.1	Introduction	61
4.2	Materials	62
4.2.1	Polypropylene (PP)	62
4.2.2	Kenaf Core	63
4.2.3	Maleic Anhydride Grafted Polypropylene (MAPP)	63
4.2.4	Nanocrystalline Cellulose (NCC) with Different Lignin Content	64
4.3	Methodology	64
4.3.1	Production of NCC of Different Lignin Content	64
4.3.2	Compounding of the PP/Kenaf Core Composites	65
4.3.3	Experimental Characterization	66
4.3.4	Methodology Flowchart	69

4.4	Results And Discussion	70
4.4.1	Preliminary Study on the Effect of PP/KC Composites with Addition of MAPP	70
4.4.2	The PP/KC/MAPP Composites Reinforced NCC of Different Lignin Content	78
4.5	Conclusion	91
<b>5</b>	<b>THERMAL PROPERTIES OF PP/KENAF CORE NANOCOMPOSITES INCORPORATED WITH NCC OF DIFFERENT LIGNIN CONTENT</b>	<b>92</b>
5.1	Introduction	92
5.2	Materials and Methods	93
5.2.1	Experimental Characterization	93
5.2.2	Methodology Flowchart	94
5.3	Results and Discussion	94
5.3.1	Thermal Gravimetric Analysis (TGA)	94
5.3.2	Differential Scanning Calorimetry (DSC)	99
5.3.3	Dynamic Mechanical Analysis (DMA)	102
5.4	Conclusion	106
<b>6</b>	<b>THE SULPHATES REMOVAL IN NANOCELLULOSE WITH DIFFERENT LIGNIN CONTENT AND ITS EFFECT IN PP/KC/MAPP NANOCOMPOSITES</b>	<b>107</b>
6.1	Introduction	107
6.2	Materials and Methods	107
6.2.1	Production of Post Alkaline Treated NCC and its Incorporation in PP/KC/MAPP Composites	107
6.2.1	Experimental Characterization	109
6.3	Results and Discussion	109
6.3.1	The Effect of Sulphate Removal on NCC with Different Lignin Content	109
6.3.2	The Effect of PP/KC/MAPP Composites Reinforced Post Alkaline Treated NCC	118
6.4	Conclusion	135
<b>7</b>	<b>SUMMARY, CONCLUSION AND RECOMMENDATIONS FOR FUTURE RESEARCH</b>	<b>136</b>
7.1	Summary and Conclusion	136
7.2	Recommendations for Future Research	138
	<b>REFERENCES</b>	<b>140</b>
	<b>BIODATA OF STUDENT</b>	<b>157</b>
	<b>LIST OF PUBLICATIONS</b>	<b>158</b>

## LIST OF TABLES

<b>Table</b>		<b>Page</b>
2.1	Chemical composition of kenaf fibres	10
2.2	Comparison of mechanical properties between kenaf and other natural and synthetic fibres	11
2.3	Nanocellulose isolation from kenaf, kenaf core and other natural fibres via different methods from various studies	16
2.4	Effect of lignin on the properties of biocomposites from various studies	21
2.5	List of techniques for composites and nanocomposites with the polymer (Saba et al., 2014)	27
2.6	Studies on the addition of NCC in natural fibre composites	28
3.1	The condition of KC pulping process	34
3.2	The bleaching condition	35
3.3	Acid hydrolysis conditions	36
3.4	The chemical composition of kenaf core pulp before acid hydrolysis process.	45
3.5	Kappa number for pulps with different lignin content	46
3.6	The DSC important values for kenaf core and all NCCs	57
3.7	The size distribution of NCC of different lignin content	58
4.1	The chemical composition of KC pulps with different lignin content	65
4.2	The composition and denotation of the PP/KC/MAPP composites for preliminary study	65
4.3	The composition and denotation of the PP/KC/MAPP nanocomposites	66
4.4	The SEM images of PP and kenaf core/PP composites with and without MAPP	75
4.5	Scanning Electron Micrographs (SEM) of fractured tensile specimens of PP/KC/MAPP composites	83
4.6	Scanning Electron Micrographs (SEM) of fractured tensile specimens of PP/KC/MAPP composites with addition of NCC of different lignin content	84
5.1	The endothermic peaks, enthalpy of fusion and the fractional crystallinity of PP/KC/MAPP nanocomposites	99
6.1	The composition and denotation of the PP/KC/MAPP composites reinforced treated NCC	108
6.2	The DSC important values for KC and all NCCs	115
6.3	The size and distribution of NCC of different lignin content	117

6.4	SEM micrographs of PP/KC/MAPP nanocomposites with addition of neutralized and non-neutralized NCC of different lignin content	123
6.5	The enthalpy of fusion, fractional crystallinity and endothermic peaks for PP/KC/MAPP nanocomposites reinforced neutralized and non-neutralized NCC of different lignin content	130





## LIST OF FIGURES

Figure		Page
2.1	Kenaf fibre structure	8
2.2	Illustration of kenaf cell wall	9
2.3	The image of nanocellulose from different extraction process	14
2.4	The illustration of lignin position between cellulose and hemicellulose	18
2.5	Lignin structure	19
3.1	Kenaf core	32
3.2	The methodology flowchart of NCC production from KC	33
3.3	The acid hydrolysis process of unbleached and bleached KC pulps	36
3.4	The Soxhlet extraction apparatus	38
3.5	The filtration apparatus used to determine the lignin	39
3.6	The preparation of Kappa Number for pulp analysis.	41
3.7	Preparation of samples using (a) ultrasonic machine and (b) post-staining of NCC solution using uranyl acid and drop of water	44
3.8	JEOL JEM 2100 Transmission Electron Microscope (TEM) used in this study	44
3.9	The kenaf core pulps after bleaching process	47
3.10	The colour comparison of NCC suspension	48
3.11	Diameter size distribution of kenaf core NCC; (a) NCC-UB, (b) NCC-B1, (c) NCC-B2 and (d) NCC-B3	49
3.12	The FTIR graph of raw kenaf core and kenaf core NCC with different lignin content	51
3.13	The XRD graph of raw kenaf core and NCCs with different lignin content	52
3.14	The thermal decomposition over temperature of raw kenaf core and kenaf core NCC with different lignin content	54
3.15	The decomposition rate over temperature of raw kenaf core and kenaf core NCC with different lignin content	55
3.16	The DSC graph of raw kenaf and kenaf core NCC with different lignin content	57
3.17	The TEM images of (a) NCC – UB and (b) NCC – B3	59
4.1	Polypropylene resin from Titan Petchem Malaysia	62
4.2	KC (a) chips and (b) powder used in this study	63
4.3	Maleic anhydride grafted polypropylene (MAPP) supplied from Sigma Aldrich	63
4.4	Different types of NCC	64

4.5	Tensile sample dimensions according to ASTM D638M	66
4.6	Flexural sample dimensions according to ASTM D790	67
4.7	Impact sample dimensions according to ASTM D256	67
4.8	JSM 6400 Scanning Electron Microscopy (SEM)	68
4.9	The methodology flowchart of mechanical analysis of PP/KC nanocomposites	69
4.10	The tensile strength (a) and modulus (b) of PP/KC with and without MAPP	71
4.11	The flexural strength (a) and modulus (b) of PP/KC with and without MAPP	73
4.12	The impact strength of PP/KC with and without MAPP	74
4.13	The water absorption properties of PP/KC composites (a) without and (b) with MAPP coupling agent; preliminary study	77
4.14	The (a) tensile strength and (b) modulus of PP/KC/MAPP added with NCC of different lignin content	79
4.15	The (a) flexural strength and (b) modulus of kenaf core/PP/MAPP added with NCC of different lignin content	81
4.16	The impact strength and modulus of PP/KC/MAPP added with NCC of different lignin content	82
4.17	The TEM images of (a) NCC-UB and (b) NCC-B3	85
4.18	The IR spectroscopy of raw kenaf core and PP/KC/MAPP nanocomposites with and without NCC	86
4.19	The X-ray diffraction patterns for PP/KC/MAPP nanocomposites with and without NCC	88
4.20	The water absorption for kenaf core/PP/MAPP added with (a) 0.5 wt. % and (b) 1 wt. % NCC of different lignin content	90
5.1	The methodology flowchart of thermal analysis of PP/KC nanocomposites	94
5.2	The TGA peaks of PP/KC/MAPP composites reinforced (a) 0.5 wt. % and (b) 1 wt. % of NCC of different lignin content	96
5.3	The thermal decomposition properties of PP/KC/MAPP reinforced (a) 0.5 wt. % and (b) 1 wt.% NCC of different lignin content	98
5.4	The DSC graphs of PP/KC/MAPP reinforced (a) 0.5 wt. % and (b) 1wt.% NCC of different lignin content	100
5.5	The storage modulus of PP/KC/MAPP reinforced NCC of different lignin content	103
5.6	The loss modulus of PP/KC/MAPP reinforced NCC of different lignin content	104
5.7	The tan delta of PP/KC/MAPP reinforced NCC of different lignin content	105
6.1	The graphical method of post alkaline treated NCC	108

6.2	The particle size distribution of KC NCC (a) unbleached NCC (NCC-UB) and (b) bleached NCC (NCC-B3) with and without post alkaline treatment	110
6.3	The FTIR graphs of KC NCC with different lignin content with and without post alkaline treatment	111
6.4	The XRD graphs of NCC after post alkaline treatment	112
6.5	The thermal decomposition over temperature of KC NCC with different lignin content with and without post alkaline treatment	113
6.6	The decomposition rate over temperature of KC NCC with different lignin content with and without post alkaline treatment	114
6.7	The DSC graphs of KC NCC with different lignin content with and without post alkaline treatment	116
6.8	The TEM images of (a) NCC-UB (T) and (b) NCC-B3 (T)	117
6.9	The tensile strength (a) and modulus (b) of PP/KC/MAPP/MAPP added with neutralized and non-neutralized NCC of different lignin content	119
6.10	The flexural strength (a) and modulus (b) of PP/KC/MAPP/MAPP added with neutralized and non-neutralized NCC of different lignin content	120
6.11	The impact strength and modulus of PP/KC/MAPP/MAPP added with neutralized and non-neutralized NCC of different lignin content	121
6.12	The FTIR peaks for PP/KC/MAPP composites incorporated neutralized and non-neutralized NCC of different lignin content	124
6.13	The XRD diffractograms of PP/KC/MAPP nanocomposites incorporated with neutralized and non-neutralized NCC of different lignin content	125
6.14	The water absorption for PP/KC/MAPP/MAPP reinforced with (a) 0.5 wt. % and (b) 1 wt. % of NCC	127
6.15	The (a) TGA and (b) DTG graphs of PP/KC/MAPP/MAPP reinforced NCC with and without NaOH neutralization	129
6.16	The DSC graphs of PP/KC/MAPP/MAPP reinforced NCC with and without NaOH neutralization	130
6.17	The storage modulus of PP/KC/MAPP/MAPP reinforced NCC with and without NaOH neutralization	132
6.18	The loss modulus of PP/KC/MAPP/MAPP reinforced NCC with and without NaOH neutralization	133
6.19	The tan delta of PP/KC/MAPP/MAPP reinforced NCC with and without NaOH neutralization	134

## LIST OF ABBREVIATIONS

$\Delta H_f$	Enthalpy of Fusion
ASTM	American Society for Testing and Materials
DMA	Dynamic Mechanical Analysis
DTG	Derivative Thermogravimetry
E'	Storage Modulus
E''	Loss Modulus
FTIR	Fourier Transform Infrared Spectroscopy
HDPE	High Density Polyethylene
KC	Kenaf Core
LDPE	Low Density Polyethylene
MAPP	Maleic Anhydride Grafted Polypropylene
MC	Moisture Content
NCC	Nanocrystalline Cellulose
NFRPC	Natural Fibre Reinforced Polymer Composites
OMMT	Organically Modified MMT
PLA	Poly Lactic Acid
PP	Polypropylene
PP	Polypropylene
PU	Polyurethane
PVC	Poly Vinyl Chloride
SEM	Scanning Electron Microscopy
Tan $\delta$	Tan Delta
T <sub>c</sub>	Crystallization Temperature
T <sub>g</sub>	Glass Transition Temperature
TGA	Thermogravimetric Analysis
UPM	Universiti Putra Malaysia

# CHAPTER 1

## INTRODUCTION

### 1.1 Overview

The issue regarding limited petroleum source has affected many parties particularly in finding other alternatives on petroleum-based products. Recent studies reported that cellulose in plants is found to be the most common organic polymer and considered as almost infinite source of raw material to fulfil the increasing request for eco-friendly and bio-compatible products. It represents about 1.5 billion tonnes of the total annual biomass production (Klemm et al., 2009). Generally, the application of natural fibres and biomass crops impart more positive than negative effects on the environment (Frenando, 2013). It is important that at the end of materials' life cycle, the products should be reused, recycled or disposed. Hence, it is vital that disposable materials or products should be compostable in a short time. Natural fibres composites have the advantages over petroleum-based composites since the latter take much longer time to be composted (Kim et al., 2015). Therefore, the potential of exploiting the use of renewable material suddenly had become more interesting and equally important (Moon, Schueneman, & Simonsen, 2016).

Fibre-reinforced polymer composites (FRPCs) consist of a polymeric medium for example polypropylene (PP), polyester, epoxy, or poly-lactic acid, and a fibrous material such as carbon fibre, glass fibre, aramid fibre or natural fibre. The denotation of the composites is usually defined based on the fibre types, e.g., carbon fibre-reinforced polymer, glass fibre-reinforced polymer, and natural fibre-reinforced polymer composite (NFRPC). The mixture of two material types which known as "composite" material imparts better properties in both form and function to that of the constituent materials in isolation. In general, the fibres provide the strength while the polymer also known as the matrix, provides dimensional stability and the transfer of shear stresses between the fibres. As a result, it produces a strong functional material which can be easily customised to deal with a wide variety of uses.

#### 1.1.1 Advantages in Using NFRPC

Research and development have shown that there is a various range of potential application for NFRPC in the industry (Mwaikambo & Ansell, 2003; Mohanty, 2009). The most successful area for NFRPC is in non-structural architectural and functional applications for example doors, door frames, skirting boards, and other decorative features. They can be architecturally and aesthetically pleasing which have potential in a wide range of applications and unique products. Their proven durability in research suggests that NFRPCs are well suited to outdoor applications such as window frames or decking (Sharba et al., 2016).

Furthermore, natural fibres have imparted good thermal properties which the application of NFRPC might be useful in situations where thermal bridging could be an issue. Natural fibres also have good acoustic dampening properties although more research is needed to verify this. Preconceptions about the inherent weaknesses of natural fibres can obscure their potential as a serious alternative to glass fibre. Researches have shown that many of the mechanical issues associated with natural fibres that can be overcome with chemical modification and that natural fibres have similar properties to glass fibres. Furthermore, NFRPCs can be easily formed into structural components such as beams, reinforcing bars, and board materials that could potentially be used in racking panels.

### **1.1.2 Nanocellulose as New Source of Reinforcement in NFRPC**

The versatility of nanocellulose as new reinforcement materials make rooms for consideration in a variety of possible applications. At the same time, the production of different grades of nanocellulose provides the opportunity for product enhancement, flexible applications, and new materials creation. Recently, researchers are focusing on the utilisation of nanocellulose in low volume and high performance applications (Salas et al., 2014).

Nanocellulose has unique combination of properties: high mechanical properties, low thermal expansion, high thermal stability, and relatively low density compared to inorganics and metals (Moon et al., 2016). High surface-area-to-volume ratio of nanocellulose allows them to exert a large effect on their local surrounding while acting as a stiff phase in suspension and composites. Its application can be varied such as a reinforcement in polymer composites, an additive in paper-based products, food packaging products, an additive in cement-based materials biomedical applications, etc. (Moon et al., 2016).

Nanocellulose can be produced by extracting cellulose from plants via purification involving chemical pretreatments which consists of alkali extraction and series of bleaching process. As reported by Dufresne (2013), the Young's modulus of nanocellulose with density for crystalline cellulose of around 1.5–1.6 g/cm<sup>3</sup> is much higher than that of the glass fibre, around 70 GPa with a density around 2.6 g/cm<sup>3</sup>. Nanocellulose also has greater axial elastic modulus than Kevlar and potentially stronger than steel. Therefore, outstanding mechanical properties can be obtained by mixing nanocellulose with a polymer matrix even at low amount of filler loading. Such properties originate from the high stiffness of crystalline cellulose, the nanoscale dimension, and high aspect ratio that provide the strength to the nanocomposites (Moon et al., 2011; Dufresne, 2013). Those great properties make nanocellulose the most suitable additive to produce high performance and environmental friendly composites materials for the future.



## 1.2 Problem Statement and Justification

Nowadays, apart from the mechanical properties, thermal stability has become increasingly important to comply with the safety requirements during application (Rault et al., 2015). Thus, the needs for high thermal stable composites are increasing. Polymer matrices such as polypropylene (PP) and polyethylene (PE), have high ability to burn easily because it is mainly composed of carbon and hydrogen. When supported with high temperature, it will easily ignite once it is mixed with the oxygen in air, and melt rapidly due to its wholly aliphatic hydrocarbon structure (Loutid et al., 2009). It becomes more crucial when the composites are added with natural fibres as it increases sensitivity of the composite to burn. In addition, most natural fibres that are used as a reinforcement are thermally unstable above 200 °C (Pickering et al., 2016). The selection of polymer matrix also limited to those with lower melting temperature at which natural fibre degrades. Therefore, only thermoplastic that softens below this temperature such as PE, PP, polyolefin, polyvinyl chloride, and polystyrene as well as thermoset are usable as matrix (Summerscales et al., 2010; Ismail et al., 2013; Pickering et al., 2016).

The low tolerance to heat made the NFRPC less desirable. Hence, the enhancement of thermal properties of NFRPC is crucial and this can be achieved by adding NCC in the matrix. However, the properties of NCC requires chemical bleaching process which is mainly to remove the lignin. In the process, the pulps undergo several steps with different chemicals. Hence, if the bleaching process can be excluded, the production cost can be reduced and the application of chemical pollutants can be avoided. Nevertheless, to exclude bleaching means some amount of lignin in the NCC will remain. Studies have shown that the presence of lignin in NCC provides good thermal resistant property and improves the thermal degradation of NFRPC even further. The amount of lignin in wood for example kenaf, flax, pine straw, wheat straw, and alfafa ranges from 12% to 39% when the amount is determined based on Klason lignin analysis (Hatakeyama & Hatakeyama, 2009; Watkins et al., 2015). According to Rozman et al., (2000), lignin also has the potential to act as a compatibiliser since it contains both polar hydroxyl groups and non-polar hydrocarbon as well as benzene rings. Thus, it is eligible to play a role as a compatibility enhancer between matrix and reinforcement and improves the mechanical properties of a composite. To determine these effects, the NCCs prepared in this study were subjected to different bleaching sequences to obtain different amount of lignin that were retained in the NCC. These NCCs were then added into the composites and its effect on the performance of resulting composites were evaluated.

## 1.3 Research Objectives

The aim of this study is to produce high mechanical and thermal stable NFRPC using kenaf core (KC) as the main source of natural fibre. The KC was used in two forms: micro-sized powder and NCC. The NCC was applied in PP/KC composites at different lignin percentage. The specific objectives of this study are:

- To characterise the NCC of different lignin content from KC
- To evaluate the effect of kenaf fibre loading PP composites as the control samples
- To evaluate the effect of NCC of different lignin contents addition on the physical, chemical, morphological and mechanical properties of PP/KC composites.
- To examine the thermal properties of PP/KC composites added with NCC of different lignin contents.
- To determine the effect of alkaline post treatment on NCC and the properties of PP/KC/MAPP nanocomposites.

#### **1.4 Scope of Study**

This research was divided into four sections: (i) preparation of NCC from KC, (ii) production of NCC of different lignin contents, (iii) evaluation of NCC loading effects on the properties of PP/KC composites, and (iv) the production of post alkaline treated NCC and its effect on PP/KC composites.

##### **1.4.1 Development of NCC with Different Lignin Percentage from KC**

In this section, the isolation and extraction processes were done upon KC as a main source of fibre to produce nanocellulose. KC was reported to have high hemicellulose (30%) and cellulose (45%) which makes it a suitable biochemical source of cellulose derivatives such as nanocellulose (Jonoobi et al., 2010). The KC was pulped using alkali treatment or pulping process and then bleached to produce different levels of lignin content. Then, the pulps were then chemically treated through acid hydrolysis process to produce NCC. Following this, the NCC were freeze dried prior to the nanocomposite production.

##### **1.4.2 Production of PP/KC Composites Reinforced with NCC of Different Lignin Content**

The optimisation of PP/KC formulation was determined by varying the KC loading by 10, 20, 30, and 40 wt %. The furnish samples were added with MAPP, a coupling agent that enhances the interfacial adhesion between the polymer matrix and natural fibres. Then, the optimum mixture was chosen according to its mechanical and thermal properties with the support of morphological tests. The sample with the optimum results was chosen to be added with different types of NCC filler. The amount of NCCs loaded in the PP/KC composites were set to be 0.5 and 1 wt %. The mixture of PP, KC with and without NCC were compounded via melt mixing process and hot pressed according to the desired mould, conditioned and tested.



### **1.4.3 Evaluation on the Effects of NCC Loading on PP/KC Composites**

The effect of KC loading on its mechanical and physical properties were evaluated by the addition of different KC loading (10 % wt., 20% wt., 30% wt. and 40% wt.) with and without addition of MAPP. Then, the effect of PP/KC and different types of NCCs were evaluated via mechanical, physio-chemical, and thermal properties. The analysis on mechanical properties of the nanocomposites were proven by the morphological analysis done via SEM.

### **1.4.4 Production of Post Alkaline Treated NCC and its Effect on PP/KC Composites**

In order to remove the sulphates by-products in NCC from acid hydrolysis process, the NCC suspension undergo a post alkaline treatment using a strong alkali. In this part, instead of rinsing the NCCs via centrifugation and dialysis using membrane cellulose, the NCCs were rinsed using NaOH until the pH is neutral. Following this, the NCC were freeze dried prior to the nanocomposite production. The treated NCC of different lignin content then incorporated in PP/KC/MAPP composites to observe the effect on its physical, chemical, mechanical and thermal properties.

## **1.5 Research Novelty**

This research mainly focuses on the production and application of NCC of different lignin content that was prepared from KC and its effect on the properties of NFRPC. Lignin contains both polar hydroxyl groups and non-polar hydrocarbon and the benzene ring. It was believed can contribute to the enhancement of compatibility between the polymer matrix and fibre reinforcement (Rozman et al., 2000; Hatakeyama & Hatakeyama, 2010). The uniqueness of this study is the variation on lignin content in the NCC which were achieved by controlling the bleaching sequence. The effect of the lignin on the properties of composites with NCC was evaluated. This study also applied two sizes of filler: KC in the form of NCC and microsized powder which also known as bimodal filler system, where the smaller particles (NCC) help to fill the interstitial space between larger particles (microsized powder) to give an increase in packing density of the fillers resulting in the improvement of composites properties (Hong et al., 2011).

## **1.6 Summary**

This chapter was initiated by overviewing the application of the NFRPC and its advantages over the conventional composites. The impact of nanocellulose as the new type of reinforcement was also highlighted in this chapter. However, there are some problems that needs to be countered which become the main focus of this study. The objective of this study was listed and elaborated in the scope of research section. Finally, the novelty of this study was stated through the explanation on its uniqueness over other studies.

## REFERENCES

- Abitbol T, Rivkin A, Cao Y, Nevo Y, Abraham E, Ben-Shalom T, Lapidot S and Sheseyov O. (2016). Nanocellulose, a Tiny Fiber with Huge Applications. *Current Opinion in Biotechnology*, 39: 76-88.
- Ahmad I, Mosadeghzad Z, Daik R and Ramli A. (2008). The Effect of Alkali Treatment and Filler Size on the Properties of Sawdust/UPR Composites Based on Recycled PET Wastes. *Journal of Applied Polymer Science*, 109: 3651-3658.
- Aji, I.S., Sapuan, S.M., Zainuddin, E.S., and Abdan, K. (2009). Kenaf s as Reinforcement for Polymeric Composites: A Review. *International Journal of Mechanical and Materials Engineering*, 4:239-248.
- Akil, H.M., Omar, M.F., Mazuki, A.A.M, Safiee, S., Ishak, Z.A.M. and Abu Bakar, A. (2011). Kenaf Fibre Reinforced Composites: A Review. *Materials and Design*, 32: 4107-4121.
- Albdiry MT, Yousif BF, and Ku H. (2013). Fracture Toughness and Toughening Mechanism of Unsaturated Polyester-Based Clay Nanocomposites. *13<sup>th</sup> International Conference on Fracture Beijing, China*. 1-10.
- Alcala M, Gonzalez I, Boufi S, Vilaseca F, and Mutje P. (2013). All Cellulose Composites from Unbleached Hardwood Kraft Pulp Reinforced with Nanofibrillated Cellulose. *Cellulose*, 20: 2909-2921
- Alemdar and Sain (2008). Isolation and Characterization of Nanofibers from Agricultural Residues – Wheat Straw and Soy Hull. *Bioresources Technology*, (6): 1664-1671.
- Alexopoulou, E., Cosentino, S.L., Danalatos, N., Picco, D., Lips, S., Van Den Berg, D., Fernando, A.L., Monti, A., Tenario, J.L., Kipriotis, E., Cadoux, S., and Cook, S. (2013). New Insight from the BIOKENAF Project. In Monti, A., and Alexopoulou, E. (Eds). *Kenaf: A Multi-Purpose Crop for Several Industrial Applications, New Insight from the Biokenaf Project*. London, England: Springer Verlag.
- Alix, S., Marais, S., Morvan, C. And Lebrun, L. (2008). Biocomposite materials from flax plants: Preparation and properties. *Composites Part A: Applied Science and Manufacturing*, 39(12): 1793-1801.
- Alexy, P., Košíková, B., & Podstránska, G. (2000). The effect of blending lignin with polyethylene and polypropylene on physical properties. *Polymer*, 41(13), 4901–4908. [https://doi.org/10.1016/S0032-3861\(99\)00714-4](https://doi.org/10.1016/S0032-3861(99)00714-4)
- Almn A. (2006). Fiber for Strengthening of Timber Structure. Lulea University of Technology.

- Alvarez VA, Fraga AN, and Vazquez A. (2004). Effects of the Moisture and Fiber Content on the Mechanical Properties of Biodegradable Polymer-Sisal Fiber Biocomposites. *Journal of Applied Polymer Science*, 91: 4007-4016.
- Amran M, Izamshah R, Hadzley M, Shahir M, Amri M, Sanusi M, and Hilmi H. (2015). The effect of Binder on Mechanical Properties of Kenaf Fibre/Polypropylene Composites Using Full Factorial Method. *Applied Mechanics and Material*, 695: 709-712.
- Anuar, H., and Zuraida, A. (2011). Thermal Properties of Injection Moulded Polylactic Acid – Kenaf Biocomposites. *Malaysian Polymer Journal*. 6(1): 51-57.
- Anuar, N. I. S., Zakaria, S., Kaco, H., Hua, C. C., Chunhong, W., & Abdullah, H. S. (2018). Physico-mechanical, chemical composition, thermal degradation and crystallinity of oil palm empty fruit bunch, kenaf and polypropylene fibres: A comparative study. *Sains Malaysiana*. <https://doi.org/10.17576/jsm-2018-4704-24>
- Asadi A, Miller M, Moon RJ and Kalaitzidou K. (2016). Improving the Interfacial and Mechanical Properties of Short Glass/Epoxy Composites by Coating the Glass Fibers with Cellulose Nanocrystals. *eXpress Polymer Letters*, 10(7): 587-597.
- ASTM D638M. (2014). Standard Test Method for Tensile Properties of Plastics. *Annual Book of ASTM Standards*, 1-15
- ASTM D790. (2011). Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials. *Annual Book of ASTM Standards*, 1-11.
- ASTM D256. (2010). Standard Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics. *Annual Book of ASTM Standards*, 1–20.
- ASTM International. (1999). ASTM D 570 – 98 – Standard Test Method for Water Absorption of Plastics. *ASTM International*, 16, 1–4.
- Atalla UP, and Agarwal RH (2010). “Vibrational Spectroscopy”, In: Lignin and Lignans: Advances in Chemistry, Heitner C, Dimmel D and Schimdt JA (Eds), Taylor & Francis.
- Azouz, K.B., Ramires, E.C., Fonteyne, W.V.D., El Kissi, N., Dufresne, A. (2012). Simple Method for the Melt Extrusion of a Cellulose Nanocrystals Reinforced Hydrophobic Polymer. *ACS Macro Letters*, 1: 236-240.
- Azwa, Z.N., and Yousif, B.F. (2013). Thermal Degradation Study of Kenaf /Epoxy Composites Using Thermo Gravimetric Analysis. *3<sup>rd</sup> Malaysian Postgraduate Conference (MPC2013)*, 16: 256-264.

- Babatunde, O.E., Jamaluddin, M.Y., Ishak, M.Y., Masoud, R., and Meisam, R. (2015). Potentials of Kenaf in Bio-Composite Production: A Review. *Jurnal Teknologi*, 77(12): 23-30.
- Baiardo M, Zaini E and Scandola M. (2004). Flax Fiberpolyester Composites. *Composites Part A*, 35: 703-710.
- Basu, G., and Roy, A. N. (2007). Blending of Jute with Different Natural Fibres. *Journal of Natural Fibres*, 4(4): 13–29.
- Bharath, V.R.R, Ramnath B.V., Manoharan, N. (2015). Kenaf Fibre Reinforced Composites: A Review. *ARPJ Journal of Engineering and Applied Science*, 30: 5483-5485
- Bismarck A, Mishra S, Lampke T. (2005). Plant Fibres as Reinforcement for Green Composites. In Mohanty AK, Mishra M, Drzal LT (Eds). *Natural Fibers Biopolymer and Biocomposites*. Boca Raton (FL): CRC Press.
- Bledzki AK, Reihmane S, Gassan J. (1996). Properties and Modification Methods for Vegetables Fibres for Natural Fibre Composites. *Applied Polymer Science*, 59: 1329-1336
- Brinchi, L., Cotana, F., Fortunati, E., and Kenny, J.M. (2013). Production of Nanocrystalline Cellulose from Lignocellulosic Biomass: Technology and Application. *Carbohydrate Polymers*, 94: 154-169.
- Cao Y, Sakamoto S, and Goda K. (2007). Effect of Heat and Alkali Treatments on Mechanical Properties of Kenaf Fibers. *Proceedings of 16<sup>th</sup> International Conference on Composites Materials*, Kyoto Japan, pp. 1-4
- Cazacu, G., Pascu, M. C., Profire, L., Kowarski, A. I., Mihaes, M., & Vasile, C. (2004). Lignin role in a complex polyolefin blend. In *Industrial Crops and Products*. <https://doi.org/10.1016/j.indcrop.2004.04.030>
- Chan, C.H., Chia, C.H., Zakaria, S., Ahmad, I., Dufresne, A. (2013). Production and Characterization of Cellulose and Nanocrystalline cellulose from Kenaf Core Wood. *Bioresources*, 8(1): 785-794.
- Charles W and Bledsoe VK. (2001). Kenaf Yield Components and Plant Composition. *National Symposium on New Crops and New Uses*. Sunnyville Avenue, USA.
- Charles W, Charles R, Robert B, and Judy B. (1998). Production Properties of Industrial Grade Kenaf Particleboard. USDA National Agricultural Library.
- Chen P, Lu C, Yu Q, Gao Y, Li J, Li X. 2006. Influence of fibre wettability on the interfacial adhesion of continuous fibre-reinforced PPESK composite. *J Appl Polym Sci*, 102(3):2544–51.

- Cheburini, F., Bird, N.D., Cowie, A., Jungmeier, G., Schlamadinger, B., and Woess-Gallasch, S. (2009). Energy- and Greenhouse Gas Based LCA of Biofuels and Bioenergy Systems: Key Issues, Ranges, and Recommendations. *Resources, Conservation, & Recycling*, 53: 34-447.
- Chirayil, Cintil Jose, Lovely Mathew, and Sabu Thomas. 2014. "Review of Recent Research in Nano Cellulose Preparation from Different Lignocellulosic Fibers." *Reviews on Advanced Materials Science* 37 (1-2): 20-28
- Chui-gen, G. uo, Yong-ming, S., Qing-wen, W., & Chang-sheng, S. (2006). Dynamic-mechanical analysis and SEM morphology of wood flour / polypropylene composites. *Journal of Forestry Research*, 17(4), 315-318.  
<https://doi.org/10.1007/s11676-006-0072-7>
- Corrales, F., Vilaseca, F., Llop, M., Gironès, J., Méndez, J.A. And Mutjè, P. (2007). Chemical Modification of Jute Fibres for the Production of Green-Composites. *Journal of Hazardous Materials*, 144(3): 730-735.
- Corcione, C. E., & Frigione, M. (2012). Characterization of nanocomposites by thermal analysis. *Materials*, 5(12), 2960-2980. <https://doi.org/10.3390/ma5122960>
- Cruz, J.M., Domínguez, J.M., Domínguez, H., and Parajó, J.C. (2001). Antioxidant and antimicrobial effects of extracts from hydrolysates of lignocellulosic materials. *Journal of Agricultural and Food Chemistry* 49: 2459-2464.
- Davoodi MM, Sapuan, SM, Ahmad D, Ali A, Khalina A, and Jonoobi M. (2010). Mechanical Properties of Hybrid Kenaf /Glass Reinforced Epoxy Composites for Passenger Car Bumper Beam. *Materials and Design*, 31(10): 4927-4932.
- Digabel LF and Averous L. (2006). Effects of Lignin Content on the Properties of Lignocellulose-based Biocomposites. *Carbohydrate Polymer*, 1-9
- Doherty, W.O.S., Mousavioun, P., and Fellows, C.M. (2011). Value-adding to cellulosic ethanol: Lignin polymers. *Industrial Crops and Products* 33, 259-276.
- Dufresne A. (2013). Nanocellulose: a New Ageless Bionanomaterial. *Materials Today*. 16(6): 220-227
- Dunmade, I. (2013). Mechanical Properties of Renewable Materials: A Study on Alpaca Fibre. *International of Engineering Science Invention*. 2(3): 56-62.
- El-Shekeil, Y. A., Salit, M. S., Abdan, K., & Zainudin, E. S. (2011). Development of a new kenaf bast fiber-reinforced thermoplastic polyurethane composite. *BioResources*, 6(4), 4662-4672.
- El-Khaoulani, A., Arrakhiz, F.Z., Benmoussa, K., Bouhfid, R., and Qaiss, A. (2013). Mechanical and Thermal Properties of Polymer Composites Based on Natural Fibres: Moroccan Hemp Fibres/Polypropylene. *Materials and Design*. 49: 203-208.



- Espert A, Vilaplana F, Karlsson S. (2004). Comparison of Water Absorption in Natural Cellulosic Fibres from Wood and One Year Crops in Polypropylene Composites and it's Influence on their Mechanical Properties. *Composites Part A*. 35: 1267-1276
- Favier V, Chanzy H, Cavaille JY. (1995). Polymer Nanocomposites Reinforced by Cellulose Whiskers. *Macromolecules*. 28(18): 6365-6367
- Fiore V, Di Bella G and Valenza A. (2015). The Effect of Alkaline Treatment on Mechanical Properties of Kenaf Fibers and Their Epoxy Composites. *Composites Part B*. 68: 14-21.
- Frenando, A.I. (2013). Chapter 5: Environmental Aspects of Kenaf Production and Use. In Monti, A. and Alexopoulou, E. (Eds). *Kenaf: A Multi-Purpose Crop for Several Industrial Applications, Green Energy and Technology* (p.83- 104). London, UK: Springer-Verlag London.
- Frost and Sullivan, 27 November, 2012. High Value Opportunities for Lignin. Retrieved 26 April 2018. London.
- Gaikwad UV and Chaudhari AR. (2016). Lignin as an Advantageous Biopolymer in Today's Era. *International Journal of Research in Science and Engineering*. 326-333
- Gassan, J. And Bledzki, A.K. (1999). Possibilities for Improving the Mechanical Properties of Jute/Epoxy Composites by Alkali Treatment of Fibres. *Composites Science and Technology*. 59(9): 1303-1309.
- Goda, K., Sreekala, M.S., Gomes, A., Kaji, T. And Ohgi, J. (2006). Improvement Of Plant Based Natural Fibres for Toughening Green Composites—Effect of Load Application During Mercerization of Ramie Fibres. *Composites Part A: Applied Science and Manufacturing*. 37(12): 2213-2220
- Gregorova A, Cibulkova Z, Kosikova B, and Simon P. (2005). Stabilization Effect of Lignin in Polypropylene and Recycled Polypropylene. *Polymer Degradation and Stability*. 89: 553-558.
- Grogoriou A, Passialis C, Voulgaridis E. (2000). Experimental Particleboard from Kenaf Plantation Grown in Greece. *Holz als Roh-und Werkstoff*, 58: 309-314.
- Guo CG, Song YM, Wang QW and Shen CS. (2006). Dynamic Mechanical Analysis and SEM micrographs of Wood Flour/Polypropylene Composites. *Journal of Forestry Research*. 17(4): 315-318.
- Habibi Y, Cahnzy H, Vignon MR. (2006). TEMPO Mediated Surface Oxidation of Cellulose Whiskers. *Cellulose*. 13: 679-687.
- Hanisah SS, Chan CC, Chia CH, Sarani Z, Sharifah Nabihah SJ. (2015). Isolation and Fractionation of Cellulose Nanocrystals from Kenaf Core. *Sains Malaysiana*. 44(11): 1635-1642.

- Hatakeyama H and Hatakeyama T (2010). Lignin, Structure, Properties and Application. *Advances Polymer Science*. 232: 1-63.
- Henriksson, M., Henriksson, G., Berglund, L.A., and Lindström, T. (2007). An environmentally friendly method for enzyme-assisted preparation of microfibrillated cellulose (MFC) nanofibers. *European Polymer Journal*, 43: 3434–3441.
- Ho M-P, Wang H, Lee J-H, Ho C-K, Lau K-T, and Leng J (2012). Critical Factors on Manufacturing Processes of Natural Fibre Composites. *Composites Part B*. 43(8), 3549–3562.
- Hong, J., Yoon, S., Hwang, T., Oh., J., Lee., Y., and Nam., J. (2011). Effect of Filler Size and Its Bimodal Distribution for Highly Thermal-Conductivity Epoxy Composites. *18<sup>th</sup> International Conference on Composites Materials*.
- Huang S, Zhou L, Li MC, Wu Q, and Zhou D. (2017). Cellulose Nanocrystalline (CNCs) from Corn Stalk: Activation Energy Analysis. *Materials*, 10(80): 1-13.
- Hubbe, A., Rojas, O.J., Lucia, L.A., and Sain, M. (2008). Cellulosic Nanocomposites: A Review. *Bioresources.com*. 3(3): 929-980.
- Huner U. (2017). Comparison of Polypropylene Composites: The Effect of Coupling Agent on Mechanical Properties. *Journal of Science and Technology*. 7(2): 28 - 40
- Ilyas R.A, Sapuan SM, Sanyang ML, Ishak MR and Zainuddin ES. (2018). Nanocrystalline Cellulose as Reinforcement for Polymeric Matrix Nanocomposites and its Potential Application: A Review. *Current Analytical Chemistry*. 14: 1-23.
- Ilyas RA, Sapuan SM, and Ishak MR. (2018a). Isolation and Characterization of Nanocrystalline Cellulose from Sugar Palm Fibres (*Arenga Pinnata*). *Carbohydrate Polymers*. 181: 1038-1051.
- Islam MR and Beg MDH. (2010). Effect of Coupling Agent on Mechanical Properties of Composites from Kenaf and Recycled Polypropylene. *National Conference in Mechanical Engineering Research and Postgraduate Studies*, 871-875.
- Ismail, A., Hassan, A., Bakar, A.A. and Jawaid, M. (2013). Flame Retardancy and Mechanical Properties of Kenaf Filled Polypropylene (PP) Containing Ammonium Polyphosphate (APP). *Sains Malaysiana*. 42(4): 429-434.
- Islam M, Beg M and Mina M. (2014). Fibre Surface Modifications through Different Treatments with the Help of Design Expert Software for Natural Fibre-Based Biocomposites. *Journal of Composites Materials*. 48(15): 1887-1899.
- Izran K, Abdul Rashid AM, Mohd Nor MY, Khairul M, Zaidon A and Abood F. (2009b). Physical and Mechanical Properties of Flame Retardant Treated *Hibiscus cannibus* Particleboard. *Journal of Modern Applied Science*. 3(8): 1-8

- Izran K, Koh MP, Tan YE, Saimin B, Nordin P, Rosli MJ, and Naziffuad N. (2010). Physical and Mechanical Assessment of Fire Retardant – Treated *Shorea Macrophylla* and *Acacia mangium* Particleboards. *Journal of Modern Applied Science*. 4(7): 3-8
- Izran K, Zaidon A, Abdul Rashid AM, Abood F, Mohamad Jani S. (2009a). Fire Propagation and Strength Performance of Fire Retardant-Treated *Hibiscus cannibus L.* Particleboard. *Asian Journal of Applied Science*. 2: 446-455
- Izran K, Zaidon, A, Abdul Rashid AM, Abood F, Mohd Nor MY, Nor Yuziah MY, Mohd Zharif AT and Khairul M. (2009c). Potential of Flame Retardant Treated *Hibiscus cannibus* Particleboard as Furniture Input. *Poster at Seminar on Wooden Furniture Industry*, Forest Research Institute Malaysia.
- Jalaluddin H. (2001). Fibre Characteristic of Kenaf and Development of Kenaf Fibre Reinforced Plastic Composites for Industrial Application. In Proceeding of the First Technical Meeting on the National Kenaf Research Project. Serdang, Malaysia.
- Jawaid, M., and Abdul Khalil, H.P.S. (2011). Cellulosic/Synthetic Fibre Reinforced Polymer Hybrid Composites: A Review. *Carbohydrate Polymers*. 86: 1-18.
- John M.J. and Anandijiwala, R.D (2008). Recent Developments in Chemical Modification and Characterization of Natural Fibre-Reinforced Composites. *Polymer Composite*. 29(2): 187-207.
- Jonoobi M, Harun J, Mathew AP, Hussein MZ and Oksman K. (2010). Preparation of Cellulose Nanofibers with Hydrophobic Surface Characteristics. *Cellulose*. 17: 299-307.
- Jonoobi M, Harun J, Paridah MT, Zaini LH, SaifulAzry S, Davoodi M. (2010b). Characteristics of Nanofibers Extracted from Kenaf Core. *Bioresources*. 5(4): 2556-2266.
- Jonoobi M, Harun J, Shakeri A, Misra M, Oksman K. (2009). Chemical Composition, Crystallinity and Thermal Degradation of Bleached and Unbleached Kenaf Bast (*Hibiscus cannabinus*) Pulp and Nanofibers. *Bioresources*. 4(2): 626-639.
- Juhaida MF, Paridah MT, Mohd Hilmi M, Sarani Z, Mohamad Zaki AR and Jalaluddin H. (2009). Production of Polyurethane form Liquefied Kenaf (*Hibiscus cannibus L.*) Core for Wood Laminating Adhesive. *Master Thesis, Universiti Putra Malaysia, Serdang*.
- Kabir, M. M., Wang, H., Lau, K. T., & Cardona, F. (2012). Chemical treatments on plant-based natural fibre reinforced polymer composites: An overview. *Composites Part B: Engineering*, 43(7): 2883–2892.
- Karimi, S., Paridah, M.T., Karimi, A., Dufresne, A., and Abdulkhani, A. (2014). Kenaf Bast Cellulosic Fibers Hierarchy: A Comprehensive Approach from Micro to Nano. *Carbohydrate Polymer*. 101: 878-885.



- Karnani R, Krishnan M and Narayan R. (1997). Biofiber Reinforced Polypropylene Composites. *Polymer Engineering and Science*. 27(2): 476 – 484.
- Khalid M, Ranthnam CT, Luqman CA, Salmiaton A, Choong TSY, Jalaludin H. (2009). Thermal and Dynamic Mechanical Behaviour of Cellulose and Oil Palm Empty Fruit Bunch (OPEFB) – filled Polypropylene Biocomposites. *Journal of Polymer*. 49: 1244-1251.
- Khalil HPSA, Yusra AH, Bhat AH, and Jawaid M. (2010). Cell Wall Ultrastructure, Anatomy, Lignin Distribution and Chemical Composition of Malaysian Cultivated Kenaf Fibre. *Industrial Crops Product*. 31(1): 113-121.
- Khalil, HPSA, Y Davoudpour, N. a. Sri Aprilia, Asniza Mustapha, Sohrab Hossain, Nazrul Islam, and Rudi Dungani. (2014). “Nanocellulose-Based Polymer Nanocomposite: Isolation, Characterization and Applications.” In Vijay Thakur Kumar (Ed). *Nanocellulose Polymer Nanocomposites*. Scrivener Publishing LLC.
- Khoshkava V and Kamal MR (2014). Effect of Drying Conditions on Cellulose Nanocrystal (CNC) Agglomerate Porosity and Dispersibility in Polymer Nanocomposites. *Powder Technology*. 261: 288-298.
- Kim JH, Shim BS, Kim HS, Lee YJ, Min SK, Jang D, Abas Z and Kim J. (2015). Review of Nanocellulose for Sustainable Future Materials. *International Journal of Precision Engineering and Manufacturing Green Technology*, 2(2): 197-213.
- Klemm D, Friederike K, Moritz, S, Lidstrom T, Ankerfors M, Gray D and Dorris A. (2011). Nanocellulose: A New Family of Nature-Based Materials. *Angewandte Chemie International Edition*. 50 (24): 5438-5466.
- Ku, H., Wang, H., Pattarachaiyakop, N., and Trada, M. (2011). A Review on the Tensile Properties of Natural Fibre Reinforced Polymer Composites. *Composites: Part B*. 42: 856-873.
- Law, T. T., & Ishak, Z. A. M. (2010). Water Absorption and Dimensional Stability of Short Kenaf Fiber-Filled Polypropylene Composites Treated with Maleated Polypropylene. *Journal of Applied Polymer Science*, 120: 563–572.
- Lee CH, Sapuan SM, and Hassan MR. (2017). Mechanical and Thermal Properties of Kenaf Fiber Reinforced Polypropylene / Magnesium Hydroxide Composites. *Journal of Engineered FIners and Fabrics*. 12 (2): 50 – 58.
- Lee KY, Aitomaki Y, Berglund LA, Oksman K and Bismarck A. (2014). On the Use of Nanocellulose as Reinforcement in Polymer Matrix Composites. *Composites Science and Technology*. 105: 15-27.
- Lee HJ, Lee HK, Lim E and Song YS. (2015). Synergistic Effect of Lignin/Polypropylene as a Compatibilizer in Multiphase Eco-Composites. *Composites Science and Technology*. 118: 193-197
- Li R, Fei J, Cai Y, Feng J, Yao J. (2009). Cellulose Whiskers Extracted from Mulberry: A Novel Biomass Production. *Carbohydrate Polymers*. 76: 94-99

- Liang H and Hu X. (2016). A Quick Review of the Application of Nanocrystalline Cellulose in Wastewater Treatment. *Journal of Bioresources and Bioproducts*, 1(4): 199-204.
- Lim YM, Lee YM, Nho YC (2005). Preparation and Characterization of PH-sensitive Poly (ethylene oxide) Grafted Methacrylic Acid and Acrylic Acid Hydrogels by Gamma-Ray Irradiation. *Macromolecular Resource*. 13: 327-333
- Lin SY and Dence CW. (1992). Method in Lignin Chemistry. *Methods in Lignin Chemistry 578*. (Springer – Verlag Berlin Heidelberg).
- Lips, S.J.J., and Van Dam, J.E.G. (2013). Chapter 6: Kenaf Fiber Crop for Bioeconomic Industrial Development. In Monti, A. and Alexopoulou, E. (Eds.), *Kenaf: A Multi-Purpose Crop for Several Industrial Application*. Green Energy and Technology. London, UK: Springer-Verlag London.
- Liu ZT, Sun C, Liu ZW, Lu J. (2008). Adjustable Wettability of Methyl Methacrylate Modified Ramie Fibre. *J Appl Polym Sci*. 109(5): 2888–94.
- Loutid, F., Bonnoud, L., Elaxandre, M., Cuesta, J.M.L., & Dubois, PP. (2009). New Prospect in Flame Retardant Polymer Materials: From Fundamental to Nanocomposites. *Materials Science and Engineering R*. 63: 100-125.
- Ludueno L, Fasce D, Alvarez A, and Stefani P.M (2011). Nanocellulose from Rice Husk Following by Alkaline Treatment to Remove Silica. *Bioresources*. 6(2): 1440-1453
- Luo S, Cao J, and Sun W. (2015). Evaluation of Kraft Lignin as Natural Compatibilizer in Wood Flour/Polypropylene Composites. *Polymer Composites*. 38(11): 2387-2394
- Mahardika M, Abral H, Kasim A, Arief S, and Asrofi M. (2018). Production of Nanocellulose from Pineapple Leaf Fibers via High-Shear Homogenization and Ultrasonication. *Fibers*. 6(28): 1-12.
- Mahfuz H, Adnan A, Rangari VK, and Jeelani S. (2005). Manufacturing and Characterization of Carbon Nanotube/Polyethylene Composites. *International Journal of Nanoscience*. 4(1): 55-72.
- Mahjoub R, Yatim JM, Mohd Sam AR, Hashemi SH. (2014). Tensile Properties of Kenaf Fibre due to Various Conditions of Chemical Fibres Surface Modifications. *Construction Build Materials*. 55: 103-113
- Majeed K, Jawaid M, Hassam A, Abu Bakar A, Abdul Khalil HPS, Salema AA, Inuwa I. (2003). Potential Materials for Food Packaging from Nanoclay/Natural Fibers Filled Hybrid Composites. *Mater. Des*. 46: 391-410.
- Malkapuram R, Kumar V, Yuvraj SN. (2008). Recent Development in Natural Fiber Reinforced Polypropylene Composites. *Journal of Reinforce Plastic Composites*. 28: 1196-1189

- Mandal A and Chakrabarty D. (2011). Isolation of Nanocellulose from Waste Sugarcane Bagasse (SCB) and Its Characterization. *Carbohydrate Polymers*.86 (3): 1291-1299.
- Mariano M, El Kissi N, and Dufresne A. (2015). Melt Processing of Cellulose Nanocrystals Reinforced Polycarbonate from Masterbatch Process. *European Polymer Journal*. 69: 208-223.
- Mazuki AAM, Akil HM, Safiee S, Ishak ZAM and Bakar AA. (2011). Degradation of Dynamic Mechanical Properties of Pultruded Kenaf Fibre Reinforced Composites after Immersion in Various Solution. *Composites Part B: Engineering*. 42(1): 71-76
- McCarthy JL and Islam A. (2000). In Lignin: Historical, Biological and Materials Perspectives. In Glasser WG, Northey RA, Shultz TP (Eds). Oxford University Press: Washington DC.
- Methacanon P, Weerawatsophon U, Sumransin N, Prahsarn C, Bergado D. (2010). Properties and Potential Application of the Selected Natural Fibres as Limited Life Geotextiles. *Carbohydrate Polymer*. 82: 1090-1096
- Misra, S., Misra, M., Tripathy, S.S., Nayak, S.K. And Mohanty, A.K. (2002). The Influence of Chemical Surface Modification on the Performance of Sisal-Polyester Biocomposites. *Polymer Composites*. 23(2): 164-170.
- Mirjalili, F., Chuah, L., & Salahi, E. (2014). Mechanical and Morphological Properties of Polypropylene / Nano  $\alpha$ -Al<sub>2</sub>O<sub>3</sub> Composites. *The Scientific World Journal*. ID 718765: 1-12.
- Mofokeng JP, Luyt AS, Tabi T and Kovacs J. (2011). Comparison of Injection Moulded, Natural Fibre-Reinforced Composites with PP and PLA as matrices. *Journal of Thermoplastic Composites Material*. 25(8): 927-948.
- Mohamed A, Bhardwaj H, Hamama A, Webber C. (1995). Chemical Composition of Kenaf (*Hibiscus cannibus L.*) Seed Oil. *Industrial Crops Products*. 4: 157-165.
- Mohammed L, Ansari MNM, Pua G, Jawaid M, Saiful Islam M. (2015). A Review on Natural Fiber Reinforced Polymer Composites and Its Application. *International Journal of Polymer Science*. 1-15.
- Mohanty AK, Misra M, and Hinrichsen G. (2000). Biofibers, Biodegradable Polymer and Biocomposites: An Overview. *Macromolecule Materials Engineering*. 276/277: 1-24.
- Mohanty, A.K., Misra, M., and Drzal, L.T. (2005). Natural Fibers, Biopolymers and their Biocomposites. CRC Press: Boca Raton.
- Mohd Shamsudin N.A., Suzana Y., Ibrahim W.A., Bokhari A., and Lai F.C. (2015). Oil Extraction from *Colaphyllum Inophyllum L.* via Soxhlet Extraction Optimization Using Response Surface Methodology (RSM). *Conference: Control Conference (ASCC), Kota Kinabalu*. 10.1109/ASCC.2015.7244791

- Monteiro, S.N., Calado, V., Rodriguez, R.J.S., Margem, F.M. (2012). Thermogravimetric Stability of Polymer Composites Reinforced with Less Common Lignocellulosic Fibres – an Overview. *Journal of Materials Research and Technology*. 1(2): 117-126.
- Moon RJ, Schueneman GT, and Simonsen J. (2016). Overview of Cellulose Nanomaterials, their Capabilities and Application. *JOM* 68(9), 2383 – 2394.
- Morais TE, Correa A, Manzoli A, Lima LF and Mattoso. (2010). Cellulose Nanofibers from White and Naturally Colored Cotton Fibers. *Cellulose*. 17(3): 595-606.
- Moran JI, Alvarez VA, Cyras VP, and Vazquez A. (2008). Extraction of Cellulose and Preparation of Nanocellulose from Sisal Fibers. *Cellulose*. 15: 149-159.
- Morandim-Gianetti AA, Agnelli JAM, Lancas BZ, Magnabosco R, Casarin SA, Bettini SHP. (2012). Lignin as Additive in Polypropylene/Coir Composites: Thermal, Mechanical and Morphological Properties. *Carbohydrate Polymers*. 87: 2563-2568
- Mosier, N., Wyman, C., Dale, B., Elander, R., Lee, Y.Y., Holtzapple, M., Ladisch, M., 2005. Features of promising technologies for pretreatment of lignocellulosic biomass. *Bioresource Technol.*, 96: 673.
- Mwaikambo, L.Y. And Ansell, M.P. (2003). Hemp fibre reinforced cashew nut shell liquid composites. *Composites Science and Technology*, 63(9): 1297-1305.
- Nishimura N, Izumi A and Kuroda KI. (2002). Structural Characterization of Kenaf Lignin: Differences among Kenaf Varieties. *Industrial Crops and Products*. 15(2): 115-122.
- Nikmatin S, Syafiuddin A, Ahmad BHK, and Maddu A. Physical, Thermal and Mechanical Properties of Polypropylene Composites Filled with Rattan Nanoparticles. *Journal of Applied Research and Technology*. 15: 386-395.
- Nosbi, N., Ishak, Z. a M., & Bakar, a A. (2009). Water Absorption Behavior of Pultruded Kenaf Fiber Reinforced Unsaturated Polyester Composites and Its Effects on. *ICCM International Conferences on Composite Materials*, (D), 1–9.
- Nor Hafizah Ab. Wahab, Paridah Md. Tahir, Yeoh Beng Hoong, Zaidon Ashaari, Nor Yuziah Mohd Yunus, Mohd Khairun Anwar Uyup, and Mohd Hamami Shahri. (2012). Adhesion Characteristics of Phenol Formaldehyde Pre-Preg Oil Palm Stem Veneers. *BioResources*. 7(4): 4545-4562.
- Norshahida S, Hanafi I, Zuraida A. (2013). The Effect of Kenaf Core Fibre Loading on Properties of Low Density Polyethylene /Thermoplastic Sago Starch/ Kenaf Core Fiber Composites. *Journal of Physical Science*. 24(2): 97-113
- Pääkko, M., Ankerfors, M., Kosonen, H., Nykänen, A., Ahola, S., Österberg, M., Ruokolainen, J., Laine, J., Larsson, P.T., Ikkala, O., et al. (2007). Enzymatic Hydrolysis Combined with Mechanical Shearing and High-Pressure

Homogenization for Nanoscale Cellulose Fibrils and Strong Gels. *Biomacromolecules*, 8: 1934–1941.

Pan M, Zhou X and Chen M. (2013). Cellulose Nano-whiskers Isolation and Properties from Acid Hydrolysis Combined with High Pressure Homogenization. *Bioresources.com*. 8(1): 933-943.

Pasquini D, Teixeira E de M, Curvelo AA da S, Belgacem MN, and Dufresne A. (2010). Extraction of Cellulose Whiskers from Cassava Baggase and their Applications as Reinforcing Agent in Natural Rubber. *Industrial Crops and Products*, 32(3): 486-490.

Paul SA, Boudenne A, Ibos L, Candau Y, Joseph K and Thomas S. (2008). Effect of Fiber Loading and Chemical Treatments on the Thermophysical Properties of Banana Fiber/Polypropylene Commingled Composites Materials. *Composites: Part A*. 39: 1582-1588.

Pawar SN, Venditti RA, Jameel H, Chang HM and Ayoub A. (2016). Engineering Physical and Chemical Properties of Softwood Kraft Lignin b Fatty Acid. *Industrial Crops and Products*. 89: 128-134

Pejic, B. M., Kostic, M. M., Skundric, P. D., & Praskalo, J. Z. (2008). The effects of hemicelluloses and lignin removal on water uptake behavior of hemp fibers. *Bioresource Technology*, 99(15): 7152–7159.

Peng BL, Dhar N, Liu HL and Tam KC. (2011). Chemistry and Application of Nanocrystalline Cellulose and Its Derivatives: A Nanotechnology Perspective. *The Canadian Journal of Chemical Engineering*. 89: 1191-1206.

Pickering, K.L. Aruan Efendy, M.G., and Le, T.M. (2016). A Review of Recent Developments in Natural Fibre Composites and Their Mechanical Performance. *Composite: Part A*.

Poletto M, Ornaghi Jr. HL, and Zattera AJ. (2014). Native Cellulose: Structure, Characterization and Thermal Properties. *Materials*. 7: 6105 – 6119.

Rahman, M.R., Huque, M.M., Islam, M.N. And Hasan, M. (2008). Improvement Of Physico-Mechanical Properties of Jute Fibre Reinforced Polypropylene Composites By Post-Treatment. *Composites Part A: Applied Science and Manufacturing*. 39(11): 1739-1747.

Ramesh M, Palanikumar K, Hemachandra Reddy K. (2013). Comparative Evaluation on Properties of Hybrid Glass Fibre Sisal/Jute Reinforced Epoxy Composites. *Process Engineering*. 51: 745-750

Ramesh M, Palanikumar K, Hemachandra Reddy K. (2013b). Mechanical Property Evaluation of Sisal-Jute-Glass Fibre Reinforced Polyester Composites. *Composites Part B*. 48: 1-9

Ramesh M. (2016). Kenaf (*Hibiscus cannibus L.*) Fibre Based Biomaterials: A Review on processing and Properties. *Progress in Materials Science*. 78-79: 1-92



- Rasha MS, Kargarzadeh H, and Abdullah I. (2015). Effect of Silane Surface Treatment of Cellulose Nanocrystals on the Tensile Properties of Cellulose-Polyvinyl Chloride Nanocomposites. *Sains Malaysiana*. 44(6): 801-810.
- Rault, F., Giraud, S., Salaun, F., and Almeras, X. (2015). Development of a Halogen Free Flame Retardant Masterbatch for Polypropylene s. *Polymers*. 7: 220-234
- Razak, NIA, Ibrahim NA, Zainuddin N, Rayung M and Saad WZ. (2014). The Influence of Chemical Modifications of Kenaf Fibre Using Hydrogen Peroxide on the Mechanical Properties of Biodegradable Kenaf Fiber/poly (Lactic Acid) Composites. *Molecules*. 19(3): 2957-2958.
- Reti, C., Casetta, M., Duquesne, S., Bourbigot, S., Delobel, R., 2008. Flammability properties of intumescent PLA including starch and lignin. *Polym. Adv. Technol.*, 19: 628.
- Rodriguez NLG, Thielemans W. and Dufresne A. (2006) Sisal Cellulose Whiskers Reinforced Polyvinyl Acetate Nanocomposites, *Cellulose*, 13(3): 261-270.
- Rosa MF, Medeiros ES, Malmonge JA, Gregorski KS, Wood DF, Mattoso LHC, Glenn G, Orts WJ, and Imam SH. (2010). Cellulos Nanowhiskers from Coconut Husk Fibers: Effect of Preparation Conditions on their Thermal and Morphological Behaviour. *Carbohydrate Polymers*. 81(1): 83-92.
- Rowell MR. (1995). A New Generation of Composites Materials from Agro-Based Fibre. In Prasad PN (Eds). *Polymers and Other Advanced Materials; Emerging Technologies and Business Opportunities*. New York, NY: Plenum Press.
- Roman, M., and Winter, W.T. (2004). Effect of sulfate groups from sulfuric acid hydrolysis on the thermal degradation behavior of bacterial cellulose. *Biomacromolecules* 5: 1671–1677.
- Rozman, H. D., Tan, K. W., Kumar, R. N., Abubakar, A., Mohd. Ishak, Z. A., & Ismail, H. (2000). The effect of lignin as a compatibilizer on the physical properties of coconut fiber–polypropylene composites. *European Polymer Journal*, 36(7): 1483–1494.
- Saad MJ. (2010). Effect of Maleated Polypropylene (MAPP) on the Tensile, Impact and Thickness Swelling Properties of Kenaf Core-Polypropylene Composites. *Journal of Science and Technology, UTHM*. 2(1): 32-44
- Saad MJ. (2012). The Effect of Maleated Polypropylene (MAPP) on the Mechanical Properties of Kenaf Core Polypropylene Composites. *Journal of Sustainable Science Management*. 7: 49-55.
- Saad MJ and Izran K. (2011). Mechanical and Physical Properties of Low Density Kenaf Core Particleboards Bonded with Different Resins. *Journal of Science and Technology*. 17-32.
- Saad MJ and Izran K. (2012). Kenaf Core Particleboard and Its Sound Absorbing Properties. *Journal of Science and Technology*. 4(2): 23-34

- Saba, N., Paridah, M.T., Jawaid, M. (2015). Mechanical Properties of Kenaf Reinforced Polymer Composites: A Review. *Construction and Building Materials*. 76: 87-96.
- Saba N, Paridah MT, Abdan K, Ibrahim NA (2016). Dynamic Mechanical Properties of Oil Palm Filler/Kenaf/Epoxy Hybrid Nanocomposites. *Constructions and Building Materials*. 124: 133-138.
- Saiful Islam M, Nur Atiqah H, Hasan M, Talib ZA, Jawaid M, Mohamad Haafiz MK. (2015). Physical, Mechanical, and Biodegradable Properties of Kenaf /Coir Hybrid Fiber Reinforced Polymer Composites. *Materials Today Communications*. 4: 69-76
- Sabharwal HS, Akhtar M, Blanchette RA and Young RA. (1994). Biological Pulping of Kenaf. *Tappi Journal*. 77: 105-112.
- Saito T, Hirota M, Tamura N, Kimura S, Fukuzumi H, Heux L and Isogai A. (2009). Individualization of Nanosized Plant Cellulose Fibrils by Direct Surface Carboxylation using TEMPO catalyst under Neutral Conditions. *Biomacromolecules*. 10(7): 1992-1996.
- Salas, C., Nypelo, T., Rodriguez-Abreu, C., Carrillo, C., and Rojas, O.J. (2014). Nanocellulose Properties and Application in Colloids and Interfaces. *Current Opinion in Colloid and Interfaces Science*. 19: 383-396.
- Sanadi AR, Caulfield DF, Jacobson RE and Rowell RM. (1995). Renewable Agricultural Fibres as Reinforcing Fillers in Plastics: Mechanical Properties of Kenaf Fiber-Polypropylene Composites. *I&EC Research*. 34: 1889-1896.
- Sarifuddin N, Ismail H and Zuraida A. (2013). The Effect of Kenaf Core Fiber Loading on Properties of Low Density Polyethylene/Thermoplastic Sago Starch/Kenaf Core Fiber Composites. *Journal of Physical Science*. 24(2): 97-115.
- Seyed Fariborz H.D., Paridah M.T., Madsen B., Jawaid M., Majid D.L., Brancheriau L, Juliana A.H. (2016). Volumetric Composition And Shear Strength Evaluation Of Pultruded Hybrid Kenaf/Glass Fibre Composites. *Journal of Composite Materials*.
- Shakhes J, Zenaly F, Marandi M, and Saghafi T. (2011). The Effect of Processing Variables on the Soda and Soda – AQ Pulping of Kenaf Bast Fiber. *Bioresources.com*. 6(4): 4626 – 4639.
- Shankar, S., Reddy, J. P., & Rhim, J. W. (2015). Effect of lignin on water vapor barrier, mechanical, and structural properties of agar/lignin composite films. *International Journal of Biological Macromolecules*, 81: 267–273.
- Shaba MJ, Leman Z, Sultan MTH, Ishak MR, Azmah Hanim MA, Jelen A. (2016). Kenaf Fibre Reinforced Composites: A Review. *Carbohydrate Polymers*, 2(1): 88-104.

- Sheikkarim AR. (2000). Properties of Particle Based Panels from Kenaf, Wood, and Sugarcane Residues Bonded with Modified Adhesive System. MS Dissertation, p. 10-41. Louisiana State University Library, Baton Rouge, LA
- Shubhra QTH, Alam AKMM and Quaiyyum MA. (2013). Mechanical Properties of Polypropylene Composites: A Review. *Journal of Thermoplastic Composite Material*. 26(3): 62-391.
- Silva, F.D.A., Chawla, N. And Filho, R.D.D.T., (2008). Tensile Behavior Of High Performance Natural (Sisal) Fibres. *Composites Science and Technology*. 68(15-16): 3438-3443
- Smook, G.A., (2002). Handbook for Pulp and Paper Technologies. 3rd Edition ed. Angus
- Socrates, G. (2004). Infrared and Raman Characteristic Group Frequencies: Tables and Charts (Third Edition). John Wiley and Sons ltd, United Kingdom, England.
- Spear, S.K., Holbrey, J.D., Roger, R.D., 2002. *J. Am. Chem. Soc.*, 124, 4874.
- Sreekumar P, Thomas SP, Saifer JM, Joseph K, Unnikrishnan G, Thomas S. (2009). Effect of the Surface Modification on the Mechanical and Water Absorption Characteristics of Sisal/Polyester Composites Fabricated by Resin Transfer Molding. *Composites Part A*. 40: 1777-1784
- Suharty N, Ismail H, Diharjo K, Handayani DS, and Firdaus M. (2016). Effect of Kenaf Fiber as a Reinforcement on the Tensile, Flexural Strength and Impact Toughness Properties of Recycled Polypropylene/Halloysite Composites.
- Summerscales, J., Dissanayake, N.P.J., Virk, A.S., and Hall, W. (2010). A Review of Bast Fibres and Their Composites. Part 1- Fibres as Reinforcement. *Composite Part A: Applied Science and Manufacturing*,.41(10): 1329-1335.
- Swamy R, Kumar GM, Vrushabhendrapa Y, Joseph V. (2004). Study of Areca Reinforced Phenol Formaldehyde Composites. *Journal of Reinforced Plastic Composites*. 23: 1373-1382
- Swatloski, R.P., Rogers, D., Holbery, J.D., 2003. *WO 2003 029 329*.
- Tahir, P.M., Amel, B.A., Syeed, O.A.S., and Zakiah, A. (2011). Retting Process of Some Bast Plants and Its Effect on Fiber Quality: A Review. *Bioresources*. 6(4): 5260-5281.
- TAPPI. (1999). Kappa Number of Pulp, T236 om-99. TAPPI.
- Thi Bach TL, Keko H, and Kenji I. (2003). Structural Characteristics of Cell Walls of Kenaf (*Hibiscus cannibus L.*) and Fixation of Carbon Dioxide. *Journal of Wood Science*. 49: 255-261.
- Thielemans W, Can E, Morye SS and Woll RP. (2001). Novel Applications of Lignin in Composites Materials. *Journal of Applied Polymer Science*. 83: 323-331.



- Toh, K., Nakano, S., Yokoyama, H., Ebe, K., Gotoh, K., Noda, H., 2005. Anti-deterioration effect of lignin as an ultraviolet absorbent in polypropylene and polyethylene. *Polym. J. (Tokyo, Jpn.)*, 37: 633.
- Tsoumis G. (1991). Science and Technology of Wood Structure, Properties, Utilization. Van Nostrand Reinhold.
- Ugartondo, V., Mitjans, M., Vinardell, M.P., 2008. Comparative antioxidant and cytotoxic effects of lignins from different sources. *Bioresour. Technol.*, 99: 6683.
- Van de Velde K and Kiekens P (2001). Thermoplastic Pultrusion of Natural Fiber Reinforced Composites. *Composite Structure*. 54: 355-360.
- Ververis C, Georghio K, Christodoulakis N, Santas P, and Santas R. (2004). Fiber Dimensions, Lignin, and Cellulose Content of Various Plant Materials and Their Suitability for Paper Production. *Industrial Crops and Products*. 19(3): 245-254.
- Visakh PM and Thomas S. (2010). Preparation of Bionanomaterials and Their Polymer Nanocomposites from Waste and Biomass. *Waste Biomass Valor*. 1: 121-134.
- Wang N, Ding E and Cheng R. (2007). Thermal Degradation Behaviours of Spherical Cellulose Nanocrystals with Sulfate Group. *Polymer*. 48: 3486 – 3493.
- Wambua P, Ivens J, and Verpoest I.(2003). Natural Fibres: Can They Replace Glass Fibre Reinforced Plastics? *Composites Sciences Technology*. 63: 1259- 1264.
- Watkins D, Nuruddin M, Hosur M, Tcherbi-Narteh A, and Jeelani S. (2015). Extraction and Characterization of Lignin from Different Biomass Resources. *Journal of Materials Research and Technology*. 4(1): 26-32.
- Wu, C. M., Lai, W. Y., & Wang, C. Y. (2016). Effects of surface modification on the mechanical properties of flax/ $\beta$ -polypropylene composites. *Materials*, 9(5): 1–11.
- Xing W, Yuan H, Zhang P, Yang H, Song L and Hu Y. (2013)/ Functionalized Lignin for Halogen- Free Flame Retardant Rigid Polyurethane Foam: Preparation, thermal Stability, Fire Performance and Mechanical Properties. *J Polym Res*. 20: 234- 246
- Xu X, Wu Q and Zhou D. (2013). Influence of Layered Structure on Physical and Mechanical Properties of Kenaf Core Particleboard. *Bioresource*. 8(4): 5219-5234.
- Xu X, He Z, Lu S, Guo D and Yu J. (2014). Enhanced Thermal and Mechanical Properties of Lignin/Polypropylene Wood-Plastic Composites by Using Flexible Segment- Containing Reactive Compatibilizer. *Macromolecular Research*, 22(10): 1084 – 1089.
- Yang H, Yang R, Chen H, Lee DH, and Zheng C. (2007). Characteristic of Hemicellulose, Cellulose and Lignin Pyrolysis. *Fuel*. 86: 1781-1788.

- Yi S, Xu S, Fang Y, Wang H, and Wang Q. (2017). Effects of Matrix Modification on the mechanical Properties of Wood-Polypropylene Composites. *Polymers*. 9(17): 1-13.
- Yu M, Yang R, Huang L, Cao X, Yang F, and Liu D. (2012). Preparation and Characterization of Bamboo Nanocrystalline Cellulose. *Bioresources.com*. 7(2): 1802-1812.
- Zaini L.H., Jonoobi M., Paridah M.T., Karimi S. (2013). Isolation and Characterization of Cellulose Whiskers from Kenaf (*Hibiscus cannabinus L.*) Bast Fiber. *Journal of Biomaterials and Nanobiotechnology*. 4: 37-44.
- Zaini, L.H., Paridah M.T., Jawaid M., Othman, A.Y., and Juliana A.H. (2015). Effect of Kenaf Cellulose Whiskers on Cellulose Acetate Butyrate Nanocomposites Properties. In Vijay Kumar Thakur (Ed). *Nanocellulose Polymer Nanocomposites*. Scrivener Publishing LLC.
- Zainuddin, N., Ahmad, I., Kargarzadeh, H., & Ramli, S. (2017). Hydrophobic kenaf nanocrystalline cellulose for the binding of curcumin. *Carbohydrate Polymers*, 163: 261–269.
- Zakaria R, Abu Bakar S, Norhamidi M, Che Hassan CH, Mohd Khairol Fadzly MR, Dulina T, Izdihar T and Nur Farhani I. (2018). The Effect of Maleic Anhydride Grafted PP (MAPP) on the Mechanical Properties of Injection Moulded Kenaf/CNT/PP Composites. *Sains Malaysiana*. 47(6): 1285-1291.
- Zampaloni, M., Pourboghraat, F., Yankovich, S.A., Rodgers, B.N., Moore, J., Drzal, L.T., Mohanty, A.K. And Misra, M., (2007). Kenaf Natural Fibre Reinforced Polypropylene Composites: A Discussion On Manufacturing Problems And Solutions. *Composites Part A: Applied Science and Manufacturing*. 38(6): 1569-1580.
- Zhou X, Yu Y, Lin Q, and Chen L. (2013). Effects on Maleic Anhydride Grafted Polypropylene (MAPP) on the Physico-Mechanical Properties and Rheological Behaviour of Bamboo Powder – Polypropylene Foamed Composites. *Bioresources*. 8(4): 6263 – 6279.
- Ziaei Tabari H, Nourbakhsh A, Hosseinpourpia R and Danesh MA. (2011). Evaluation of Mechanical and Morphological Behaviour of Polypropylene / Wood Fiber Nanocomposites Prepared by Melts Compounding. *International Conference on Nanotechnology and Biosensors, 28<sup>th</sup> – 30<sup>th</sup> December 2010, Hong Kong*. 2: 20-23.