

Characterisation of Physicochemical Properties of Propionylated Corn Starch and Its Application as Stabiliser

Lee-Fen Hong¹, Lai-Hoong Cheng², Chong Yew Lee¹ and Kok Khiang Peh^{1*}

¹School of Pharmaceutical Sciences, Universiti Sains Malaysia, USM, 11800 Minden, Penang, Malaysia

²Food Technology Division, School of Industrial Technology, Universiti Sains Malaysia, USM, 11800 Minden, Penang, Malaysia

Received: September 20, 2014

Accepted: May 13, 2015

Summary

A series of propionylated starches with different degrees of substitution (DS) was synthesised and their physicochemical properties and application as a stabiliser were investigated. Starch propionates with moderate DS were prepared by esterification of native corn starch with propionic anhydride. By varying the reaction times of the esterification process, twelve starch propionates with DS of 0.47 to 0.94 were prepared. FTIR and NMR confirmed the introduction of propionyl groups to the starch. X-ray diffraction pattern showed reduced crystallinity in the starch propionates. The contact angle was found to increase proportionately with the increase in DS. Swelling power results showed that starch propionates were able to swell more than native corn starch at low temperature (40 °C). Oil-in-water (O/W) emulsions prepared using starch propionates (DS of 0.64 to 0.86) showed exceptional stability when challenged by centrifugation stress test. These stable O/W emulsions had viscosities in the range of 1236.7–3330.0 mPa·s. In conclusion, moderately substituted short-chain (propionylated) starches could be a promising cold swelling starch, thickener and O/W emulsion stabiliser in food, pharmaceutical and cosmetic industries.

Key words: starch propionate, degree of substitution, physicochemical properties, oil-in-water emulsion, stabiliser

Introduction

Plenty of work has been done to expand the usefulness and versatility of starch as a property-enhancing material in food. Modification of starch by means of esterification provides ample opportunities to alter the physicochemical properties of macromolecules. Starch esters exhibit unique properties, namely lower gelatinization temperature, lower retrogradation and lower tendency to form gels (1) as well as enhanced hydrophobic properties (2,3) when compared to the native counterpart. These unique properties make starch esters suitable for use in refrigerated and frozen foods and as an emulsion stabiliser and encapsulating agent. Two common starch esters used in

foods are acetylated starch and octenyl succinic (OS) starch. Acetylated starch is prepared with short-chain (C2) while octenyl succinylated starch with medium-chain (C12) fatty acids. Owing to the different fatty acid chain lengths, acetylated and OS starch showed different properties, especially emulsion stabilising and encapsulating properties. Comparatively, OS starch showed much better emulsion stabilising and encapsulating properties when compared to acetylated starch (4).

From a nutritional point of view, acetylated starch appeared to be resistant (3,5). The nondigestible starch fraction was found to be able to reduce postprandial blood glucose and insulin concentration (6), which helps to

*Corresponding author: Phone: +604 654 2257; Fax: +604 657 0017; E-mail: kkepeh@usm.my, kkepeh@gmail.com

maintain a healthy glycemic profile. Anison *et al.* (5) reported that acylated starch survived intestinal passage and produced short-chain fatty acids from bacterial fermentation in the large bowel. The reduction of colonic pH by short-chain fatty acids was found to promote colonic health (7,8). *In vitro* or *in vivo* studies also showed that different short-chain fatty acid profiles were produced when different resistant starch ester was used. Ferguson and Jones (9) conducted an *in vitro* fermentation on OS starch and showed that it released the highest amount of butyric acid among other short-chain fatty acids. The release of propionate was found to be interesting as it has been linked to the reduction of cholesterol in serum and liver in rats (10). Animal study revealed that propionate released in caecal digesta was 95.6 μmol from starch propionate, 41.2 μmol from starch acetate, 36.3 μmol from starch butyrate and 12.1 μmol from control starch (5).

Despite the health benefits of starch propionate, not much study, however, has been conducted on the characterisation of moderately substituted starch propionate. In this paper, we present a simple method to prepare starch propionate using propionic anhydride and sodium hydroxide as catalyst. Physicochemical properties of starch propionates were then characterised. The potential of starch propionates as a stabiliser was also evaluated.

Materials and Methods

Raw materials

Native corn starch (20.2 % amylose and 79.8 % amylopectin) was purchased from Zhucheng Xingmao Corn Developing Company (Shandong, PR China). Propionate anhydride was obtained from Merck (Kenilworth, NJ, USA). Olive pomace oil was purchased from Basso Fedele and Figli Srl (San Michele di Serino, AV, Italy). Ethanol, 99.7 %, was purchased from QR&C (Chonburi, Thailand). Iodine and potassium iodide were obtained from Sigma-Aldrich (St. Louis, MO, USA). All other reagents used were of analytical reagent grade.

Preparation of starch propionate using alkaline catalyst

A mass of 140 g of corn starch (0.864 mol of anhydroglucose unit) was stirred with 674.8 g (5.185 mol) of propionic anhydride in 2-litre Schott bottle for 5 min in a water bath maintained at 30 °C. The catalyst, 50 % (by mass per volume) of sodium hydroxide solution was added to the mixture using biuret at the rate of 0.25–0.33 mL/min. A mass of 0.15 g of sodium hydroxide solution, 50 % (by mass per volume), was added per each g of starch. The starch suspension was then transferred to a water bath controlled at 70 °C and stirred for 12 h using hotplate (Thermo Fisher Scientific, Waltham, MA, USA). A sample of 67.9 mL was drawn hourly over a reaction time of 12 h. The sample was added to water (3 times volume) to terminate the chemical reaction and centrifuged at 2000 \times g for 5 min. The supernatant was discarded and the sediment was washed with 4.5 volumes of water 16 times until reaching pH=5.0–5.5 (SevenEasy pH meter, Mettler Toledo, Columbus, OH, USA) and conductivity below 2.0 $\mu\text{S}/\text{cm}$ (sensION+ EC5 portable conductivity meter, Hach, Loveland, CO, USA). The starch propionate was dried in an oven at 40 °C for 48 h. After drying, starch propionate

was ground manually and sieved through a 250- μm diameter sieve. Starch propionate samples collected hourly over a period of 12 h were coded as SP1-SP12.

Determination of the degree of substitution

Degree of substitution (DS) was determined using the method reported by Bhandari and Singhal (11). A mass of 1 g of native corn starch or starch propionate was accurately weighed into 50 mL of 75 % (by volume) ethanol solution and stirred at 60 rpm on a hotplate for 30 min at 50 °C. The starch slurry was then cooled to room temperature (30 °C) and mixed with 40 mL of 0.5 M NaOH at 60 rpm using hotplate for 2 min. After mixing, the starch slurry was placed in an orbital shaker at 40 rpm and 30 °C for 72 h. Phenolphthalein indicator was dropped to the starch slurry and excess of alkali was back titrated with 0.5 M of hydrochloric acid. Native corn starch was treated in the same manner to obtain blank value. The propionyl content and DS were calculated using the equations proposed by Xia *et al.* (12). The propionyl content (in %) was calculated using the following equation:

$$w(\text{propionyl}) = \frac{(V(\text{blank}) - V(\text{sample})) \cdot c(\text{HCl}) \cdot 57 \cdot 10^{-3}}{m(\text{sample})} \cdot 100 \quad /1/$$

where V is titration volume in mL, m is mass in g, c is concentration in mol/L, 57 is the formula mass of propionyl group and 10^{-3} is a factor of conversion of mL to L.

The degree of substitution (DS) was defined as the average number of sites per α -D-glucose unit that possesses a substituent group, and it was calculated as follows:

$$\text{DS} = \frac{180 \cdot 0.9 \cdot w(\text{propionyl})}{57 \cdot 100 - (57 - 1) \cdot w(\text{propionyl})} \quad /2/$$

where 180 is the molecular mass of α -D-glucose, 0.9 is the stoichiometric constant for conversion of glucose to starch, 57 is the formula mass of propionyl group, and 1 is the atomic mass of hydrogen.

Fourier transform infrared spectroscopy

The Fourier transform infrared (FTIR) spectra were obtained with a BIO-RAD FTS 3000 IR Spectrum Scanner (BioRad Laboratories, Hercules, CA, USA).

Nuclear magnetic resonance

The nuclear magnetic resonance (NMR) spectra were recorded using an Ascend 500 spectrometer (Bruker, Ettlingen, Germany) operating at 500 MHz for ^1H NMR. 2D H-H NMR measurement was conducted to obtain the detailed information on the structure of starch propionate. Native corn starch and starch propionates of 7 mg each were dissolved in 0.7 mL of deuterated dimethyl sulphoxide (DMSO) with gentle stirring for 6 h at room temperature to obtain clear solutions.

Powder diffraction

X-ray patterns of native corn starch and starch propionate powders with different DS values were analyzed

between $2\theta=4$ and 45° using a D8 Advance X-ray diffractometer (Bruker, Berlin, Germany) with Cu-K α radiation at a voltage of 40 kV and 40 mA.

Measurement of contact angle

Contact angle measurement was performed using a Theta Lite optical tensiometer (Attension, Espoo, Finland). Attension Theta software was used to control the drop volume and measure the contact angle. The drop volume of water was fixed at 30 μ L. Sample preparation was carried out according to the method described by Thielemans *et al.* (13) with slight modifications. Starch pellet was prepared by compressing native corn starch or starch propionate under a pressure of 170.9 kg/(m 2) using a hydraulic bench top laboratory press (Carver, Wabash, IL, USA).

Swelling power and percentage of leaching

Swelling power and percentage of leaching were measured according to the method described by Bordenave *et al.* (14) with slight modifications. A mass of native corn starch and starch propionate of 0.1 g (m_1) was weighed separately and put into 1.5-mL microcentrifuge tube. A volume of 1.0 mL of distilled water was added and the starch suspension was vortexed with vortex mixer (Labnet International Inc., Edison, NJ, USA) followed by heating at 40 or 90 $^\circ$ C for 5 min.

After that, the tubes were cooled to room temperature for 30 min and subsequently centrifuged at 14 000 \times g for 5 min (1–15 Microfuge, Sigma Laborzentrifugen GmbH, Osterode am Harz, Germany). After centrifugation, the supernatant in the tubes was transferred into a moist dish and the swelled starch precipitate was weighed (m_2). The precipitate and the supernatant were dried separately in an oven at 100 $^\circ$ C for 20 h. The dried supernatant was weighed and labelled m_3 , while dried precipitate was weighed and labelled m_4 .

The swelling power was calculated as follows:

$$\text{Swelling power} = m_2/m_4 \quad /3/$$

and the percentage of leaching was calculated with the following equation:

$$\text{Percentage of leaching} = m_3/m_1 \cdot 100 \quad /4/$$

Preparation of oil-in-water emulsions

Olive oil (20 %, by mass) and water (80 %, by mass) were weighed separately. Starch propionate at 15 % (by mass) based on aqueous phase was weighed. Starch propionate was mixed with water and oil. The emulsion was homogenized using an Ultra Turrax T25 homogenizer (IKA Labor Technik, Staufen, Germany) at a speed of 4838.4 \times g for 5 min. A control emulsion was prepared using native corn starch.

Centrifugation stress study

The oil-in-water (O/W) emulsions were centrifuged at 4000 \times g for 30 min (Heraeus Multifuge X1, Thermo Fisher Scientific). The emulsion stability (ES) parameter pro-

posed by Taherian *et al.* (15) was used to evaluate the stability of the emulsion. The ES was calculated as follows:

$$ES = h_t/h_s \cdot 100 \quad /5/$$

where h_t is the total height of emulsion and h_s is the height of sediment layer. Stable O/W emulsion has ES value of 100 %.

Measurement of emulsion viscosity

The viscosity of the emulsion was measured using an SV-10 Sine-wave Vibro Viscometer (A&D, Tokyo, Japan). The emulsion sample was placed in a plastic sample cup and viscosity was measured at 30 $^\circ$ C.

Statistical analysis

The results are presented as mean values \pm standard deviation (S.D.). The results were analysed using one-way analysis of variance (SPSS software, v. 13.0 for Windows; SPSS Inc., Chicago, IL, USA). When there was a statistically significant difference ($p < 0.05$), Duncan's post-hoc test was performed.

Results and Discussion

Effect of reaction time on the degree of substitution of starch propionates

Fig. 1 shows that when corn starch was treated with propionic anhydride for a period of 12 h, the degree of substitution (DS) increased steadily with reaction time. The range of DS values of starch propionates was between 0.47 and 0.94. This trend may be attributed to an increase in diffusion of acylating reagent into and adsorption onto starch molecules with prolonged reaction time (16). Besides, the progressive increase in DS with time could be partly attributed to alkaline treatment. In the presence of alkali, protons of the hydroxyl groups may dissociate, leaving negative charges on starch molecules. The negatively charged starch molecules may then repel each other causing dissociation of the double helices of amylopectin (17), which leads to the exposure of more reactive sites on the macromolecule for the acylating reagent to react upon.

Xu *et al.* (18) synthesised starch acetate with a DS of approx. 1.6, at 0.15 g of NaOH per g of starch, reaction




Fig. 1. Degree of substitution (DS) of various starch propionates (SP) prepared over a period of 12 h. Values with different letters are significantly different ($p < 0.05$)

temperature of 123 °C, reaction time of 60 min, and starch/ acetic anhydride mass ratio of 1:4. In contrast, the present study produced starch propionate with DS values of 0.47–0.94, which are considered moderate, at a condition of 0.15 g of NaOH per g of starch, reaction temperature of 70 °C, reaction time of 1–12 h, and starch/propionic anhydride mass ratio of 1:4.82. Differences in the substitution degree of acylated starches could be due to differences in reaction conditions such as temperature and type of anhydride. Increasing temperature produced starch with higher DS, indicating that higher temperature favoured acceleration of the forward reaction (19,20). In the present study, starch propionate with lower DS was obtained because a lower reaction temperature was used. Other authors showed that acyl anhydride with longer chain lengths of fatty acids tends to form starch ester with lower DS (20,21). The reaction occurred at slower rate due to the steric effects of larger molecular size of reagent and a lower diffusion rate in the starch matrix.

The common practice to prepare propionylated starch is to use propionic anhydride. Various catalysts have been used such as 1-methylimidazole (5), sodium hydroxide (18), formamide (22) and pyridine (23). The selection of catalyst was based on its suitability and safety in the preparation of starch propionate as food, cosmetic and pharmaceutical additives. Sodium hydroxide was chosen as catalyst since it is water soluble and can be easily washed off after the esterification process.

Fourier transform infrared spectroscopy of native starch and starch propionates

FTIR spectra of native corn starch and starch propionates SP1, SP6 and SP12 are presented in Fig. 2. Absorption bands at 3423.51, 2928.17, 1650.13 and 1239.09 corresponded to hydrogen-bonded hydroxyl, CH₂ symmetrical stretching vibrations, scissoring of two OH bonds of absorbed water molecules and C-O-H deformation, respectively (12,24,25).

All starch propionates gave a new peak at 1743.48 cm⁻¹, indicating stretching of ester carbonyl C=O (12,18,23) and successful propionylation. Two new bands were also seen at 2878.26 and 2986.96 cm⁻¹ in the spectra indicating




Fig. 2. FTIR spectra of: native corn starch (a), SP1 (DS=0.47) (b), SP6 (DS=0.76) (c) and SP12 (DS=0.94) (d). DS=degree of substitution, SP=starch propionate

methyl and methylene C–H stretching of propionyl groups in esterified starch (24,26,27).

Nuclear magnetic resonance spectroscopy of native starch and starch propionate

The ¹H NMR spectra of native starch and starch propionate SP12 (DS=0.94) are shown in Fig. 3. For native starch, ¹H-chemical shift at 5.4963 ppm was assigned to OH-3, at 5.3985 ppm to OH-2, at 5.1051 ppm to H-1, at 4.5731 ppm to OH-6, at 3.6518 ppm to H-3 and at 3.5843 ppm to H-5 (2,28,29). After propionylation, all starch samples exhibited characteristic peaks similar to native starch. The new ¹H-chemical shifts were observed at 2.3470 and 1.0324 ppm, corresponding to CH₂ and CH₃ protons, respectively (30). These observations indicated a successful propionylation. This result was also corroborated by the two new bands evident at 2878.26 and 2986.96 cm⁻¹ in the FTIR spectra, indicating methyl and methylene C–H stretching of propionyl groups in starch propionate. This shows that propionylation possibly occurred at OH-2, OH-3 and OH-6 of the anhydroglucose units.




Fig. 3. ¹H NMR spectra of: a) native corn starch and b) SP12 (DS=0.94). SP=starch propionate, DS=degree of substitution

Crystalline patterns of native starch and starch propionates

Fig. 4 shows the powder diffraction patterns of native starch, SP1 (DS=0.47), SP6 (DS=0.76) and SP12 (DS=0.94).




Fig. 4. Powder X-ray patterns of: native corn starch (a), SP1 (DS=0.47) (b), SP6 (DS=0.76) (c) and SP12 (DS=0.94) (d). DS=degree of substitution, SP=starch propionate

Native corn starch showed an A pattern with strong diffraction peaks at 2θ of 15.22, and unresolved doublet at 17.08, 18.02 and 23.29 (2θ). The crystallinity of starch was formed by the double helices of amylopectin chains (31,32). According to Xu *et al.* (18), the intra- and intermolecular hydrogen bonds account for highly ordered crystalline structure in starch granule. The peak intensities of SP1 were found to be lower than the characteristic peaks of the native corn starch. Only part of the hydroxyl groups was replaced with propionyl group. The remaining hydroxyl groups may still form hydrogen bonds, resulting in the decrease of diffraction peak intensities in SP1 (18). Further propionylation caused progressive changes in the X-ray diffraction patterns as shown by the formation of broad peaks in SP6 and SP12. These changes indicated the disruption of starch granule crystallinity through the replacement of the hydroxyl groups with propionyl groups on the starch molecules upon esterification (2,18).

Effect of propionylation on the hydrophobicity of starch

Table 1 shows contact angle values of various starch propionates. It is evident that the contact angle values progressively increased with propionylation time. The gradual increase in contact angle from samples SP1–SP11 was due to an increase in the hydrophobicity which was

Table 1. Contact angle (θ) values of the prepared various starch propionates

Sample (DS value)	$\theta/^\circ$
SP1 (0.47)	(70.9±1.9) ^a
SP3 (0.64)	(73.6±1.9) ^b
SP5 (0.73)	(76.1±1.7) ^c
SP7 (0.80)	(79.6±2.3) ^d
SP9 (0.86)	(81.2±2.3) ^{de}
SP11 (0.92)	(82.2±1.7) ^e

Data are presented as mean values±standard deviations of six independent replicates. Values in the same column with different letters in superscript differ significantly ($p<0.05$). DS=degree of substitution, SP=starch propionate

caused by propionylation of the starch. It can be deduced that in the process of propionylation, hydrophilic hydroxyls were substituted with more hydrophobic ester groups. The same observation was reported by Chi *et al.* (2). Contact angle value of native corn starch was not measured because when water was dropped onto the surface of the pellet, it quickly disintegrated. It was concluded that native corn starch is too hydrophilic for the measurement of contact angle.

Effect of propionylation on the swelling and leaching behaviour of starch

Table 2 shows swelling power values of native corn starch and various starch propionates. Native corn starch exhibited swelling power of 2.3 and 10.9 g/g at incubation temperatures of 40 and 90 °C, respectively. At 40 °C, 0.4 % of starch polymers leached out of native corn starch. Leaching increased to 1.6 % when native corn starch was incubated at 90 °C. As shown by Bordenave *et al.* (14), native corn starch showed a swelling power of 7.84 g/g and leaching of 1.72 % when the experiment was conducted at 23 °C for 30 min. Native corn starch has been reported to exhibit swelling power of about 12.81 g/g and leaching >5 % when the starch was incubated at 90 °C for 1 h (33). In the present study, native corn starch had much lower swelling power and percentage of leaching, which was probably due to the short incubation period of 5 min.

Table 2. Swelling power and percentage of leaching of native corn starch and various starch propionates at different incubation temperatures

Sample (DS value)	Temperature/°C			
	40		90	
	Swelling power/(g/g)	Leaching/%	Swelling power/(g/g)	Leaching/%
Native (0.00)	(2.3±0.1) ^a	(0.4±0.1) ^a	(10.9±0.2) ^f	(1.6±0.1) ^a
SP1 (0.47)	(5.1±0.1) ^b	(1.9±0.2) ^b	(9.97±0.09) ^e	(5.6±0.9) ^b
SP3 (0.64)	(6.79±0.08) ^f	(2.4±0.3) ^b	(8.4±0.3) ^d	(5.1±1.0) ^b
SP5 (0.73)	(6.8±0.2) ^f	(4.2±0.9) ^c	(7.5±0.2) ^c	(5.8±1.0) ^b
SP7 (0.80)	(6.45±0.01) ^e	(5.6±1.1) ^{cd}	(7.06±0.04) ^b	(5.9±0.6) ^b
SP9 (0.86)	(5.7±0.1) ^d	(5.8±0.7) ^d	(6.3±0.2) ^a	(6.0±0.7) ^b
SP11 (0.92)	(5.5±0.2) ^c	(5.7±0.7) ^{cd}	(6.1±0.2) ^a	(5.9±0.9) ^b

Data are presented as mean values±standard deviations of three independent replicates. Values in the same column with different letters in superscript differ significantly ($p<0.05$). DS=degree of substitution, SP=starch propionate

After propionylation, corn starch showed a higher swelling power compared to native corn starch at incubation temperature of 40 °C. According to some authors, acylation could weaken the intermolecular hydrogen bonding within starch granule, making it readily swollen when heated at a lower temperature (34). It was observed that swelling power and percentage of leaching of starch propionates increased from SP1 (DS=0.47) to SP5 (DS=0.73). The weak intermolecular hydrogen bonding present within starch propionate was substantiated by the X-ray patterns seen in Fig. 4. On the other hand, from SP5 (DS=0.73) to SP11 (DS=0.92) swelling power decreased but percentage of leaching reached plateau because of the enhanced hydrophobicity of starch propionates when more and more hydroxyl groups were replaced by propionyl groups.

At 90 °C, a lower swelling power was evident in starch propionates when compared with native corn starch. Native corn starch with intact granules can swell to its maximum when heated in water. Starch propionates having hydroxyl groups replaced with propionyl groups became more hydrophobic than native corn starch, thus resulting in a lower degree of swelling. Swelling power of starch propionates decreased significantly from SP1 (DS=0.47) to SP9 (DS=0.86), but there was no significant difference between SP9 (DS=0.86) and SP11 (DS=0.92). The weakened granular structure of starch propionates contributed to a significantly higher percentage of leaching than the native corn starch. The increase in percentage of leaching in starch propionates from SP1 (DS=0.47) to SP11 (DS=0.92) was not significantly different. The findings showed that percentage of leaching was independent of DS and not significantly affected by the degree of propionylation.

The ability of starch propionate to swell and thicken at low and high temperatures shows that it has the potential for use as a cold swelling starch and thickener.

Physical stability of emulsions with starch propionates

In a preliminary study, emulsions were prepared with 10, 15 and 20 % (by mass) of starch propionates (SP1–SP12). Emulsions prepared with 10 % of starch propionates separated immediately after centrifugation. At 15 % of starch propionates, O/W emulsions prepared with SP3–SP9 (DS=0.64–0.86) were stable while others separated. At 20 % of starch propionates, emulsions were stable. Hence, 15 % of starch propionate was selected for the study as this fraction could discern the effect of DS of starch propionates on the stability of O/W emulsions. Stability of emulsions prepared with 15 % of starch propionate at different DS is shown in Fig. 5. Emulsions were best stabilised with starch propionates SP3–SP9 (DS=0.64–0.86). A control emulsion was prepared using native corn starch. When emulsion was prepared with native corn starch granules at 15 %, it separated quickly after homogenization. The good emulsion stabilising properties of starch propionate indicated that it is better compared to starch acetate. Starch acetate is not known to be a good emulsion stabiliser (4). Thus, the starch propionate produced in the present study could be a promising emulsion stabiliser.




Fig. 5. Emulsion stability (ES) of various oil-in-water emulsions prepared with different degrees of substitution of starch propionates (SP). Values with different letters are significantly different ($p < 0.05$)

Viscosity of emulsions with starch propionates

The viscosity of emulsions prepared with starch propionates at different DS levels is shown in Table 3. There is an increase in the viscosity of the emulsion from SP1 (DS=0.47) to SP5 (DS=0.73), followed by a decrease after SP5. These changes could be due to the swelling of the starch propionate granules as shown in Table 2. Crosbie (35) reported that viscosity of starch was correlated with its swelling power.

Table 3. Viscosities of oil-in-water emulsions (η) prepared with different degrees of substitution (DS) of starch propionates (SP)

Sample (DS value)	η /(mPa·s)
SP1 (0.47)	(179.4±25.1) ^a
SP3 (0.64)	(2990.0±325.1) ^e
SP5 (0.73)	(3330.0±294.6) ^f
SP7 (0.80)	(1886.7±119.3) ^d
SP9 (0.86)	(1236.7±56.9) ^c
SP11 (0.92)	(565.3±51.0) ^b

Data are presented as mean values±standard deviations of three independent replicates. Values in the same column having different letters in superscript differ significantly ($p < 0.05$)

The present study found that SP3–SP9 (DS=0.64–0.86) produced stable emulsions with viscosities in the range of 1236.7–3330.0 mPa·s. On the other hand, SP1 (DS=0.47) and SP11 (DS=0.92) produced unstable O/W emulsions with viscosities in the range of 179.4–565.3 mPa·s. This means that starch propionate with DS between 0.64 and 0.86 can cause sufficient viscosity to stabilise emulsions.

According to McClements (36), in order to be an effective emulsifier, biopolymers must rapidly adsorb to the surface of the oil droplets during homogenization and provide a membrane to prevent aggregation of oil droplets. All biopolymers are capable of providing physical barrier *via* thickening ability to prevent droplets from getting sufficiently close together to coalesce. Hence, in the present study, the mechanism of emulsion stabilisation was due to viscosity enhancement caused by starch propionate, which prevented the oil droplets from coming close together.

Conclusions

In conclusion, starch propionates with degree of substitution (DS) values of 0.47–0.94 were produced throughout a 12-hour propionylation process. Contact angle values were found to increase proportionately with an increase in DS values, indicating increasing hydrophobicity of the starch propionate. Samples SP1–SP11 showed higher swelling power than the native corn starch at 40 °C, indicating cold swelling and thickening properties. Swelling power was found to decrease with increasing DS. Stable oil-in-water (O/W) emulsions were produced at DS values of 0.64–0.86 and viscosities between 1236.7 and 3330.0 mPa·s. This shows that starch propionate with the above characteristics has a great potential to be used as a cold swelling starch, thickener as well as O/W emulsion stabiliser in food, pharmaceutical and cosmetic industries.

Acknowledgements

This study is funded by Postgraduate Research Grant Scheme (1001/PFARMASI/846066). The authors would like to thank Institute of Postgraduate Studies, Universiti Sains Malaysia for providing fellowship.

References

- Singh J, Kaur L, McCarthy OJ. Factors influencing the physico-chemical, morphological, thermal and rheological properties of some chemically modified starches for food applications – a review. *Food Hydrocolloid.* 2007;21:1–22. <http://dx.doi.org/10.1016/j.foodhyd.2006.02.006>
- Chi H, Xu K, Wu X, Chen Q, Xue D, Song C, et al. Effect of acetylation on the properties of corn starch. *Food Chem.* 2008;106:923–8. <http://dx.doi.org/10.1016/j.foodchem.2007.07.002>
- Sweedman MC, Tizzotti MJ, Schäfer C, Gilbert RG. Structure and physicochemical properties of octenyl succinic anhydride modified starches: a review. *Carbohydr Polym.* 2013; 92:905–20. <http://dx.doi.org/10.1016/j.carbpol.2012.09.040>
- Murúa-Pagola B, Beristain-Guevara CI, Martínez-Bustos F. Preparation of starch derivatives using reactive extrusion and evaluation of modified starches as shell materials for encapsulation of flavoring agents by spray drying. *J Food Eng.* 2009;91:380–6. <http://dx.doi.org/10.1016/j.jfoodeng.2008.09.035>
- Annisson G, Illman RJ, Topping DL. Acetylated, propionylated or butyrylated starches raise large bowel short-chain fatty acids preferentially when fed to rats. *J Nutr.* 2003;133:3523–8.
- Bird AR, Lopez-Rubio A, Shrestha A, Gidley MJ. Resistant starch in vitro and in vivo: factors determining yield, structure, and physiological relevance. In: Kasapis S, Norton IT, Ubbink JB, editors. *Modern biopolymer science*. London, UK: Academic Press; 2009. pp. 449–510.
- Englyst HN, Kingman SM, Cummings JH. Classification and measurement of nutritionally important starch fractions. *Eur J Clin Nutr.* 1992;46:S33–50.
- Haralampu SG. Resistant starch – a review of the physical properties and biological impact of RS₃. *Carbohydr Polym.* 2000;41:285–92. [http://dx.doi.org/10.1016/S0144-8617\(99\)00147-2](http://dx.doi.org/10.1016/S0144-8617(99)00147-2)
- Ferguson MJ, Jones GP. Production of short-chain fatty acids following in vitro fermentation of saccharides, saccharide esters, fructo-oligosaccharides, starches, modified starches and non-starch polysaccharides. *J Sci Food Agr.* 2000;80:166–70. [http://dx.doi.org/10.1002/\(SICI\)1097-0010\(20000101\)80:1<166::AID-JSFA512>3.0.CO;2-K](http://dx.doi.org/10.1002/(SICI)1097-0010(20000101)80:1<166::AID-JSFA512>3.0.CO;2-K)
- Cheng HH, Lai MH. Fermentation of resistant rice starch produces propionate reducing serum and hepatic cholesterol in rats. *J Nutr.* 2000;130:1991–5.
- Bhandari PN, Singhal RS. Studies on the optimisation of preparation of succinate derivatives from corn and amaranth starches. *Carbohydr Polym.* 2002;47:277–83. [http://dx.doi.org/10.1016/S0144-8617\(01\)00202-8](http://dx.doi.org/10.1016/S0144-8617(01)00202-8)
- Xia L, Wenyuan G, Qianqian J, Luqi H, Changxiao L. Study on the morphology, crystalline structure, and thermal properties of *Fritillaria ussuriensis* Maxim. starch acetates with different degrees of substitution. *Starch.* 2011;63:24–31. <http://dx.doi.org/10.1002/star.201000055>
- Thielemans W, Belgacem MN, Dufresne A. Starch nanocrystals with large chain surface modifications. *Langmuir.* 2006; 22:4804–10. <http://dx.doi.org/10.1021/la053394m>
- Bordenave N, Janaswamy S, Yao Y. Influence of glucan structure on the swelling and leaching properties of starch microparticles. *Carbohydr Polym.* 2014;103:234–43. <http://dx.doi.org/10.1016/j.carbpol.2013.11.031>
- Taherian AR, Fustier P, Ramaswamy HS. Effect of added oil and modified starch on rheological properties, droplet size distribution, opacity and stability of beverage cloud emulsions. *J Food Eng.* 2006;77:687–96. <http://dx.doi.org/10.1016/j.jfoodeng.2005.06.073>
- Khalil MI, Hashem A, Hebeish A. Preparation and characterization of starch acetate. *Starch.* 1995;47:394–8. <http://dx.doi.org/10.1002/star.19950471005>
- Chen J, Jane J. Properties of granular cold-water-soluble starches prepared by alcoholic-alkaline treatments. *Cereal Chem.* 1994;71:623–6.
- Xu Y, Miladinov V, Hanna MA. Synthesis and characterization of starch acetates with high substitution. *Cereal Chem.* 2004;81:735–40.
- Junistia L, Sugih AK, Manurung R, Picchioni F, Janssen LPBM, Heeres HJ. Experimental and modelling studies on the synthesis and properties of higher fatty esters of corn starch. *Starch.* 2009;61:69–80. <http://dx.doi.org/10.1002/star.200800076>
- Muljana H, van der Knoop S, Keijzer D, Picchioni F, Janssen LPBM, Heeres HJ. Synthesis of fatty acid starch esters in supercritical carbon dioxide. *Carbohydr Polym.* 2010;82:346–54. <http://dx.doi.org/10.1016/j.carbpol.2010.04.067>
- Junistia L, Sugih AK, Manurung R, Picchioni F, Janssen LPBM, Heeres HJ. Synthesis of higher fatty acid starch esters using vinyl laurate and stearate as reactants. *Starch.* 2008; 60:667–75. <http://dx.doi.org/10.1002/star.200800025>
- Rivard C, Moens L, Roberts K, Brigham J, Kelley S. Starch esters as biodegradable plastics: effects of ester group chain length and degree of substitution on anaerobic biodegradation. *Enzyme Microb Tech.* 1995;17:848–52. [http://dx.doi.org/10.1016/0141-0229\(94\)00120-G](http://dx.doi.org/10.1016/0141-0229(94)00120-G)
- Santayanon R, Wootthikanokkhan J. Modification of cassava starch by using propionic anhydride and properties of the starch-blended polyester polyurethane. *Carbohydr Polym.* 2003;51:17–24. [http://dx.doi.org/10.1016/S0144-8617\(02\)00109-1](http://dx.doi.org/10.1016/S0144-8617(02)00109-1)
- Cael JJ, Koenig JL, Blackwell J. Infrared and Raman spectroscopy of carbohydrates. Part VI: Normal coordinate analysis of V-amylose. *Biopolymers.* 1975;14:1885–903. <http://dx.doi.org/10.1002/bip.1975.360140909>
- Zhang L, Xie W, Zhao X, Liu Y, Gao W. Study on the morphology, crystalline structure and thermal properties of yel-

- low ginger starch acetates with different degrees of substitution. *Thermochim Acta.* 2009;495:57–62.
<http://dx.doi.org/10.1016/j.tca.2009.05.019>
26. Fang JM, Fowler PA, Tomkinson J, Hill CAS. The preparation and characterisation of a series of chemically modified potato starches. *Carbohydr Polym.* 2002;47:245–52.
[http://dx.doi.org/10.1016/S0144-8617\(01\)00187-4](http://dx.doi.org/10.1016/S0144-8617(01)00187-4)
27. Sun RC, Fang JM, Tomkinson J, Geng ZC, Liu JC. Fractional isolation, physico-chemical characterization and homogeneous esterification of hemicelluloses from fast-growing poplar wood. *Carbohydr Polym.* 2001;44:29–39.
[http://dx.doi.org/10.1016/S0144-8617\(00\)00196-X](http://dx.doi.org/10.1016/S0144-8617(00)00196-X)
28. Namazi H, Fathi F, Dadkhah A. Hydrophobically modified starch using long-chain fatty acids for preparation of nano-sized starch particles. *Sci Iran.* 2011;18:439–45.
<http://dx.doi.org/10.1016/j.scient.2011.05.006>
29. Peng QJ, Perlin AS. Observations on N.M.R. spectra of starches in dimethyl sulfoxide, iodine-complexing, and solvation in water-di-methyl sulfoxide. *Carbohydr Res.* 1987; 160:57–72.
[http://dx.doi.org/10.1016/0008-6215\(87\)80303-8](http://dx.doi.org/10.1016/0008-6215(87)80303-8)
30. Liebert T, Kulicke WM, Heinze T. Novel approach towards hydrolytically stable starch acetates for physiological applications. *React Funct Polym.* 2008;68:1–11.
<http://dx.doi.org/10.1016/j.reactfunctpolym.2007.10.025>
31. Waigh TA, Donald AM, Heidelbach F, Riekel C, Gidley MJ. Analysis of the native structure of starch granules with small angle x-ray microfocus scattering. *Biopolymers.* 1999;49:91–105.
[http://dx.doi.org/10.1002/\(SICI\)1097-0282\(199901\)49:1<91::AID-BIP9>3.0.CO;2-9](http://dx.doi.org/10.1002/(SICI)1097-0282(199901)49:1<91::AID-BIP9>3.0.CO;2-9)
32. Zobel HF. Molecules to granules: a comprehensive starch review. *Starch.* 1988;40:44–50.
<http://dx.doi.org/10.1002/star.19880400203>
33. Yousif EI, Gadallah MGE, Sorour AM. Physico-chemical and rheological properties of modified corn starches and its effect on noodle quality. *Ann. Agric. Sci.* 2012;57:19–27.
<http://dx.doi.org/10.1016/j.aoas.2012.03.008>
34. Lawal OS. Composition, physicochemical properties and retrogradation characteristics of native, oxidised, acetylated and acid-thinned new cocoyam (*Xanthosoma sagittifolium*) starch. *Food Chem.* 2004;87:205–18.
<http://dx.doi.org/10.1016/j.foodchem.2003.11.013>
35. Crosbie GB. The relationship between starch swelling properties, paste viscosity and boiled noodle quality in wheat flours. *J Cereal Sci.* 1991;13:145–50.
[http://dx.doi.org/10.1016/S0733-5210\(09\)80031-3](http://dx.doi.org/10.1016/S0733-5210(09)80031-3)
36. McClements DJ. Lipid-based emulsions and emulsifiers. In: Akoh CC, Min DB, editors. *Food lipids: chemistry, nutrition, and biotechnology.* London, UK: CRC Press; 2008. pp. 63–97.