



OPEN

Polymer-Derived Ceramic Functionalized MoS₂ Composite Paper as a Stable Lithium-Ion Battery Electrode

L. David*, R. Bhandavat*, U. Barrera & G. Singh

SUBJECT AREAS:
TWO-DIMENSIONAL
MATERIALS
BATTERIES
MATERIALS CHEMISTRY

Received
16 October 2013

Accepted
19 March 2015

Published
8 April 2015

Correspondence and
requests for materials
should be addressed to
G.S. (gurpreet@ksu.
edu)

*These authors
contributed equally to
this work.

Department of Mechanical and Nuclear Engineering, Kansas State University, Manhattan, KS 66506, USA.

A facile process is demonstrated for the synthesis of layered SiCN-MoS₂ structure via pyrolysis of polysilazane functionalized MoS₂ flakes. The layered morphology and polymer to ceramic transformation on MoS₂ surfaces was confirmed by use of electron microscopy and spectroscopic techniques. Tested as thick film electrode in a Li-ion battery half-cell, SiCN-MoS₂ showed the classical three-stage reaction with improved cycling stability and capacity retention than neat MoS₂. Contribution of conversion reaction of Li/MoS₂ system on overall capacity was marginally affected by the presence of SiCN while Li-irreversibility arising from electrolyte decomposition was greatly suppressed. This is understood as one of the reasons for decreased first cycle loss and increased capacity retention. SiCN-MoS₂ in the form of self-supporting paper electrode (at 6 mg·cm⁻²) exhibited even better performance, regaining initial charge capacity of approximately 530 mAh·g⁻¹ when the current density returned to 100 mA·g⁻¹ after continuous cycling at 2400 mA·g⁻¹ (192 mAh·g⁻¹). MoS₂ cycled electrode showed mud-cracks and film delamination whereas SiCN-MoS₂ electrodes were intact and covered with a uniform solid electrolyte interphase coating. Taken together, our results suggest that molecular level interfacing with precursor-derived SiCN is an effective strategy for suppressing the metal-sulfide/electrolyte degradation reaction at low discharge potentials.

Layered transition metal dichalcogenides (TMDs) such as molybdenum disulfide (MoS₂) and tungsten disulfide (WS₂) have garnered increased research interest because of applications in several emerging areas such as hydrogen storage¹, chemical catalysis², double-layer capacitors and rechargeable metal-ion battery electrodes³⁻⁹. Application as Li-ion battery electrode is particularly of interest because of weak van der Waals interactions between TMD layers and unique conversion chemistry with Li that allows continuous Li-ion cycling with lower volume expansion and pulverization compared to alloying anodes such as silicon and metal oxides.^{10,11} Theoretically, conversion reaction in one mole of MoS₂ leads to four moles of stored Li⁺ ions resulting in a specific capacity of 670 mAh·g⁻¹ (approximately 1.8 times the traditional graphite anode)¹².

Reports on electrochemical performance of bulk MoS₂ began in the 1980s when TMDs were investigated as cathode material for use in Li-metal batteries.¹³ However, safety issues lead to discontinuation of such batteries. Recent advances in nanotechnology, such as development of efficient liquid phase exfoliation methods,¹⁴⁻²⁰ improved understanding of the electrode/electrolyte interfaces, and recent success with fabrication of single layer MoS₂ transistors and membranes^{21,22} have motivated researchers to reconsider nanostructured MoS₂ as potential Li host material. Highly porous MoS₂ or MoS₂/carbon electrodes prepared by hydrothermal and solvothermal techniques, gas-phase reaction of MoO₃ with H₂S or S vapor, and thermal decomposition of ammonium thiomolybdate have demonstrated performance improvements in response to challenges presented by MoS₂ nanosheet use.²³⁻³² As a result, capacity values as high as ~ 1200 mAh·g⁻¹ have been achieved for such electrodes, particularly at low active weight loadings.³³ More recently, MoS₂-based hybrid nanocomposites (obtained by interfacing with carbon nanotubes or graphene) have been of interest because CNT or graphene offers high electrical conductivity³⁴, thereby allowing high rate capability and reversibility.³⁵⁻⁴² Nevertheless, some new challenges have emerged that hinder the introduction of TMD nanosheets for practical applications. These challenges include: (a) high costs due to complex procedures that limit production in large quantities (gram levels or higher), (b) capacity degradation for thick electrodes or the low volumetric capacity of nanostructured/porous electrode design, (c) low thermodynamic and chemical stability in moisture²¹ and degradation reaction with the battery electrolyte at low discharge potentials.¹⁷ Efforts to cost-effectively produce large quantities of TMDs flakes via chemical exfoliation are promising; therefore, a matter of intense research^{19,20}.



Here, we report a one-step facile approach to synthesize a TMD/glass composite material. This approach could prove vital in retaining the useable (reversible) Li-ion capacity of TMD electrodes by mitigating the effect of phase-III electrolyte degradation reaction and polysulfide dissolution typically observed in these materials. The composite consists of a Si-based polymer-derived ceramic (or PDC)^{43–46} chemically interfaced with the surfaces of exfoliated MoS₂. PDCs are high-temperature glasses prepared by thermal decomposition of organosilicon polymers. Monolayer thick films of PDC can be formed on a variety of substrate materials to achieve resistance to oxidation and chemical degradation without compromising the physical properties of base material; PDC/CNT and PDC/graphene are some examples.^{43–48} Liquid-phase polymeric precursor allowed easy dispersion and functionalization (attainment of molecular level interfacial) of exfoliated MoS₂ flakes. Polymer molecules diffuse within exfoliated sheets,⁴⁹ forming an alternating MoS₂ and ceramic-layered morphology on pyrolysis, thereby exhibiting ideal candidate material for rechargeable battery electrodes. The composite has a tap density of $\sim 1.5 \text{ g.cm}^{-3}$ and could be processed as either a thick film on copper foil or freestanding paper with active weight loading as high as 6 mg.cm^{-2} . This layered morphology may be essential for achieving long-term stable Li-cycling in Li-S and Li-ion batteries because it puts a check on the TMD/organic electrolyte degradation reaction observed at low discharge potentials.^{17,50–51}

Experimental

Material preparation. Acid-treated MoS₂ was prepared in a manner similar to our recent work on TMDs, described in Ref. 17 and 18. SiCN-MoS₂ composite nanosheets were prepared following the procedures shown in Figure 1. Approximately 30 wt. % of poly(ureamethylvinyl)silazane (commercial name: CerasetTM, Clariant) was added to acid-treated MoS₂, stirred for 24 h, and dried at 100°C in an inert atmosphere. To allow cross-linking of the intercalated polymer, the dried polymer-MoS₂ mix was heated to 400°C in nitrogen (held at 15 min) and then heated at 1000°C for 1 h, resulting in thermal decomposition of the polymer into amorphous SiCN ceramic on MoS₂ surfaces. Under these processing conditions, the polymeric precursor showed a ceramic yield of approximately 70 to 75 wt. % [see Supplementary Figure S1], resulting in approximately 20 wt. % of SiCN ceramic in SiCN-MoS₂ composite.

Cell assembly and testing. Traditional electrode: These were prepared using active materials (exfoliated MoS₂ or SiCN-MoS₂ composite), acetylene black (Alfa Aesar, 99.9%) as conducting agent and polyvinylidene fluoride (Sigma Aldrich) as a binding agent with a weight ratio of 8:1:1, respectively. Few drops of

N-methyl pyrrolidone (Fisher) were added to obtain homogeneously viscous slurry. Approximately 125 μm uniformly thick coating was then prepared on copper current collector (9 μm thick) and dried in an inert medium at 80°C for 4 h. They were then punched into circles of diameter 1.4 cm for use as working electrode in a coin cell (2032 coin cell) with Li-metal foil acting as the counter electrode. A polyethylene monolayer membrane (Celgard) soaked in 1.0 M of LiPF₆ in EC:DMC electrolyte (Novolyte Technologies) separated the two electrodes. The cells were assembled in a high-precision argon glove box.

Paper-based electrode: Freestanding papers were prepared in a manner similar to recent work.⁵² Dispersion of SiCN-MoS₂ composite with 20 wt. % graphene oxide⁵³ was prepared in 1:1 water: Isopropanol solution. The dispersion was then vacuum-filtered through a 10 μm filter membrane (HPLC grade, Millipore). The paper was separated from the membrane and thermally reduced at 500°C under argon atmosphere for 2 h. Because GO to rGO yield is approximately 50% [Supplementary Figure S2], the amount of rGO in the final paper was approximately 10 wt. % of the final composite. Four-point electrical conductivity of the paper was observed to be 0.11 S/cm. The heat-treated paper was then punched into small circles and directly utilized as a working electrode in the Li-ion battery half-cell.

Material characterization. Scanning electron microscopy (SEM) was performed by use of Carl Zeiss EVO 10 SEM and transmission electron microscopy (TEM) was carried out on Philips CM 100 TEM (100 kV). EDX map was obtained using FEI Company Nova NanoSEM 430 with an Oxford X-Max Large Area Analytical EDS silicon drift detector (SDD) (80mm²). Material characterization was made using an X-ray diffractometer (XRD) operating at room temperature with nickel-filtered Cu K α radiation ($\lambda = 1.5418 \text{ \AA}$). Thermogravimetric analysis (TGA) was performed using Shimadzu 50 TGA (limited to 800°C). Samples weighing, $\sim 2.5 \text{ mg}$, were heated in a platinum pan at a rate of 10°C/min in air flowing at 20 mL/min. Surface chemical composition of the powdered specimens were determined using X-ray photoelectron spectroscopy (XPS), by PHI Quantera SXM with Al K α monochromatic X-radiation (beam size $< 9 \mu\text{m}$) at 45° angle of incidence. The assembled cells were tested using Arbin BT2000 multichannel potentiostat in atmospheric conditions. The batteries were cycled from 10 mV to 3V at a constant current density of 100 mA.g⁻¹ during discharge and charge cycles.

Results and discussion

Schematic representing synthesis of MoS₂-SiCN composite is presented in Figure 1. Electron microscopy of the acid-treated MoS₂




Figure 1 | Schematic representation showing synthesis of SiCN-MoS₂ composite from in-situ pyrolysis of polysilazane molecules. Liquid-phase polysilazane functionalized MoS₂ flakes undergo organic-to-inorganic transformation at 1000°C in flowing nitrogen leading to SiCN-MoS₂-SiCN type morphology. Sheet like morphology of MoS₂ is retained.




Figure 2 | Material characterization. SEM micrograph of (a) acid-treated MoS_2 show stacked sheets with lateral dimension of $2 \mu\text{m}$ to $5 \mu\text{m}$. (b) SEM image of SiCN/MoS_2 and (c) its corresponding EDX map show presence of Mo (blue), Si (Green) and C (red) distributed in the composite. (d,e) TEM images of SiCN/MoS_2 sheet composite show intact morphology of MoS_2 sheets after pyrolysis. The SAED pattern in the insert corresponds to crystalline MoS_2 . SEM images of SiCN/MoS_2 freestanding paper (f) cross-section, (g) top view and (h) corresponding EDX map. The insert in Figure (f) is an optical photograph of SiCN/MoS_2 freestanding and flexible paper.

specimen demonstrated a large number of layered MoS_2 sheets with lateral dimensions varying between $2 \mu\text{m}$ to $5 \mu\text{m}$ (Figure 2(a)). SiCN functionalized MoS_2 composite also showed layered morphology, as shown in the SEM and TEM images (Figures 2(b–e)). The EDX map of $\text{SiCN}-\text{MoS}_2$ in Figure 2(c) (Mo-blue, Si-green and C-red) shows an unevenly spread amorphous SiCN ceramic intercalated into MoS_2 sheets. Interlayer separation and presence of pores or gaps was evident in $\text{SiCN}-\text{MoS}_2$ composite. The SAED pattern in the insert of Figure 2(d) is similar to crystalline MoS_2 pattern, indicating the presence of intact sheets even after pyrolysis. The cross-section, top view, and EDX map of freestanding papers prepared by vacuum filtration (approximately 10 wt. % rGO) are presented in Figures 2(f–h).

X-ray diffraction data for MoS_2 , polymer-derived SiCN , $\text{SiCN}-\text{MoS}_2$ powder, and freestanding paper is presented in Supplementary Figure S3. XPS analysis was performed on the composite material to ascertain the presence and chemical functionalization of MoS_2 by SiCN ceramic phase (Supplementary Figure S4). High-resolution elemental Mo3d XPS spectra showed doublets at 227.8 eV and 230.9 eV. The doublets are deconvoluted into the original Mo-S state at 226.8 eV and 227.8 eV due to the Mo-Si/Mo-C bond, and the high energy 230.9 eV peak could be due to Mo-O

bonds with multiple oxidation states of Mo.^{54–57} A high-resolution sulfur peak emerged as a doublet at 160.7 eV and 161.9 eV due to reduced (S^{2-}) and pristine sulfur, respectively. Single and broad Si2p peak at 101.7 eV could be assigned to Si-C, Si-C/Si-N, Si-N and Si-O/Mo-Si peaks at 100.2, 101.4, 101.7 and 102.1 eV, respectively⁵⁷. The broad oxygen peak at 531 eV could be fitted by doublets Mo-O₂ (530.2 eV and 531 eV) and more electronegative Mo-O₃ (at 531.6 eV). High-resolution C1s peak could be deconvoluted into Mo-C, Si-C and $-\text{sp}^2$ carbon at 282.7, 283.4 and 284.4 eV, respectively. Therefore, a possibility of chemical interaction/bond formation exists between MoS_2 sheets and SiCN ceramic, confirmed by the presence of Mo-C, Mo-Si bonds.

Electrochemical performance of acid-treated MoS_2 and $\text{SiCN}-\text{MoS}_2$ composite electrodes was studied and compared by performing galvanostatic cycling experiments of the half-cell under constant current conditions. When cycled between 10 mV to 3 V at $100 \text{ mA}\cdot\text{g}^{-1}$ constant current, first cycle discharge capacity of $698.9 \text{ mAh}\cdot\text{g}^{-1}$ (or $89.84 \text{ mAh}\cdot\text{g}^{-1}_{\text{electrode}}$, i.e., when normalized with respect to total weight of the electrode including the current collector) and charge capacity of $476.3 \text{ mAh}\cdot\text{g}^{-1}$ (or $61.2 \text{ mAh}\cdot\text{g}^{-1}_{\text{electrode}}$) were observed for the acid-treated MoS_2 specimen (Figure 3). Cycle hysteresis of approximately 0.5V was also observed, which is typical of a conversion



type reaction. After 20 cycles, the reversible capacity decayed to $124.2 \text{ mAh}\cdot\text{g}^{-1}$ or 26% of initial capacity, which was slightly lower than the theoretical capacity of $167 \text{ mAh}\cdot\text{g}^{-1}$ for bulk MoS_2 (considering one mole of Li^+ intercalation reaction). Under cycling at similar conditions, the SiCN-MoS_2 traditional electrode exhibited first cycle discharge capacity of $574.1 \text{ mAh}\cdot\text{g}^{-1}$ (or $126.1 \text{ mAh}\cdot\text{g}^{-1}_{\text{electrode}}$) and reversible capacity of $457.6 \text{ mAh}\cdot\text{g}^{-1}$ (or $100.5 \text{ mAh}\cdot\text{g}^{-1}_{\text{electrode}}$). During the cycling test for 20 cycles the initial reversible capacity was retained at $477 \text{ mAh}\cdot\text{g}^{-1}$ (or $104.7 \text{ mAh}\cdot\text{g}^{-1}_{\text{electrode}}$). For the free-standing SiCN-MoS_2 composite paper electrode cycled under similar conditions, the first-cycle discharge capacity of $726.4 \text{ mAh}\cdot\text{g}^{-1}$ and reversible capacity $532.1 \text{ mAh}\cdot\text{g}^{-1}$ were observed. These capacities were retained after 20 cycles at $445.6 \text{ mAh}\cdot\text{g}^{-1}$ (73% of initial value). Anticipated intercalation and conversion reactions for exfoliated MoS_2 are given as:

At counter electrode,



Intercalation at working electrode



Conversion reaction at working electrode,



Where, x represents the number of moles of intercalating Li-ions (or corresponding electrons) in the host material. Based on varying slope

of capacity versus voltage plot, the cycling profile for these electrode materials was divided into three phases, as shown Figures 3(a) and 3(c).^{50,58–60} Individual contribution of each phase to overall capacity of initial and last tested cycles for MoS_2 and SiCN-MoS_2 are shown in Figure 3(f).

The changing voltage slope and plateaus observed in the cycled electrodes can be studied further by differentiating capacity with respect to the voltage as shown in Supplementary Figure S5. The plateaus or steep slope observed in the cycling plot, appear as distinct peaks (labeled) in corresponding dQ/dV plots. Varying intensity of each peak indicates changing rates of Li-ion interaction within the host material, further signifying various reactions and structural phases involved. First-cycle dQ/dV for exfoliated MoS_2 showed prominent lithiation peaks at approximately 1.1 V and 0.57 V, corresponding to conversion reaction whereby Li_xMoS_2 converts to Mo metal and Li_2S (Equation 3). The delithiation peak at 2.2 V is known to originate from the crystalline nature of MoS_2 .¹² For the second cycle, prominent lithiation peaks were observed at approximately 1.9 and 0.3 V, and an delithiation peak was observed at 2.3 V. These results are consistent with data from literature on transition metal sulfide electrodes.^{9,12,17} For the first-cycle of SiCN-MoS_2 electrode, a slight shift in potential of lithiation peaks were observed at approximately 0.93 V, 0.56 V, 0.3 V, and 40 mV (when compared to MoS_2 first-cycle behavior). For the second cycle, major reduction peaks were observed at approximately 2 V, 1.1 V, and 0.4 V, but no change was observed in delithiation peak position. The SiCN-MoS_2 free-standing paper electrode experienced reduction and oxidation peaks




Figure 3 | Electrochemical data. Comparison of first, second and twentieth electrochemical cycle (voltage-capacity plots) of half-cells of (a) acid-treated MoS_2 ($85 \text{ mA}\cdot\text{g}^{-1}$), (b) SiCN-MoS_2 (at $116 \text{ mA}\cdot\text{g}^{-1}$) composite and (c) SiCN-MoS_2 freestanding composite paper electrodes. (d) Electrochemical cycling performance of traditional electrodes (acid-treated MoS_2 , SiCN , SiCN-MoS_2 composite) and freestanding electrode (SiCN-MoS_2 paper) for initial 20 cycles. (e) C-rate cycling performance comparison of SiCN-MoS_2 composite and SiCN-MoS_2 paper. (f) Comparison of total capacity for initial (1st and 2nd) and final (20th) cycles and contribution of various reactions for acid-treated MoS_2 and SiCN-MoS_2 electrodes.

Table 1 | Summary of the electrochemical data and comparison with literature on other exfoliated-MoS₂ based electrodes

Electrode Type	Active Material (mg)	First Reversible Capacity (mAh·g ⁻¹)	ICL (%)	First Reversible Capacity (mAh·g ⁻¹ _{electrode})	Reversible capacity in (mAh·g ⁻¹ _{electrode}) (20 cycles)
MoS ₂ traditional	1.66	595.3	32	61.22	16
SiCN traditional	1.12	13	86.6	7.17	2
SiCN-MoS ₂ traditional	3.49	572.05	20.2	100.5	104.8
SiCN-MoS ₂ paper electrode	6.4	623.5	27	498.8	417.8
MoS ₂ exfoliated traditional (Ref. 16)	N.A.	~766	32	N.A.	N.A.
MoS ₂ bulk traditional (Ref. 16)	N.A.	275	54	N.A.	N.A.
MoS ₂ paper (Ref. 20)	N.A.	375	N.A.	~375	~125
MoS ₂ /CNT (Ref. 20)	N.A.	280	N.A.	~280	~225

similar to SiCN-MoS₂ traditional electrodes. Lithiation (0.05 and 0.75 V) and delithiation (0.15 V) peaks of rGO (graphene)⁶¹ were not distinguishable from primary peaks of SiCN-MoS₂ because contribution of rGO (10% or less mass loading) to overall specific capacity was negligible.

Figure 3 (d) compares the charge capacity of SiCN-MoS₂ composite (traditional and paper electrodes) to acid-treated MoS₂ and ‘neat’ SiCN ceramic electrodes cycled under similar conditions. The figure shows that SiCN-MoS₂ electrodes had approximately 26% higher capacity retention at 20 cycles when compared to MoS₂. In addition, the ‘neat’ SiCN electrode had negligible reversible capacity of approximately 20 mAh·g⁻¹. Figure 3 (e) shows the C-rate performance of SiCN-MoS₂ traditional and paper electrodes. First-cycle charge capacities were 465.9 mAh·g⁻¹ and 530 mAh·g⁻¹ for traditional and paper electrodes, respectively. When current density increased to 2400 mA·g⁻¹, respective charge capacities dropped to 326.4 mAh·g⁻¹ and 191.9 mAh·g⁻¹. However, most of the capacity was recovered when the current density was decreased to 100 mA·g⁻¹, reaching 414.8 mAh·g⁻¹ (83% retained) and 509.2 mAh·g⁻¹ (96% retained) for traditional and paper electrodes, respectively. A summary of the electrochemical data is presented in Table 1.

After 20 electrochemical cycles, the half-cells were disassembled and the electrode was recovered (delithiated state) for further investigation of structure and chemical composition. Figures 4(a through c) are SEM images of the disassembled cells. The inserts are corresponding optical camera images in which the MoS₂ electrode exhibited signs of microcracks, coating delamination and slight discoloration, suggesting susceptibility to volume and chemical changes during the intercalation (Phase I) and conversion (Phase II) reactions. However, SiCN-MoS₂ cycled electrodes appeared to be largely intact without any change in color from the original (pre-cycled) state. SEM imaging also provided additional details regarding the effects of electrochemical cycling at the micro-scale. The cycled MoS₂ electrode showed uneven surface and mud cracks (Figure 4(a)), while the SiCN-MoS₂ electrodes (traditional and paper) were relatively more porous and consisted of an uninterrupted solid electrolyte interphase (SEI) film on the active material (Figures 4 (b,c)).

The chemical composition of the cycled SiCN-MoS₂ electrode was also analyzed by XPS. As shown in Figure 4(d) the Mo3d elemental peak evolved into three slightly overlapping peaks at 229.13 eV, 232.48 eV and 235.81 eV. Low energy peaks at 229.13 eV and




Figure 4 | Post electrochemical analysis. SEM images of disassembled cells (a) acid-treated MoS₂, (b) SiCN-MoS₂ composite and (c) SiCN-MoS₂ paper electrodes after testing for 20 cycles. The insert shows digital images of corresponding electrode surfaces. (d) Elemental X-ray photoelectron spectra of the disassembled SiCN-MoS₂ composite electrode show Mo, S, and C phase modifications with additional Li peaks. Scale bar is 10 μm.



232.1 eV were attributed to Mo-S and Mo-O type bonds, respectively. Higher energy doublets at 232.48 eV and 235.81 eV could be assigned to the more electronegative Mo-O₂/MoO₃ and Mo-O_x species, respectively.^{54–57} Both sulfur peaks shifted to higher energies of 161.06 eV and 162.02 eV, likely due to S²⁻ and polysulfide (Li-S) entities, respectively.^{56,57} Broad silicon elemental peak with weak intensity could be attributed to Si-C and Si-O type bonds. The shifted oxygen peak at 530.5 eV could be fitted by a peak at 530.46 eV due to Mo-O type bonds and fitted by a peak at 531.54 eV due to multiple entities of more electronegative Li₃PO₄, Li₂CO₃, Li₂O, LiOH, and Mo-O₃ compounds.⁵⁶ High-resolution C1s peak was deconvoluted into Mo-C, Si-C, C-sp², C-O, and Li-C-O at 282.7 eV, 283.6 eV, 285.5 eV, 286.2 eV, 287.5 eV, and 289.8 eV, respectively. Lastly, the Li1s elemental peak at 55.4 eV was assigned to Li-C (Li₂CO₃) and Li-O (Li₂O) at 55.22 eV, and 55.48 eV, respectively.

Conclusion. Acid-treated MoS₂ was utilized to prepare polysilazane/MoS₂ composite, which upon pyrolysis in an inert environment, resulted in formation of SiCN-MoS₂ nanosheets. Electron microscopy revealed uniform distribution of SiCN-MoS₂ stacked sheets in the composite. XPS analysis revealed formation of Mo-C and Mo-O bonds, indicating chemical bonding of the SiCN's carbon phase with molybdenum atoms. Electrochemical performance of the composite was studied as working electrode in LIB half-cell, revealing an increasingly stable cycling and higher capacity retention compared to 'neat' MoS₂ after 20 cycles. The contribution of electrolyte decomposition (Phase III) to overall capacity decreased for SiCN-MoS₂ electrodes. This decrease is one of the reasons for decreased first-cycle loss and increased capacity retention for SiCN-MoS₂ composite. Additionally, the electrically conductive nature of SiCN ceramics may have resulted in faster Li-ion diffusion. These observations suggests that chemical interfacing of MoS₂ surfaces with precursor-derived ceramics is a promising approach toward achieving stable Li-cycling in rechargeable batteries composed of transition metal sulfide electrodes.

- Chen, J., Kuriyama, N., Yuan, H., Takeshita, H. T. & Sakai, T. Electrochemical hydrogen storage in MoS₂ nanotubes. *J. Am. Chem. Soc.* **123**, 11813–11814 (2001).
- Hu, K. H., Hu, X. G. & Sun, X. J. Morphological effect of MoS₂ nanoparticles on catalytic oxidation and vacuum lubrication. *Appl. Surf. Sci.* **256**, 2517–2523 (2010).
- Fang, X. *et al.* Lithium storage performance in ordered mesoporous MoS₂ electrode material. *Micropor. Mesopor. Mat.* **151**, 418–423 (2012).
- Cheng, F., Liang, J., Tao, Z. & Chen, J. Functional materials for rechargeable batteries. *Adv. Mater.* **23**, 1695–1715 (2011).
- Etacheri, V., Marom, R., Elazari, R., Salitra, G. & Aurbach, D. Challenges in the development of advanced Li-ion batteries: A review. *Energy Environ. Sci.* **4**, 3243–3262 (2011).
- Li, H., Li, W., Ma, L., Chen, W. & Wang, J. Electrochemical lithiation/delithiation performances of 3D flowerlike MoS₂ powders prepared by ionic liquid assisted hydrothermal route. *J. Alloys Compd.* **471**, 442–447 (2009).
- Feng, C. *et al.* Synthesis of molybdenum disulfide (MoS₂) for lithium ion battery applications. *Mater. Res. Bull.* **44**, 1811–1815 (2009).
- Du, G. *et al.* Superior stability and high capacity of restacked molybdenum disulfide as anode material for lithium ion batteries. *Chem. Commun.* **46**, 1106–1108 (2010).
- Imanishi, N., Toyoda, M., Takeda, Y. & Yamamoto, O. Study on lithium intercalation into MoS₂. *Solid State Ionics* **58**, 333–338 (1992).
- Xu, X., Wen, L., Youngsik, K. & Cho, J. Nanostructured transition metal sulfides for lithium ion batteries: Progress and challenges. *Nano Today* **9**, 604–630 (2014).
- Chan, C. K. *et al.* High-performance lithium battery anodes using silicon nanowires. *Nat. Nanotechnol.* **3**, 31–35 (2008).
- Papageorgopoulos, C. A. & Jaegermann, W. Li intercalation across and along the van-der-waals surfaces of MoS₂ (0001). *Surf. Sci.* **338**, 83–93 (1995).
- Haering, R. R., Stiles, J. A. R., Brandt, K., inventors; Haering, R. R., Stiles, J. A. R. & Brandt, K., assignee. *Lithium molybdenum disulfide battery cathode*. *United States patent US 4224390*. 1980 September 23.
- Chhowalla, M. *et al.* The chemistry of two-dimensional layered transition metal dichalcogenide nanosheets. *Nat. Chem.* **5**, 263–275 (2013).
- Rao, C. N. R., Matte, H. S. S. R. & Maitra, U. Graphene analogues of inorganic layered materials. *Angew. Chem. Int. Ed.* **52**, 13162–13185 (2013).

- Xiao, J. *et al.* Exfoliated MoS₂ nanocomposite as an anode material for lithium ion batteries. *Chem. Mater.* **22**, 4522–4524 (2010).
- Bhandavat, R., David, L. & Singh, G. Synthesis of surface-functionalized WS₂ nanosheets and performance as Li-ion battery anodes. *J. Phys. Chem. Lett.* **3**, 1523–1530 (2012).
- David, L., Bhandavat, R. & Singh, G. MoS₂/graphene composite paper for sodium-ion battery electrodes. *ACS Nano* **8**, 1759–1770 (2014).
- Coleman, J. N. *et al.* Two-dimensional nanosheets produced by liquid exfoliation of layered materials. *Science* **331**, 568–571 (2011).
- Smith, R. J. *et al.* Large-Scale Exfoliation of inorganic layered compounds in aqueous surfactant solutions. *Adv. Mater.* **23**, 3944–+ (2011).
- Radisavljevic, B., Radenovic, A., Brivio, J., Giacometti, V. & Kis, A. Single-layer MoS₂ transistors. *Nat. Nanotechnol.* **6**, 147–150 (2011).
- Brivio, J., Alexander, D. T. L. & Kis, A. Ripples and layers in ultrathin MoS₂ membranes. *Nano Lett.* **11**, 5148–5153 (2011).
- Liu, H. *et al.* Highly ordered mesoporous MoS₂ with expanded spacing of the (002) crystal plane for ultrafast lithium ion storage. *Adv. Energy Mater.* **2**, 970–975 (2012).
- Wang, S. *et al.* Hydrothermal synthesis of molybdenum disulfide for lithium ion battery applications. *Chin. J. Chem. Eng.* **18**, 910–913 (2010).
- Sen, U. K. & Mitra, S. High-rate and high-energy-density lithium-ion battery anode containing 2d MoS₂ nanowall and cellulose binder. *ACS Appl. Mater. Interfaces* **5**, 1240–1247 (2013).
- Choi, S. H., Ko, Y. N., Lee, J. K. & Kang, Y. C. 3D MoS₂-graphene microspheres consisting of multiple nanospheres with superior sodium ion storage properties. *Adv. Funct. Mater.* DOI: 10.1002/adfm.201402428 (2015).
- Chang, K. & Chen, W. L-Cysteine-Assisted Synthesis of layered MoS₂/graphene composites with excellent electrochemical performances for lithium ion batteries. *ACS Nano* **5**, 4720–4728 (2011).
- Lin, Y. C. *et al.* Wafer-scale MoS₂ thin layers prepared by MoO₃ sulfuration. *Nanoscale* **4**, 6637–6641 (2012).
- Zhan, Y., Liu, Z., Najmaei, S., Ajayan, P. M. & Lou, J. Large-area vapor-phase growth and characterization of MoS₂ atomic layers on a SiO₂ substrate. *Small* **8**, 966–971 (2012).
- Shi, Y. *et al.* van der Waals epitaxy of MoS₂ layers using graphene as growth templates. *Nano Lett.* **12**, 2784–2791 (2012).
- Liu, K. K. *et al.* Growth of large-area and highly crystalline MoS₂ thin layers on insulating substrates. *Nano Lett.* **12**, 1538–1544 (2012).
- Zhou, W. *et al.* Synthesis of Few-layer MoS₂ nanosheet-coated TiO₂ nanobelt heterostructures for enhanced photocatalytic activities. *Small* **9**, 140–147 (2013).
- Chang, K. & Chen, W. In situ synthesis of MoS₂/graphene nanosheet composites with extraordinarily high electrochemical performance for lithium ion batteries. *Chem. Commun.* **47**, 4252–4254 (2011).
- Hu, L. *et al.* Highly conductive paper for energy-storage devices. *PNAS* **106**, 21490–21494 (2009).
- Chen, D. *et al.* In situ nitrogenated graphene-few-layer WS₂ composites for fast and reversible Li+ storage. *Nanoscale* **5**, 7890–7896 (2013).
- Hwang, H., Kim, H. & Cho, J. MoS₂ Nanoplates consisting of disordered graphene-like layers for high rate lithium battery anode materials. *Nano Lett.* **11**, 4826–4830 (2011).
- Shi, Y. *et al.* Self-assembly of hierarchical MoS_x/CNT nanocomposites (2<x<3): towards high performance anode materials for lithium ion batteries. *Sci. Rep.* **3**, Article number: 2169 (2013).
- Wang, J. Z. *et al.* Development of MoS₂-CNT composite thin film from layered MoS₂ for lithium batteries. *Adv. Energy Mater.* **3**, 798–805 (2013).
- Wang, Z. *et al.* CTAB-assisted synthesis of single-layer MoS₂-graphene composites as anode materials of Li-ion batteries. *J. Mater. Chem. A* **1**, 2202–2210 (2013).
- Xiao, J. *et al.* Electrochemically induced high capacity displacement reaction of POE/MoS₂/graphene nanocomposites with lithium. *Adv. Funct. Mater.* **21**, 2840–2846 (2011).
- Yu, H. *et al.* Three-dimensional hierarchical architectures constructed by graphene/MoS₂ nanoflake arrays and their rapid charging/discharging properties as lithium-ion battery anodes. *Chem-Eur. J.* **19**, 5818–5823 (2013).
- Zhou, X., Wan, L. J. & Guo, Y. G. Synthesis of MoS₂ nanosheet-graphene nanosheet hybrid materials for stable lithium storage. *Chem. Commun.* **49**, 1838–1840 (2013).
- Shah, S. R. & Raj, R. Nanodevices that explore the synergies between PDCs and carbon nanotubes. *J. Eur. Ceram. Soc.* **25**, 243–249 (2005).
- Lehman, J. H. *et al.* Core-shell composite of SiCN and multiwalled carbon nanotubes from toluene dispersion. *J. Mater. Sci.* **45**, 4251–4254 (2010).
- Cai, Y. *et al.* Carbon nanotubes welded by precursor-derived silicoboron carbonitride ceramics: A TEM study. *Phys. Status Solidi A* **193**, R13–R15 (2002).
- David, L., Asok, D. & Singh, G. Synthesis and extreme rate capability of Si–Al–C–N functionalized carbon nanotube spray-on coatings as li-ion battery electrode. *ACS Appl. Mater. Interfaces* **6**, 16056–16064 (2014).
- Kroke, E. *et al.* Silazane derived ceramics and related materials. *Mat. Sci. Eng. R* **26**, 97–199 (2000).
- Ramakrishnan, P. A. *et al.* Silicoboron-carbonitride ceramics: A class of high-temperature, dopable electronic materials. *Appl. Phys. Lett.* **78**, 3076–3078 (2001).



49. Divigalpitiya, W. M. R., Frindt, R. F. & Morrison, S. R. Inclusion systems of organic-molecules in restacked single-layer molybdenum-disulfide. *Science* **246**, 369–371 (1989).
50. Cabana, J., Monconduit, L., Larcher, D. & Rosa Palacin, M. beyond intercalation-based Li-ion batteries: the state of the art and challenges of electrode materials reacting through conversion reactions. *Adv. Mater.* **22**, E170–E192 (2010).
51. Oxley, J. D., Mdleleni, M. M. & Suslick, K. S. Hydrodehalogenation with sonochemically prepared Mo₂C and W₂C. *Catal. Today* **88**, 139–151 (2004).
52. David, L. & Singh, G. reduced graphene oxide paper electrode: opposing effect of thermal annealing on Li and Na cyclability. *J. Phys. Chem. C* **118**, 28401–28408 (2014).
53. Hummers, W. S. & Offeman, R. E. Preparation of graphitic oxide. *J. Am. Chem. Soc.* **80**, 1339–1339 (1958).
54. Levasseur, A., Vinatier, P. & Gonbeau, D. X-ray photoelectron spectroscopy: A powerful tool for a better characterization of thin film materials. *B. Mater. Sci.* **22**, 607–614 (1999).
55. Baker, M. A., Gilmore, R., Lenardi, C. & Gissler, W. XPS investigation of preferential sputtering of S from MoS₂ and determination of Mo_xS_y stoichiometry from Mo and S peak positions. *Appl. Surf. Sci.* **150**, 255–262 (1999).
56. Wagner, C. D., Naumkin, A. V., Kraut-Vass, A., Allison, J. W., Powell, C. J., & Rumble Jr, J. R. *NIST X-ray photoelectron spectroscopy database 20*, Version 4.1. Available at: <http://srdata.nist.gov/xps/> (Accessed 6th January 2015).
57. Benoist, L. *et al.* XPS analysis of lithium intercalation in thin-films of molybdenum oxysulfides. *Surf. Interface Anal.* **22**, 206–210 (1994).
58. Julien, C., Saikh, S. I., & Nazri, G. A. Electrochemical studies of disordered MoS₂ as cathode material in lithium batteries. *Mat. Sci. Eng. B-Solid* **15**, 73–77 (1992).
59. Julien, C. M. Lithium intercalated compounds - Charge transfer and related properties. *Mat. Sci. Eng. R* **40**, 47–102 (2003).
60. Selwyn, L. S., Mckinnon, W. R., Vonsacken, U. & Jones, C. A. Lithium electrochemical-cells at low-voltage - decomposition of Mo and W dichalcogenides. *Solid State Ionics* **22**, 337–344 (1987).
61. David, L. *et al.* Synthesis of graphene films by rapid heating and quenching at ambient pressures and their electrochemical characterization. *ACS Appl. Mater. Interfaces* **5**, 546–552 (2013).

Acknowledgments

This research is based upon work supported by the National Science Foundation (CMMI NSF CAREER Award) grant no. 1454151 to G.S. U.B. is supported by the Kansas State University First Generation Scholars program. Authors would like to thank Dr. Jerry Hunter and Andrew Gio (Virginia Tech) for help with the XPS. G.S. thanks Professor Vikas Berry (University of Illinois at Chicago) for useful discussions related to synthesis of graphene oxide. Publication of this article was funded in part by the Kansas State University Open Access Publishing Fund.

Author contribution

R.B. prepared SiCN-MoS₂ composite, traditional electrodes, performed SEM and XPS analysis. L.D. prepared paper-based electrodes and their XRD, TGA and TEM analysis. U.B. assisted R.B. and L.D. with coin cell preparation and electrochemical testing. G.S. conceived the idea, designed the experiments and wrote the manuscript with inputs from R.B. and L.D. All authors discussed the results and commented or revised the manuscript.

Additional information

Supplementary information accompanies this paper at <http://www.nature.com/scientificreports>

Competing financial interests: The authors declare no competing financial interests.

How to cite this article: David, L., Bhandavat, R., Barrera, U. & Singh, G. Polymer-Derived Ceramic Functionalized MoS₂ Composite Paper as a Stable Lithium-Ion Battery Electrode. *Sci. Rep.* **5**, 9792; DOI:10.1038/srep09792 (2015).



This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder in order to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>