

The effect of every day drinks on composite restorations aesthetics: in vitro study

Andreevski Aleksandar¹, Kovachevska Ivona²

¹*PZU AA Dental, Bitola, RN Macedonia*

²*Faculty of Medical Sciences, Dental Medicine, University "Goce Delcev" – Štip, RN Macedonia*

Abstract:

Aim: The main objectives of this in vitro study is, within its limitations, is to evaluate whether every day drinks affect the aesthetics of the dental composite resin materials.

Method: Thirty microhybrid composite resin (Gradia Direct) discs were made (15 mm in diameter and 2mm thick) and randomly divided into five groups. The groups were immersed in colorants as red wine, coca-cola, filter coffee, aronia tea and distilled water as control group. Spectrophotometer X-RITE RM 200 was used to follow the changes in color with three measurements, first one at the beginning (baseline), second at the middle, third at the end of the research. Each group was immersed in its colorant twice a day for the duration of the study. The received data was analyzed according the CIE L*a*b* color system.

Result: Three out of four colorants have surpassed the clinically acceptable threshold of discoloration which is $\Delta 2.7$. Significant discoloration was observed with the warm drinks compared with the ones used on room temperature. The tea caused most significant discoloration ($\Delta 22.17$) followed by coffee ($\Delta 16.73$) and wine ($\Delta 12.10$). The drink that caused the least discoloration was the coca-cola ($\Delta 1.24$).

Conclusion: The color stability of the composite resin restorations is affected by the everyday drinks that are consumed, from some more than others.

Key words: discoloration; composite resin; spectrophotometer;

Reference

- [1]. Afzali BM, Ghasemi A, Mirani A, Abdolazimi Z, Baghban AA, Kharazifard MJ. "Effect of Ingested Liquids on Color Change of Composite Resins". JDT August 2015; Vol. 12, No. 8
- [2]. Al Kheraif AAA, Qasim SSB, Ramakrishnaian R, Rehman I. "Effect of different beverages on the color stability an degree of conversion of nano and microhybrid composites". Dental Materials Journal 2013; 32(2): 326-331
- [3]. Antonov M, Lenhardt L, Manojlovic D, Milicevic B, Zekovic I, Dramacanicin MD. "Changes of Color and Fluorescence of Resin Composites Immersed in Beer". Journal of Esthetic and Restorative Dentistry 2016 Vol 00, No 00,
- [4]. Avsar A, Yuzbasioglu E, Sarac D. "The Effect of Finishing and Polishing Techniques on the Surface Roughness and the Color of Nanocomposite Resin Restorative Materials". Adv Clin Exp Med 2015, 24, 5, 881-890
- [5]. Awliya WY, Al-Alwani DJ, Gashmer ES, Al-Mandil HB. "The effect of commonly used types of coffe on surface microhardness and color stability of resin-based composite restorations" The Saudi Dental Journal (2010) 22, 177 – 181
- [6]. Barbosa SH, Zanata RL, Navarro MF de Lima, Nunes OB, "Effect of different finishing and polishing techniques on the surface roughness of microfilled, hybrid and packable composite resins" Brazilian Dental Journal (2005) 16(1): 39 – 44, ISSN 0103 – 6440
- [7]. Domingos PAS, Garcia PPNS, de Oliveira ALBM, Palma-Dibb RG. "Composite resin color stability: influence of light sources and immersion media". J Appl Oral Sci. 2011;19(3):204-11
- [8]. Ergücü Z, Türkün LS, Aladağ A. "Color Stability of Nanocomposites Polished with One-Step Systems". Operative Dentistry, 2008, 33-4, 413-420
- [9]. Ertas E, Güler AU, Yücel AC, Köprülü H, Güler E. "Color Stability of Resin Composites after Immersion in Different Drinks". Dental Materials Journal 2006 25(2):371-376
- [10]. Festuccia MSCC, Garcia LFR, Cruvinel DR, Pires-de-souza FCP. "Color stability, surface roughness and microhardness of composite submitted to mothrinsing action". J Appl Oral Sci. 2012; 20 (2): 200-5
- [11]. Güler AU, Güler E, Yücel AÇ, Ertaş E. "Effects of polishing procedures on color stability of composite resins" Journal of Applied Oral Science, 2009;17(2):108 – 12
- [12]. Khatri A, Nandlal B. "Staining of a Conventional and a Nanofilled Composite Resin Exposed in vitro to Liquid Ingested by Children". International Journal of Clinical Pediatric Dentistry, Sep-Dec 2010;3(3): 183-188
- [13]. Kumari RV, Nagaraj H, Siddaraju K, Poluri RK. "Evaluation of the Efect of Surface Polishing, Oral Beverages and Food Colorants on Color Stability and Surface Roughness of Nanocomposite Resins". Journal of International Oral Health 2015; 7(7):63-70
- [14]. Lee YK, Yu B, Lim HN, Lim JI. "Difference in the color stability of direct and indirect resin composites" Journal of Applied Oral Science 2011;19(2):154 – 60
- [15]. Manojlovic D, Lenhardt L, Milicevic B, Antonov M, Miletic V, Dramacanicin MD. "Evaluation of Staining – Dependant Colour Changes in Resin Composites Using Principal Component Analysis". Scientific Reports 5:14638
- [16]. Özdaş DÖ, Kazak M, Çilingir A, Subaşı MG, Tiryaki M and Günal Ş,. "Color Stability of Composites After Short-term Oral Simulation: An *in vitro* Study" The Open Dentistry Journal, 2016, 10, 431-437
- [17]. Park JK, Kim TH, Ko CC, Garcia-Godoy F, Kim HI, Kwon YH. "Effect of staining on discoloration of resin nanocomposites". Am J Dent. 2010 February ; 23(1): 39-42
- [18]. Samra APB, Pereira SK, Delgado LC, Borges CP. "Color stability evaluation of aesthetic restorative materials". Braz Oral Res 2008;22(3):205-10
- [19]. Sarkis E. "Color change of some aesthetic dental materials: Effect of immersing solutions and finishing of their surfaces" The Saudi Dental Journal (2012) 24, 85 – 89
- [20]. Spina DRF, Grossi JRA, Cunali RSC, Filho FB, da Cunha LF, Gonzaga CC, Correr GM. "Evaluation of Discoloration Remuval by Polishing Resin Composites Submitted to Staining in Different Drink Solutions". International Scholarly Research Notices Volume 2015, Article ID 853975, 5 pages
- [21]. Tanthanuch S, Kukiattrakoon B, Peerasukprasert T, Chanmanee N, Chaisomboonphun P, Rodklai A. "The effect of red and white wine on color changes of nanofilled and nanohybrid resin composites" Restorative Dentistry & Endodontics ISSN 2234 – 7658 (print) / ISSN 2234 – 7666 (online) <http://dx.doi.org/10.5395/rde.2016.41.2.130>
- [22]. Tekce N, Tuncer S, Demirci M, Serim ME, Baydemir C. "The effect of different drinks on the color stability of different restorative materials after one month". Restorative Dentistry & Endodontics RDE 2015.40.4.255