



ELSEVIER

The Spine Journal 12 (2012) 265–272

**THE
SPINE
JOURNAL**

Basic Science

Osteoblasts exhibit a more differentiated phenotype and increased bone morphogenetic protein production on titanium alloy substrates than on poly-ether-ether-ketoneRene Olivares-Navarrete, DDS, PhD^a, Rolando A. Gittens, MS^b, Jennifer M. Schneider, MS^c, Sharon L. Hyzy, BS^{a,d}, David A. Haithcock, BS^a, Peter F. Ullrich, MD^e, Zvi Schwartz, DMD, PhD^{a,f}, Barbara D. Boyan, PhD^{a,*}^aWallace H. Coulter Department of Biomedical Engineering at Georgia Tech and Emory University, Georgia Institute of Technology, 315 Ferst Drive NW, Atlanta, GA 30332-0363, USA^bSchool of Materials Science and Engineering, Georgia Institute of Technology, 711 Ferst Drive NW, Atlanta, GA 30332, USA^cTitan Spine, LLC, 6140 W. Executive Drive, Suite A, Mequon, WI 53092, USA^dSchool of Biology, Georgia Institute of Technology, 315 Ferst Drive NW, Atlanta, GA 30332-0363, USA^eNeuroSpine Center of Wisconsin, 5320 West Michaels Drive, Appleton, WI 54913, USA^fDepartment of Periodontics, University of Texas Health Science Center at San Antonio, 7703 Floyd Curl Drive, San Antonio, TX 78229, USA

Received 1 February 2011; revised 3 October 2011; accepted 7 February 2012

Abstract

BACKGROUND CONTEXT: Multiple biomaterials are clinically available to spine surgeons for performing interbody fusion. Poly-ether-ether-ketone (PEEK) is used frequently for lumbar spine interbody fusion, but alternative materials are also used, including titanium (Ti) alloys. Previously, we showed that osteoblasts exhibit a more differentiated phenotype when grown on machined or grit-blasted titanium aluminum vanadium (Ti6Al4V) alloys with micron-scale roughened surfaces than when grown on smoother Ti6Al4V surfaces or on tissue culture polystyrene (TCPS). We hypothesized that osteoblasts cultured on rough Ti alloy substrates would present a more mature osteoblast phenotype than cells cultured on PEEK, suggesting that textured Ti6Al4V implants may provide a more osteogenic surface for interbody fusion devices.

PURPOSE: The aim of the present study was to compare osteoblast response to smooth Ti6Al4V (sTiAlV) and roughened Ti6Al4V (rTiAlV) with their response to PEEK with respect to differentiation and production of factors associated with osteogenesis.

STUDY DESIGN: This in vitro study compared the phenotype of human MG63 osteoblast-like cells cultured on PEEK, sTiAlV, or rTiAlV surfaces and their production of bone morphogenetic proteins (BMPs).

METHODS: Surface properties of PEEK, sTiAlV, and rTiAlV discs were determined. Human MG63 cells were grown on TCPS and the discs. Confluent cultures were harvested, and cell number, alkaline phosphatase-specific activity, and osteocalcin were measured as indicators of osteoblast maturation. Expression of messenger RNA (mRNA) for BMP2 and BMP4 was measured

FDA device/drug status: Not applicable.

Author disclosures: **RON:** Nothing to disclose. **RAG:** Nothing to disclose. **JMS:** Stock Ownership: Titan Spine, LLC (4,000 shares, 1%). **SLH:** Nothing to disclose. **DAH:** Nothing to disclose. **PFU:** Royalties: Titan Spine (D); Stock Ownership: Titan Spine (45,000,000 shares, 33%); Trips/Travel: Titan Spine (Nonfinancial); Board of Directors: Titan Spine (Nonfinancial). **ZS:** Royalties: University of Texas (B); Stock Ownership: SpherIngenics (15%); Research Support (Staff/Materials): MTF ITI (E, Paid directly to institution/employer); Grants: Titan Spine (E, Paid directly to institution/employer). **BDB:** Stock Ownership: Carticept Medical, Inc. (150,000 shares), SpherIngenics, Inc. (35% ownership), ArthroCare, Inc. (15,000 shares); Private Investments: MedShape Solutions, Inc. (5,000 shares); Consulting: Musculoskeletal Transplant Foundation

(Financial and Nonfinancial), Exactech (Financial); Trips/Travel: Titan Spine (A), MTF (A); Board of Directors: Carticept Medical, Inc. (Nonfinancial), SpherIngenics, Inc (Nonfinancial); Scientific Advisory Board: Exactech (A); Research Support (Staff/Materials): MTF (A, Paid directly to institution/employer), Titan Spine (D, Paid directly to institution/employer); Grants: ITI Foundation (F, Paid directly to institution/employer).

The disclosure key can be found on the Table of Contents and at www.TheSpineJournalOnline.com.

* Corresponding author. Wallace H. Coulter Department of Biomedical Engineering, Georgia Institute of Technology, 315 Ferst Drive NW, Atlanta, GA 30332-0363, USA. Tel.: (404) 385-4108; fax: (404) 894-2291.

E-mail address: barbara.boyan@bme.gatech.edu (B.D. Boyan)

by real-time polymerase chain reaction. Levels of BMP2, BMP4, and BMP7 proteins were also measured in the conditioned media of the cell cultures.

RESULTS: Although roughness measurements for sTiAlV ($S_a=0.09\pm 0.01$), PEEK ($S_a=0.43\pm 0.07$), and rTiAlV ($S_a=1.81\pm 0.51$) varied, substrates had similar contact angles, indicating comparable wettability. Cell morphology differed depending on the surface. Cells cultured on Ti6Al4V had lower cell number and increased alkaline phosphatase specific activity, osteocalcin, BMP2, BMP4, and BMP7 levels in comparison to PEEK. In particular, roughness significantly increased the mRNA levels of BMP2 and BMP4 and secreted levels of BMP4.

CONCLUSIONS: These data demonstrate that rTiAlV substrates increase osteoblast maturation and produce an osteogenic environment that contains BMP2, BMP4, and BMP7. The results show that modifying surface structure is sufficient to create an osteogenic environment without addition of exogenous factors, which may induce better and faster bone during interbody fusion. © 2012 Elsevier Inc. All rights reserved.

Keywords:

Ti6Al4V; PEEK; Osteoblast; BMP; Roughness

Introduction

Currently, spine surgeons have multiple biomaterial choices when performing an interbody fusion. Recently, poly-ether-ether-ketone (PEEK) has gained significant popularity as the biomaterial of choice for interbody fusion, particularly in the lumbar spine because of its radiolucency and reports that it has a modulus similar to that of bone [1–3]. However, PEEK does not integrate well with the surrounding bone and may form a fibrous connective interface [3–5]. As a result, micromotion is possible, eventually leading to implant failure [6,7].

Implant osseointegration, or direct contact between the implant surface and surrounding bone under loading conditions [8,9], depends on both bone quality and the host environment. Osseointegration is slower in osteopenic bone than in normal bone [10] and has been shown to be 50% slower in osteoporotic animals than in normal animals [11,12]. Thus, it is important that spinal fusion devices present an osteogenic surface during the fusion process.

Titanium aluminum vanadium (Ti6Al4V) alloys have a well-established history of use as bone graft cages or spacers in lumbar spine fusion procedures. Previous studies have shown that these alloys support good bone to implant contact and are well osseointegrated with the surrounding bone [13–15]. In vitro experiments comparing the responses of immature osteoblasts to machined and smooth Ti6Al4V (sTiAlV) substrate surfaces indicate that the differentiation of the cells is greater when the surface has a texture with micron-scale roughness [16]. These observations were confirmed using Ti6Al4V that had been grit blasted to create micron-scale roughness [17]. Moreover, when the same surface treatment was applied to Ti6Al4V pedicle screws and tested in vivo in sheep spines, the force required to pull out the screws was doubled compared with screws that had a smooth surface [17].

In the body, osteoblasts mature in osteoclast-conditioned areas of bone that present a micron-scale roughness [18], suggesting that surface texture is an important variable in bone formation. Studies using commercially pure titanium (Ti) substrates have shown that surfaces with micron- and

submicron-scale features promote greater osteoblast differentiation, matrix deposition, and production of osteogenic growth factors [19–21], which regulate the cells via autocrine and paracrine pathways [22–24], than do cells cultured on smooth surfaces. Similarly, microtextured Ti6Al4V surfaces support increased osteoblastic differentiation compared with sTiAlV surfaces [17]. Moreover, cells on Ti or Ti6Al4V are more differentiated than cells on traditional cell culture plastic [16,25,26]. These differences indicate that both surface chemistry and surface microtexture play a role and bring into question whether responses to materials typically used in interbody fusion, Ti6Al4V or PEEK, differ and if so, how.

The purpose of the present study was to compare the osteoblast phenotype of human osteoblast-like MG63 cells to smooth and microtextured Ti6Al4V surfaces with their phenotype on PEEK. MG63 cells are an immature osteoblast cell line used by many laboratories as a model to examine factors that promote osteoblast differentiation [27,28]. Of particular interest is whether cells grown on these biomaterials contribute to peri-implant bone formation by generating an osteogenic environment through production of osteoinductive factors. To test this, we assessed whether expression of bone morphogenetic proteins (BMPs) and their secretion into the medium were affected by the substrate surface. Because of the high doses used to induce bone formation and side effects derived from the clinical use of BMP2 for spine fusion [29–31], implant topographies that enhance cell-produced BMPs may enhance the osteogenic microenvironment and improve the stability of the interbody construct through bony on-growth to the interbody device [32].

Methods

Disc preparation and characterization

Surgical-grade Ti alloy (Ti6Al4V) and PEEK discs were used in this study (Titan Spine, LLC., Mequon, WI, USA). The discs were 15 mm in diameter and fit snugly in a well of a 24-well culture plate. Smooth Ti6Al4V discs were machined, tumbled to remove any burs, and passivated

through an acid bath, which removes inorganic contaminants on the surface and forms a stable oxide layer that reduces the reactivity of the bulk material with the environment. To create a roughened surface texture (roughened Ti6Al4V [rTiAlV]), Ti6Al4V discs were machined, treated with a proprietary etch process, and passivated. Poly-ether-ether-ketone substrates were machined and subsequently tumbled. Before use in cell culture studies, all discs were ultrasonically cleaned, sonicated in ultrapure water (Millipore, Billerica, MA, USA), and sterilized by autoclave (Tuttnauer, Hauppauge, NY, USA) for 20 minutes at 121°C and 15 PSI.

The surface topography was evaluated qualitatively using a field emission gun scanning electron microscope (Ultra 60 FEG-SEM; Carl Zeiss SMT Ltd., Cambridge, UK). Scanning electron microscope images were recorded using a 5-kV accelerating voltage and 30- μm aperture. Poly-ether-ether-ketone samples were coated with a thin layer of gold-palladium (Au-Pd) to avoid charging. Surface roughness was quantitatively analyzed using a confocal laser microscope (CLM) (OLS4000 CLM, Lext; Olympus, Center Valley, PA, USA). Each CLM analysis was performed over an area of 644 μm \times 644 μm using a scan height step of 50 nm, a 20 \times objective, and a cutoff wavelength of 100 μm to determine the mean values of surface roughness (S_a). Qualitative atomic concentration close to the surface was obtained by energy-dispersive X-ray spectroscopy (INCAx-act EDX; Oxford Instruments, Concord, MA, USA) to determine if there were any gross compositional changes as a result of surface treatment of the Ti alloys. Energy-dispersive X-ray spectroscopy spectra were collected using a magnification of 500 \times and a working distance of 10 mm. Contact angle measurements were obtained using a goniometer (CAM 100; KSV, Helsinki, Finland) equipped with a digital camera and image analysis software. Ultrapure water was used as the wetting liquid, with a drop size of 5 μL .

Cell culture

Human MG63 osteoblast-like cells (American Type Culture Collection, Manassas, VA, USA) were cultured on tissue culture polystyrene (TCPS), PEEK, sTiAlV, or rTiAlV at an initial cell density of 10,000 cells/cm². Media were changed 24 hours after plating and then every 48 hours until cells reached confluence on TCPS. When MG63 cultures reached confluence on TCPS, all cultures were treated for 24 hours with fresh media. At harvest, cell number was determined. To ensure that cells were completely removed from surfaces, cells were released with two sequential 10-minute incubations in 0.25% trypsin at 37°C and counted (Z1 cell and particle counter; Beckman Coulter, Fullerton, CA, USA).

Biochemical analysis

Cells were lysed by freeze thawing in 0.05% Triton X-100 (Sigma Aldrich, St. Louis, MO, USA). Specific

activity of alkaline phosphatase [orthophosphoric monoester phosphohydrolase, alkaline; E.C. 3.1.3.1], an early marker of osteoblast maturation that reaches a peak just before matrix mineralization [33], was assayed in the cell lysates by measuring the release of *p*-nitrophenol from *p*-nitrophenylphosphate at pH 10.2. Enzyme activity was normalized to total protein content (BCA Protein Assay; Thermo Fisher Pierce, Rockford, IL, USA) of the cell lysates.

Conditioned media were collected and assayed for secreted proteins and factors as described previously [34]. Osteocalcin, an extracellular matrix protein important in modulating hydroxyapatite crystal formation that is a later marker of osteoblast maturation [35], was measured using a commercially available radioimmunoassay kit (Human Osteocalcin RIA Kit; Biomedical Technologies, Stoughton, MA, USA). BMP2, BMP4, and BMP7 were assayed in the conditioned media using commercially available enzyme-linked immunosorbent assays (ELISA DuoSet; R&D Systems, Minneapolis, MN, USA) following manufacturer's instructions. Results of immunoassays were normalized to total cell number.

Molecular analysis

To determine the possible mechanism of increased osteogenic maturation of cells grown on Ti6Al4V substrates, we examined messenger RNA (mRNA) levels for BMP2, BMP4, and BMP7. When MG63 cultures reached confluence on TCPS, all cultures were treated for 12 hours with fresh media. RNA was isolated using TRIzol (Invitrogen, Carlsbad, CA, USA) and quantified using a NanoDrop spectrophotometer (Thermo Scientific, Waltham, MA, USA). Reverse transcription was performed with 125 ng of RNA using a High Capacity Reverse Transcription cDNA kit (Applied Biosystems, Carlsbad, CA, USA) to create complementary DNA templates. Real-time quantitative polymerase chain reaction was then performed with gene-specific primers using the StepOnePlus Real-time PCR System and Power SYBR Green Master Mix (Applied Biosystems, Carlsbad, CA, USA). Fluorescence values were quantified as starting quantities of mRNA using a standard curve created from known dilutions of MG63 cells cultured on TCPS. Genes are presented as normalized to glyceraldehyde 3-phosphate dehydrogenase (F: 5'-GCT CTC CAG AAC ATC ATC C-3'; R: 5'-TGC TTC ACC ACC TTC TTG-3'). Primers to BMP2 (F: 5'-GCG TGA AAA GAG AGA CTG C-3'; R: 5'-CCA TTG AAA GAG CGT CCA C-3') and BMP4 (5'-ACG GTG GGA AAC TTT TGA TGT G-3'; 5'-CGA GTC TGA TGG AGG TGA GTC-3') were designed using Beacon Designer software (PREMIER Biosoft, Palo Alto, CA, USA) and synthesized by Eurofins MWG Operon (Huntsville, AL, USA).

Statistical analysis

For each experiment, there were six independent cultures per experimental surface. Experiments were repeated

to ensure validity of the results. Data presented are from representative experiments. Data were first analyzed by analysis of variance; when statistical differences were detected, the Student *t* test was used with post hoc for multiple comparisons using Tukey method and *p* values less than .05 were considered significant.

Results

Materials characterization

Scanning electron microscopic images of the surfaces revealed different topographies of the samples (Fig. 1). The PEEK surface exhibited a machined surface finish with no distinct features except for parallel grooves along the entire surface because of processing (Fig. 1A). The high magnification images confirm the lack of smaller features (Fig. 1B). In a similar way, the sTiAlV surface also presented a machined finish with shallower grooves (Fig. 1C) and additional random scratches, evident at higher magnifications (Fig. 1D). The rTiAlV surface presented 100- to 300- μ m craters with superimposed micron-scale features (Fig. 1E). At higher magnifications, micron-scale features were more easily distinguished, resembling small terraces with faint submicron-scale texture (Fig. 1F).

Confocal laser microscopy confirmed the qualitative evaluation by scanning electron microscope (Fig. 2). The roughness of the sTiAlV surface ($S_a=0.09\pm0.01$) was the lowest of all the samples followed by the PEEK surface ($S_a=0.43\pm0.07$). The rTiAlV surface had the highest roughness ($S_a=1.81\pm0.51$).

Energy-dispersive X-ray spectroscopy (Table 1) showed a clear distinction in chemical composition between the PEEK samples and the Ti alloy samples. Poly-ether-ether-ketone samples were composed of carbon (C) and oxygen. The spectra also recorded small traces of Au originating from the Au coatings used to avoid charging from the

impeding electrons. In the case of the Ti alloy samples, both sTiAlV and rTiAlV were composed of Ti, aluminum, and vanadium with no significant compositional differences between the two. These analyses were qualitative and do not represent a quantitative assay of the alloy compositions.

Surface wettability assessed by contact angle measurements revealed that PEEK, sTiAlV, and rTiAlV substrates presented similar contact angles (Table 2).

Osteoblast maturation

Cell number was lower on PEEK substrates than on TCPS, but cell number on sTiAlV was 20% lower than on PEEK and cell number on rTiAlV was 65% of the number on PEEK (Fig. 3, Left). Alkaline phosphatase specific activity was the same in cells on TCPS and PEEK, but levels were higher on sTiAlV and highest on rTiAlV (Fig. 3, Middle). Osteocalcin was more than 55% higher on Ti6Al4V than on TCPS or PEEK, but there was no effect of roughness (Fig. 3, Right).

Bone morphogenetic protein expression

Both BMP2 and BMP4 mRNAs were lower on PEEK than on TCPS (Fig. 4). Cells on sTiAlV had more BMP2 and BMP4 mRNA than PEEK, but the highest expression was found on rTiAlV. Levels of BMP2, BMP4, and BMP7 in the conditioned media were the same in cells cultured on TCPS as on PEEK (Fig. 5). However, BMP2 was twofold higher on sTiAlV and rTiAlV than on PEEK (Fig. 5, Left). BMP4 was higher on sTiAlV than on PEEK and further increased in cells cultured on rTiAlV (Fig. 5, Middle). BMP7 was 50% higher in cells on sTiAlV and rTiAlV than on PEEK (Fig. 5, Right). The results show that culture on Ti surfaces stimulates production of BMPs at higher levels than cells cultured on PEEK.




Fig. 1. Scanning electron microscope images of (A, B) PEEK, (C, D) sTiAlV, and (E, F) rTiAlV surfaces at low and high magnifications. The low magnification images show the high levels of roughness of the (E) rTiAlV samples when compared with both (A) PEEK and (C) sTiAlV. High magnification images reveal the presence of microgrooves on the (B) PEEK and (D) sTiAlV samples, whereas the (F) rTiAlV samples have micron- and submicron-scale terraces and ridges. PEEK, poly-ether-ether-ketone; sTiAlV, smooth Ti6Al4V; rTiAlV, roughened Ti6Al4V.




Fig. 2. Confocal laser microscopy images and average roughness (S_a) values of (Left) PEEK, (Middle) sTiAlV, and (Right) rTiAlV surfaces. The rTiAlV samples have the highest S_a values, evident from its surface topography image of a $644 \times 644\text{-}\mu\text{m}^2$ field. PEEK, poly-ether-ether-ketone; sTiAlV, smooth Ti6Al4V; rTiAlV, roughened Ti6Al4V; SD, standard deviation.

Discussion

Surface properties of implants have been recognized as one of the most important determinants of device success [36]. Scanning electron microscope analyses of the different samples showed that both PEEK and sTiAlV samples were relatively smooth at the micron and submicron levels when compared with rTiAlV samples. These results were confirmed quantitatively by CLM measurements, with rTiAlV samples having a significantly higher average roughness (S_a) than PEEK and sTiAlV samples. Increased surface roughness has been shown to enhance osteoblast differentiation and local factor production in vitro, as well as bone-to-implant contact and torque removal forces in vivo on both commercially pure Ti [37,38] and Ti alloys (ie, Ti6Al4V) [39]. A possible hypothesis is that the enhancement in osseointegration may occur through osteoblast activation and reduced osteoclast activity [39].

Energy-dispersive X-ray spectroscopy chemical analysis of the different samples revealed that PEEK samples were composed of C and oxygen, as its chemical formula suggests. Conversely, both sTiAlV and rTiAlV samples had very similar chemistries that included Ti, aluminum, and vanadium. Surface contact angle, which is an indirect way of measuring surface energy, was similar for all samples. Both surface chemistry [40,41] and surface energy [42,43] have been demonstrated to have a direct effect on osteoblast response and implant osseointegration. In

this study, because the contact angles were similar, this suggests that the surface texture was the main reason for the difference in osteoblast behavior between the materials tested.

Surface roughness modifications can be applied to most of the biomaterials used in orthopedic applications. However, limitations in the physical, mechanical, and chemical properties of polymeric and ceramic biomaterials, and differences in the modification techniques, have limited their surface topographic modifications. Common spinal fusion biomaterials such as allograft and PEEK could be modified to present surface roughness and tested in vitro. Because of limitations in production, it would be difficult to manufacture these two types of materials to have the same surface roughness as Ti to decouple whether surface roughness or other surface properties are responsible for the enhanced osteogenic environment. However, this is partially examined in this study because we examine smooth PEEK and smooth Ti and found differential cell responses.

Although MG63 cells are human-derived osteosarcoma cells, they have been found to have comparable behavior to normal human osteoblasts, neonatal mouse calvarial osteoblasts, fetal rat calvarial osteoblasts, and adult rat calvarial osteoblasts when cultured on Ti surfaces [20,34,44–46] and are regarded as a valuable model for studying cell response to Ti [47]. In addition, their responses have been found to correlate well with quality of osseointegration in dental and orthopedic implants [16,17,48].

Osteoblast phenotype has been defined in three distinct periods: a growth period (proliferation), a period of matrix development, and a period of mineralization [33]. Our results showed that rTiAlV substrates promote

Table 1
Elemental composition of Ti6Al4V discs analyzed by energy-dispersive X-ray spectroscopy

Sample	Concentration (atomic % ± SD)				
	C	O	Ti	Al	V
PEEK*	85.1 ± 0.5	14.6 ± 0.5	–	–	–
sTiAlV	–	–	84.6 ± 3.2	10.5 ± 0.6	3.4 ± 0.1
rTiAlV	–	–	86.3 ± 1.0	10.1 ± 1.2	3.6 ± 0.3

Ti, titanium; SD, standard deviation; C, carbon; O, oxygen; Al, aluminum; V, vanadium; PEEK, poly-ether-ether-ketone; sTiAlV, smooth titanium aluminum vanadium; rTiAlV, roughened titanium aluminum vanadium; Au, gold; Pd, palladium.

* PEEK samples were Au-Pd coated for analysis, with Au and Pd concentration less than 0.5%.

Table 2
Contact angle measurements of disc surfaces

Sample	Contact angle (°) ± SD
PEEK	82 ± 12
sTiAlV	82 ± 22
rTiAlV	85 ± 7

SD, standard deviation; PEEK, poly-ether-ether-ketone; sTiAlV, smooth titanium aluminum vanadium; rTiAlV, roughened titanium aluminum vanadium.




Fig. 3. Human MG63 osteoblast-like cells were harvested 24 hours after confluence on TCPS. (Left) Cell number, (Middle) alkaline phosphatase-specific activity in cell lysates, and (Right) levels of osteocalcin in the conditioned media were measured. * $p < .05$ versus TCPS; # $p < .05$ versus PEEK; \$ $p < .05$ versus sTiAlV. TCPS, tissue culture polystyrene; PEEK, poly-ether-ether-ketone; sTiAlV, smooth Ti6Al4V; rTiAlV, roughened Ti6Al4V.

osteoblast maturation, decreasing cell number but increasing alkaline phosphatase activity and osteocalcin levels. Alkaline phosphatase activity increases as a result of decreased proliferation and maturation of the extracellular matrix. This enzyme is responsible for the early osteogenic microenvironment that leads to the maturation and mineralization of the extracellular matrix. Osteocalcin, the second most common protein in bone, is known as a late marker of osteoblast phenotype because of its presence in mature or mineralizing extracellular matrix [49]. Osteocalcin binds with high affinity to calcium and hydroxyapatite and is a modulator of crystal formation. Our results confirm our previous findings that rough substrates promoted osteogenic maturation through the decrease of cell number and the increase of important markers of mature osteoblast phenotype. These findings suggest that this type of cellular response could enhance early bone formation.

Previous studies have shown that PEEK allows osteoblast and fibroblast attachment and cell proliferation and have emphasized the lack of a negative effect of this material on cell growth [50,51]. However, to support osteoblastic differentiation, groups have modified the PEEK surface with coatings such as hydroxyapatite, tricalcium phosphate, diamond-like carbon, and Ti [3,52]. All these coatings have shown a better osteoblastic response when compared with noncoated PEEK, suggesting that PEEK by itself does not provide an osteogenic surface.

Our group has shown previously that osteoblasts grown on rough substrates increase levels of autocrine and paracrine factors such as osteoprotegerin, vascular endothelial growth factor, prostaglandin E2, and transforming growth factor beta 1 [16,37,53,54], all of which contribute to increased osteoblast differentiation and reduced osteoclastic activity, both of which are needed to achieve net new peri-implant bone formation.

In this study, we examined the effect of rTiAlV surfaces on mRNA expression and protein levels of three BMPs associated with osteoinduction. BMP2 is currently commercially available, and several clinical and in vivo studies have shown the increase in bone formation in the BMP2-treated area [55,56]. However, there is also some concern about the high doses used, as well as some side effects derived from the use of BMP2 [29–31]. Our results showed that osteoblasts cultured on Ti6Al4V substrates increased BMP2, BMP4, and BMP7 mRNA and protein levels. This increase is most robust on rTiAlV substrates with a more than twofold increase. Interestingly, PEEK failed to increase these molecules, demonstrating similar levels to the control group.

Conclusions

Taken together, this study demonstrates that rTiAlV substrates increase osteoblast maturation and produce an osteogenic environment that contains BMP2, BMP4, and




Fig. 4. Human MG63 osteoblast-like cells were harvested 12 hours after confluence on TCPS. Levels of messenger RNA for (Left) BMP2 and (Right) BMP4 were measured by real-time qPCR and normalized to GAPDH. * $p < .05$ versus TCPS; # $p < .05$ versus PEEK; \$ $p < .05$ versus sTiAlV. TCPS, tissue culture polystyrene; BMP, bone morphogenetic protein; qPCR, quantitative polymerase chain reaction; GAPDH, glyceraldehyde 3-phosphate dehydrogenase; PEEK, poly-ether-ether-ketone; sTiAlV, smooth Ti6Al4V; rTiAlV, roughened Ti6Al4V.




Fig. 5. Human MG63 osteoblast-like cells were harvested 24 hours after confluence on TCPS. (Left) Secreted BMP2, (Middle) BMP4, and (Right) BMP7 were measured in the conditioned media. Levels are normalized to total cell number. * $p < .05$ versus TCPS; # $p < .05$ versus PEEK; \$ $p < .05$ versus smooth Ti6Al4V. TCPS, tissue culture polystyrene; BMP, bone morphogenetic protein; PEEK, poly-ether-ether-ketone; sTiAl4V, smooth Ti6Al4V; rTiAl4V, roughened Ti6Al4V.

BMP7. The results show that modifying surface structure is sufficient to create an osteogenic environment that could enhance bone formation and implant stability, without addition of exogenous growth factors.

Acknowledgments

This research was supported by National Institutes of Health grant AR052102. Ti6Al4V and PEEK substrates were provided as gifts by Titan Spine, LLC.

References

- Toth JM, Wang M, Estes BT, et al. Polyetheretherketone as a biomaterial for spinal applications. *Biomaterials* 2006;27:324–34.
- Bruner HJ, Guan Y, Yoganandan N, et al. Biomechanics of polyaryletherketone rod composites and titanium rods for posterior lumbosacral instrumentation. Presented at the 2010 Joint Spine Section Meeting. Laboratory investigation. *J Neurosurg Spine* 2010;13:766–72.
- Kurtz SM, Devine JN. PEEK biomaterials in trauma, orthopedic, and spinal implants. *Biomaterials* 2007;28:4845–69.
- Santos ER, Goss DG, Morcom RK, Fraser RD. Radiologic assessment of interbody fusion using carbon fiber cages. *Spine* 2003;28:997–1001.
- Anjarwalla NK, Morcom RK, Fraser RD. Supplementary stabilization with anterior lumbar intervertebral fusion—a radiologic review. *Spine* 2006;31:1281–7.
- Bauer TW, Schils J. The pathology of total joint arthroplasty.II. Mechanisms of implant failure. *Skeletal Radiol* 1999;28:483–97.
- Brunski JB. In vivo bone response to biomechanical loading at the bone/dental-implant interface. *Adv Dent Res* 1999;13:99–119.
- Branemark PI, Hansson BO, Adell R, et al. Osseointegrated implants in the treatment of the edentulous jaw. Experience from a 10-year period. *Scand J Plast Reconstr Surg Suppl* 1977;16:1–132.
- Branemark P-I, Zarb GA, Albrektsson T. *Tissue-integrated prostheses: osseointegration in clinical dentistry*. Chicago, IL: Quintessence Publishing, 1985.
- Tsolaki IN, Madianos PN, Vrotsos JA. Outcomes of dental implants in osteoporotic patients. A literature review. *J Prosthodont* 2009;18:309–23.
- Ozawa S, Ogawa T, Iida K, et al. Ovariectomy hinders the early stage of bone-implant integration: histomorphometric, biomechanical, and molecular analyses. *Bone* 2002;30:137–43.
- Okamura A, Ayukawa Y, Iyama S, Koyano K. Effect of the difference of bone turnover on peri-titanium implant osteogenesis in ovariectomized rats. *J Biomed Mater Res A* 2004;70:497–505.
- Stenport VF, Johansson CB. Evaluations of bone tissue integration to pure and alloyed titanium implants. *Clin Implant Dent Relat Res* 2008;10:191–9.
- De Leonardi D, Garg AK, Pecora GE. Osseointegration of rough acid-etched titanium implants: 5-year follow-up of 100 minimatic implants. *Int J Oral Maxillofac Implants* 1999;14:384–91.
- Linder L. Osseointegration of metallic implants. I. Light microscopy in the rabbit. *Acta Orthop Scand* 1989;60:129–34.
- Lincks J, Boyan BD, Blanchard CR, et al. Response of MG63 osteoblast-like cells to titanium and titanium alloy is dependent on surface roughness and composition. *Biomaterials* 1998;19:2219–32.
- Schwartz Z, Raz P, Zhao G, et al. Effect of micrometer-scale roughness of the surface of Ti6Al4V pedicle screws in vitro and in vivo. *J Bone Joint Surg Am* 2008;90:2485–98.
- Boyan BD, Schwartz Z, Lohmann CH, et al. Pretreatment of bone with osteoclasts affects phenotypic expression of osteoblast-like cells. *J Orthop Res* 2003;21:638–47.
- Brunette DM, Ratkay J, Chehroudi B. Behaviour of osteoblasts on micro-machined surfaces. In: Davies JE, ed. *Bone-Biomaterial Interface*. Toronto, ON, Canada: University of Toronto Press, 1991:170–80.
- Martin JY, Schwartz Z, Hummert TW, et al. Effect of titanium surface roughness on proliferation, differentiation, and protein synthesis of human osteoblast-like cells (MG63). *J Biomed Mater Res* 1995;29:389–401.
- Deligianni DD, Katsala N, Ladas S, et al. Effect of surface roughness of the titanium alloy Ti-6Al-4V on human bone marrow cell response and on protein adsorption. *Biomaterials* 2001;22:1241–51.
- Schwartz Z, Olivares-Navarrete R, Wieland M, et al. Mechanisms regulating increased production of osteoprotegerin by osteoblasts cultured on microstructured titanium surfaces. *Biomaterials* 2009;30:3390–6.
- Boyan BD, Lohmann CH, Sisk M, et al. Both cyclooxygenase-1 and cyclooxygenase-2 mediate osteoblast response to titanium surface roughness. *J Biomed Mater Res* 2001;55:350–9.
- Bessho K, Carnes DL, Cavin R, et al. BMP stimulation of bone response adjacent to titanium implants in vivo. *Clin Oral Implants Res* 1999;10:212–8.
- Zhao G, Raines AL, Wieland M, et al. Requirement for both micron- and submicron scale structure for synergistic responses of osteoblasts to substrate surface energy and topography. *Biomaterials* 2007;28:2821–9.
- Zhao G, Schwartz Z, Wieland M, et al. High surface energy enhances cell response to titanium substrate microstructure. *J Biomed Mater Res A* 2005;74:49–58.
- Bachle M, Kohal RJ. A systematic review of the influence of different titanium surfaces on proliferation, differentiation and protein synthesis of osteoblast-like MG63 cells. *Clin Oral Implants Res* 2004;15:683–92.
- Yoshida T, Kikuchi M, Koyama Y, Takakuda K. Osteogenic activity of MG63 cells on bone-like hydroxyapatite/collagen nanocomposite sponges. *J Mater Sci Mater Med* 2010;21:1263–72.

- [29] Singh K, Dumonski M, Stanley T, et al. Repeat use of human recombinant bone morphogenetic protein-2 for second level lumbar arthrodesis. *Spine* 2011;36:192–6.
- [30] Boraiah S, Paul O, Hawkes D, et al. Complications of recombinant human BMP-2 for treating complex tibial plateau fractures: a preliminary report. *Clin Orthop Relat Res* 2009;467:3257–62.
- [31] Lewandrowski KU, Nanson C, Calderon R. Vertebral osteolysis after posterior interbody lumbar fusion with recombinant human bone morphogenetic protein 2: a report of five cases. *Spine J* 2007;7:609–14.
- [32] Lu Z, Zreiqat H. The osteoconductivity of biomaterials is regulated by bone morphogenetic protein 2 autocrine loop involving alpha2beta1 integrin and mitogen-activated protein kinase/extracellular related kinase signaling pathways. *Tissue Eng Part A* 2010;16:3075–84.
- [33] Stein GS, Lian JB, Owen TA. Relationship of cell growth to the regulation of tissue-specific gene expression during osteoblast differentiation. *FASEB J* 1990;4:3111–23.
- [34] Olivares-Navarrete R, Hyzy SL, Chaudhri RA, et al. Sex dependent regulation of osteoblast response to implant surface properties by systemic hormones. *Biol Sex Differ* 2010;1:4.
- [35] Boskey AL, Gadaleta S, Gundberg C, et al. Fourier transform infrared microspectroscopic analysis of bones of osteocalcin-deficient mice provides insight into the function of osteocalcin. *Bone* 1998;23:187–96.
- [36] Wilson CJ, Clegg RE, Leavesley DI, Percy MJ. Mediation of biomaterial-cell interactions by adsorbed proteins: a review. *Tissue Eng* 2005;11:1–18.
- [37] Raines AL, Olivares-Navarrete R, Wieland M, et al. Regulation of angiogenesis during osseointegration by titanium surface microstructure and energy. *Biomaterials* 2010;31:4909–17.
- [38] Cochran DL, Nummikoski PV, Higginbottom FL, et al. Evaluation of an endosseous titanium implant with a sandblasted and acid-etched surface in the canine mandible: radiographic results. *Clin Oral Implants Res* 1996;7:240–52.
- [39] Schwartz Z, Raz P, Zhao G, et al. Effect of micrometer-scale roughness of the surface of Ti6Al4V pedicle screws in vitro and in vivo. *J Bone Joint Surg Am* 2008;90:2485–98.
- [40] Smith KE, Hyzy SL, Sunwoo M, et al. The dependence of MG63 osteoblast responses to (meth)acrylate-based networks on chemical structure and stiffness. *Biomaterials* 2010;31:6131–41.
- [41] Anselme K, Linez P, Bigerelle M, et al. The relative influence of the topography and chemistry of TiAl6V4 surfaces on osteoblastic cell behaviour. *Biomaterials* 2000;21:1567–77.
- [42] Hao L, Lawrence J. Wettability modification and the subsequent manipulation of protein adsorption on a Ti6Al4V alloy by means of CO₂ laser surface treatment. *J Mater Sci Mater Med* 2007;18:807–17.
- [43] Zhao G, Schwartz Z, Wieland M, et al. High surface energy enhances cell response to titanium substrate microstructure. *J Biomed Mater Res A* 2005;74:49–58.
- [44] Lohmann CH, Tandy EM, Sylvia VL, et al. Response of normal female human osteoblasts (NHOst) to 17beta-estradiol is modulated by implant surface morphology. *J Biomed Mater Res* 2002;62:204–13.
- [45] Schneider GB, Perinpanayagam H, Clegg M, et al. Implant surface roughness affects osteoblast gene expression. *J Dent Res* 2003;82:372–6.
- [46] Dekker RJ, van Blitterswijk CA, Hofland I, et al. Studying the effect of different macrostructures on in vitro cell behaviour and in vivo bone formation using a tissue engineering approach. *Novartis Found Symp* 2003;249:148–67; discussion 167–9, 170–4, 239–41.
- [47] Schwartz Z, Nasazky E, Boyan BD. Surface microtopography regulates osteointegration: the role of implant surface microtopography in osteointegration. *Alpha Omegan* 2005;98:9–19.
- [48] Anselme K, Bigerelle M, Noel B, et al. Qualitative and quantitative study of human osteoblast adhesion on materials with various surface roughnesses. *J Biomed Mater Res* 2000;49:155–66.
- [49] Hauschka PV, Lian JB, Cole DE, Gundberg CM. Osteocalcin and matrix Gla protein: vitamin K-dependent proteins in bone. *Physiol Rev* 1989;69:990–1047.
- [50] Briem D, Strametz S, Schroder K, et al. Response of primary fibroblasts and osteoblasts to plasma treated polyetheretherketone (PEEK) surfaces. *J Mater Sci Mater Med* 2005;16:671–7.
- [51] Morrison C, Macnair R, MacDonald C, et al. In vitro biocompatibility testing of polymers for orthopaedic implants using cultured fibroblasts and osteoblasts. *Biomaterials* 1995;16:987–92.
- [52] Wang H, Xu M, Zhang W, et al. Mechanical and biological characteristics of diamond-like carbon coated poly aryl-ether-ether-ketone. *Biomaterials* 2010;31:8181–7.
- [53] Schwartz Z, Lohmann CH, Sisk M, et al. Local factor production by MG63 osteoblast-like cells in response to surface roughness and 1,25-(OH)₂D₃ is mediated via protein kinase C- and protein kinase A-dependent pathways. *Biomaterials* 2001;22:731–41.
- [54] Zhao G, Zinger O, Schwartz Z, et al. Osteoblast-like cells are sensitive to submicron-scale surface structure. *Clin Oral Implants Res* 2006;17:258–64.
- [55] Kraiwattanapong C, Boden SD, Louis-Ugbo J, et al. Comparison of Healos/bone marrow to INFUSE(rhBMP-2/ACS) with a collagen-ceramic sponge bulking agent as graft substitutes for lumbar spine fusion. *Spine* 2005;30:1001–7; discussion 7.
- [56] Rihn JA, Kirkpatrick K, Albert TJ. Graft options in posterolateral and posterior interbody lumbar fusion. *Spine* 2010;35:1629–39.