

Near-Infrared (NIR) Organic Light-Emitting Diodes (OLEDs): Challenges and Opportunities

Andrea Zampetti, Alessandro Minotto, and Franco Cacialli*

Adv. Funct. Mater. **2019**, *29*, 1807623


DOI: 10.1002/adfm.201807623

In the initially published version of this article, in Table 1 the “Osmium complex” class is missing. The correct Table 1 is as follows:

Class	Atom	NIR PL peak [nm]	ϕ_{PL} [%]	NIR EL peak [nm]	Maximum EQE [%]	Year/reference
Lanthanide	Er	1522	N/A	1533	N/A	1999 ^[56]
	Er	1540	N/A	1540	N/A	2000 ^[57]
	Nd	890	0.07	890	8 mcd A ⁻¹	2001 ^[58]
	Yb	977	N/A	977	0.001	2001 ^[59]
Os complex	Os	731	4.0	718	1.5	2009 ^[60]
	Os	805	0.2	814	2.7	2009 ^[60]
Ir complex	Ir	720	N/A	720	0.25	2006 ^[61]
	Ir	765	17.0	760	4.5	2017 ^[62]
	Ir	710	16.0	714	3.07	2017 ^[63]
	Ir	775	6.0	775	0.5	2015 ^[64]
	Ir	777	3.6	780	2.2	2013 ^[65]
Pt complex	Pt	740	81.0	740	24	2017 ^[6]
	Pt	705	31.0	705	10.5	2007 ^[66]
	Pt	720	24.0	720	8.5	2007 ^[66]
	Pt	760	80.0	772	8.5	2007 ^[67]
	Pt	760	80.0	765	6.3	2007 ^[68]
	Pt	842	22.0	848	2.8	2016 ^[69]
	Pt	883	22.0	886	3.8	2016 ^[70]
	Pt	773	35.0	773	8.0	2011 ^[38]
	Pt	891	15.0	900	3.8	2011 ^[38]
Pt	1022	8.0	1005	0.12	2011 ^[38]	

The authors apologize for any inconvenience or misunderstanding that this error may have caused.

In the initially published version of this article, the “ELECTRON-DONORS” and “ELECTRON-ACCEPTORS” labels in Figure 9 are switched. The correct Figure 9 is as follows:



The authors apologize for any inconvenience or misunderstanding that this error may have caused.