

Proceedings of the 2nd World Congress on Recent Advances in Nanotechnology (RAN'17)
Barcelona, Spain – April 4 – 6, 2017
Paper No. ICNNFC 144
ISSN: 2371-5308
DOI: 10.11159/icnnfc17.144

Layered Composites Based on Recycled PET/Functionalized Woven Flax Fibres

Sönmez Maria¹, Alexandrescu Laurentia¹, Nituica Mihaela¹, Georgescu Mihai¹, Gurau Florentina Dana¹, Ficai Denisa², Ficai Anton², Trusca Roxana², Constantinescu Doina³

¹National Research and Development Institute for Textiles and Leather–division

Leather and Footwear Research Institute

93 Ion Minulescu St., Bucharest, Romania

maria.sonmez@icpi.ro; laurentia.alexandrescu@icpi.ro; mihaela.nituica@icpi.ro; mihai.georgescu@icpi.ro;

dana.gurau@icpi.ro

²Politehnica University of Bucharest, Faculty of Applied Chemistry and Material Science

1-7 Polizu St., Bucharest, Romania

denisa.ficai@yahoo.ro; anton.ficai@upb.ro; truscaroxana@yahoo.com

³SC MONOFIL S.R.L

1 Uzinei St., Savinesti, Romania

monofil.srl@gmail.com

Extended Abstract

Plastic waste is generated by a variety of sources including packaging, automotive, consumer goods, electrical and electronics industries, leading to a significant growth in the volume of waste and the impetuous need to reduce it [1]. Recycling of used products is considered one of the best ways to save money and protect the environment, although technologies must be designed and managed so as to avoid environmental pollution [2]. Global warming and diminishing oil reserves have prompted scientists to focus more on the use of natural fibers from renewable resources such as jute, hemp, cotton, flax, coconut fiber, fibers from pineapple and banana leaves [3-4], etc., for the reinforcement of composite materials [5]. Due to the high hydrophilicity of all natural fibers, adhesion to polymers most frequently used as matrix (hydrophobic) is rather problematic [6]. This problem can be solved by fiber surface modification through, physical, chemical, and mechanical methods or by changing the chemical composition of the polymer matrix.

The paper aims at developing new layered composite materials based on recycled thermoplastic polymer (PET-polyethylene terephthalate) from the food industry reinforced with woven flax fiber functionalized with nano (micro) particles of titanium or alumina and testing the composite in terms of physico-mechanical (tensile strength, bending, shock, etc.), morphological (SEM), structural (FTIR), and thermal (Vicat) properties. Based on this technology, the new composite will exhibit improved physical, mechanical and thermal properties, as well as resistance to mold attack. In this regard, in the first stage, the surface of flax fibers were chemically modified using aluminum (AlCl₃), and titanium (titanium butoxide) precursors followed by precipitation. The woven flax whose surface was functionalized with nano (micro) alumina or TiO₂ particles were subsequently used to obtain layered composite materials. Layered composite materials were obtained by alternating functionalized / not functionalized woven flax fiber with sheets made from recycled PET. The recycled PET sheets and layered composites based on recycled PET and functionalized / not functionalized woven flax fiber were obtained by press molding using an electrical press at the following optimum parameters: plate temperature - 254°C, preheating time - 8 min; pressing time - 2 min; cooling time - 15 min; pressing force - 100 kN. Special attention must be paid to the pre-drying process (at 100-110°C) to remove adsorbed water. In the absence of the pre-drying operation, the resulting sheets exhibit holes, porosity and discontinuities, making them unusable for the development of layered composite materials.

Physical, mechanical and thermal analyses results for specimens of layered composite materials based on recycled PET / functionalised woven flax fiber show significantly improved values compared with the control samples obtained from recycled PET / not functionalized flax fiber. Improved mechanical and thermal properties are due to links developed at the woven flax fiber / polymer phase interphase. Results have also been confirmed by SEM, while the degree of adhesion and the interpenetration of polymer phase / woven flax fiber are superior in the case of composites made of functionalized flax fibers in comparison with the unfunctionalized ones.

Keywords: PET, recycling, surface functionalization, natural fibers

Acknowledgements:

This research was financed through PN-III-P2-2.1-PTE-2016 project: Recovery of recycled thermoplastic polymers by reinforcement with functionalized natural fibres to obtain new added value products, ctr. No. 20PTE/2016, supported by MECS-UEFISCDI.

References

- [1] U. Riedel, J. Nickel, "Applications of natural fiber composites for constructive parts in aerospace, automobiles, and other areas," Ed. Germany: Wiley, pp. 1-11, 2010.
- [2] J. Sahari, S. M. Sapuan, "Natural fibre reinforced biodegradable polymer composites," *Rev. Adv. Mater. Sci.*, vol. 30, pp. 166-174, 2011.
- [3] A. Ticoalu, T. Aravinthan, F. Cardona, "A review of current development in natural fiber composites for structural and infrastructure applications," *Southern Region Engineering Conference*, Toowoomba, Australia, 2010.
- [4] I. S. Fahim, S. M. Elhaggar, "Reinforcement of Plastic Waste with Treated Natural Fibers," *Natural Resources*, vol. 3, pp. 6-10, 2012.
- [5] D. Verma, P. C. Gope, A. Shandilya, A. Gupta, M. K. Maheshwari, "Coir Fibre Reinforcement and Application in Polymer Composites: A Review," *J. Mater. Environ. Sci.*, vol. 4, no. 2, pp. 263-276, 2013.
- [6] N. Saba, P. M. Tahir, M. Jawaid, "A Review on Potentiality of Nano Filler/Natural Fiber Filled Polymer Hybrid Composites," *Polymers*, vol. 6, pp. 2247-2273, 2014.