



Science Arts & Métiers (SAM)

is an open access repository that collects the work of Arts et Métiers Institute of Technology researchers and makes it freely available over the web where possible.

This is an author-deposited version published in: <https://sam.ensam.eu>

Handle ID: <http://hdl.handle.net/10985/20178>

To cite this version :

Yaasin A. MAYI, Morgan DAL, Patrice PEYRE, Michel BELLET, Charlotte METTON, Clara MORICONI, Remy FABBRO - Erratum: "Transient dynamics and stability of keyhole at threshold in laser powder bed fusion regime investigated by finite element modeling" [J. Laser Appl. 33, 012024 (2021)] - Journal of Laser Applications - Vol. 33, n°2, p.029902 - 2021

Erratum: “Transient dynamics and stability of keyhole at threshold in laser powder bed fusion regime investigated by finite element modeling” [J. Laser Appl. 33, 012024 (2021)]

Yaasin A. Mayi,^{1,2}  Morgan Dal,² Patrice Peyre,² Michel Bellet,³ Charlotte Metton,¹ Clara Moriconi,¹ and Remy Fabbro²

AFFILIATIONS

¹Safran Additive Manufacturing, A Technology Platform of Safran Tech, Rue des Jeunes Bois, Chateaufort, 78114 Magny-Les-Hameaux, France

²Laboratoire PIMM, Arts et Metiers Institute of Technology, CNRS, Cnam, HESAM University, 151 boulevard de l'Hopital, 75013 Paris, France

³MINES ParisTech, PSL Research University, CEMEF – Centre de Mise en Forme des Matériaux, CNRS UMR 7635, CS10207 rue Claude Daunesse, 06904 Sophia Antipolis Cedex, France

The authors would like to inform the readers that erroneous Figs. 4 and 5 were unfortunately uploaded during the proof revision process of the original paper.¹ The correct figures are below.

The authors wish to apologize for any inconvenience caused by this error.

REFERENCES

- ¹Y. A. Mayi, M. Dal, P. Peyre, M. Bellet, C. Metton, C. Moriconi, and R. Fabbro, “Transient dynamics and stability of keyhole at threshold in laser powder bed fusion regime investigated by finite element modeling,” *J. Laser Appl.* **33**, 012024 (2021).




FIG. 4. Distribution of normalized absorbed laser intensity (log scale) at different instants.




FIG. 5. Keyhole depth (with and without RT) and absorptance over time in the static configuration.