

PAPER • OPEN ACCESS

## Appraisal of MC2010 shear resistance approaches coupled with a residual flexural strength prediction model

To cite this article: T D S Valente *et al* 2019 *IOP Conf. Ser.: Mater. Sci. Eng.* **596** 012004

View the [article online](#) for updates and enhancements.



**IOP | ebooks™**

Bringing you innovative digital publishing with leading voices to create your essential collection of books in STEM research.

Start exploring the [collection](#) - download the first chapter of every title for free.

# Appraisal of MC2010 shear resistance approaches coupled with a residual flexural strength prediction model

T D S Valente<sup>1</sup>, J A O Barros<sup>2</sup>, B N Moraes-Neto<sup>3</sup> and Y H Moussa<sup>4</sup>

<sup>1</sup>PhD Candidate, CiviTest, Lda, V.N. Famalicão, Portugal

<sup>2</sup>Full Professor, ISISE, IB-S, Dep. Civil Eng. Minho University, Portugal

<sup>3</sup>Assistant Prof., Dep. Civil Eng. Federal University of Pará, Brazil

<sup>4</sup>MSC Student, Dep. Civil Eng. Federal University of Pará, Brazil

E-mail: tiagovalente@civitest.com, tel: +351252315199

**Abstract.** In the present work the predictive performance of the two approaches proposed by Model Code 2010 for the evaluation of the shear capacity of fiber reinforced concrete (FRC) elements flexurally reinforced with conventional steel bars is assessed considering a database (DBs) constituted by 80 FRC beams do not including conventional transverse reinforcements. The accuracy of these shear models is evaluated by statistical analysis of the prediction ratio between the experimental and estimated shear capacity of the beams of the DBs, and applying the Demerit Points Classification approach for further information about the reliability of the two approaches in design context. Due to the absence of the post-cracking experimental characterization of the FRC used in several beams considered in the DBs, an approach was developed for estimating the residual flexural strength parameters from the most relevant known variables of steel fiber reinforcement mechanisms for concrete, namely the fiber volume and aspect ratio, and the concrete compressive and tensile strength. The residual flexural strength prediction model is assessed and its influence on the performance of the shear resistance models is evaluated.

## 1. Introduction

Regarding the use of discrete fibers in concrete reinforcement, previous research has already pointed that it increases concrete shear resistance and deformation capacity, decreases crack width and spacing, and can change the type of fracture mode for members without transverse conventional reinforcements, from brittle to a ductile one [1–5]. In addition, the fiber reinforcement can be adopted for partial or total replacement of steel stirrups in structural elements preserving the required shear capacity to the member [2,6,7].

Based on the extensive research already carried out regarding the experimental assessment of the shear behavior of fiber reinforced concrete (FRC) members, a database (DB<sub>s</sub>) that collects the shear tests data of beams flexurally reinforced with conventional steel bars and made by steel fiber reinforced concrete (SFRC) has been developed [8]. These beams are herein abbreviated by the acronym R/SFRC. The DB<sub>s</sub> has already been used for the appraisal of R/SFRC shear resistance prediction models [9–11]. Currently, the DB<sub>s</sub> is being extended, and some difficulties have been encountered in using the data of some shear tests due to the lack of some key information, namely the residual flexural strength of the SFRC, which is used in both approaches proposed by CEB *fib* Model Code 2010 (MC2010) [12] for the evaluation of the shear capacity of FRC elements flexurally reinforced with conventional steel bars.



In fact, the final version of MC2010 [12], published in 2013, covers the design guidelines and recommendations for the dimensioning process of FRC structural members, including two shear resistance prediction models. Considering the expansion of the FRC shear tests DB<sub>s</sub>, a new opportunity has been found to appraise two of the most widely used FRC shear resistance prediction models, coupled with a residual flexural strength prediction model. In the context of a model for predicting the punching capacity of SFRC slabs, Moraes-Neto *et al.* [13] have mounted a database (DB<sub>f</sub>) formed by results from three point notched beam bending tests (3PNBBT) with specimens of concrete reinforced with hooked ends steel fibers (SFRC), executed according to the RILEM TC 16-TDF [14] and MC2010 recommendations. Treating statistically the results from the DB<sub>f</sub>, the authors derived simple equations for determining the residual flexural tensile strength parameters ( $f_{Ri}$ ,  $(i=1,2,3,4)$ ) from the volume content ( $V_f$ ) and aspect ratio ( $l_f/d_f$ ) of the hooked ends steel fibers. The authors have recognized that one of the debilities of the proposed equations is their independence of the quality of the matrix, since the fiber reinforcement mechanisms, and consequently the post-cracking tensile capacity of a FRC, depend on this property. In the present work the DB<sub>f</sub> is extended in order to have enough information for including the concrete strength as a variable making part of a new generation of more reliable and consistent equations for determining  $f_{Ri}$ . These equations are used to estimate the contribution of the fiber reinforcement for the SFRC shear capacity according to the two approaches of the MC2010 whenever  $f_{Ri}$  are not known experimentally.

## 2. MC2010 FRC shear resistance prediction models

The Model Code 2010 presents two models to predict the shear resistance of FRC structural members based on: (i) the concept of the residual flexural strength of FRC ( $f_{Ri}$ ); (ii) the simplified modified compression field theory (SMCFT) [15] coupled with the Variable Engagement Model (VEM) [16].

The resistance of FRC members using the model based on the concept of the residual flexural strength, denoted in this paper as MC2010\_EEN, is determined by the expression [12]:

$$V_{Rd,F} = \left\{ \frac{0.18}{\gamma_c} \cdot k \cdot \left[ 100 \cdot \rho_{sl} \left( 1 + 7.5 \cdot \frac{f_{Fruk}}{f_{ck}} \right) \cdot f_{ck} \right]^{1/3} + 0.15 \cdot \sigma_{cp} \right\} b_w \cdot d ; \sigma_{cp} < 0.2 \cdot f_{cd} \quad (1)$$

where  $\gamma_c$  is the partial safety factor for concrete without fibers;  $k = 1 + \sqrt{200/d} \leq 2.0$  is a factor that takes into account the beam's size effect;  $d$  is the effective depth of the cross section [mm];  $\rho_{sl} = A_{sl}/(b_w \cdot d)$  is the longitudinal reinforcement ratio;  $A_{sl}$  is the cross-sectional area of the longitudinal reinforcement [mm<sup>2</sup>];  $f_{Fruk}$  is the characteristic value of the ultimate residual tensile strength of the FRC [MPa];  $f_{ck}$  is the characteristic tensile strength for the concrete without fibers [MPa];  $f_{ck}$  is the concrete characteristic compressive strength [MPa];  $\sigma_{cp}$  is the average axial stress acting in the cross-section [MPa],  $f_{cd}$  is the design value of the concrete compressive strength; and  $b_w$  is the smallest width of the tensile zone of the cross-section [mm].

The shear resistance,  $V_{Rd,F}$ , is assumed to be not smaller than the minimum value,  $V_{Rd,F,\min}$ , obtained from [12]:

$$V_{Rd,F,\min} = (v_{\min} + 0.15 \cdot \sigma_{cp}) \cdot b_w \cdot d ; v_{\min} = 0.035 \cdot k^{3/2} \cdot f_{ck}^{1/2} \quad (2)$$

For evaluation of the shear resistance, the ultimate residual tensile strength is computed from equation (3) considering the residual flexural strength parameters of FRC,  $f_{Ri}$  ( $i=1,3$ ) and the ultimate crack width equal to  $w_u = 1.5\text{mm}$ . For the design situations of FRC members, in equation (3) should be considered the characteristic values of the residual flexural strength of the FRC.

$$f_{Ftu} = f_{Fts} - \frac{w_u}{CMOD_3 (= 2.5mm)} \cdot (f_{Fts} - 0.5 \cdot f_{R3} + 0.2 \cdot f_{R1}) \geq 0 ; f_{Fts} = 0.45 \cdot f_{R1} \quad (3)$$

The MC2010\_EEN model is based on the shear contribution of plain concrete members without transverse reinforcements, as proposed in Eurocode 2 [17]. The increased post-cracking toughness and crack-opening restriction provided by the fiber reinforcement to the concrete is empirically considered by multiplying the longitudinal reinforcement ratio by the factor  $(1 + 7.5 f_{Ftuk} / f_{ctk})$ . Thus, the fiber reinforcement contribution is considered as an additional flexural reinforcement [18].

According to the model based on the SMCFT/VEM theory, hereafter denoted as MC2010\_MCFT, the general expression that predicts the shear resistance of FRC member is equal to:

$$V_{Rd} = V_{Rd,F} + V_{Rd,s} \quad (4)$$

where  $V_{Rd,F}$  is the FRC shear resistance contribution, while  $V_{Rd,s}$  is the added shear resistance provided by the transverse conventional reinforcement.

The FRC shear resistance,  $V_{Rd,F}$ , is the shear resistance contribution of the concrete matrix,  $V_{Rd,c}$ , plus of the contribution of the fibers bridging the shear failure crack,  $V_{Rd,f}$ , being determined by the following expression[12]:

$$V_{Rd,F} = V_{Rd,c} + V_{Rd,f} = \frac{1}{\gamma_F} \cdot [k_v \cdot \sqrt{f_{ck}} + k_{fd} \cdot f_{Tk}(w_u) \cdot \cot \theta] \cdot z \cdot b_w, \quad \sqrt{f_{ck}} \leq 8MPa \quad (5)$$

where  $k_v$  is the parameter that determines the contribution of the aggregate interlock mechanism for the shear strength of the cross section ((6));  $k_{fd}$  is a fiber dispersion reduction factor [19], assuming the value of  $k_{fd} = 0.8$ ;  $f_{Tk}(w_u)$  is the characteristic value of the post-cracking tensile capacity of FRC, determined from direct tensile tests, evaluated at the ultimate crack width of  $w_u$ ;  $\theta$  is the inclination of the compressive stress field, corresponding to the inclination of the critical diagonal crack;  $z$  is the internal lever arm that can be estimated as  $z = 0.9 \cdot d$  [mm] [12].

The  $k_v$  is function of the parameter that considers the aggregate size influence,  $k_{dg}$  (equation (7)), of the longitudinal strain at the mid depth of the effective shear area,  $\varepsilon_x$ , and of the transverse reinforcement ratio of the cross-section,  $\rho_w$ . In equation (7) the term  $d_g$  is the maximum aggregate dimension in the concrete matrix [mm].

$$k_v = \begin{cases} \frac{0.4}{1+1500 \cdot \varepsilon_x} \cdot \frac{1300}{1000+z \cdot k_{dg}} & \text{for } \rho_w < 0.08 \cdot \sqrt{f_{ck}/f_{yk}} \\ \frac{0.4}{1+1500 \cdot \varepsilon_x} & \text{for } \rho_w \geq 0.08 \cdot \sqrt{f_{ck}/f_{yk}} \end{cases} > 0.0 \quad (6)$$

$$k_{dg} = \begin{cases} \frac{32}{16+d_g} \geq 0.75 & \text{for } f_{ck} \leq 70MPa \\ 2.0 & \text{for } f_{ck} > 70MPa \text{ and for lightweight concrete} \end{cases} \quad (7)$$

The strain,  $\varepsilon_x$ , at mid-depth of the effective shear area is defined as half the tension chord strain,  $\varepsilon_x = \varepsilon_s / 2$ , namely [12,20]:

$$\varepsilon_x = 0 \leq \frac{1}{2 \cdot E_s \cdot A_{sl}} \left[ \frac{M_{Ed}}{z} + \frac{V_{Ed}}{2} \cot \theta + N_{Ed} \left( \frac{1}{2} \pm \frac{\Delta e}{z} \right) \right] \leq 0.003 \quad (8)$$

where  $\Delta e$  is the eccentricity of the beam axis with respect to its mid-depth of the effective shear area;  $M_{Ed}$  and  $V_{Ed}$  correspond to the acting bending moment and shear force at the cross-section (assumed positive values) and  $N_{Ed}$  is the axial force at the cross-section (positive for tension and negative for compression).

According to MC2010, the value of  $\theta$  can be freely chosen in the interval of  $\theta_{\min} \leq \theta \leq 45^\circ$ , while the value of  $\theta_{\min}$  is related with the longitudinal strain level in the mid-depth of the cross-section,  $\varepsilon_x$ , [12]:

$$\theta_{\min} = (29^\circ + 7000 \cdot \varepsilon_x) \quad (9)$$

Based on the work of [21], where a  $\sigma - w$  relationship of FRC was derived from inverse analysis using the results of prism bending tests, the direct post-cracking tensile capacity of FRC can be estimated from the expression [9]:

$$f_{Tk}(w) = k_G \min(0.4f_{R2k} + 1.2(f_{R4k} - f_{R2k}) \xi(w), f_{ctk, \min}) ; \xi(w) = \alpha w - 0.25 \quad (10)$$

The factor  $k_G$  takes into account fibre alignment due to casting bias and wall influences that occur in the prism bending test. In Table 1 is presented the value of  $k_G$  considering the different prism bending test standards. The value for the factor  $\alpha$  also depends on the prism bending test configuration and is presented in Table 1.

**Table 1.** Value of  $k_G$  and  $\alpha$  depending on prism bending test standard [9].

Prism bending test standard	$k_G$	$\alpha$
ASTM C1609 [22]	0.70	1/3
EN 14651 [23]	0.60	5/12
RILEM TC 162-TDF [14]	0.60	5/12
UNI 11039 [24]	0.60	43/84

The ultimate crack width,  $w_u$ , orthogonal to the critical diagonal crack is determined according to equation (11) [12].

$$w_u = (0.2 + 1000 \cdot \varepsilon_x) \geq 0.125 \text{ mm} \quad (11)$$

The shear reinforcement resistance,  $V_{Rd,s}$ , is determined according to the following equation [12]:

$$V_{Rd,s} = A_{sw}/s_w \cdot z \cdot f_{ywd} \cdot (\cot \theta + \cot \alpha) \cdot \sin \alpha \quad (12)$$

where  $A_{sw}$  is the shear reinforcement area [ $\text{mm}^2$ ],  $f_{ywd}$  is the design value of the yield stress of the shear reinforcement, and  $\alpha$  is the inclination of the transverse reinforcement.

The design shear resistance cannot exceed the crushing capacity of concrete in the web, determined as [12]:

$$V_{Rd, \max} = k_c \cdot \frac{f_{ck}}{\gamma_c} \cdot b_w \cdot z \cdot \frac{\cot \theta + \cot \alpha}{1 + \cot^2 \theta} \quad (13)$$

where  $k_c$  is a strength reduction factor defined by  $k_c = k_\varepsilon \cdot \eta_{fc}$ ;  $k_\varepsilon$  is a factor that takes into account the strain in the web of the structural element, being determined according to the level of approximation defined in MC2010 (level of approximation I:  $k_\varepsilon = 0.55$ ; level of approximation II and III: equation (14));  $\eta_{fc}$  is a factor to consider the influence of the concrete strength class on the level of the shear failure brittleness, being determined from equation (15).

$$k_\varepsilon = (1.2 + 55 \cdot \varepsilon_1)^{-1} \leq 0.65 ; \varepsilon_1 = \varepsilon_x + (\varepsilon_x + 0.002) \cot^2 \theta \quad (14)$$

$$\eta_{fc} = (30/f_{ck})^{1/3} \leq 1.0 \quad (f_{ck} \text{ in MPa}) \quad (15)$$

Both models can only be adopted if conventional steel longitudinal reinforcement is present in the cross-section of the FRC member.

### 3. FRC beams shear tests database (DB<sub>s</sub>)

An extended version of a database (DB<sub>s</sub>) comprising shear tests of FRC beams [8] is considered for the assessment of the MC2010 shear prediction models.

The DB<sub>s</sub> includes the data of 113 steel fiber reinforced concrete (R/SFRC) beams submitted to shear, collected from the following sources [1,5,21,25–38]. In terms of cross section configuration of the beams considered in the DB<sub>s</sub>, 99 beams are of rectangular shape, while 14 are of T-shape. Within the 113 R/SFRC beams, 99 are of deep type cross section ( $d/b_w > 1.0$ ) and 14 of current and shallow type cross section ( $d/b_w \leq 1.0$ ). The effective shear span ratio,  $a/d$ , ranges from 2.0 to 4.0, therefore it is assured the applied load is not directly conducted to the closest support of the beam in any of the R/SFRC of the DB<sub>s</sub>.

All the R/SFRC of the DB<sub>s</sub> are flexurally reinforced with passive steel bars (prestress effect is not treated in the present work). The flexural reinforcement ratio varies between 1.0 to 3.1%, and the effective depth of the cross-section,  $d$ , is within the interval 150 to 1440 mm. None of the R/SFRC beams is shear reinforced with conventional reinforcements (like stirrups). In the 113 R/SFRC beams of the DB<sub>s</sub> only hooked end type of fibers were used, with a fiber aspect ratio,  $l_f/d_f$  ( $l_f$  and  $d_f$  are the length and diameter of the fiber, respectively) varying from 48 to 80. The fiber volume,  $V_f$ , ranges from 0.25% to 1.5%. The concrete maximum aggregate size,  $d_g$ , varies between 10 and 25 mm, while the average compressive strength of the SFRC ranges between 19.2 to 64.6 MPa. Regarding the SFRC residual flexural tensile strength, the average values of  $f_{R1}$  and  $f_{R3}$  are not reported for 39 samples, while for  $f_{R2}$  and  $f_{R4}$  are not provided for 59 samples. In the DB<sub>s</sub> three different prism bending test standards were used, namely the EN 14651 [23], RILEM TC 162-TDF [14], the ASTM C1609 [22] and the UNI 11039[24]. Considering the main differences for the evaluation of the residual flexural strength using the referenced standards, the EN 14651 and RILEM TC 162-TDF adopt a 3-point bending test configuration with notched FRC beams, while the ASTM C1609 and UNI 11039 adopt a 4-point bending test, the former one with un-notched beams, and the later with notched beams.

Due to the use of un-notched SFRC samples on the prisms bending tests performed according to the ASTM C1609, the crack appears at the weakest point between the two loading points, and the measurement of the crack mouth opening displacement (CMOD) is not possible due to the unknown location of the crack. Consequently, in order to calculate the residual flexural strength of the SFRC samples of the database, the CMODs were obtained by correlating the CMOD with the measured mid-span deflection of the SFRC prisms using the methodology proposed in [39] that considers a rigid body kinematic mechanism similar to the one adopted in 3-point bending tests of notched beams [40]. Due to this simplification, the residual flexural strength values that were determined according to the ASTM C1609 can present some error.

Due to the significant number of R/SFRC beams of the DB<sub>s</sub> were the residual flexural strength is not reported, there was the need to adopt a model to predict these mechanical properties, which is discussed in the next section.

After implementation of this prediction model, the extreme values of the residual flexural strength of the R/SFRC beams studied in the DB<sub>s</sub> are:  $f_{R1} = [1.5-8.5]$  MPa,  $f_{R2} = [1.8-8.9]$  MPa,  $f_{R3} = [1.5-8.9]$  MPa and  $f_{R4} = [1.1-7.9]$  MPa.

A first analysis of the DB<sub>s</sub> has consisted in the exclusion of test results where a flexural-shear failure mechanism could be feasible. For this purpose, the flexural capacity of each R/SFRC beam was assessed following the guidelines of MC2010. For the samples where the ultimate resisting bending moment was lower than 95% of the acting bending moment (due to shear capacity registered experimentally), the shear test results were not considered in this study. After this analysis, a total of 80 R/SFRC beams were considered for the assessment of the shear resistance prediction models, within which the complete data of the post-cracking residual flexural strength ( $f_{Ri}$ ,  $i = 1, 2, 3, 4$ ) was available for 42 beams, and partial information ( $f_{Ri}$ ,  $i = 1, 3$ ) was provided for 59 beams. Since some of the beams in the DB<sub>s</sub> are casted with the same SFRC mix, the results of the experimental characterization of the post-cracking residual strength for these beams is the same. The 59 beams with experimental data of  $f_{R1}$  and  $f_{R3}$  were casted from 44 different SFRC mixes, while the 42 beams with  $f_{R2}$  and  $f_{R4}$  resulted from 35 different SFRC mixes. In Table 2 is presented the different standards considered in the evaluation of the available residual flexural strength values, considering the different SFRC mixes present in the DB<sub>s</sub>.

**Table 2.** Prism bending test standards adopted for the evaluation of the residual flexural strength,  $f_{Ri}$ , considering the different SFRC mixes present in the DB<sub>s</sub>.

Number of samples	Prism bending standards				Total
	EN 14651	RILEM TC 16	ASTM C1609	UNI 11039	
$f_{R1}$ and $f_{R3}$	9	9	25	1	44
$f_{R2}$ and $f_{R4}$	9	0	25	1	35

#### 4. Prediction model of residual flexural strength of SFRC

Based on the analysis of a database (DB<sub>f</sub>) formed by 89 samples of hooked end steel fiber reinforced concrete (SFRC) notched beams submitted to 3-point bending according to EN 14651 [23], in [41] is described in detail a strategy for establishing a relationship between the residual flexural strength of SFRC,  $f_{Ri}$ , ( $i = 1, 2, 3, 4$ ), and other material properties capable of being easily obtained in design context.

For the DB<sub>f</sub> under consideration, a very good agreement was obtained for the relation between the  $f_{R1}$ , the reinforcement index,  $IR$ , and the concrete average tensile strength,  $f_{cm}$ . The reinforcement index is defined as:

$$IR = V_f \cdot l_f / d_f \tag{16}$$

The derived relationship between  $f_{R1}$ ,  $IR$  and  $f_{cm}$  is:

$$f_{R1} = k_{1,R1} \cdot f_{cm} \cdot (IR)^{k_{2,R1}} \tag{17}$$

where  $k_{1,R1}$  and  $k_{2,R1}$  are model coefficients.

Due to the inherit complexity to perform direct and indirect tensile tests, the tensile strength of concrete can be estimated from the concrete compressive strength by the expression presented in MC2010:

$$f_{cm} = \begin{cases} 0.3 \cdot (f_{ck})^{2/3} & , f_{ck} \leq 50MPa \\ 2.12 \cdot \ln[1 + 0.1 \cdot (f_{ck} + 8)] & , f_{ck} > 50MPa \end{cases} \tag{18}$$

Strong correlation between  $f_{Ri}$  ( $i = 2, 3, 4$ ) and  $f_{R1}$  was also verified in [41], namely:

$$f_{Ri} = k_{1,Ri} \cdot (f_{R1})^{k_{2,Ri}} \quad i = 2, 3, 4 \quad (19)$$

Based on the results of the  $DB_f$ , three intervals of average compressive strength were adopted for best correlate the coefficients  $k_{1,Ri}$  and  $k_{2,Ri}$ , ( $i = 1, 2, 3, 4$ ) with the  $f_{cm}$  [MPa], having been obtained the following equations:

$$k_{1,R1} = \begin{cases} 3.2 & , f_{cm} < 25 \\ \frac{1.1}{1000} \cdot f_{cm}^2 - \frac{f_{cm}}{10} + 5 & , 25 \leq f_{cm} \leq 65 \\ 3.2 & , f_{cm} > 65 \end{cases} ; k_{2,R1} = \begin{cases} 0.5 & , f_{cm} < 25 \\ \frac{8}{1000} \cdot f_{cm} + 0.32 & , 25 \leq f_{cm} \leq 65 \\ 0.85 & , f_{cm} > 65 \end{cases} \quad (20)$$

$$k_{1,R2} = \begin{cases} 0.9 & , f_{cm} < 25 \\ \frac{-3.8 \cdot f_{cm}^2}{10000} + \frac{3.2 \cdot f_{cm}}{100} + 0.35 & , 25 \leq f_{cm} \leq 65 \\ 0.8 & , f_{cm} > 65 \end{cases} ; k_{2,R2} = \begin{cases} 1.1 & , f_{cm} < 25 \\ \frac{3 \cdot f_{cm}^2}{10000} - \frac{2.8 \cdot f_{cm}}{100} + 1.6 & , 25 \leq f_{cm} \leq 65 \\ 1.1 & , f_{cm} > 65 \end{cases} \quad (21)$$

$$k_{1,R3} = \begin{cases} 0.88 & , f_{cm} < 25 \\ \frac{-8 \cdot f_{cm}^2}{10000} + \frac{6.05 \cdot f_{cm}}{100} - 0.14 & , 25 \leq f_{cm} \leq 65 \\ 0.4 & , f_{cm} > 65 \end{cases} ; k_{2,R3} = \begin{cases} 1.12 & , f_{cm} < 25 \\ \frac{8 \cdot f_{cm}^2}{10000} - \frac{6.78 \cdot f_{cm}}{100} + 2.31 & , 25 \leq f_{cm} \leq 65 \\ 1.3 & , f_{cm} > 65 \end{cases} \quad (22)$$

$$k_{1,R4} = \begin{cases} 0.8 & , f_{cm} < 25 \\ \frac{-1.06 \cdot f_{cm}^2}{1000} + \frac{8.4 \cdot f_{cm}}{100} - 0.66 & , 25 \leq f_{cm} \leq 65 \\ 0.3 & , f_{cm} > 65 \end{cases} ; k_{2,R4} = \begin{cases} 1.12 & , f_{cm} < 25 \\ \frac{1.1 \cdot f_{cm}^2}{1000} - \frac{9.26 \cdot f_{cm}}{100} + 2.75 & , 25 \leq f_{cm} \leq 65 \\ 1.38 & , f_{cm} > 65 \end{cases} \quad (23)$$

The use of equations (17), (19)-(23) is restricted for  $f_{cm} \leq 70MPa$ , as the formulation tends to overestimate the residual flexural strength of SFRC for  $f_{cm} > 70MPa$  (few data exist in this interval).

The prediction model of the residual flexural strength presented a very good agreement with the  $DB_f$  studied in [41], as the average ratio between the experimental,  $f_{Ri,exp}$ , and predicted,  $f_{Ri,mod}$ , values of the residual flexural strength ranged between 1.02 to 1.09, while the coefficient of variation varied between 17.8% to 28.94% (Table 3). It is verified that the coefficient of variation has increased with the crack opening at which the  $f_{Ri}$  is evaluated, which is a consequence of the increase of the dispersion of the results from  $f_{R1}$  to  $f_{R4}$ .

The prediction model was also applied to the set of SFRC mixes used in the beams of the  $DB_s$  where the residual flexural strength was experimentally characterized (Table 2). In Table 4 is presented the average and coefficient of variation (COV) of the ratio between experimental,  $f_{Ri,exp}$ , and estimated values,  $f_{Ri,est}$ , of the residual flexural strength, considering the prism bending test standard adopted in the evaluation of the experimental values. It is possible to verify that when comparing the estimated and experimental  $f_{Ri}$  values determined from the test configuration that adopts notched beams (EN 14651/RILEM TC 162-TDF/UNI 11039), the model exhibits an higher dispersion and average values of the ratio  $f_{Ri,exp}/f_{Ri,est}$  than the observed in [41]. For the samples tested according to the ASTM C1609, the model presents in average a slight underestimation of the SFRC residual flexural strength, which can be related with lower values of  $f_{Ri,exp}$  due to cracking on the weakest section between the loading



points of the un-notched beams, and to the simplification adopted in the adopted correlation between the mid-span deflection and CMOD.

**Table 3.** Statistical results of the residual flexural strength prediction model [41].

Residual flexural strength	$f_{Ri,exp}/f_{Ri,mod}$		
	Average	SD <sup>a</sup>	COV <sup>b</sup> (%)
$f_{R1}$	1.02	0.18	17.78
$f_{R2}$	1.08	0.22	20.61
$f_{R3}$	1.09	0.26	23.68
$f_{R4}$	1.05	0.30	28.94

<sup>a</sup> Standard deviation; <sup>b</sup> Coefficient of variation.

**Table 4.** Statistical analysis of the ratio between the experimental and estimated values of the residual flexural strength,  $f_{Ri}$ .

Residual flexural strength	$f_{Ri,exp}/f_{Ri,est}$					
	Global		EN 14651/RILEM TC 162-TDF/UNI 11039		ASTM C1609	
	Average	COV <sup>a</sup> (%)	Average	COV <sup>a</sup> (%)	Average	COV <sup>a</sup> (%)
$f_{R1}$	1.06	26.9	1.23	24.4	0.92	19.4
$f_{R2}$	1.14	28.9	1.49	21.0	0.99	20.2
$f_{R3}$	1.14	31.9	1.35	27.6	0.99	27.8
$f_{R4}$	1.09	37.9	1.49	28.3	0.93	30.4

<sup>a</sup> Coefficient of variation.

## 5. Appraisal of MC2010 shear resistance and residual flexural strength prediction models

The predictive performance of shear models MC2010\_EEN and MC2010\_MCFT is appraised by using the information collected in the R/SFRC beams shear tests database (DB<sub>s</sub>). The shear resistance obtained by both models,  $V_{u,model}$ , is compared with the experimentally obtained shear resistance of each R/SFRC beam,  $V_{u,exp}$ , and the prediction ratio  $\lambda = V_{u,exp}/V_{u,model}$  is obtained. For the evaluation of the strain at mid-depth of the effective shear area,  $\varepsilon_x$ , in the MC2010\_MCFT model (equation (8)), the internal forces in the member are determined for a control section at the distance  $a/2$  from the beam's support, being  $a$  the shear span, where shear failure has occurred, considering that the reaction at the support is equal to the beam's shear resistance. During the analysis, the partial safety factors adopted in the theoretical models are set to 1.0, and average values for the SFRC material properties are adopted, in order to properly compare the experimental and theoretical results, being the predictive performance of the model considered as better as closer to 1.0 is  $\lambda = V_{u,exp}/V_{u,model}$ . In the case of the samples where the residual flexural strength data was not experimentally assessed, it was adopted the prediction model presented in the previous section to estimate the values of this material properties. The characteristic value of the SFRC compressive strength was evaluated from average value present in the DB<sub>s</sub>, considering the expression  $f_{ck} = f_{cm} - 8MPa$  proposed by MC2010.

In Figure 1 is presented a statistical analysis of the prediction ratio,  $\lambda$ , for each shear resistance model considering the source of the residual flexural strength values (experimental/estimated). When assessing the influence of the use of experimental or estimated values of the residual flexural strength of SFRC for the MC2010\_EEN and MC2010\_MCFT, it is possible to denote that the average values of the prediction ratio,  $\lambda$ , is slightly higher when using estimated values of  $f_{Ri}$ , which is related to the slight underestimation of the estimated values of  $f_{Ri}$ , as shown in the column "Global" of Table 4. However, when considering the source of the residual flexural strength values the average values of the prediction ratio  $\lambda$  for the analyzed scenarios have very small differences, including the coefficients of

variation. Due to this, it is possible to conclude that the residual flexural strength prediction model presented in the previous section is suitable to be used in the evaluation of the shear resistance of R/SFRC beams, when the values of  $f_{Ri}$  are absent in the database. When analysing the global performance of the shear prediction models, both models present a satisfactory approximation to the experimental results (average value of  $\lambda$  equal to 1.26), with acceptable values of dispersion (coefficient of variation lower than 20%). It should be noticed the existence of only one outlier in 80 samples ( $\approx 1\%$ ), which corresponds to a sample of the MC2010\_EEN model.





Figure 1. Statistical analysis of  $\lambda$  for both MC2010 shear resistance models considering the use of experimental and estimated values of  $f_{Ri}$ .

In Figure 2a is presented the comparison between the experimental and prediction values of the shear resistance for each beam. The results are also divided in categories considering the source of the residual flexural strength values considered in the shear resistance model. As can be seen, the predictive performance of the shear models is very similar and a satisfactory agreement with the experimental values of the DB<sub>s</sub> is attained. Considering the influence of the source of the residual flexural strength values, it is possible to observe that the use of the  $f_{Ri}$  prediction model appears to be related with a more pronounced underestimation of the shear resistance (a relatively high percentage of results is in the interval of  $V_{u,exp} = 1.5 \cdot V_{u,model}$  to  $V_{u,exp} = 2.0 \cdot V_{u,model}$ ) for the R/SFRC beams under analysis. In Figure 2b is presented the overall analysis of both models, regarding that the prediction values are safe for  $\lambda \geq 1$  and unsafe for  $\lambda < 1$ . From these results is possible to verify that the MC2010\_MCFT model presents a slightly higher percentage of safe predictions when compared to the MC2010\_EEN model. In addition, the comparison between the performance of both MC2010 models was assessed according to an adapted version of the *Demerit Points Classification* proposed in [42]. This classification is based on the determination of the cumulative number of penalties for each value of  $\lambda$ . The penalty points scale is defined in Table 5, and the lower the number of penalties is, the safer is the performance of the model. For this case, both models present a very similar number of total penalties points, with a slight better performance of the MC2010\_MCFT model presenting 62 penalty points while the MC2010\_EEN model has 68 penalty points.

Table 5. Adapted version of the *Demerit Points Classification*.

$\lambda = V_{u,exp} / V_{u,model}$	Classification	Penalty
< 0.50	Extremely Dangerous	10
[0.50-0.85[	Dangerous	5
[0.85-1.15[	Appropriate Safety	0
[1.15-2.00[	Conservative	1
$\geq 2.00$	Extremely Conservative	2



**Figure 2.** a) Comparison of experimental and shear strength determined from both MC2010 prediction models.  
 b) Predictive performance of theoretical model, safe ( $\lambda \geq 1$ ) and unsafe ( $\lambda < 1$ ).

### 6. Conclusions

In the present work was assessed the performance of the two shear resistance models available in CEB *fib* Model Code 2010 (MC2010) by comparison of its predictive capability in a database that includes the results of 80 samples of steel fiber reinforced concrete (R/SFRC) beams submitted to shear.

Due to the absence of the characterization of the residual flexural strength of the SFRC used in several tests, a model that estimates these mechanical parameters based on the reinforcement index and concrete strength class was proposed and coupled with the shear resistance models.

For the assessment of the suitability of the residual flexural strength prediction model a comparison of the prediction ratio,  $\lambda$ , was performed, which was computed by considering estimated and experimentally obtained values of the residual flexural strength of the SFRC. The obtained results demonstrated a very small difference between the average and dispersion of the prediction ratio,  $\lambda$ , which validates the use of the residual flexural strength prediction model in the assessment of the shear resistance of FRC elements.

For evaluating the overall performance of the shear models a statistical analysis of the prediction ratio,  $\lambda$ , was conducted, which revealed that the performance of the MC2010\_MCFT and MC2010\_EEN models is very similar, with the MC2010\_MCFT presenting a very slightly minor coefficient of variation for the  $\lambda$  than the MC2010\_EEN model (18.4%-19.7%). For the majority of the cases, both MC2010 shear models predict safe values for the shear resistance of the R/SFRC beams, and when the partial safety factor is introduced, the models always return safe predictions.

An additional comparison of the MC2010 shear models was done considering the Demerit Points Classification, having both approaches presented similar performance in this regard (the difference was only 6 penalty points between both models).

### Acknowledgements

The first Author would like to acknowledge the grant SFRH/BDE/96381/2013 co-funded by CiviTest - Pesquisa de Novos Materiais para a Engenharia Civil, Lda. and by FCT - Portuguese Foundation for Science and Technology. The authors also acknowledge the support provided by the FCT project

PTDC/ECM-EST/2635/2014.

## References

- [1] Kwak Y-K, Eberhard M O, Kim W-S and Kim J 2002 Shear strength of steel fiber-reinforced concrete beams without stirrups *ACI Struct. J.* **99** 530–538
- [2] Noghabai K 2000 Beams of fibrous concrete in shear and bending: experiment and model *J. Struct. Eng.* **126** 243–251
- [3] Soltanzadeh F, Barros J A O and Santos R F C 2015 High performance fiber reinforced concrete for the shear reinforcement: Experimental and numerical research *Constr. Build. Mater.* **77** 94–109
- [4] Adebar P, Mindess S, St Pierre D and Olund B 1997 Shear tests of fiber concrete beams without stirrups *ACI Struct. J.* **94**
- [5] Aoude H, Belghiti M, Cook W D and Mitchell D 2012 Response of steel fiber-reinforced concrete beams with and without stirrups *ACI Struct. J.* **109** 359
- [6] Imam M, Vandewalle L, Mortelmans F and Van Gemert D 1997 Shear domain of fibre-reinforced high-strength concrete beams *Eng. Struct.* **19** 738–47
- [7] Kiang-Hwee Tan P P and K Murugappan 1995 Steel Fibers as Shear Reinforcement in Partially Prestressed Beams *Struct. J.* **92**
- [8] Foster S J and Argarwal A 2017 *Database for testing shear models for SFRC beams and one-way slabs without stirrups* (Sydney, Australia: School of Civil and Environmental Engineering, UNSW Sydney)
- [9] Foster S J, Agarwal A and Amin A 2017 Design of steel fiber reinforced concrete beams for shear using inverse analysis for determination of residual tensile strength *Struct. Concr.*
- [10] Cuenca E, Conforti A, Minelli F, Plizzari G A, Navarro Gregori J and Serna P 2018 A material-performance-based database for FRC and RC elements under shear loading *Mater. Struct.* **51**
- [11] Soetens T 2015 *Design models for the shear strength of prestressed precast steel fibre reinforced concrete girders* PhD Thesis (Ghent University)
- [12] fib-federation internationale du beton 2013 *fib Model Code for Concrete Structures 2010* (John Wiley & Sons)
- [13] Moraes Neto B N, Barros J A O and Melo G S S A 2013 A model for the prediction of the punching resistance of steel fibre reinforced concrete slabs centrally loaded *Constr. Build. Mater.* **46** 211–23
- [14] RILEM TC 162-TDF 2002 Recommendations of RILEM TC 162-TDF: Test and design methods for steel fibre reinforced concrete: bending test *Mater. Struct.* **35** 579–82
- [15] Bentz E C, Vecchio F J and Collins M P 2006 Simplified modified compression field theory for calculating shear strength of reinforced concrete elements *ACI Struct. J.* **103** 614
- [16] Ng T S, Foster S J, Htet M L and Htet T N S 2014 Mixed mode fracture behaviour of steel fibre reinforced concrete *Mater. Struct.* **47** 67–76
- [17] European Committee for Standardization 2010 *Eurocode 2: Design of concrete structures Part 1-1: General rules and rules for buildings* vol NP EN 1992-1-1
- [18] Marco di Prisco, Giovanni Plizzari and Lucie Vandewalle 2010 MC2010: Overview on the shear provisions for FRC *Shear and punching shear in RC and FRC elements (workshop proceedings)* fib Bulletin (Lausanne: fédération internationale du béton) pp 61–76
- [19] Stephen Foster 2010 Design of FRC beams for shear using the VEM and the draft Model Code approach *Shear and punching shear in RC and FRC elements (workshop proceedings)* fib Bulletin (Lausanne: fédération internationale du béton) pp 195–210
- [20] Sigrist V, Bentz E, Ruiz M F, Foster S and Muttoni A 2013 Background to the fib Model Code 2010 shear provisions - part I: beams and slabs *Struct. Concr.* **14** 195–203
- [21] Amin A, Foster S J and Muttoni A 2015 Derivation of the  $\sigma$ - $w$  relationship for SFRC from prism bending tests *Struct. Concr.* **16** 93–105

- [22] ASTM International 2012 *Standard Test Method for Flexural Performance of Fiber-Reinforced Concrete (Using Beam With Third-Point Loading)* vol ASTM C1609
- [23] European Committee for Standardization 2005 *Test method for metallic fibered concrete - Measuring the flexural tensile strength (limit of proportionality (LOP), residual)* vol EN 14651
- [24] Italian Board for Standardization 2003 *Steel Fiber Reinforced Concrete—Part I: Definitions, Classification Specification and Conformity—Part II: Test Method for Measuring First Crack Strength and Ductility Indexes* vol UNI 11039
- [25] Dinh H H, Parra-Montesinos G J and Wight J K 2011 Shear Strength Model for Steel Fiber Reinforced Concrete Beams without Stirrup Reinforcement *J. Struct. Eng.* **137** 1039–51
- [26] Cuenca E 2015 *On Shear Behavior of Structural Elements Made of Steel Fiber Reinforced Concrete* PhD Thesis (Valencia, Spain: Universitat Politècnica de València)
- [27] Rosenbusch J and Teutsch M 2003 Shear design with- method *Proc. RILEM TC* 105–117
- [28] Minelli F 2005 *Plain and fiber reinforced concrete beams under shear loading: Structural behavior and design aspects* PhD Thesis (Brescia, Italy: Department of Civil Engineering, University of Brescia)
- [29] Singh B and Jain K 2014 An Appraisal of Steel Fibers as Minimum Shear Reinforcement in Concrete Beams *ACI Struct. J.* **111**
- [30] Conforti A, Minelli F and Plizzari G A 2013 Wide-shallow beams with and without steel fibres: A peculiar behaviour in shear and flexure *Compos. Part B Eng.* **51** 282–90
- [31] Jain K and Singh B 2014 Investigation of steel fibres as minimum shear reinforcement *Proc. Inst. Civ. Eng. - Struct. Build.* **167** 285–99
- [32] Al-lami K 2000 *Experimental Investigation of Fiber Reinforced Concrete Beams* MSc Thesis (Portland State University)
- [33] Bryan Erick Barragán 2002 *Failure and toughness of Steel Fiber Reinforced Concrete under tension and shear* PhD Thesis (Barcelona, Spain: Universitat Politècnica de Catalunya)
- [34] Greenough T and Nehdi M 2008 Shear behavior of fiber-reinforced self-consolidating concrete slender beams *Mater. J.* **105** 468–477
- [35] Bertozzi A and Reggia A 2006 *Steel fibers for the minimum shear reinforcement of the beams* MSc Thesis (Brescia, Italy: University of Brescia)
- [36] Conforti A 2008 *Variable truss model for the shear design of fibre reinforced concrete beams: experimental and analytical study* MSc Thesis (Brescia, Italy: University of Brescia)
- [37] Minelli F, Plizzari G A and Vecchio F J 2007 Influence of steel fibers on full-scale RC beams under shear loading *Fracture Mechanics of Concrete Structures – High Performance Concrete, Brick-Masonry and Environmental Aspects* (London: Taylor and Francis) pp 1523–31
- [38] Conforti A, Minelli F and Plizzari G A 2017 Influence of Width-to-Effective Depth Ratio on Shear Strength of Reinforced Concrete Elements without Web Reinforcement *ACI Struct. J.* **114**
- [39] Stephen J. Foster, Ankit Agarwal and Ali Amin 2017 Design of SFRC Beams for Shear using Inverse Analysis for determination of Residual Tensile Strength *Struct. Concr.* **19** 129–40
- [40] Vandewalle L and Dupont D 2003 BENDING TEST AND INTERPRETATION *International RILEM Workshop on Test and Design Methods for Steel Fibre Reinforced Concrete - Background and Experiences* International RILEM Workshop on Test and Design Methods for Steel Fibre Reinforced Concrete - Background and Experiences (RILEM Publications SARL) pp 1–13
- [41] Moussa Y H 2017 *Steel fiber efficiency for flexural reinforcement of reinforced concrete beams with minimum reinforcement ratio* MSc thesis (Belém, Brasil: Universidade Federal do Pará)
- [42] Collins M 2001 *Evaluation of shear design procedures for concrete structures* (Canada: A Report prepared for the CSA technical committee on reinforced concrete design)