

PAPER • OPEN ACCESS

## Bottom ash utilization: A review on engineering applications and environmental aspects

To cite this article: M H Abdullah *et al* 2019 *IOP Conf. Ser.: Mater. Sci. Eng.* **527** 012006

View the [article online](#) for updates and enhancements.

### Recent citations

- [Effect of Temperature on Rare Earth Elements Recovery from Coal Fly Ash Using Citric Acid](#)  
Pramesti Pihutami *et al*



**240th ECS Meeting** ORLANDO, FL

Orange County Convention Center **Oct 10-14, 2021**

Abstract submission deadline extended: April 23rd

**SUBMIT NOW**

# Bottom ash utilization: A review on engineering applications and environmental aspects

M H Abdullah<sup>1\*</sup>, A S A Rashid<sup>1</sup>, U H M Anuar<sup>1</sup>, A Marto<sup>2</sup> and R Abuelgasim<sup>3</sup>

<sup>1</sup>School of Civil Engineering, Faculty of Engineering, Universiti Teknologi Malaysia, 81310 Johor Bahru, Johor, Malaysia

<sup>2</sup>Dept. of Environmental Engineering and Green Technology (EGT) Malaysia-Japan International Institute of Technology (MJIIT) Universiti Teknologi Malaysia, Jalan Sultan Yahya Petra, 54100 Kuala Lumpur, Malaysia

<sup>3</sup>Geotechnical Engineering Department, Building and Road Research Institute, University of Khartoum, Khartoum, Sudan

\*Corresponding e-mail: feezi998@yahoo.com

**Abstract.** Bottom ash produced from coal-fired power plants has been utilized in engineering applications for the purpose of recycling and solving disposal issue of bottom ash. This study reviews various applications of bottom ash in engineering fields. The engineering properties exhibited by bottom ash in terms of free draining, granular, lightweight and interlocking nanostructures allow them to be used for different functions. The bottom ash used is not limited to its raw state, but can be mixed and modified for advanced applications without neglecting the impacts on the environmental. The presence of metals in bottom ash are well known and being discussed whether they are harmful to the environment. Many countries have their own threshold limit of maximum contaminants, hence TCLP result will determine the hazardous status of bottom ash. This review helps in promoting the solution and potential usage of bottom ash, since coal is one of the dominant source of energy in power generation sector.

**Keywords:** bottom ash; engineering applications; environment

## 1. Introduction

The rapid growth of global population boosted the economic growth, especially in energy sectors. China, India and USA account for the top three countries in the world with the highest demand of fossil fuels and rapidly increasing every year [1]. Table 1 present the production of bottom ash from different countries. Among the fossil fuel resources, coal is the most demanded compare to oil and gas because it is the cheapest and most abundant in the world [2].

However, rising demand for coal lead to new challenges. The consumption of coal in the boiler produce two main waste product bottom ash and fly ash in the range of 10-30 and 70-90 % respectively [3], [4] and [5].



**Table 1.** Bottom ash production.

Reference/Year	Bottom ash (tonnes) / year
USA [6]	10 million
Europe [7]	18 million
China [8]	~ 60 million
India [9]	100 million
Tanjung Bin (Malaysia), [10]	96 thousand
Catalonia (Spain), [11]	200 thousand

This huge amount of waste has become a global issue and required serious attention from those countries that consume coal for their energy resources. Since the amount of bottom ash accumulated keep on increasing, the cost for opening new landfill area, transporting to a disposal site and maintaining the reclamation facilities will increase significantly. Therefore, plant operators started to collaborate with researchers and industries in order to fully utilize the vast amount of accumulated bottom ash.

Bottom ash generally disposed of in slurry condition by mixing with water and being discharged into ash ponds [12] and [13]. Researchers commonly collect samples from ash pond and ensure that they are in compliance with local authority standard.

In recent years, the utilization of bottom ash in engineering field has received considerable attention due to its potential application including aggregate replacement, concrete products, embankment fill, road construction and reclamation work [14] and [15]. In order to utilize bottom ash, the physical, chemical properties as well as the method of application must be studied. This paper aims to review the engineering application use of bottom ash and its environmental impact through literature finding.

## 2. Engineering Application of Bottom Ash

Generally, the bottom ash particles have dark, angular shapes with porous textures and rough surface. The particle size ranging from gravel of 40 mm to fine sand of 0.075 mm [14]. Most researchers believed that the properties of bottom ash are similar to natural sand material [13,16-18].

Bottom ash has been utilized in civil engineering field, agriculture and manufacturing soil products industry [19]. According to [14], bottom ash is mainly used in civil engineering field. It is reported that the European Union and United States used about 50% and 35% of the produced bottom ash respectively in this field. Such waste materials are widely used as replacement materials in construction including natural silt, clay, sand and gravel. Hence, bottom ash has the potential application in road construction, concrete, various cement products and reclamation fills.

### 2.1 Road construction

Bottom ash is listed as one of waste materials suitable for recycling in road construction [20] and by far is the most popular outlet for the material. Bottom ash is targeted to substitute sand or fine aggregates in road construction either as partially or full replacement due to its similar properties to natural sand.

Coal Combustion Products Utilization Handbook [19], conducted a study on the performance of bottom ash in subgrade using plate load bearing tests. After one season, the road pavement was found to be in good condition indicating that the subgrade performed satisfactorily. In order to enhance the performance of the pavement, a recommendation has been made to use bottom ash in a 2 to 1 thickness ratio compared to normal base course material.

[5] summarized the uses of bottom ash as subbase, road-base materials and as bituminous mixes for binder layer. From the report, it is found that bottom ash provides adequate bearing capacity for lower strength application such as subbase materials and embankment fills [5]. On the other hand, the utilization of bottom ash in road base materials depends on the percentage content because the compressive strength is said to be reduced with an increase of bottom ash replacement percentage [5,12]. Besides that, low content of bottom ash in bituminous mixes is found practical as the ash not modify the

mechanical characteristics of the mixture. Conversely higher content of bottom ash in the mix requires higher amount of bitumen in order to satisfy Marshall Mix design limit [5, 21].

In addition, replacement material formulated with bottom ash and fly ash in subbase and road-base was found suitable for road embankment construction. The limitation is that low bottom ash to high fly ash ratio (ranging from 50 to 100% of fly ash content) was suggested for better performance and stability [22-23]. In four season country, a field study to identify the potential of bottom ash as insulation layer also has been conducted by [24]. The results indicate that bottom ash performed well as heat insulator and was effective in reducing frost penetration into the subgrade.

### *2.2 Aggregate Replacement in concrete*

The potential of bottom ash to be used as replacement material in concrete has been explored by numerous researchers. The ash either can use as fine aggregate or coarse aggregate replacement. The replacement will cause some changes on the properties of concrete such as the workability, compressive strength and durability.

[16] found that the workability of concrete reduces with the use of bottom ash as fine aggregate replacement due to physical properties of bottom ash (irregular shape, rough texture and high porosity) increased the inter particles friction and thereby hinders the flow characteristics of fresh concrete. Other than that, the higher water absorption capability of bottom ash itself reduced the workability. This finding has confirmed by [25] which has stated that the increased of bottom ash percentage by weight in concrete has decreased the workability by 4% to 9%. Meanwhile, [26] examined the effect of slump flow values of fresh concrete with bottom ash as the replacement and found the slump value decreases with increasing percentage of bottom ash. This indicate the fact that as water absorbed internally by the porous bottom ash particles increased, huge amount of water was required in order to mix the concrete.

In term of compressive strength, [26] studied the effect of bottom ash as fine and coarse aggregate in concrete mix at 7 days and 28 days curing age. Based on observation, the compressive strengths were found not significantly affected by the replacements of fine bottom ash. However, for the 7-day curing period, the compressive strength of concrete mixes containing 50% and 100% bottom ash decreased about 9% and 15.16% compared to the strength of the control samples, respectively [27]. The lower compressive strength is related to the strength of replacement material in concrete mix. Studies show that bottom ash are more porous and weak than natural sand. As mentioned before, the higher water absorption by bottom ash has increased amount of mixing water, which contribute to more volume of pores left by water. These pores prevented the strong bonding of cement paste with the aggregate. As a result, the transition zone between the aggregate and cement paste becomes weak and porous which eventually reduces the strength of bottom ash concrete mix [13].

Nevertheless, [28] found that with long-term duration of curing age, up to 60 days, the compressive strength increased up to 10%. Similar finding was observed by [29], where 30% sand replacement is used in the concrete mix and the compressive strength recorded the highest value at the curing ages up to 60 days. Therefore, it can be concluded that concrete with bottom ash content will reach its optimum strength beyond 28 days.

### **3. Environmental Aspects**

From environmental point of view, utilization of bottom ash in engineering field is a potential solution for the disposal issue of the material. However, [30] stated that bottom ash disposal must be properly managed to prevent or minimize any environmental impacts since utilization of bottom ash is still lacking and at low percentage. In contrast, fly ash has been used by cement industries and some plants has made agreement with power plant operators to collect their fly ash regularly. Therefore, study on the chemical composition of bottom ash is important to investigate the risk and behavior that it may impact the environment. Table 2 tabulates the chemical compositions of bottom ash samples obtained from different sources.

**Table 2.** Chemical composition of bottom ash from various sources (%).

Component	Thailand [15]	Indonesia [31]	India [18]	USA [19]	Cyprus [32]	USA [33]	Morocco [34]	Malaysia [35]	India [25]
SiO <sub>2</sub>	36.84	50.03	56.00	82.73	61.00	46.60	55.10	43.1	45.64
Al <sub>2</sub> O <sub>3</sub>	18.28	3.68	26.7	1.89	25.40	26.10	28.10	19.89	18.2
Fe <sub>2</sub> O <sub>3</sub>	15.46	32.88	5.80	5.10	6.60	12.40	8.30	9.57	8.74
CaO	18.43	3.80	0.80	2.17	1.50	8.31	1.10	16.38	8.18
MgO	2.62	4.01	0.60	1.10	1.00	1.26	0.30	3.83	3.80
SO <sub>3</sub>	0.74	-	0.10	1.51	-	0.30	0.30	0.44	-
K <sub>2</sub> O	2.29	0.32	2.60	-	0.20	1.34	1.50	0.42	2.01
Na <sub>2</sub> O	0.75	-	0.20	-	0.90	0.62	-	0.25	-
TiO <sub>2</sub>	0.9	-	1.30	-	-	1.84	-	1.51	0.98
P <sub>2</sub> O <sub>5</sub>	0.17	-	-	-	-	0.62	-	0.45	0.98
SiO <sub>2</sub> , Al <sub>2</sub> O <sub>3</sub> , Fe <sub>2</sub> O <sub>3</sub>	70.58	86.59	88.5	89.72	93.0	85.1	91.5	72.56	72.58
LOI (Loss on Ignition)	2.02	3.99	4.60	1.80	-	-	3.90	-	-

The chemical composition of bottom ash samples was investigated using XRF and XRD analysis by various researchers. In general, the major contents of bottom ash were silica, alumina, iron and calcium oxide. Others were magnesium, kalium, barium, potassium, sodium and titanium oxides in smaller percentage less than 4%. Referring to Table 2, it shows that bottom ash classified as ASTM C 618 as Class F ash with the percentage combination of SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub> and Fe<sub>2</sub>O<sub>3</sub> ranging from 70 to 93% which exceeds 70% [19, 25, 31 and 36]. Loss on ignition (LOI) of bottom ash range from 1.8 to 3.99 due to the amount of carbon to measures the quantity of CO<sub>2</sub> [37]. Variability of coal ash sources, processing of coal ash (combustion temperature, residence time, turbulence) and ignition temperatures contribute to the variation in LOI results [5]. For example, LOI threshold of 5% has been set by the French Ministry and Netherlands to promote full utilization of bottom ash.

With respect to utilization of bottom ash, the amount of heavy metals must be considered because bottom ash is often considered as not harmful. The reactivity and potential of heavy metal release by reaction of bottom ash with CO<sub>2</sub> and water will further reduce as time pass by through aging and weathering process which result in more stable complex compounds in bottom ash [38-39]. Therefore, the quality of bottom ash can eventually improve due to aging and weathering making its recycling a viable option.

For the beneficial utilization of bottom ash, many countries had implemented their own policies and regulations with regard to ash management. In order for bottom ash to be considered as non-hazardous waste, it required to pass the Toxicity Characteristic Leaching Procedure (TCLP) [40, 41]. An effort was made to compile limitation values among different country standards as summarized in Table 3.

**Table 3.** Maximum concentration of contaminations TCLP in various countries (mg/L).

Element	USA [42]	USA Drinking Water Standard [43]	Malaysia [41]	Singapore [44]	China [45]	Australia [46]
Antimony (Sb)	-	0.006	15.0	-	-	-
Arsenic (As)	5.0	0	5.0	5.0	5.0	5.0
Barium (Ba)	100.0	2.0	100.0	100.0	-	-
Beryllium (Be)	-	0.004	0.75	-	-	1.0
Cadmium (Cd)	1.0	0.005	1.0	1.0	1.0	1.0
Chlorine (Cl)	-	4.0	-	-	-	-
Chromium (Cr)	5.0	0.1	5.0	5.0	5.0	-
Chromium-VI (CrVI)	-	-	5.0	-	-	5.0
Cobalt (Co)	-	-	80.0	-	-	-
Copper (Cu)	-	1.3	25.0	100.0	100.0	-
Fluorine (F)	-	4.0	-	150.0	-	-
Lead (Pb)	5.0	0	5.0	5.0	5.0	5.0
Manganese (Mn)	-	0.05	-	50.0	-	-
Mercury (Hg)	0.2	0.002	0.2	0.2	0.1	0.2
Molybdenum (Mo)	-	-	350.0	-	-	5.0
Nickel (Ni)	-	-	20.0	5.0	5.0	2.0
Selenium (Se)	1.0	0.05	1.0	1.0	-	1.0
Silver (Ag)	5.0	0.1	5.0	-	-	5.0
Thallium (TI)	-	0.0005	7.0	-	-	-
Vanadium (V)	-	-	24.0	-	--	-
Zinc (Zn)	-	5.0	250.0	100.0	100.0	-

According to [12-13, 47-48], bottom ash contains heavy metals, i.e. Manganese (Mn), Copper (Cu), Zinc (Zn), Arsenic (As), Lead (Pb), Cadmium (Cd), Cobalt (Co), Chromium (Cr) and Nickel (Ni). The presence of these elements can be harmful to the environment as it can be leached out to surrounding soil and groundwater. However, TCLP test conducted on bottom ash shows that the amount of heavy metals does not exceed the maximum concentration in their respective country regulations [47-48]. Traces of Mercury (Hg) also found in bottom ash, but [49] reported that during the combustion process, a large portion of Hg is vaporized and remaining Hg is tightly bound and not easily released into the environment.

Heavy metal contents in bottom ash from three sources of coal power plants with different capacities S1 (750 MW), S2 (840 MW) and S3 (2,100 MW) were studied by [50]. It is observed that the concentration of heavy metals in three different sources of bottom ash is highest from lower capacity boiler (source 1>source 2>source 3).

Although bottom ash has passed toxicity test, there are risks of heavy metals release to the environment. In order to reduce the risk, [47] suggest that utilization of bottom ash in the topmost exposed layer must not be practiced. In recent years, many research focused on treatments for leaching of bottom ash. Contaminants are extracted and pre-leach before being utilized or transport to landfill. For instance, in USA, USEPA has supported research projects on ash utilization, indicating no adverse environmental or health impacts using bottom ash in pavement works since 1995 [51]. Moreover,

utilization of bottom ash in roads construction in some countries was successful and gain support from the local authorities as the leaching of metals during service life comply with standards [52-55].

Another effective technique to completely stabilize heavy metals is by waste vitrification [56]. Vitrification process destroys hazardous organic compound that presents in bottom ash and yields a highly homogeneous glass to be used in many applications [16]. The transformation into more valuable products with glassy nature can compensate for the high energy demand of the process.

#### 4. Conclusions

Utilization of bottom ash in engineering and their impact on the environment are reviewed in this paper. Recycling of bottom ash able to conserve usage of natural resources (sand, gravel, limestone) needed for cement production or road constructions. Recently, some countries reported that natural sources for aggregates from viable quarries are decreasing. Thus, similarities properties shown by bottom ash with fine aggregates allow them to be partially replaced. In term of economic benefits, it helps plant operator to save cost in terms of opening new landfill, land acquisition and ash management.

Many countries like Malaysia has a very low percentage of bottom ash utilization due to environmental issue as the ash contains heavy metals that may leach into the environment. Bottom ash composition of heavy metals that poses environmental hazards which can leach into the environment. Based on this review, bottom ash can be categorized as non-hazardous and safe to be utilized and recycled as long as the contaminant levels do not exceed the permissible limits set by the respective regulatory bodies.

Nowadays, majority researchers focus on advanced technology to reduce the contaminants. Hence, allow bottom ash to be fully utilized and less concern on their impact to the environment. Political support is strongly needed. Some government imposed strict regulations on hazardous materials and their potential used as recycled materials in civil engineering applications. The implementation will require the government to revise their current environmental act which is a very long process. While, one government should consider to make some exclusion to certain act by detailed monitoring of specific cases for the beneficial use of bottom ash.

#### 5. References

- [1] International Energy Agency 2017 [Available from: [www.iea.org/publications/freepublications/publication/KeyWorld2017.pdf](http://www.iea.org/publications/freepublications/publication/KeyWorld2017.pdf).] Accessed 22.11.2018
- [2] Jamaludin A. 2009 Energy mix and alternatives energy for sustainable development in Malaysia. Tokyo, Japan: 9th International Students Summit on Food, Agriculture and Environment in the New Century.
- [3] Kizgut S, Cuhadaroglu D, Samanli S. 2010 Stirred grinding of coal bottom ash to be evaluated as a cement additive. *Energy Sources, Part A: Recovery, Utilization, and Environmental Effects*. 32(16):1529-39.
- [4] Levandowski J, Kalkreuth W. 2009 Chemical and petrographical characterization of feed coal, fly ash and bottom ash from the Figueira Power Plant, Paraná, Brazil. *International Journal of Coal Geology*. 77(3-4):269-81.
- [5] Lynn CJ, Ghataora GS, OBE RKD. 2017 Municipal incinerated bottom ash (MIBA) characteristics and potential for use in road pavements. *International Journal of Pavement Research and Technology*. 10(2):185-201.
- [6] American Coal Ash Association 2017 [Available from: [www.aaa-usa.org/Portals/9/Files/PDFs/2017-Charts.pdf](http://www.aaa-usa.org/Portals/9/Files/PDFs/2017-Charts.pdf).] Accessed 26.11.2018
- [7] Confederation of European Waste-to-Energy Plants 2017 [Available from: [www.cewep.eu/wp-content/uploads/2017/09/FINAL-Bottom-Ash-factsheet.pdf](http://www.cewep.eu/wp-content/uploads/2017/09/FINAL-Bottom-Ash-factsheet.pdf).] Accessed 26.11.2018
- [8] Ma S, Xu M, Qiqige X-HW, Zhou X. 2017 Challenges and Developments in the Utilization of Fly Ash in China. *Int J Environ Sci Dev*. 8(11):781-5.

- [9] Singh G, Kumar S, Mohapatra S, Kumar K. 2017 Comprehensive characterization of grounded bottom ash from Indian thermal power plant. *Journal of Residuals Science & Technology*.
- [10] Malakoff Corporation Berhad Annual Report 2017.
- [11] Izquierdo M, Vazquez E, Querol X, Barra M, Lopez A, Plana F, editors. 2001 Use of bottom ash from municipal solid waste incineration as a road material. *International ash utilization symposium, 4th, Lexington, KY, United States*.
- [12] Jayaranjan MLD, Van Hullebusch ED, Annachhatre AP. 2014 Reuse options for coal fired power plant bottom ash and fly ash. *Reviews in Environmental Science and Bio/Technology*. 13(4):467-86.
- [13] Mandal A, Sinha O. 2014 Review on current research status on bottom ash: An Indian prospective. *Journal of The Institution of Engineers (India): Series A*. 95(4):277-97.
- [14] Kim H, Lee H-K. 2015 Coal bottom ash in field of civil engineering: A review of advanced applications and environmental considerations. *KSCE Journal of Civil Engineering*. 19(6):1802-18.
- [15] Torkittikul P, Nochaiya T, Wongkeo W, Chaipanich A. 2017 Utilization of coal bottom ash to improve thermal insulation of construction material. *Journal of Material Cycles and Waste Management*. 19(1):305-17.
- [16] Singh M, Siddique R. 2013 Effect of coal bottom ash as partial replacement of sand on properties of concrete. *Resources, conservation and recycling*. 72:20-32.
- [17] Marto A, Hasan M, Hyodo M, Makhtar AM. 2014 Shear strength parameters and consolidation of clay reinforced with single and group bottom ash columns. *Arabian Journal for Science and Engineering*. 39(4):2641-54.
- [18] Ramadoss P, Sundararajan T. 2014 Utilization of lignite-based bottom ash as partial replacement of fine aggregate in masonry mortar. *Arabian Journal for Science and Engineering*. 39(2):737-45.
- [19] Coal Combustion Products Utilization Handbook. 3rd ed: We Energies Publication; 2013. 448 p.
- [20] Poulidakos L, Papadaskalopoulou C, Hofko B, Gschösser F, Falchetto AC, Bueno M, et al. 2017 Harvesting the unexplored potential of European waste materials for road construction. *Resources, Conservation and Recycling*. 116:32-44.
- [21] Colonna P, Berloco N, Ranieri V, Shuler S. 2012 Application of bottom ash for pavement binder course. *Procedia-Social and Behavioral Sciences*. 53:961-71.
- [22] Kim B. Properties of coal ash mixtures and their use in highway embankments. 2003.
- [23] Kim B, Prezzi M, Salgado R. 2005 Geotechnical properties of fly and bottom ash mixtures for use in highway embankments. *J Geotech Geoenviron Eng*. 131(7):914-24.
- [24] Haghi NT, Nassiri S, Shafiee MH, Bayat A. 2014 Using field data to evaluate bottom ash as pavement insulation layer. *Transportation Research Record*. 2433(1):39-47.
- [25] Sadon SN, Beddu S, Naganathan S, Kamal NLM, Hassan H. 2017 Coal Bottom Ash as Sustainable Material in Concrete—A Review. *Indian Journal of Science and Technology*. 10(36).
- [26] Kim H-K, Lee H-K. 2011 Use of power plant bottom ash as fine and coarse aggregates in high-strength concrete. *Construction and Building Materials*. 25(2):1115-22.
- [27] Singh M, Siddique R. 2014 Strength properties and micro-structural properties of concrete containing coal bottom ash as partial replacement of fine aggregate. *Construction and Building Materials*. 50:246-56.
- [28] Aggarwal P, Aggarwal Y, Gupta S. 20017 Effect of bottom ash as replacement of fine aggregates in concrete.



- [29] Sani MSHM, Muftah F, Muda Z. 2011 The properties of special concrete using washed bottom ash (WBA) as partial sand replacement. *International Journal of Sustainable Construction Engineering and Technology*. (2):65-76.
- [30] Razak HA, Naganathan S, Hamid SNA. 2010 Controlled low-strength material using industrial waste incineration bottom ash and refined kaolin. *Arabian Journal for Science and Engineering*. 35(2B):53-67.
- [31] Ahmad RI, Yasufuku N, Omine K, Tsuji K. 2010 Utilization of Coal Ash As Recycling Material Options in View Point of Geoenvironment. *Advances in Environmental Geotechnics: Springer*. p. 715-20.
- [32] Aydin E. 2016 Novel coal bottom ash waste composites for sustainable construction. *Construction and Building Materials*. 124:582-8.
- [33] Martín-Fernández J, Olea RA, Ruppert LF. 2018 Compositional Data Analysis of Coal Combustion Products with an Application to a Wyoming Power Plant. *Mathematical Geosciences*. 50(6):639-57.
- [34] Taoufiq L, Laamyem A, Essediqi E, Monkade M, Zradba A. 2018 Recycling coal fly ash and coal bottom ash from Moroccan thermal power plant in concrete manufacturing.
- [35] Marto A, Kassim KA, Makhtar AM, Wei LF, Lim YS. 2010 Engineering characteristics of Tanjung Bin coal ash. *Electronic Journal of Geotechnical Engineering*. 15:1117-29.
- [36] Arickx S, De Borger V, Van Gerven T, Vandecasteele C. 2010 Effect of carbonation on the leaching of organic carbon and of copper from MSWI bottom ash. *Waste Management*. 30(7):1296-302.
- [37] Santos RM, Mertens G, Salman M, Cizer Ö, Van Gerven T. 2013 Comparative study of ageing, heat treatment and accelerated carbonation for stabilization of municipal solid waste incineration bottom ash in view of reducing regulated heavy metal/metalloid leaching. *Journal of environmental management*. 128:807-21.
- [38] Leaching Environmental Assessment Framework (LEAF) [Available from: [www.vanderbilt.edu/leaching/leaf/](http://www.vanderbilt.edu/leaching/leaf/)] Accessed 30.11.2018
- [39] Guidelines for the application of special management of scheduled waste. Regulation 7(1), Environmental Quality (Scheduled Waste) Regulation 2005. Department of Environment Malaysia.
- [40] Code of Federal Regulation CFR 40-261.24, EPA Toxicity Characteristics Data. 1987, U.S. Environmental Protection Agency (U.S. EPA), Washington, DC.
- [41] Drinking Water Contaminants. EPA 816-F-09-0004. 2009, U.S. Environmental Protection Agency (U.S. EPA), Washington DC.
- [42] National Environment Agency (NEA), Singapore. NEA leaching test. [Available from: [www.nea.gov.sg/docs/default-source/e-services-forms-docs/licences-permits-building-plan-clearances/leaching-test.pdf](http://www.nea.gov.sg/docs/default-source/e-services-forms-docs/licences-permits-building-plan-clearances/leaching-test.pdf)] Accessed 4.12.2018
- [43] Ministry of Environmental Protection of the People's Republic of China, Beijing (MEP China). 2007. Solid waste-extraction procedure for leaching toxicity
- [44] Environment Protection Authority (EPA), NSW. Waste Classification Guidelines 2009
- [45] Patra S, Whaung ST, Kwan WL. 2017 Analysis of heavy metals in Incineration Bottom Ash in Singapore and potential impact of pre-sorting on ash quality. *Energy Procedia*. 143:454-9.
- [46] Asokbunyarat V, van Hullebusch ED, Lens PN, Annachhatre AP. 2015 Coal bottom ash as sorbing material for Fe (II), Cu (II), Mn (II), and Zn (II) removal from aqueous solutions. *Water, Air, & Soil Pollution*. 226(5):143.
- [47] Fairbrother A, Bigham G, Pietari J, Mohsen F. 2010 Coal ash: hazard, waste, or resources. *News! Expon Environ Eco Sci Pract*. 1:1-11.

- [48] Sushil S, Batra VS. 2006 Analysis of fly ash heavy metal content and disposal in three thermal power plants in India. *Fuel*. 85(17-18):2676-9.
- [49] Phillips JA. 1998 *Managing America's Solid Waste*. Colorado: National Renewable Energy Laboratory. 162 p.
- [50] Dabo D, Badreddine R, De Windt L, Drouadaine I. 2009 Ten-year chemical evolution of leachate and municipal solid waste incineration bottom ash used in a test road site. *Journal of hazardous materials*. 172(2-3):904-13.
- [51] Hjelmar O, Holm J, Crillesen K. 2007 Utilisation of MSWI bottom ash as sub-base in road construction: first results from a large-scale test site. *Journal of hazardous materials*. 139(3):471-80.
- [52] Izquierdo M, Querol X, Josa A, Vazquez E, López-Soler A. 2008 Comparison between laboratory and field leachability of MSWI bottom ash as a road material. *Science of the total environment*. 389(1):10-9.
- [53] Olsson S, Kärman E, Gustafsson JP. 2006 Environmental systems analysis of the use of bottom ash from incineration of municipal waste for road construction. *Resources, conservation and recycling*. 48(1):26-40.
- [54] Bingham P, Hand R. 2006 Vitrification of toxic wastes: a brief review. *Advances in applied ceramics*. 105(1):21-31.
- [55] Rincón A, Marangoni M, Cetin S, Bernardo E. 2016 Recycling of inorganic waste in monolithic and cellular glass- based materials for structural and functional applications. *Journal of Chemical Technology & Biotechnology*. 91(7):1946-61.
- [56] M.H. Abdullah RA, A.S.A. Rashid, N.Z.M. Yunus, editor *Engineering Properties of Tanjung Bin Bottom Ash 2018: MATEC Web of Conference*.

### **Acknowledgment**

The authors also would like to acknowledge the Universiti Teknologi Malaysia (UTM) for financing this research through the Research University Grant Scheme - Consolidation Behavior of Soft Ground Treated with a Group of Bottom Ash Columns - Vote No. Q.J130000.2522.19H75. The cooperation given by all parties involved in this research is greatly acknowledged.