



**Delori, Amit and Urquhart, Andrew J. and Oswald, Iain D. H. (2016)
Supramolecular hair dyes : a new application of cocrystallization.
CrystEngComm. ISSN 1466-8033 , <http://dx.doi.org/10.1039/C6CE01001F>**

This version is available at <https://strathprints.strath.ac.uk/56680/>

Strathprints is designed to allow users to access the research output of the University of Strathclyde. Unless otherwise explicitly stated on the manuscript, Copyright © and Moral Rights for the papers on this site are retained by the individual authors and/or other copyright owners. Please check the manuscript for details of any other licences that may have been applied. You may not engage in further distribution of the material for any profitmaking activities or any commercial gain. You may freely distribute both the url (<https://strathprints.strath.ac.uk/>) and the content of this paper for research or private study, educational, or not-for-profit purposes without prior permission or charge.

Any correspondence concerning this service should be sent to the Strathprints administrator: strathprints@strath.ac.uk

The Strathprints institutional repository (<https://strathprints.strath.ac.uk>) is a digital archive of University of Strathclyde research outputs. It has been developed to disseminate open access research outputs, expose data about those outputs, and enable the management and persistent access to Strathclyde's intellectual output.

Supramolecular Hair Dyes: A New Application of Cocrystallization

Amit Delori,^{[a]*} Andrew J. Urquhart^{[b]*} and Iain D. H. Oswald^{[a]*}Received 00th January 20xx,
Accepted 00th January 20xx


DOI: 10.1039/x0xx00000x

www.rsc.org/

Abstract: The manuscript presents the first report of hair dyes of various colors formed by the cocrystallization reactions. Unlike the most popular oxidative hair dye (OHD) products, these dyes are NH₃ free and do not require H₂O₂ as a color developer. The importance of these new hair dyes products is further enhanced by recent reports which indicate that some of the OHDs may be carcinogenic.

Introduction

OHDs hold a dominant share of the multi-billion dollar hair dye industry (70–80%).¹ These dyes are marketed in their colorless form and the dye molecules are synthesized by the end users via simply mixing the contents of the two tubes provided, widely known as colorant and developer tubes. While the colorant tube contains color components i.e. dye precursor and coupler in a basic media, the developer tube contains H₂O₂. By altering the precursor-coupler combination, hair dyes of different colors can be obtained as shown in **Scheme 1**.²



Scheme 1. Coupling reaction used in OHDs.

OHDs contain some harsh chemicals such as ammonium hydroxide (i.e. NH₄OH) and H₂O₂, which have been further linked with increase in hair porosity,^{3,4} hair loss,^{3,5,6} dermatitis⁵,

and chemical burns.⁷ H₂O₂ and NH₄OH are the constituents of piranha base, which is well known for its corrosive nature especially with regard to organic matter including hairs which are largely proteinaceous.² H₂O₂-NH₄OH combination, present in OHDs, breaks the disulphide bond of the cystine moiety of hair proteins, which compromises the mechanical strength of the hairs.^{4,8} Further concerns about the safety of the OHDs have been raised in the past 20 years due to their potential carcinogenic nature.⁹


Each of the additives have their place, H₂O₂ oxidizes the phenylenediamine to form quinonediimine for reaction with the couplers. NH₄OH creates the basic environment and also lifts the scales of the hairs for the easier penetration of dye molecules before conditioners are used to reverse this effect.^{10,11} Scales may lose their elasticity on repetitive use of OHDs (by a combination of repetitive scale lifting-smoothing cycles and chemical degradation by H₂O₂-NH₄OH mixture) resulting in hairs that are permanently damaged and porous. Porous hairs absorb significantly higher amount of water which accelerates the hair loss due to sheer weight of the absorbed water.^{3,5,12} Further problems arise from this effect where the hairs are prone to moisture loss as well as the loss of the hair dye molecules themselves.¹⁰

Despite the negative attributes of OHDs they hold a dominant share of the hair-dye industry due to the unavailability of equally durable and economical permanent hair dye products. Here we show how crystal engineering can be used to create H₂O₂ and NH₄OH free hair dyes by cocrystallization. Cocrystallization reactions are known for their ease and have been well explored to improve the physical properties such as solubility,^{13,14} phase transition temperatures,¹⁵ melting points,¹⁴ tableting properties,¹⁶ stability,¹⁷ fluorescence,¹⁸ elasticity,¹⁹ color^{18,20,21} etc. In a hunt for molecules which can form colored cocrystals/salts, we chose p-Phenylenediamine (PPD) and N-Phenyl-p-phenylenediamine (NPPPD), as these molecules are already precursors for many OHDs (**Scheme 2**). Though NPPPD itself is colored, the freshly prepared PPD is colorless but oxidizes in air causing a change to a light-pink color.

^a Dr. A. Delori and I.D.H. Oswald
Strathclyde Institute of Pharmacy and Biomedical Sciences, University of Strathclyde, 161 Cathedral Street, Glasgow, G4 0RE, UK. E-mail: amitdelori@gmail.com (AD), iain.oswald@strath.ac.uk (IDHO)

^b Dr. A.J. Urquhart
Technical University of Denmark, Department of Micro- and Nanotechnology, Ørsted's Plads, Building 345Ø, 2800 Kgs. Lyngby, Denmark, anur@nanotech.dtu.dk (AJU)

Supporting information: CIF file (CCDC deposition number CCDC 1435836-1435840), Crystallographic Tables, Experimental Details, PXRD patterns, DSC Spectra, TGA Spectra, IR Spectra



Scheme 2. Chemical structure of reactants used for cocrystallization.

The cocrystallization reactions were initially carried out in 1:1 ratio from methanol and were accompanied by the color changes. The color changes were characterized using UV-visible spectrophotometer, which revealed a bathochromic shift with respect to their respective amines (see **Figure 1**).

To determine whether a chemical or supramolecular reaction had occurred, all the materials were characterized structurally via single crystal X-ray diffraction. They all showed that salt formation had occurred, where the deprotonated cofomer interacted with the amine/ammonium group of protonated amines through $N-H\cdots O$, $N-H\cdots O^-$, $N^+-H\cdots O$, $N^+-H\cdots O^-$ hydrogen bonds, using carboxylic acid/carboxylate/keto/ O^- functionalities (**Figure 2**). The structures revealed that while **PPD-SebA** and **PPD-L** form in 2:1 and 1:2 respectively, reactants of all the other salts preferred to interact in 1:1 (see supplementary information (SI-1) for crystallographic tables). **NPPPD-DGA** exists in 2 forms, both of which were obtained from a cocrystallization reaction in methanol. Form 2 of **NPPPD-DGA** has only been obtained once.




Figure 1. a) Color change and (b) bathochromic shift observed in salts of **PPD** and **NPPPD**.

Using the stoichiometric information from the solution chemistry we have been able to synthesize the salts by a greener liquid-assisted grinding (LAG) route, which makes use of

minimal amount of solvent. Powder diffraction patterns of all the materials obtained by LAG were Pawley-fitted using the unit cell obtained from their respective crystal structures and revealed that we were successful in synthesizing all the three salts of **PPD** and Form 1 of **NPPPD-DGA** (See SI-3).

The colored solutions formed during cocrystallization were investigated for their hair dyeing performance. For this test we chose to dye grey hairs to allow a clear indication of the dyeing potential i.e. failure to dye would be clearly apparent (**Figure 3a**). This was performed by immersing 200mg of grey hairs in 15ml of 6.67 % (w/v) methanolic solutions of the salts before letting the solutions evaporate to dryness. The excess hair dye that adhered to the surface of hair was removed with an excess of hot water (50°C). After dyeing the sample hairs were initially washed for 30 minutes, and later for a more prolonged 24 hours by stirring in 200 ml of hot soapy water (50°C); the latter experiment as an extreme test of color fastness. All the hair dyes worked well and retained their color (**Figure 3b & c**). In these experiments the water was changed 5 and 20 times respectively during 30 minutes and 24 hour washings.



Figure 3. (a) Undyed hairs. (b and c) Dyed hairs after washing for 30 minutes and 24 hours respectively.

Comparison of the SEM images of undyed hairs (**Figure 4a**) with the hairs dyed with supramolecular hair dyes (**SHDs**) revealed no significant change in the surface properties of the hairs after dyeing (**Figure 4 (c-f)**), indicating that these dyes are not harsh on the hair surface.

From an industrial perspective, scalability and ease of processing are very important factors. Considering this in mind, one of the hair dyes (**PPD-SebA**) was chosen for scale up, based upon the cost and availability of the chemicals. The system was scaled up to 275g scale both by LAG and solution methods (**SI-2c** and **2d**). The materials obtained from LAG (pinkish-white) and solution crystallizations (dark bluish-black) differ in color, but PXRD analysis shows that the products of both these methods are the same (**Figure 5**). Such differences in color of the materials obtained by grinding and solution crystallizations have been reported by some other groups too.^{20, 22} These color differences indicate that solvent plays an important role in color generation probably via affecting the extent of crystallization and crystal size.




Figure 4. (a) Surface of a hair sample before dyeing showing the scales. (b) measurement of the thickness of scales on the hair samples and pore size. Hairs dyed with (c) PPD- SebA (d) PPD- TMA (e) PPD-L and (f) Form 1 of NPPD-DGA.




Figure 5. Comparison of the PXRD patterns of PPD-SebA salts obtained from (a) LAG and (b) solution crystallization with (c) its PXRD pattern simulated from its crystal structure.

After bulk preparation, we attempted to formulate the PPD-SebA salt into a formulation that could be applied to hairs directly on potential customers. For this purpose, 4ml of a concentrated solution of PPD-SebA in methanol (SI-2e) was diluted with the addition of 2 ml of water to form a solution. To this 6g of solid PPD-SebA (obtained from solution crystallization from methanol (SI-2d)) was added to form a paste. During the paste formation the mixture was kneaded to break up the solid that had agglomerated (Figure 6a). This paste was used to dye the wet grey hairs (soaked in water for 2 minutes

to swell the hair) for 30 minutes. The excess hair dye, which was adhering to the surface of the hairs, was easily recovered by rubbing the hairs between the finger tips. Interestingly, even this simple formulation dyed the hairs reasonably well (Figure 6c). The dyed hairs were tested for their dyeing performance by washing them 25 times with soapy water and found to retain the color (Figure 6d). To investigate the reusability of this SHD for dyeing, 3g of the recovered material was again converted to a paste by adding 1ml of water and 2 ml of concentrated solution of PPD-SebA. Dyeing was done for 30 minutes, which was followed by 25 washings with soapy water. The dyeing performance of the recovered material was same as that of dye used for the first time. It is noteworthy to mention that OHDs are not reusable and any hair dye left after use is simply discarded.



Figure 6. (a) Strong color observed during PPD-SebA paste formation. (b) Undyed hairs (c) Hairs dyed with paste formulation after (c) first washing (d) twenty fifth washing.

Diffusion of the dye molecules into hairs is an important parameter and is directly related to the dyeing times. The relative dimensions of dye molecules and pores of the hairs dictate this diffusion process.¹⁰ While the dimension of the molecules is a fixed quantity, pore size can be increased to a great extent by a phenomenon known as swelling.²³ Swelling is induced by the addition of chemical additives (such as solvents, amines, organic and inorganic acids, salts, urea, formamide etc.),^{5, 10, 24} which can disrupt the hydrogen bonding present in hairs. In OHDs, NH₄OH is added to swell the hairs. NH₄OH also serve to generate the basic environment which is required for the proper functioning of OHDs.² The swelling action of amines increases with the increase of pH however the decomposition of keratin also takes place at high pH, so the ideal environment for OHDs is to operate between pH range 9-10.² In our paste formulation we used water which is a well-known swelling agent.²³ Water increases the pore size by couple of hundred of nanometers in little as 5 minutes.^{23, 25} Before applying the paste formulation to hairs, they were submerged in water for 2 minutes to induce swelling and hence increase the rate of dye intake. Since the dimensions of the molecules used for our study were only few angstrom in size (<15 Å) we expected the dyeing process to be rapid which is what we observed.

Hair dye performance is determined by the binding forces between hairs and dye. The dye molecules primarily bind the hairs using hydrogen bonds.^{2, 26} Hair dye companies aim at increasing the strength of these hydrogen bonds for better product performance. The SHDs presented in this paper are ionic and hence have the potential to form stronger charge assisted

hydrogen bonds with the hairs in comparison to the neutral molecules formed via the oxidative reaction.

One of the prime requirements of the hair dye industry is to produce a range of colors. **OHD** industries rely on changing the dye precursor-coupler combination to achieve the same. The precursors and couplers are chosen in such a way that they can form the more conjugated colored end product. Unfortunately, **OHD** industry is limited in terms of the number of approved safe molecules (around 100) which they can use as dye precursors and couplers.^{2,27} **SHDs** appear to have an edge over **OHDs** in terms of the number of safe molecules (thousands of safe cofomers for **SHD** can be chosen from EAFUS²⁸ and GRAS²⁹ lists), but also a major drawback in terms of control of outcome of cocrystallization reaction.

Conclusion: A technological breakthrough has been achieved in synthesizing the H₂O₂ and NH₃ free hair dyes by using a cocrystallization based hair dye technology. The dyeing performance of the hairs dyes presented in this paper is comparable to the permanent hair dyes which last for more than 24 washings. SEM analysis revealed that the application of these hair dyes did not appear to have a detrimental effect on the hairs themselves. The scalability of these hair dyes was demonstrated by taking a representative example, in which **PPD-SebA** salt was scaled up to a 275g scale and used to dye hair samples with relative ease.

Acknowledgements: The authors would like to thank The Leverhulme Trust for funding (grant code number RPG-2012-598). Late Shri Gurdip Chand Rishi, Nan Dickson, Gillian Fleming, Stephen MacDonough and Simon MacPartland are acknowledged for their help in providing the hair samples. We would also like to acknowledge the Strathclyde Institute of Pharmacy and Biomedical Sciences for the provision of funds for the microsource.

Keywords: Cocrystallization, colored salts • supramolecular hair dye • permanent hair dye • supramolecular chemistry • H₂O₂-NH₄OH free hair dye

- H. S. Freeman and A. T. Peters, *Colorants for Non-Textile Applications*, Elsevier, 2000.
- O. J. X. Morel and R. M. Christie, *Chemical Reviews*, 2011, **111**, 2537-2561.
- A. Guerra-Tapia and E. Gonzalez-Guerra, *Actas Dermo-Sifiliográficas (English Edition)*, 2014, **105**, 833-839.
- L. J. Wolfram, K. Hall and I. Hui, *Journal of cosmetic science*, 1970, **21**, 875-900.
- J.-A. Seo, I.-H. Bae, W.-H. Jang, J.-H. Kim, S.-Y. Bak, S.-H. Han, Y.-H. Park and K.-M. Lim, *Journal of Dermatological Science*, 2012, **66**, 12-19.
- J. A. Swift, *International Journal of Cosmetic Science*, 1999, **21**, 227-239.
- C. E. Orfanos and E. Imcke, in *Hair and Hair Diseases*, eds. C. Orfanos and R. Happle, Springer Berlin Heidelberg, 1990, pp. 887-925; W. F. Bergfeld, in *Hair Research*, eds. C. Orfanos, W. Montagna and G. Stüttgen, Springer Berlin Heidelberg, 1981, pp. 507-512.
- A. N. Parbhu, W. G. Bryson and R. Lal, *Biochemistry*, 1999, **38**, 11755-11761; V. N. E. Robinson, *Journal of cosmetic science*, 1976, **27**, 155-161.
- M. Gago-Dominguez, J. Esteban Castelao, J. M. Yuan, M. C. Yu and R. K. Ross, *International Journal of Cancer*, 2001, **91**, 575-579; W. Rojanapo, P. Kupradinun, A. Tepsuwan, S. Chutimataewin and M. Tanyakaset, *Carcinogenesis*, 1986, **7**, 1997-2002; http://ec.europa.eu/health/scientific_committees/consumer_safety/docs/sccs_o_094.pdf Accessed 25th April, 2016; C. La Vecchia and A. Tavani, *Eur.J. Cancer Prev.*, 1995, **4**, 31-43.
- C. R. Robbins, *Chemical and physical behavior of human hair*, 2002.
- C. R. Robbins, Fernee, K. M., *Journal of cosmetic science*, 1983, **34**, 21-34.
- Y. K. Kamath and H. D. Weigmann, *J APPL POLYM SCI*, 1982, **V 27**, 3809-3833.
- R. Thakuria, A. Delori, W. Jones, M. P. Lipert, L. Roy and N. Rodríguez-Hornedo, *Int. J. Pharm.*, 2013, **453**, 101-125; N. J. Babu and A. Nangia, *Cryst. Growth Des.*, 2011, **11**, 2662-2679; M. L. Cheney, N. Shan, E. R. Healey, M. Hanna, L. Wojtas, M. J. Zaworotko, V. Sava, S. J. Song and J. R. Sanchez-Ramos, *Cryst. Growth Des.*, 2010, **10**, 394-405.
- C. B. Aakeröy, S. Forbes and J. Desper, *J. Am. Chem. Soc.*, 2009, **131**, 17048-17049.
- A. Delori, P. Maclure, R. M. Bhardwaj, A. Johnston, A. J. Florence, O. B. Sutcliffe and I. D. H. Oswald, *CrystEngComm*, 2014, **16**, 5827-5831.
- S. Karki, T. Friščić, L. Fábíán, P. R. Laity, G. M. Day and W. Jones, *Advanced Materials (Weinheim, Germany)*, 2009, **21**, 3905-3909.
- A. V. Trask, W. D. S. Motherwell and W. Jones, *Cryst. Growth Des.*, 2005, **5**, 1013-1021.
- D. Yan, A. Delori, G. O. Lloyd, T. Friščić, G. M. Day, W. Jones, J. Lu, M. Wei, D. G. Evans and X. Duan, *Angew. Chem., Int. Ed.*, 2011, **50**, 12483-12486.
- S. Ghosh and C. M. Reddy, *Angew. Chem., Int. Ed.*, 2012, **51**, 10319-10323.
- D.-K. Bucar, S. Filip, M. Arhangelskis, G. O. Lloyd and W. Jones, *CrystEngComm*, 2013, **15**, 6289-6291.
- C. L. Jones, C. C. Wilson and L. H. Thomas, *CrystEngComm*, 2014, **16**, 5849-5858; A. R. Pallipurath, J. M. Skelton, a. delori, C. Duffy, A. Erxleben and W. Jones, *CrystEngComm*, 2015, **17**, 7684-7692.
- G. E. Christidis, P. Makri and V. Perdikatsis, *Clay Minerals*, 2004, **39**, 163-175.
- R. Dawber, *Clinics in Dermatology*, 1996, **14**, 105-112.
- E. I. Valko, *Journal of cosmetic science*, 1952, **3**, 108-117.
- S. D. O'Connor, K. L. Komisarek and J. D. Baldeschwieler, *Journal of Investigative Dermatology*, 1995, **105**, 96-99.
- T. Clausen, A. Schwan-Jonczyk, G. Lang, W. Schuh, K. D. Liebscher, C. Springob, M. Franzke, W. Balzer, S. Imhof, G. Maresch and R. Bimczok, in *Ullmann's Encyclopedia of Industrial Chemistry*, Wiley-VCH Verlag GmbH & Co. KGaA, 2000.
- http://ec.europa.eu/health/ph_risk/committees/04_sccp/docs/sccp_o_067.pdf Accessed 25th April 2016.

28 Everything added to food in the United States (EUFAS) list of chemicals published by the US-FDA. , <http://www.accessdata.fda.gov/scripts/fcn/fcnNavigation.cfm?rpt=eafusListing&displayAll=true>, Accessed 25th April, 2016.

29 Lists of chemicals generally recognized as safe (GRAS) by US-FDA

<http://www.fda.gov/Food/IngredientsPackagingLabeling/GRAS/SCOGS/default.htm>, Accessed 25th April, , 2016.

30