



UNIVERSITI PUTRA MALAYSIA

**EFFECT OF DOPANTS AND MECHANOCHEMICAL TREATMENT
ON VANADIUM PHOSPHATE CATALYSTS
FOR PARTIAL OXIDATION OF *n*-BUTANE TO MALEIC ANHYDRIDE**

NOR ASRINA BINTI SAIRI

FS 2007 21

**EFFECT OF DOPANTS AND MECHANOCHEMICAL TREATMENT
ON VANADIUM PHOSPHATE CATALYSTS
FOR PARTIAL OXIDATION OF *n*-BUTANE TO MALEIC ANHYDRIDE**

By

NOR ASRINA BINTI SAIRI

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia
in Fulfilment of the Requirements for the Degree of Master of Science**

June 2007



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Master of Science

**EFFECT OF DOPANTS AND MECHANOCHEMICAL TREATMENT
ON VANADIUM PHOSPHATE CATALYSTS
FOR PARTIAL OXIDATION OF *n*-BUTANE TO MALEIC ANHYDRIDE**

By

NOR ASRINA BINTI SAIRI

June 2007

Chairman : Associate Professor Dr. Taufiq Yap Yun Hin, PhD

Faculty : Science

Oxidation of *n*-butane to maleic anhydride catalyzed by vanadium phosphate catalyst is one of significant worldwide commercial interest since decades. Introductions of dopants and/or mechanochemical treatment are the most promising approach for the improvement of the catalytic performance of vanadium phosphate catalyst. Tellurium doped vanadium phosphate catalyst (VPDTe) was prepared via $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$ phase after calcinating the tellurium doped precursor, $\text{VOHPO}_4 \cdot 0.5\text{H}_2\text{O}$ at 733 K in a flowing of *n*-butane/air for 18 h. VPDTe catalyst gave very high for *n*-butane conversion, 80% compared to only 47% for the undoped catalyst. The crystallite size, morphology, surface reactivity and reducibility of the catalyst have been affected by the addition of tellurium.

VPDTe catalyst has result a higher existence of V^{5+} phase in the catalyst bulk with having nearly the optimum amount of $\text{V}^{5+}/\text{V}^{4+}$ ratio, 0.23. The SEM micrographs showed that the tellurium altered the arrangement of the platelets from “rose-like” clusters to layer with irregular shape. The sizes of platelets are even thicker and



bigger which led to lower surface area compared to undoped VPD catalyst. An addition of 1% tellurium has markedly lowered the reduction activation energies of the vanadium phosphate catalyst as revealed by TPR profiles. The amount of oxygen species removed from the peak associated with V^{4+} phase for VPDTe catalyst significantly higher. These phenomenon suggested that the O=V bond of the VPDTe catalyst are weaker with higher mobility and more reactive of the oxygen as compared to the undoped counter part.

All mechanochemical treated VPD catalysts have shown an increased surface P/V ratio, reduced the crystallite size of the catalysts and displayed different degree of crystallinity. TPR results demonstrated that both reduction peaks for every mechanochemical treated catalyst shifted to lower temperature and improved the amount of oxygen removed from the catalysts. VPDM catalyst gave 57% of conversion, 10% higher from the untreated VPD catalyst. The presence of cobalt in mechanochemical treated vanadium phosphate catalyst has slightly lowered the *n*-butane conversion to 54%. Meanwhile, treating the tellurium doped catalyst through mechanochemical treatment *i.e.* milling in stainless steel (VPDTeM) or agate (VPDTeM-ag) with ethanol as solvent has reduced the conversion from 80% to 58% and 50%, respectively. The selectivity of all catalysts prepared was almost retained in all cases (~ 33%) except for VPDCoM catalyst (19%).



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Sarjana Sains

**KESAN DOPAN DAN RAWATAN KIMIA-MEKANIKAL TERHADAP
MANGKIN VANADIUM FOSFORUS OKSIDA UNTUK PENGOKSIDAAN
SEPARA *n*-BUTANA KEPADA MALIK ANHIDRIDA**

Oleh

NOR ASRINA BINTI SAIRI

Jun 2007

Pengerusi: Profesor Madya Dr. Taufiq Yap Yun Hin, PhD

Fakulti: Sains

Pengoksidaan *n*-butana kepada malik anhidrida oleh vanadium fosfat merupakan salah satu antara cabang tindak balas komersial yang diberi perhatian di seluruh dunia. Penambahan pelbagai dopan dan/atau rawatan kimia-mekanikal adalah pendekatan yang biasanya dilihat akan meningkatkan kadar prestasi pemangkinan bagi mangkin vanadium fosfat. Mangkin yang ditambah dengan tellurium ini disintesis melalui fasa $\text{VOPO}_4 \cdot 2\text{H}_2\text{O}$ setelah prekursor yang telah ditambah dengan tellurium, $\text{VOHPO}_4 \cdot 0.5\text{H}_2\text{O}$ diaktifkan pada 733 K dalam aliran *n*-butana/udara selama 18 jam. Mangkin VPDTe memberikan kadar penukaran *n*-butana 80% berbanding hanya 47% bagi mangkin yang tidak ditambah dengan tellurium. Saiz kristal, morfologi, kereaktifan permukaan and ciri penurunan mangkin tersebut dipengaruhi oleh penambahan tellurium.

Mangkin VPDTe menunjukkan kewujudan fasa V^{5+} yang lebih tinggi dengan hampir mencapai nisbah optimum $\text{V}^{5+}/\text{V}^{4+}$, 0.23. Mikrograf-mikrograf SEM menunjukkan tellurium telah mengubah susunan platlet-platlet dari gugusan seperti ros kepada lapisan dengan bentuk tidak tetap. Saiz platlet-platlet juga semakin tebal and besar

yang mana telah membawa kepada penurunan luas permukaan jika dibandingkan dengan mangkin VPD yang tidak ditambah dengan tellurium. Penambahan 1% tellurium telah menyebabkan penurunan ketara terhadap tenaga pengaktifan penurunan bagi mangkin vanadium fosfat seperti yang dinyatakan melalui profil TPR. Jumlah spesis oksigen yang disingkirkan dari puncak yang mewakili fasa V^{4+} bagi mangkin VPDTe adalah jauh lebih tinggi. Fenomena ini mencadangkan ikatan O=V bagi mangkin VPDTe adalah lebih lemah dengan pergerakan oksigen untuk mengaktifkan butana adalah lebih tinggi dan lebih reaktif berbanding mangkin yang tidak ditambah tellurium.

Semua mangkin VPD yang dirawat dengan kimia-mekanikal telah menunjukkan peningkatan nisbah permukaan P/V, penurunan saiz kristal dan kepelbagaian darjah penghabluran. Keputusan TPR menunjukkan kedua-dua puncak penurunan bagi setiap mangkin yang dirawat dengan kimia-mekanikal bergerak ke arah suhu yang lebih rendah dengan jumlah oksigen yang disingkirkan dari mangkin turut meningkat. Mangkin VPDM menunjukkan kadar penukaran *n*-butana 57% iaitu 10% lebih tinggi berbanding mangkin VPD yang tidak ditambah dengan tellurium. Kehadiran kobalt dalam mangkin yang dirawat dengan kimia-mekanikal telah mengakibatkan sedikit penurunan kadar penukaran *n*-butana kepada 54%. Dalam pada itu, rawatan kimia-mekanikal yang dilakukan terhadap mangkin yang ditambah dengan tellurium sama ada di dalam peralatan besi tahan karat atau silika dengan etanol sebagai pelarut telah menyebabkan kadar penukaran butana menurun dari 80% kepada 58% dan 50%. Kadar pemilihan bagi malik anhidrida kesemua mangkin

hampir dikekalkan pada kadar yang sama (~ 33%) bagi semua kes kecuali bagi mangkin VPDCoM (19%).

ACKNOWLEDGEMENTS

In the name of Allah S.W.T., The Compassionate and The Merciful. My utmost gratitude is to Allah S.W.T. for his blessings before, during and after then whole writing process. Alhamdulillah.

First of all, I would like to express my sincere and deepest appreciation to my supervisor; Assoc. Professor Dr. Taufiq Yap Yun Hin and co-supervisor Professor Dr. Mohd Zobir bin Hussein for their dedicated supervision, invaluable guidance, unfailing help and superb tolerance throughout the course of this work.

Special appreciations are also due to all lecturers, laboratory assistants in Department of Chemistry and Institute of Bioscience for their help and advice.

Heartfelt thanks are extended to laboratory mates, Mr. Tang Wen Jiunn, Miss Woi Pei Meng, Miss Siti Murni, Mrs. Sharmila, Miss Tan Yee Wean, Mr. Ali Asghar Rownaghi and the only science officer, Mrs. Zaidina for their favourable help, suggestions, encouragement and companion in sustaining the morale and enthusiasm. Not forgetting to other graduate students, friends and all those who had contributed to the success of this works in one way or another.

Finally, I would like to express my deepest gratitude to my beloved family who has always believes in me, and endured with me during difficult times. Without their unconditional and endless love, it would not have been possible for me to complete this Master of Science thesis.



I certify that an Examination Committee met on 5th June 2007 to conduct the final examination of Nor Asrina binti Sairi on her Master of Science thesis entitled “Effect of Dopants and Mechanochemical Treatment on Vanadium Phosphate Catalysts for Partial Oxidation of *n*-Butane to Maleic Anhydride” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination are as follows:

Asmah Haji Yahaya, Ph.D.

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairperson)

Anuar Kassim, Ph.D.

Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

Imad (Moh’D Khair) Rashid Hamadneh, Ph.D.

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

Mohd Ambar Yarmo, Ph.D.

Professor
Faculty of Science and Technology
Universiti Kebangsaan Malaysia
(Independent Examiner)

HASANAH MOHD GHAZALI, PhD

Professor/Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 21st JUNE 2007



This thesis submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirements for the degree of Master of Science. The members of Supervisory Committee are as follows:

Taufiq Yap Yun Hin, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Mohd Zobir Hussein, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

AINI IDERIS, Ph.D.
Professor/Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 17th JULY 2007



DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations, which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.

NOR ASRINA BINTI SAIRI

Date: 5th JUNE 2007

TABLE OF CONTENTS

	Page
ABSTRACT	ii
ABSTRAK	iv
ACKNOWLEDGEMENTS	iv
APPROVAL SHEETS	vii
DECLARATION FORM	ix
TABLE OF CONTENTS	x
LIST OF TABLES	xiv
LIST OF FIGURES	xvi
LIST OF ABBREVIATIONS	xix
CHAPTER	
1 INTRODUCTION	
1.1 An Outlook in Catalytic Oxidation Process	1
1.2 General Requirements of the Catalysts for Industrial Processes	3
1.3 Catalytic Selective Oxidation Process	4
1.4 Functionality of Alkane in Selective Oxidation	5
1.5 Industrial Process of Maleic Anhydride Synthesis	9
1.5.1 Oxidation of Benzene to Maleic Anhydride	9
1.5.2 Oxidation of <i>n</i> -Butane to Maleic Anhydride	10
1.6 Maleic Anhydride	12
1.6.1 Exploitation of Maleic Anhydride for Its Derivatives	13
1.6.2 Commercial Analysis of Maleic Anhydride	16
1.7 Objectives of the Study	17
1.8 Significant of the Study	17
1.9 Scope of the Study	19
2 LITERATURE REVIEW	
2.1 Vanadium Phosphate Catalyst	20
2.2 Structural Aspect of Vanadium Phosphate Catalyst	20
2.3 Valence State of Vanadium	24
2.4 Preparation of Vanadium Phosphate Catalyst	28
2.4.1 Different Routes in Preparation of Catalyst Precursors	30
2.4.2 Comparison of the Different Routes	34
2.5 On Topotactic Transformation of the Precursor	36
2.6 Activation Procedure	38
2.7 Role of Phosphorus/Vanadium Procedure	43
2.8 Reaction Mechanism at Vanadium Phosphate Catalyst Surface	45
2.9 Role of Lattice Oxygen Species	51
2.10 Physical and Chemical Modification of Vanadium Phosphate Catalyst	53
2.10.1 Role of Dopant/Promoter	55
2.10.2 Mechanochemical Treatment	55



3	CATALYSTS SYNTHESIS AND CHARACTERIZATIONS	
3.1	Materials and Gases	64
3.2	Preparation of the Precursor, VOHPO ₄ ·0.5H ₂ O via VOPO ₄ ·2H ₂ O Phase	65
3.2.1	Preparation of the Undoped VOHPO ₄ ·0.5H ₂ O	65
3.2.2	Preparation of the Cobalt- and Tellurium- Doped VOHPO ₄ ·0.5H ₂ O	66
3.3	Mechanochemical Treatment	66
3.4	Activation of the Precursors	67
3.5	Catalysts Characterization	67
3.5.1	Elemental Analysis	68
3.5.2	Redox Titration Method	69
3.5.3	BET Surface Area	70
3.5.4	X-ray Diffraction (XRD)	71
3.5.5	Scanning Electron Microscopy (SEM)	72
3.5.6	Temperature Programmed Reduction (TPR)	73
3.6	Catalytic Test	73
4	EFFECT OF TELLURIUM DOPANT TO VANADIUM PHOSPHATE CATALYST FOR PARTIAL OXIDATION OF <i>n</i>-BUTANE TO MALEIC ANHYDRIDE	
4.1	Introduction	75
4.2	Chemical Analysis	77
4.3	Redox Titration Method	78
4.4	BET Surface Area	80
4.5	Phases Identification and Crystallite Size	81
4.6	Surface Morphology	86
4.7	Temperature Programmed Reduction	88
4.8	Catalytic Evaluation	91
5	EFFECT OF MECHANOCHEMICAL TREATMENT TO VANADIUM PHOSPHATE CATALYSTS FOR PARTIAL OXIDATION OF <i>n</i>-BUTANE TO MALEIC ANHYDRIDE	
5.1	Introduction	96
5.2	Chemical Analysis	97
5.3	Redox Titration Method	99
5.4	BET Surface Area	102
5.5	Phases Identification and Crystallite Size	104
5.6	Surface Morphology	112
5.7	Temperature Programmed Reduction	117
5.8	Catalytic Evaluation	123
6	SUMMARY AND CONCLUDING REMARKS	131



REFERENCES	133
APPENDICES	143
BIODATA OF THE AUTHOR	146
LIST OF THE SEMINAR/ CONFERENCE/ WORKSHOP ATTENDED	147
PAPER PUBLISHED IN PROCEEDING OF CONFERENCES, SEMINARS, AND WORKSHOPS	149



LIST OF TABLES

Table		Page
1.1	Oxidation catalysis in industry	2
1.2	Industrial processes and processes under study or development for The oxidative transformation of light alkanes (C ₁ -C ₅)	8
2.1	<i>n</i> -Butane conversion to maleic anhydride for VPA, VPO, VPD and VPH catalysts	37
2.2	Main steps in the mechanism of <i>n</i> -butane oxidation	52
4.1	The atomic ratios for the composition of the VPD and VPDTe catalysts	78
4.2	Average vanadium valence and percentages of V ⁴⁺ and V ⁵⁺ oxidation state present in vanadyl pyrophosphate catalysts after a series of reaction with fresh catalysts	80
4.3	XRD data for VPD and VPDTe catalysts	87
4.4	Amount of oxygen removed and reduction activation energies obtained by temperature programmed reduction of H ₂ with VPD and VPDTe catalysts	92
4.5	The catalytic performance of undoped catalyst, VPD and tellurium doped catalyst, VPDTe in <i>n</i> -butane oxidation to maleic anhydride	94
5.1	The phosphorus/vanadium atomic ratios for the composition of the VPD, VPDM, VPDCoM, VPDTe, VPDTeM and VPDTeM-ag catalysts	100
5.2	Average vanadium valence and percentages of V ⁴⁺ and V ⁵⁺ oxidation states present in VPD, VPDM, VPDCoM, VPDTe, VPDTeM and VPDTeM-ag catalysts	102
5.3	BET data for VPD, VPDM, VPDCoM, VPDTe, VPDTeM and VPDTeM-ag catalysts	104
5.4	XRD data for VPD, VPDM, VPDCoM, VPDTe, VPDTeM and VPDTeM-ag catalysts	111
5.5	Amount of oxygen removed and reduction activation energies	121



obtained by temperature programmed reduction in H₂ with VPD, VPDM, VPDCoM, VPDTe, VPDTeM and VPDTeM-ag catalysts

- 5.6 The catalytic performances of VPD, VPDM, VPDCoM, VPDTe, VPDTeM and VPDTeM-ag catalyst in *n*-butane oxidation to maleic anhydride 125



LIST OF FIGURES

Figure		Page
1.1	Structure of maleic anhydride	12
1.2	Maleic anhydride derivative tree	14
1.3	Global maleic anhydride demand by region, 2004	16
2.1 (a)	The layered structure of $(VO)_2P_2O_7$ (3 dimensional)	23
2.1 (b)	The layered structure of $(VO)_2P_2O_7$ (2 dimensional)	23
2.2	Idealized vanadyl pyrophosphate structure (only vanadyl groups) in (020) plane	24
2.3	Catalytic oxidation of <i>n</i> -butane on the surface of plate-like $(VO)_2P_2O_7$ crystal. Selective oxidation to maleic anhydride takes place on the (020) basal plane and deep oxidation on the side planes	25
2.4	Selective and unselective oxidation site on crystal faces of $(VO)_2P_2O_7$	25
2.5	<i>n</i> -Butane conversion as a function of amount of oxygen removed associated with V^{5+}	27
2.6	Maleic anhydride selectivity as a function of amount of oxygen removed associated with V^{5+}	28
2.7	<i>n</i> -Butane conversion as a function of amount of oxygen removed associated with V^{4+}	29
2.8	<i>n</i> -Butane conversion as a function of V^{4+}	29
2.9	Diagram of phase transformations among vanadium phosphate catalysts and precursors	39
2.10	Transformation of precursor to the active phase	42
2.11	Scheme of proposed evolution of the vanadium phosphate catalyst with activation time (1) oxydehydration; (2) topotactic transformation; (3, 5) reduction V^{5+} to V^{4+} ; and (4) isovalence transformation	43



2.12	Mechanism of <i>n</i> -butane oxidation on vanadium phosphorus oxide catalysts mechanism of <i>n</i> -butane oxidation on vanadium phosphorus oxide catalysts	49
2.13	Theory for the catalytic oxidation of hydrocarbons on metal oxide catalysts	50
2.14	Consecutive alkenyl mechanism	51
2.15	Schematic of an oxygen sublattice of a reducible metal oxide having face-centered cubic arrangement of oxygen being reduced by butane	56
2.16 (a)	Selectivity to maleic anhydride (S_{MA}) versus V^{5+}/V^{4+} ratio (from LRS)	61
2.16 (b)	Selectivity to maleic anhydride (S_{MA}) versus V^{5+}/V^{4+} ratio (from XPS)	61
3.1	Scheme of fixed-bed laboratory micro reactor for catalyst testing	76
4.1	XRD patterns for PVPD and PVPDTe, precursor of the catalysts	84
4.2	XRD patterns for VPD and VPDTe catalysts	85
4.3 (a)	SEM micrograph of VPD catalyst	89
4.3 (b)	SEM micrograph of VPDTe catalyst	89
4.4	TPR profiles for VPD and VPDTe catalysts	91
4.5	Changes of <i>n</i> -butane conversion and maleic anhydride selectivity with the addition of tellurium dopant to the vanadium phosphate catalyst	94
5.1	XRD patterns for PVPD, PVPDM, PVPDCoM, PVPDTe, PVPDTeM and PVPDTeM-ag precursors of the catalysts	107
5.2	XRD patterns for VPD, VPDM, VPDCoM, VPDTe, VPDTeM and VPDTeM-ag catalysts	109
5.3	Effect of mechanochemical treatment to crystallite sizes at (020) and (204) planes of the catalysts	113
5.4 (a)	SEM micrograph of VPD catalyst	115
5.4 (b)	SEM micrograph of VPDM catalyst	115



5.4 (c)	SEM micrograph of VPDCoM catalyst	117
5.4 (d)	SEM micrograph of VPDTe catalyst	117
5.4 (e)	SEM micrograph of VPDTeM catalyst	118
5.4 (f)	SEM micrograph of VPDTeM-ag catalyst	118
5.5	TPR profiles for VPD, VPDM, VPDCoM, VPDTe, VPDTeM and VPDTeM-ag catalysts	120
5.6	Changes of <i>n</i> -butane conversion with the effect of mechanochemical treatment in the presence of different dopants	126
5.7	Effect of mechanochemical treatment to undoped, cobalt- and tellurium- doped vanadium phosphate catalysts towards <i>n</i> -butane conversion and its relationship to BET surface area value of the catalysts	128
5.8	<i>n</i> -Butane conversion as a function of amount of oxygen removed associated with V ⁴⁺ .	129
5.9	Influence of the amount of oxygen atoms removed from the reduction peak (TPR) associated with V ⁵⁺ phase on the <i>n</i> -butane conversion of the catalysts	131
5.10	Maleic anhydride selectivity as a function of amount of oxygen removed associated with V ⁵⁺	132



LIST OF ABBREVIATIONS

BET	Brunauer-Emmer-Teller
EPA	Environmental Protection Energy
FWHM	Full Width of Half Maximum
GHSV	Gas Hourly Space Velocity
ICP-AES	Inductive Couple Plasma – Atomic Emission Spectroscopy
JCPDS	Joint Committee on Powder Diffraction Standards
JEOL	Japan Electron Optics Laboratory
LRS	Low Resolution Spectroscopy
OSHA	Occupational Safety and Health Organization
PTMEG	Polytetramethylene Ether Glycol
SEM	Scanning Electron Microscopy
T _{max}	Temperature at Peak Maximum
TCD	Thermal Conductivity Detector
TPD/R/O	Temperature Programmed Desorption/Reduction/Oxidation
TPR	Temperature Programmed Reduction
VPA	Aqueous Method
VPD	Dihydride Method
VPH	Hydrothermal Method
VPO	Organic Method
XPS	X-ray Photoelectron



XRD

X-ray Diffraction



CHAPTER 1

INTRODUCTION

1.1 An Outlook in Catalytic Oxidation Process

Oxidation reaction has vastly contributed to the science of catalysis and also to the development of modern society (Taufiq-Yap, 1997). More than 60% of the chemicals and intermediates synthesized via catalytic processes are products of oxidation. Today, catalytic oxidation is the basis for the synthesis of a large percentage of the monomers or modifier used for the production of synthetic fibers and plastics and include large volume products such as ethylene oxides, acrylonitrile, vinyl chloride, maleic and phthalic anhydride (Centi *et al.*, 2000).

In organic chemistry and technology, oxidation processes are defined as conversions of compounds under the influence of various oxidizing agent. A distinction is made between complete and partial oxidation. Complete oxidation is an undesirable side process in organic synthesis which leads to the formation of CO, CO₂ and H₂O. It is partial oxidation which is important. This reaction leads to a special product in which the rate of production of the desired product is being formed over others (Taufiq-Yap, 1997).



Partial oxidation processes using air or oxygen are used to manufacture a variety of chemicals, and complete catalytic oxidation is a practicable method for elimination of organic pollutants in gaseous streams. In the manufacture of chemicals, oxygen may be incorporated into the final products, as in the oxidation propylene to acrolein or *o*-xylene to phthalic anhydride: or the reaction may be an oxidative dehydrogenation in which oxygen does not appear in the desired product, as in the conversion of butene to butadiene. The desired reaction may or may not involve C-C bond scission (Taufiq-Yap, 1997). The role of oxidation catalysis in industry in which examples are given of its application in different branches of industry is illustrated in Table 1.1.

Table 1.1: Oxidation catalysis in industry (Taufiq-Yap, 1997).

Industrial	Catalyst(s)
1. Inorganic Industry	
Nitric acid oxidation of ammonia	Pt, Rh
Sulphuric acid by oxidation of SO ₂	V ₂ O ₅
2. Synthetic Rubber	
Butadiene by oxydehydrogenation of C ₄	(Co, Ni) ₃ (PO ₄) ₂
Styrene by oxydehydrogenation of ethylbenzene	Fe ₂ O ₃
3. Plastics	
Formaldehyde by oxidation of methanol	Fe ₂ (MoO ₄) ₃
Phthalic anhydride from <i>o</i> -xylene	V ₂ O ₅ /TiO ₂
4. Synthetic Fibers	
Ethylene oxide	Ag/Al ₂ O ₃
Acrylonitrile by ammoxidation of propene	Bi ₂ (MoO ₄) ₃
Maleic anhydride from C ₄	(VO) ₂ P ₂ O ₇
5. Pollution Control and Environmental Protection	
Catalytic car mufflers	Pt/Al ₂ O ₃
Combustion of hydrocarbons in flue gases	CuCo ₂ O ₄

Although rough estimates place the worth of the world products that have undergone a catalytic oxidation step at \$ 20 to \$ 40 billion, there are some important limitations in catalytic oxidation, which can be summarized as follows (Centi *et al.*, 2000):

- i) Because of the formation of undesired by-products, none of the reactions runs at maximum selectivity, and few reactions attain total or close-to-total conversion
- ii) Processes can generate co-products that are not always of economic interest
- iii) Some raw materials and products are suspected or proven carcinogens
- iv) Some processes require expensive oxidizing agents.

1.2 General Requirements of the Catalysts for Industrial Processes

The criteria for industrially successful catalysts are very stringent. First, the catalyst must be able to affect the desired reaction at an acceptable rate under conditions of temperature and pressure that are practicable (Taufiq-Yap, 1997). Chemical technology has advanced to the point where temperatures as high as 1600 K and pressure up to 350 atm. If however good yields can be obtained at low temperatures and pressures, then there is every incentive to find a catalyst that will operate under the mildest possible conditions, since the use of extreme conditions is very costly. It is concurrently



important that side-reactions are minimal, especially those leading to poisoning or deactivation through carbon deposition on catalyst.

Second, the catalyst must be able to sustain the desired reaction over prolonged periods: in some processes, a catalyst life of several years is not uncommon, and is economically necessary. Clearly the longer it lasts, the smaller will be the contribution that its initial cost makes to the overall cost of the process. Initial cost is rarely of over-riding importance: it is usually cheaper in the long run to use an expensive catalyst that will last a long time than a cheap one that has to be replaced frequently.

1.3 Catalytic Selective Oxidation Process

A large segment of the modern chemical industry is based on catalytic selective oxidation processes. Therefore, research in the area of selective oxidation is rapidly changing. In fact, the economic potential of any improvements in this area is enormous. It may be recalled, for example, that the economic impact deriving from the expected selectivity improvements in the largest scale petrochemical oxidation processes, is about US\$ 1.4 billion, worldwide (Centi *et al.*, 2000).

In brief, selectivity is the key aspect in the industrial development of oxidation processes, usually more than activity itself. The selectivity of a reaction is the fraction of the starting material that is converted to the desired product. It facilitates maximum