



UNIVERSITI PUTRA MALAYSIA

**ADSORPTION AND PHOTOCATALYTIC PROPERTIES OF
IMMOBILISED TITANIUM DIOXIDE-LOADED ACTIVATED CARBON
FOR DYE REMOVAL**

CHANG SOOK KENG

FS 2007 28

**ADSORPTION AND PHOTOCATALYTIC PROPERTIES OF IMMOBILISED
TITANIUM DIOXIDE-LOADED ACTIVATED CARBON
FOR DYE REMOVAL**

By

CHANG SOOK KENG

**Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia,
in Fulfilment of the Requirement for the Degree of Master of Science**

May 2007



*Dedicated with much love and affection
to
my parents,
with deep gratitude for all their loving help,
to
my family, who,
by their love and faith in me, have always been a source of great
encouragement to me.*



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment
of the requirement for the degree of Master of Science

**ADSORPTION AND PHOTOCATALYTIC PROPERTIES OF IMMOBILISED
TITANIUM DIOXIDE-LOADED ACTIVATED CARBON
FOR DYE REMOVAL**

By

CHANG SOOK KENG

May 2007

Chairman: Professor Zulkarnain Zainal, PhD

Faculty: Science

With the development of industries and mushrooming of factories venturing into textiles, dyes, pigments, paints and so on, the condition and safety level of water bodies have worsened. Channeling these pollutants into the rivers may lead to unwanted and unsolved environmental problems. Therefore, various methods have been developed to overcome this escalating problem. Activated carbon adsorption is known as a remarkable process due to its large adsorption capacity without forming harmful intermediates or substances while photocatalytic degradation by TiO_2 is a powerful process as it is capable of removing a wide range of organic compounds and achieving a complete mineralization of organics at the end of the process. Combining these two techniques will lead to the enhancement of the removal system.

In this study, adsorption and photocatalytic degradation processes of Methylene Blue were conducted using immobilised mixture of titanium dioxide/activated carbon (TiO_2/AC) under the illumination of ultraviolet (UV) lamp. Immobilised TiO_2/AC was



prepared by applying TiO₂/AC onto a thin layer of PVA/formaldehyde binder that has been spread on glass. The physico-chemical properties of TiO₂/AC were studied by Particle Size Analysis (PSA), Scanning Electron Microscopy (SEM), X-ray Diffraction (XRD), Thermogravimetric Analysis (TGA), Accelerated Surface Area and Porosimetry Analysis (ASAP) and Infrared Analysis (IR). The removal process was studied by varying several parameters such as ball milling of AC in TiO₂/AC, ratio of TiO₂ and AC, suspension loading in the preparation of immobilised TiO₂/AC, initial dye concentration, temperature and light source. The effects of UV light and supply of air towards the removal of cationic dyes: Methylene Blue (MB) and Victoria Blue R (VBR) and anionic dyes: Indigo Carmine (IC) and Naphthol Blue Black (NBB) using immobilised TiO₂, AC and TiO₂/AC were studied in terms of first-order and intraparticle diffusion models. Besides that, isotherm studies were done to determine the adsorption capacity of AC and TiO₂/AC by testing 1000 ppm Methylene Blue using immobilised AC and TiO₂/AC that varies in the number of glasses applied (1-5 glasses).

Immobilised TiO₂/AC showed its best performance under UV illumination with the usage of 1.5 g 30% TiO₂/70% AC. Increasing the dye concentration leads to lower rate constant as the workload of the removal system has increased. The removal of Methylene Blue was an exothermic process. Besides that, immobilised samples containing AC was suitable for the removal of cationic dyes while anionic dyes were better removed by immobilised samples containing TiO₂. The highest rate constants were obtained for these dyes under the illumination of UV light and air supply. The data also fitted well in intraparticle diffusion model. The adsorption capacity of AC and

TiO₂/AC was 370.37 mg/g and 344.83 mg/g respectively. The Langmuir equation gave a better fit to the adsorption isotherm than the Freundlich equation.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Master Sains

**SIFAT PENJERAPAN DAN FOTOPEMANGKINAN KARBON TERAKTIF
TERMUAT-TITANIUM DIOKSIDA YANG DISEKAT GERAK
UNTUK PENYINGKIRAN PEWARNA**

Oleh

CHANG SOOK KENG

Mei 2007

Pengerusi: Profesor Zulkarnain Zainal, PhD

Fakulti: Sains

Pembangunan sektor industri dan pertambahan dalam pembinaan kilang dalam bidang tekstil, pewarna, cat dan sebagainya telah mengakibatkan kemerosotan keadaan dan tahap keselamatan sumber air. Pengaliran bahan pencemar ini ke dalam sungai telah menyebabkan wujudnya masalah-masalah pencemaran alam yang sukar untuk diselesaikan. Dengan ini, pelbagai cara telah dilaksanakan untuk menangani masalah yang semakin ketara ini. Penjerapan karbon teraktif merupakan suatu cara yang baik disebabkan kapasiti penjerapannya yang tinggi tanpa kewujudan bahan perantara atau produk yang bahaya. Proses fotodegradasi dengan titanium dioksida merupakan suatu proses yang berkesan kerana ia dapat menyingkirkan banyak bahan organik dan menukarkan bahan-bahan ini ke bentuk yang tidak bahaya pada akhir proses. Penggabungan dua teknik ini akan meningkatkan kecekapan system penyingkiran.

Dalam kajian ini, proses penjerapan dan fotopemangkinan *Methylene Blue* telah dijalankan dengan menggunakan titanium dioksida/karbon teraktif (TiO_2/AC) tersekat

gerak di bawah penyinaran lampu ultralembayung (UV). TiO₂/AC tersekat gerak disediakan dengan memegunkan TiO₂/AC pada lapisan nipis PVA/formaldehid yang disapukan pada kepingan kaca. Sifat-sifat fizik dan kimia TiO₂/AC dikaji melalui Analisis Saiz Zarah (PSA), Mikroskopi Pengimbasan Elektron (SEM), Pembelauan Sinar-X (XRD), Termogravimetrik (TGA), Luas Permukaan dan Keliangan (ASAP) dan Inframerah (IR). Proses penyingkiran dikaji dengan perubahan beberapa parameter seperti pengisaran bebola pada AC, nisbah TiO₂ dan AC, amaun ampaian dalam penyediaan TiO₂/AC tersekat gerak, kepekatan awal pewarna, suhu dan sumber cahaya. Kesan UV dan bekaln udara terhadap penyingkiran pewarna kationik: *Methylene Blue* (MB) dan *Victoria Blue R* (VBR) dan pewarna anionik: *Indigo Carmine* (IC) dan *Naphthol Blue Black* (NBB) dengan menggunakan TiO₂, AC and TiO₂/AC tersekat gerak dikaji dari segi tertib kinetik pertama dan model penyebaran intrapartikel. Selain itu, kajian isoterma juga dilakukan untuk menentukan kapasiti penjerapan AC dan TiO₂/AC terhadap *Methylene Blue* pada kepekatan 1000 ppm dengan menggunakan bilangan AC dan TiO₂/AC tersekat gerak yang berlainan (1-5 kepingan kaca).

TiO₂/AC tersekat gerak mempamerkan keputusan terbaik dengan penggunaan 1.5 g 30% TiO₂/70% AC di bawah sinaran UV. Pertambahan kepekatan pewarna mengakibatkan penurunan dalam pemalar kadar kerana sistem penyingkiran perlu bekerja dengan lebih kuat. Penyingkiran *Methylene Blue* merupakan proses eksotermik. Selain itu, sampel tersekat gerak yang mengandungi AC adalah lebih sesuai untuk penyingkiran pewarna kationik manakala pewarna anionik lebih sesuai disingkirkan dengan sampel tersekat gerak yang mengandungi TiO₂. Pemalar kadar tertinggi

ditunjukkan oleh pewarna-pewarna ini di bawah penyinaran lampu UV dan bekal udara. Data juga mematuhi model penyebaran intrapartikel. Muatan penjerapan AC dan TiO₂/AC adalah sebanyak 370.37 mg/g dan 344.83 mg/g masing-masing. Data penjerapan isoterma lebih mematuhi persamaan Langmuir daripada persamaan Freundlich.

ACKNOWLEDGEMENTS

I wish to acknowledge with thanks the significant contributions of my project supervisor, Professor Dr. Zulkarnain Zainal who has given me his informative explanations regarding this project. I owe a considerable debt to his patience, wisdom, understanding, invaluable guidance and continuous supervision. I am greatly indebted to my co-supervisor, Associate Professor Dr. Abdul Halim Abdullah, whose intellectual and guidance ensured my continuing enthusiasm for my studies.

The help from Associate Professor Dr. Fauziah Othman and staffs from Microscopy and Microanalysis Unit, Enzyme and Microbe Technology Laboratory, Bioscience Institute, Universiti Putra Malaysia are very much appreciated in ensuring SEM analysis conducted on my samples. Not forgetting Department of Chemistry, Universiti Putra Malaysia for the provision of laboratory facilities.

Once again, I have benefited immeasurably from my association with superb individuals, who have assisted me in performing many tasks in the production of this project. Unfortunately, there are just too many to name individually and I would hesitate to do so in any event in the fear of inadvertently omitting someone. Sincere appreciation and special thanks attributed to my labmates for their helpfulness, willingness and kindness in guiding and helping out throughout the whole duration of my project.



I have pleasure in expressing my cordial thanks to my family members and all my friends for their endless support, full strength encouragement and concern towards the completion of this project. They have my profound thanks and gratitude.

Finally, I would like to express my heartfelt thanks for financial support from IRPA funding.



I certify that an Examination Committee has met on 21st May 2007 to conduct the final examination of Chang Sook Keng on her Master of Science thesis entitled “Adsorption and Photocatalytic Properties of Immobilised Titanium Dioxide-Loaded Activated Carbon for Dye Removal” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

Anuar Kassim, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Zaizi Desa, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

Irmawati Ramli, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

Musa Ahmad, PhD

Professor
Faculty of Graduate Studies
Universiti Kebangsaan Malaysia
(External Examiner)

HASANAH MOHD. GHAZALI, PhD

Professor/Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 21st JUNE 2007



This thesis submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Master of Science. The members of the Supervisory Committee are as follows:

Zulkarnain Zainal, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Abdul Halim Abdullah, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

AINI IDERIS, PhD

Professor/Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 17th JULY 2007



DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.

CHANG SOOK KENG

Date: 18th JUNE 2007



TABLE OF CONTENTS

	Page
DEDICATION	ii
ABSTRACT	iii
ABSTRAK	vi
ACKNOWLEDGEMENTS	ix
APPROVAL	xi
DECLARATION	xiii
LIST OF TABLES	xviii
LIST OF FIGURES	xx
LIST OF ABBREVIATIONS	xxvii
CHAPTER	
1 INTRODUCTION	1
1.1 What is Semiconductor?	4
1.2 Theory of Semiconductors	4
1.3 Properties of Titanium Dioxide	7
1.4 Production of Titanium Dioxide	12
1.5 Applications of Titanium Dioxide	14
1.6 What is Photocatalysis?	15
1.7 Nature of Light	16
1.8 Light Absorption	18
1.9 Photodegradation Process on Semiconductor	19
1.10 Supports in Photocatalysis	22
1.11 Activated Carbon	27
1.12 Raw Materials Used in the Production of Activated Carbon	28
1.13 Manufacture of Activated Carbon	29
1.13.1 Carbonization Process	29
1.13.2 Activation Process	30
1.14 Uses of Activated Carbon	32
1.15 Structure and Chemical Nature of the Surface of Activated Carbon	33
1.15.1 Molecular, Crystalline and Porous Structure of Activated Carbon	33
1.15.2 Surface Functional Groups of	37



Activated Carbon	
1.16 Classification of Pore Sizes	39
1.17 Adsorption Process	40
1.18 Surface Transport of Adsorbed Molecules in Activated Carbon	41
1.19 Properties of Dyes	43
1.19.1 Methylene Blue	45
1.19.2 Victoria Blue R	46
1.19.3 Indigo Carmine	46
1.19.4 Naphthol Blue Black	47
1.20 Kinetic Models	52
1.20.1 First-order rate law	52
1.20.2 Pseudo-second-order rate law	53
1.21 Intraparticle Diffusion	54
1.22 Adsorption Isotherms	55
1.22.1 Langmuir Isotherm	55
1.22.2 Freundlich Isotherm	56
1.23 Objectives	57
2 LITERATURE REVIEW	58
2.1 Removal of Organic Pollutants by Activated Carbon and Titanium Dioxide	58
2.2 Removal of Various Pollutants by Adsorption Process	61
2.3 Removal of Various Pollutants by Photodegradation Process	66
3 MATERIALS AND METHODOLOGY	70
3.1 Preparation of Mixture TiO ₂ /AC	70
3.2 Preparation of Immobilised TiO ₂ /AC	70
3.3 Preparation of Dyes Solutions	71
3.4 Determination of Wavelength at Maximum Absorption (λ_{\max}) and Construction of Standard Calibration Curve	72
3.5 Characterization of TiO ₂ /AC	72
3.5.1 Particle Size Analysis of Titanium	72

Dioxide (TiO ₂) and Activated Carbon (AC) Powders	
3.5.2 Scanning Electron Microscopy (SEM) Analysis	73
3.5.3 X-ray Diffractometry (XRD) Analysis	73
3.5.4 Thermogravimetric (TGA) Analysis	73
3.5.5 Accelerated Surface Area and Porosimetry (ASAP) Analysis	74
3.5.6 Fourier Transform-Infrared (FT- IR) Analysis	74
3.6 Photocatalytic Degradation Studies	74
3.7 Adsorption Studies	75
3.8 Photocatalytic Degradation and Adsorption Studies of Methylene Blue Using TiO ₂ /AC	76
3.8.1 Effect of Ball Milling of AC in TiO ₂ /AC	76
3.8.2 Effect of Ratio of TiO ₂ and AC	76
3.8.3 Effect of Suspension Loading in the Preparation of Immobilised TiO ₂ /AC	77
3.8.4 Effect of Initial Dye Concentrations	77
3.8.5 Effect of Temperature	77
3.8.6 Effect of Light Sources	77
3.9 Removal of Various Dyes Using Immobilised TiO ₂ , AC and TiO ₂ /AC	78
3.10 Adsorption Isotherms	78
4 RESULTS AND DISCUSSION	80
4.1 Particle Size Analysis of Titanium Dioxide (TiO ₂) and Activated Carbon (AC) Powders	80
4.2 Surface Morphology of Immobilised AC and TiO ₂ /AC	81
4.3 XRD Characteristics of Immobilised TiO ₂ , AC and TiO ₂ /AC	83

4.4	Thermogravimetric (TGA) Analysis	85
4.5	Accelerated Surface Area and Porosimetry (ASAP) Analysis	87
4.6	Fourier Transform-Infrared (FT-IR) Analysis	90
4.7	Preliminary Tests	93
4.8	Effect of Ball Milling of AC in TiO ₂ /AC	100
4.9	Effect of Ratio of TiO ₂ and AC	112
4.10	Effect of Suspension Loading in the Preparation of immobilised TiO ₂ /AC	114
4.11	Effect of Initial Dye Concentrations	118
4.12	Effect of Temperature	124
4.13	Effect of Light Sources	131
4.14	Removal of Various Dyes Using Immobilised TiO ₂ , AC and TiO ₂ /AC	134
4.14.1	Removal of Various Dyes by Immobilised TiO ₂	134
4.14.2	Removal of Various Dyes by Immobilised AC	139
4.14.3	Removal of Various Dyes by immobilised TiO ₂ /AC	143
4.14.4	Intraparticle Diffusion Model on Various Dyes	148
4.14.5	Comparisons between Cationic and Anionic Dyes	150
4.15	Adsorption Isotherms	151
4.15.3	AC Adsorption Isotherm	151
4.15.4	TiO ₂ /AC Adsorption isotherm	153
5	CONCLUSION AND RECOMMENDATIONS	156
5.1	Conclusion	156
5.2	Recommendations	159
	REFERENCES	162
	APPENDICES	175
	BIODATA OF THE AUTHOR	201

LIST OF TABLES

Table		Page
1.1	Band-gap energies for some common semiconductor materials.	7
1.2	Crystallographic properties of anatase, brookite and rutile.	11
1.3	Raw materials that have been studied for the production of activated carbon.	28
1.4	Classification of pores according to their width.	39
1.5	Properties of Methylene Blue.	48
1.6	Properties of Victoria Blue R.	49
1.7	Properties of Indigo Carmine.	50
1.8	Properties of Naphthol Blue Black.	51
2.1	List of adsorbents from the literature.	65
3.1	Labels of various samples by varying the number of ball milling.	76
3.2	Labels of various samples with different ratios.	76
3.3	Labels of different conditions in the removal of various dyes.	78
4.1	Comparison of experimental and standard d (Å) values of immobilised TiO_2 and TiO_2/AC .	85
4.2	Surface area (Langmuir and BET) and average pore diameter of TiO_2 , AC and TiO_2/AC .	90
4.3	Absorption of bonds in TiO_2 , AC and TiO_2/AC .	91
4.4	Removal of various dyes as a function of irradiation time in the the presence of immobilised TiO_2 , AC and TiO_2/AC run in the dark in 4 hours.	94



4.5	Removal of various dyes as a function of irradiation time in the presence of immobilised TiO ₂ , AC and TiO ₂ /AC under UV illumination in 4 hours.	95
4.6	Kinetic parameters for the effect of ball milling in the removal of Methylene Blue conducted in the dark.	111
4.7	Kinetic parameters for the effect of ball milling in the removal of Methylene Blue conducted under UV illumination.	111
4.8	Percentage of removal for the effect of ratio in the removal of Methylene Blue conducted in the dark and under UV illumination.	114
4.9	Half-life time for the effect of suspension loading in the preparation of immobilised TiO ₂ /AC in the removal of Methylene Blue.	117
4.10	Half-life time for the effect of initial dye concentrations in the removal of Methylene Blue.	124
4.11	Half-life time for the effect of temperature in the removal of Methylene Blue.	127
4.12	Thermodynamic parameter (ΔG°) for 10 ppm Methylene Blue removal on immobilised TiO ₂ /AC.	130
4.13	Rate constant and half-life time for the effect of light sources in the removal of Methylene Blue.	133
4.14	Kinetic parameters of intraparticle diffusion for the removal of various dyes at different conditions.	150
4.15	Parameters of Langmuir and Freundlich isotherms plots for the adsorption of Methylene Blue by immobilised AC and TiO ₂ /AC.	155

LIST OF FIGURES

Figure		Page
1.1	The energy gap difference between the conductor, insulator and semiconductor.	6
1.2	The energy diagram for a semiconductor showing the band gap energy.	7
1.3	The crystal structure of anatase TiO ₂ .	9
1.4	The crystal structure of rutile TiO ₂ .	10
1.5	The crystal structure of brookite TiO ₂ .	10
1.6	Formation of surface hydroxyls (OH) on the anatase TiO ₂ surface i) An uncovered surface. ii) Coordination of Ti ⁴⁺ ions by water molecules. iii) The formation of surface hydroxyl ions by proton transfer from water to O ²⁻ ions.	12
1.7	Process for the production of fumed titanium dioxide.	14
1.8	Spectrum of electromagnetic radiation.	16
1.9	The excitation process.	18
1.10	Schematic representation of the photochemical activation of a semiconductor and formation of the hydroxyl radical. VB: valence band; CB: conduction band; A: electronic acceptor compound; D: electronic donating compound.	20
1.11	Schematic illustration of several functions assigned to a support in a photocatalytic system.	24
1.12	Conceptual model for photocatalytic reaction in thin-film catalyst: (a) system configuration and (b) coordinate system and concentration profile.	25

1.13	Flowsheet of the production of activated carbon with steam activation.	31
1.14	Order of carbon atoms in a crystal of graphite.	34
1.15	Comparison of three-dimensional crystal lattice of (a) graphite and (b) turbostratic structure.	35
1.16	Schematic illustration of the structure of activated carbon: (a) easily undergoing graphitization and (b) undergoing graphitization to a small degree.	37
1.17	Surface functional groups of activated carbon.	38
1.18	Different regimes of diffusion and flow of adsorbate molecules through a pore.	43
1.19	General structure of cationic dyes.	44
3.1	Coating of TiO ₂ /AC onto glass slide. The same procedures were carried out to immobilise TiO ₂ and AC on glass slide.	71
3.2	Experimental set-up for photodegradation process.	75
4.1	Graph of particle size of original TiO ₂ and AC (Blend, Sift, No ball milling) powders.	80
4.2	Scanning electron micrograph of AC: 1000 x magnification.	81
4.3	Scanning electron micrograph of AC: 5000 x magnification.	82
4.4	Scanning electron micrograph of TiO ₂ /AC: 1000 x magnification.	82
4.5	Scanning electron micrograph of TiO ₂ /AC: 5000 x magnification.	83
4.6	XRDs for TiO ₂ , AC and TiO ₂ /AC coated on glass slide.	84
4.7	TGA thermograms of TiO ₂ , AC and TiO ₂ /AC.	86
4.8	Nitrogen desorption/adsorption isotherm for TiO ₂ , AC and TiO ₂ /AC.	88

4.9	Pore size distributions and pore volume obtained from nitrogen desorption isotherms for TiO ₂ , AC and TiO ₂ /AC.	89
4.10	IR spectra of TiO ₂ .	92
4.11	IR spectra of AC.	92
4.12	IR spectra of TiO ₂ /AC.	92
4.13	Removal of various dyes as a function of irradiation time in the presence of immobilised TiO ₂ . [Conditions: 5 pieces of glass slides, 200 mL of 20 ppm dye solution and temperature 28 °C].	97
4.14	Removal of various dyes as a function of irradiation time in the presence of immobilised AC. [Conditions: 5 pieces of glass slides, 200 mL of 20 ppm dye solution and temperature 28 °C].	98
4.15	Removal of various dyes as a function of irradiation time in the presence of immobilised TiO ₂ /AC. [Conditions: 5 pieces of glass slides, 200 mL of 20 ppm dye solution and temperature 28 °C].	99
4.16	Removal of Methylene Blue as a function of irradiation time on the effect of ball milling. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution and temperature 28 °C].	101
4.17	Graph of capacity versus time on the removal of Methylene Blue by immobilised TiO ₂ /AC for the effect of ball milling. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, run in the dark and temperature 28 °C].	104
4.18	Graph of first-order kinetics of Methylene Blue onto immobilised TiO ₂ /AC for the effect of ball milling. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, run in the dark and temperature 28 °C].	105

4.19	Graph of pseudo-second-order kinetics of Methylene Blue onto immobilised TiO ₂ /AC for the effect of ball milling. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, run in the dark and temperature 28 °C].	106
4.20	Graph of intraparticle diffusion of Methylene Blue onto immobilised TiO ₂ /AC for the effect of ball milling. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, run in the dark and temperature 28 °C].	107
4.21	Graph of capacity versus time on the removal of Methylene Blue by immobilised TiO ₂ /AC for the effect of ball milling. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, light source (1 ultraviolet lamp) and temperature 28 °C].	108
4.22	Graph of first-order kinetics of Methylene Blue onto immobilised TiO ₂ /AC for the effect of ball milling under the presence of UV light. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, light source (1 ultraviolet lamp) and temperature 28 °C].	109
4.23	Graph of intraparticle diffusion of Methylene Blue onto immobilised TiO ₂ /AC for the effect of ball milling under the presence of UV light. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, light source (1 ultraviolet lamp) and temperature 28 °C].	110
4.24	Graph of rate constant, k_1 of Methylene Blue removal for the effect of ratio. [Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution and temperature 28 °C].	113
4.25	Graph of capacity versus time on the removal of Methylene Blue	115

- by immobilised TiO₂/AC for the effect of suspension loading in the preparation of immobilised TiO₂/AC.
[Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, light source (1 ultraviolet lamp) and temperature 28 °C].
- 4.26 Graph of rate constant, k_1 of Methylene Blue removal for the effect of suspension loading in the preparation of immobilised TiO₂/AC. 117
[Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution, light source (1 ultraviolet lamp) and temperature 28 °C].
- 4.27 Removal of Methylene Blue as a function of irradiation time on the effect of initial dye concentrations. 120
[Conditions: 5 pieces of glass slides, 200 mL of Methylene Blue solution, light source (1 ultraviolet lamp) and temperature 28 °C].
- 4.28 Amount of Methylene Blue removed by immobilised TiO₂/AC versus initial dye concentrations run in the dark and under UV illumination for 4 hours. 121
[Conditions: 5 pieces of glass slides, 200 mL of Methylene Blue solution and temperature 28 °C].
- 4.29 Graph of capacity versus time on the removal of Methylene Blue by immobilised TiO₂/AC for the effect of initial dye concentrations. 122
[Conditions: 5 pieces of glass slides, 200 mL of Methylene Blue solution, light source (1 ultraviolet lamp) and temperature 28 °C].
- 4.30 Graph of rate constant, k_1 of Methylene Blue removal for the effect of initial dye concentrations. 123
[Conditions: 5 pieces of glass slides, 200 mL of Methylene Blue solution, light source (1 ultraviolet lamp) and temperature 28 °C].
- 4.31 Graph of rate constant, k_1 of Methylene Blue removal for the effect of temperature. 126
[Conditions: 5 pieces of glass slides, 200 mL of 10 ppm Methylene Blue solution and light source (1 ultraviolet lamp)].