



UNIVERSITI PUTRA MALAYSIA

**PREPARATION AND CHARACTERIZATION OF NATURAL RUBBER-,
POLYETHYLENE- AND NATURAL RUBBER/POLYETHYLENE-CLAY
NANOCOMPOSITES**

MOHD AIDIL ADHHA BIN ABDULLAH

FS 2007 57

**PREPARATION AND CHARACTERIZATION OF NATURAL RUBBER-,
POLYETHYLENE- AND NATURAL RUBBER/POLYETHYLENE-CLAY
NANOCOMPOSITES**

By

MOHD AIDIL ADHHA BIN ABDULLAH

**Thesis Submitted to the School of Graduates Studies,
Universiti Putra Malaysia, in Fulfilment of the Requirements
for the Degree of Doctor of Philosophy**

December 2007



DEDICATION

While this dissertation was in preparation, my beloved father, Abdullah bin Chik passed away after a lengthy illness. I dedicate this thesis special to him. I also dedicate this dissertation to my beloved family for their prayers and moral support

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment
of requirement for the Degree of Doctor of Philosophy

**PREPARATION AND CHARACTERIZATION OF NATURAL RUBBER-,
POLYETHYLENE- AND NATURAL RUBBER/POLYETHYLENE-CLAY
NANOCOMPOSITES**

By

MOHD AIDIL ADHHA ABDULLAH

December 2007

Chairman: Associate Professor Mansor Hj Ahmad @ Ayob, PhD

Faculty: Science

The present research aims at studying the influence of organoclay on the properties of natural rubber (NR), low density polyethylene (LDPE) and NR/LDPE blend. Two types of clays, namely montmorillonite, (MMT) (cationic clay) and layered double hydroxide (LDH) (anionic clay) were used in this study. Secondly, to identify the influence of the organoclay on the thermal and mechanical properties effectively, a thoroughly investigation of the NR-clay and LDPE-clay single-phase and NR/LDPE-clay blend were performed. These nanocomposites were evaluated by X-ray diffraction (XRD), transmission electron microscopy (TEM), thermogravimetric analysis (TGA) and mechanical properties.

The organo-montmorillonite (OMMT) and organo-LDH (OLDH) samples were prepared via ion exchange reaction using organic surfactants;



cetyltrimethylammonium (CTA), n-dodecyl trimethylammonium (DDT), protonated octadecylamines (ODA) and dodecylamines (DDA) as well as dodecylsulphate (DS). The characterization of organoclay were carried out by the Fourier Transform Infrared spectroscopy (FTIR) and the Carbon, Hydrogen, Nitrogen and Sulphur (CHNS) elemental analysis, Scanning Electron Microscopy (SEM) as well as Surface Area and Porosity Analysis (ASAP).

The preparation of a NR nanocomposite may be accomplished either by solvent method or by melt-blending technique. However, the melt-blending technique was applied in this study which is the industrially preferred process. The expansion of the interlayer spacing of the clay indicates the formation of intercalated as well as exfoliated types of nanocomposites which supported by TEM images and XRD diffractograms. Both the tensile strength and the modulus of the nanocomposite increased while elongation at break decreased with the addition of the clay. The Dynamic Mechanical Analysis (DMA) of nanocomposites exhibited enhancement of the storage modulus indicated that the elastic responses of pure NR towards deformation were strongly influenced by the presence of nanodispersed nano-layered material. The thermogravimetric analysis that showed the presence of clay layers in NR matrix gave insignificant improvement in thermal stability of NR-clay nanocomposites.

LDPE-clay nanocomposites were prepared by in-situ grafting-intercalating in melt. The organoclay was first modified with maleic anhydride (MAH). It was then blended with LDPE in melt. The grafting MAH onto LDPE chain favors the exfoliation and intercalation of the organoclay, hence resulting better dispersion of

clay layers in the LDPE matrix. Tensile properties revealed that the tensile strength increased up to 3 parts per hundred polymer by weight (php) while elongation at break decreased with the addition of the clay. Enhancement in storage modulus observed were the characteristic of reinforcing fillers. Thermally stable LDPE-clay nanocomposites were obtained with the increase of the clay content at higher temperature (≥ 400 °C).

Polymer blends with ratio 70/30 amount of LDPE and NR with N, N-m-phenylenebismaleimide (HVA-2) as a compatibilizer was developed. The introduction of cross-links into the elastomer phase has contributed to the improvement of the tensile properties of dynamically vulcanized LDPE/NR blends. These results are supported by scanning electron microscopy (SEM) and Atomic Force Microscopy (AFM) images of extracted surfaces of the blends.

Finally, NR/LDPE-clay nanocomposites were successfully prepared by melt intercalation technique. XRD results revealed the formation of both intercalated and exfoliated nanocomposites. The tensile properties enhanced resulted from melt compounding of NR/LDPE with 3 php or less modified organoclay. All nanocomposites formed in this investigation showed enhancement in the mechanical properties which are the characteristic of reinforcing fillers. The TEM micrograph revealed the clay layers was dominantly distributed in NR domain and manifested by insignificant improvement in thermal stability of the nanocomposites.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**PENYEDIAAN DAN PENCIRIAN NANOKOMPOSIT GETAH ASLI-,
POLIETILENA- DAN GETAH ASLI/ POLIETILENA -TANAH LIAT**

Oleh

MOHD AIDIL ADHHA ABDULLAH

Disember 2007

Pengerusi : Profesor Madya Mansor bin Hj Ahmad @Ayob, PhD

Fakulti : Sains

Matlamat kajian ini adalah untuk mengetahui kesan penggunaan organo-tanah liat ke atas sifat adunan getah asli (NR), polietilena berketumpatan rendah (LDPE) dan adunan NR/LDPE. Dua jenis tanah liat, iaitu montmorilonit (MMT) (tanah liat bercas positif) dan hidroksida berlapis ganda (LDH) (tanah liat bercas negatif), telah digunakan bagi kajian ini. Keduanya, bagi menentukan kesan organo-tanah liat terhadap sifat termal dan mekanikal secara berkesan, penyiasatan keseluruhan terhadap NR-tanah liat dan LDPE-tanah liat fasa-tunggal dan adunan LDPE/NR-tanah liat dijalankan. Nanokomposit ini kemudiannya dinilai menggunakan pembelauan sinar-X (XRD), mikroskop transmisi elektron (TEM), analisis termogravimetrik (TGA) dan sifat mekanikal.

Sampel organo-montmorillonit (OMMT) dan organo-LDH (OLDH) disediakan melalui tindak balas penukar ion menggunakan surfaktan; setiltrimetilammonium

(CTA), n-dodesiltrimetil ammonium (DDT), oktadesilamina (ODA) dan dodesilamina (DDA) terprotoin dan juga dodesil sulfat (DS). Pencirian organo-tanah liat dijalankan menggunakan spektroskopi penukar Fourier infra-merah (FTIR), analisis unsur Karbon, Hidrogen, Nitrogen dan Sulfur (CHNS), mikroskop imbasan elektron (SEM) dan juga analisis luas permukaan dan keliangan (ASAP).

Nanokomposit NR boleh disediakan samada dengan menggunakan kaedah pelarut atau kaedah pengadunan leburan. Walau bagaimanapun, kaedah pengadunan leburan diaplikasikan dalam kajian ini kerana ianya merupakan kaedah yang biasa digunakan oleh industri. Pengembangan ruang antara lapisan tanah liat menunjukkan pembentukan nanokomposit jenis interkalasi dan terkelupas yang mana ianya disokong oleh imej TEM dan diffraktogram XRD. Kedua-dua kekuatan tegasan dan modulus bagi nanokomposit meningkat manakala pemanjangan pada takat putus menurun dengan pertambahan tanah liat. Analisis Mekanikal Dinamik bagi nanokomposit menunjukkan peningkatan modulus simpanan yang membuktikan tindak balas kekenyalan NR tulen terhadap canggaan sangat dipengaruhi oleh kehadiran sebaran bahan nano-lapisan. Analisis termogravimetrik menunjukkan kehadiran lapisan tanah liat memberikan peningkatan yang tidak signifikan terhadap kestabilan termal bagi nanokomposit NR-tanah liat.

Nanokomposit LDPE-tanah liat disediakan melalui kaedah *in-situ* cangkukan-interkalasi di dalam leburan. Organo-tanah liat mulanya diubahsuai menggunakan maleik anhidrida (MAH). Ia kemudiannya diadunkan dengan LDPE dalam keadaan lebur. Cangkukan MAH pada rantaian LDPE menghasilkan organo-tanah liat pengelupasan dan interkalasi dan seterusnya menjadikan sebaran lapisan tanah liat

dalam matrik LDPE lebih baik. Sifat tegasan menunjukkan kekuatan tegasan meningkat sehingga 3 bahagian bagi seratus polimer mengikut berat (php) sementara pemanjangan pada takat putus menurun dengan penambahan tanah liat. Peningkatan modulus simpanan yang perhatikan menunjukkan ciri-ciri bagi pengisi penguat. Nanokomposit LDPE-tanah liat berkestabilan termal diperolehi dengan peningkatan kandungan tanah liat pada suhu yang lebih tinggi ($\geq 400^{\circ}\text{C}$).

Adunan polimer dengan nisbah kandungan 70/30 LDPE dan NR bersama N, N-m-fenilinbismalemida (HVA-2) sebagai pengserasi telah dibangunkan. Pengenalan rangkai silang kepada fasa elastomer telah menyumbang kepada peningkatan sifat tegangan bagi komposit adunan pemvulkanan dinamik NR/LDPE. Keputusan ini disokong oleh imej yang diperolehi dengan mikroskop pengimbasan elektron (SEM) dan mikroskop daya pengatoman (AFM) bagi sampel adunan setelah pengestrakan permukaan dilakukan.

Akhirnya, nanokomposit NR/LDPE-tanah liat telah berjaya disediakan melalui keadah pengadunan leburan. Keputusan XRD menunjukkan pembentukan kedua-dua jenis nanokomposit interkalasi dan terkelupas. Sifat tegasan meningkat hasil daripada pengadunan leburan bagi NR/LDPE dengan 3 php atau kurang organo-tanah liat. Kesemua nanokomposit yang terhasil dalam ujikaji ini menunjukkan peningkatan sifat mekanikal yang mana ia merupakan ciri bagi pengisi penguat. Mikrograf TEM menunjukkan lapisan tanah liat mendominasi fasa NR merupakan punca kepada peningkatan yang tidak signifikan terhadap kestabilan termal bagi nanokomposit.

ACKNOWLEDGEMENTS

In The Name of Allah, The Most Merciful and Most Beneficent

I would like to express my deepest thanks to Associate Professor Dr. Mansor Hj Ahmad for his inspiration, guidance, and suggestions, which were the key to the successful completion of my studies. I would also like to express my sincere appreciation to my other committee members Prof. Dr. Wan Md. Zin Wan Yunus, Assoc. Prof. Dr. Zaki and Dr. Khairul Zaman Dahlan for their time, effort, and support.

Thanks are also extended to all staff members of chemistry and physic department; especially Mrs. Rosnani, Mr. Kamal Margona, Mr. Nazeri, Mrs Yusmawati and Mrs Yusnita. I am also pleased to thank to Dr. Fauziah Othman, Ms. Azilah and Mr. Ho from the Electron Microscopy Unit, Institute Bioscience, for their assistance for obtaining the transmission electron micrographs.

Thanks are given to the wonderful people in the Polymer Research Group especially to Dr. Dedy Suhendra, Dr. Faraj Abu Ilawi, Dr. Jamaliah, Dr. Nor Azowa, Muhammad Khawaldeh, Ali Muhammad Ali, Su Fang, Wei Chee, Mrs Jamarosliza, Yehya, Chee Siong and Sharil for all kinds of help, suggestions and friendship they have offered. I thank all the people in the chemistry department for their friendly support.

Further, I would like to acknowledge Universiti Malaysia Terengganu for financial support, Lembaga Getah Malaysia and Agensi Atom Malaysia for providing me the required materials and instrument for this study.

Finally, thanks to my beloved wife, Mazidah bt Mamat, family and my best friends; Ali and Adila for their deepest love and reserveless support. My appreciation to them can never be expressed by words and sentences.

I certify that an Examination Committee met on 28 December 2007 to conduct the final examination of Mohd Aidil Adhha bin Abdullah on his Doctor of Philosophy thesis entitle” Preparation and characterization of Natural Rubber-, Polyethylene-and Natural Rubber/Polyethylene-Clay Nanocomposites” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulation 1981. The committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

Mohd Zaizi Desa, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Asmah Hj. Yahaya, PhD

Associate Professor
Faculty of Graduate Studies
Universiti Putra Malaysia
(Member)

Mohd Zobir Hussein, PhD

Professor
Faculty of Graduate Studies
Universiti Putra Malaysia
(Member)

Gan Seng Neon , PhD

Professor
Faculty of Graduate Studies
Universiti Putra Malaysia
(Independent Examiner)

Professor and Deputy Dean,
School of Graduate Studies
Universiti Putra Malaysia

Date:



This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Mansor Hj. Ahmad, PhD

Associate Professor

Faculty of Science

Universiti Putra Malaysia

(Chairman)

Wan Md Zin Wan Yunus, PhD

Professor

Faculty of Science

Universiti Putra Malaysia

(Member)

Mohd Zaki Ab. Rahman, PhD

Associate Professor

Faculty of Science

Universiti Putra Malaysia

(Member)

Khairul Zaman Dahlan, PhD

Director

Division of Radiation Processing Technology

Malaysian Nuclear Agency

(Member)

AINI IDERIS, PhD

Professor and Dean

School of Graduate Studies

Universiti Putra Malaysia

Date: 10 April 2008



DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations, which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or any other institutions.

MOHD AIDIL ADHHA ABDULLAH

Date: 19 February 2008



TABLE OF CONTENTS

	Page
DEDICATION	ii
ABSTRACT	iii
ABSTRAK	vi
ACKNOWLEDGEMENTS	ix
APPROVAL	xi
DECLARATION	xiii
LIST OF TABLES	xviii
LIST OF FIGURES	xx
LIST OF ABBREVIATIONS	xxx
 CHAPTER	
1 INTRODUCTION	1
1.1 Clay reinforced polymer	2
1.2 Polymer-Clay nanocomposites	3
1.3 Thermoplastic elastomer (TPE)	5
1.4 Research Approach	5
1.5 Objectives	6
2 LITERATURE REVIEW	7
2.1 Natural Rubber	7
2.1.1 Chemical structure	7
2.1.2 Standard Malaysia Rubber- Viscosity stabilized (SMR CV)	10
2.1.3 Vulcanization of Natural Rubber	12
2.1.4 Application of Natural Rubber	16
2.2 Polyethylene	16
2.3 Natural Rubber/Polyethylene blend	18
2.4 Clay	19
2.4.1 Cationic clay	20
2.4.2 Anionic clay	23
2.4.3 Ion Exchange process	26
2.5 Polymer Nanocomposites	27
2.5.1 Polymer-clay nanocomposites	28
2.5.2 Preparation of polymer-clay nanocomposites	30
2.5.3 Characterization of Polymer-Clay Structure	32
2.5.4 Properties of nanocomposites	34
2.5.4.1 Tensile properties	35
2.5.4.2 Elongation at break	36
2.5.4.3 Dynamic Mechanical Analysis	37
2.5.4.4 Thermal Stability	38
2.5.5 Natural Rubber nanocomposites	39
2.5.6 Polyethylene-Clay nanocomposites	40
2.5.7 Polymer blend-Clay nanocomposites	41

3	MATERIAL AND METHOD	43
3.1	Material and equipments	43
3.2	Preparation of organo-montmorillonite (OMMT)	46
3.3	Preparation of layered double hydroxide (LDH)	48
3.3.1	Preparation of hydrophilic LDH (HLDH)	49
3.3.2	Preparation of organo-LDH (OLDH)	51
3.4	Preparation of modified organoclay	52
3.5	Preparation of Nanocomposites	52
3.5.1	Preparation of Natural Rubber-Clay composites	52
3.5.1.1	Solvent Casting Method	52
3.5.1.2	Melt Intercalation Method	54
3.5.2	Preparation of LDPE-Clay nanocomposites	54
3.5.2.1	Melt Intercalation Method	54
3.5.2.2	In-situ grafting-intercalating method	55
3.5.3	Preparation of Polyethylene/Natural Rubber Blends	55
3.5.4	Preparation of LDPE/NR-Clay nanocomposites	57
3.6	Characterization of clay and nanocomposites	57
3.6.1	X-ray Diffraction	57
3.6.2	Fourier Transform Infra-Red	58
3.6.3	Elemental analysis	58
3.6.4	Surface area and porosity	59
3.6.5	Thermogravimetric Analysis	59
3.6.6	Rheometry	59
3.6.7	Scanning Electron Microscopy	60
3.6.8	Atomic Force Microscopy	60
3.6.9	Transmission Electron Microscopy	60
3.6.10	Tensile Properties Measurements	61
3.6.11	Dynamic Mechanical Analysis	61
3.6.12	Swelling Index Measurement	62
4	RESULTS AND DISCUSSION I: PREPARATION AND CHARACTERIZATION OF ORGANOCLAY	63
4.1	Preparation of organo-montmorillonite (OMMT)	63
4.2	Preparation of organo-LDH (OLDH)	64
4.3	Characterization of Organoclay	65
4.3.1	X-Ray Diffraction Analysis	65
4.3.2	Elemental Analysis	68
4.3.3	Fourier Transform Infrared (FTIR)	71
4.3.4	Surfactant arrangement in the interlayer	75
4.3.5	Surface Properties	76
4.3.6	Surface morphology	84
4.3.7	Thermogravimetric Analysis	92
4.3.8	Modification of organoclay	101
4.4	Summary	105

5	RESULTS AND DISCUSSION II: NATURAL RUBBER-CLAY NANOCOMPOSITES	106
5.1	Preparation of Natural Rubber-Clay Nanocomposites	106
5.2	Comparative studies of solvent casting and melt intercalation method	106
5.2.1	X-Ray Diffractogram	107
5.2.2	Tensile properties	109
5.3	Characterization of Natural Rubber-Clay Nanocomposites	111
5.3.1	Vulcanizations characteristics	111
5.3.2	Swelling Index	115
5.3.3	Analysis of the clay dispersion	115
5.3.4	Tensile Properties	128
5.3.5	DMA Properties	133
5.3.6	Thermogravimetric Analysis	140
5.4	Summary	145
6	RESULTS AND DISCUSSION III: POLYETHYLENE-CLAY NANOCOMPOSITES	146
6.1	Preparation of Polyethylene-Clay Nanocomposites	146
6.2	Characterization of LDPE-Organoclay nanocomposites	148
6.2.1	Analysis of clay dispersion	148
6.2.2	Fourier Transform Infrared Analysis	153
6.2.3	Tensile Properties	156
6.2.4	DMA Properties	158
6.2.5	Thermogravimetric Analysis.	162
6.3	Summary	172
7	RESULTS AND DISCUSSION IV: POLYETHYLENE/NATURAL RUBBER-CLAY NANOCOMPOSITES	175
7.1	Preparation of Polyethylene/Natural Rubber Blend	175
7.1.1	Effect of HVA-2 on Tensile strength of Polyethylene/Natural Rubber Blend	175
7.1.2	Swelling Index	176
7.1.3	Surface Morphology	178
7.1.4	Dynamic Mechanical Analysis	182
7.2	Preparation of LDPE/NR-Clay Nanocomposites	186
7.3	Characterization of LDPE/NR-Clay nanocomposites	186
7.3.1	Analysis of clay dispersion	186
7.3.2	Tensile properties	191
7.3.3	Dynamic Mechanical Analysis	195
7.3.4	Thermogravimetric Analysis	201
7.4	Summary	210
8	CONCLUSIONS AND FURTHER STUDIES	212
8.1	Conclusion	212
8.2	Recommendations for Further Studies	217
BIBLIOGRAPHY		219
APPENDICES		233

**BIODATA OF THE AUTHOR
LIST OF PUBLICATIONS**

240
241



LIST OF TABLES

Table		Page
2.1	Subgrade of SMR CV and producer limits on Mooney viscosity	11
2.2	Properties of SMR-CV (Nair, 1975)	11
2.3	Type of non-sulfur crosslinking agents (RRIM, 1979)	13
3.1	List of chemicals and their manufacturers	43
3.2	List of equipments and their manufacturers	45
3.3	Name, abbreviation and structure of ionic surfactants used to prepare organoclay	47
3.4	Formulation of intercalant, distilled water and hydrochloric acid in the preparation of OMMT	48
3.5	Amount of NR and organoclay used in preparing the nanocomposites	53
3.6	Formulation for vulcanization of natural rubber composite	53
3.7	The formulation of LDPE composites	55
3.8	Amount of HVA-2 used in study of preparation of 70/30 LDPE/NR blends	56
3.9	Ingredients for preparation of 70/30 LDPE/NR/organoclay blend	57
4.1	Basal spacing of Na-MMT, CTA-MMT, DDT MMT, DDA-MMT and ODA-MMT	67
4.2	Basal spacing of HLDH and OLDH	69
4.3	The total carbon content and the amount of surfactants intercalated in the MMT	70
4.4	The carbon, nitrogen and sulfur content in LDH	70
4.5	Band assignment of FTIR spectra of Na-MMT, CTA-MMT, DDT-MMT, DDA-MMT and ODA-MMT	73

4.6	Summary of gallery height, surfactant and orientation of surfactant molecule for organophilic clays	76
4.7	Surface properties of Na-MMT, CTA-MMT, DDT-MMT, DDA-MMT, ODA-MMT, HLDH and OLDH	77
4.8	Total weight loss for each step of the decomposition of MMT obtained from Figs. 4.24 - 4.28	98
4.9	The summary of major species evolved from each decomposition step of MMT sample	98
4.10	Basal spacing of organoclay and modified organoclay	104
5.1	2θ and interlayer distance of composites NR-CTA-MMT and NR-ODA-MMT	109
5.2	Scorch time and torque values of NR and composite of NR-MMT and NR-LDH	112
5.3	Swelling index of composites NR-MMT	116
5.4	Swelling index of composites NR-LDH	116
5.5	Basal spacing of MMT, LDH and its composites	120
5.6	Effect of clay content on storage modulus of NR-Clay nanocomposites	138
5.7	Effect of clay content on thermal stability of NR-Clay nanocomposites	144
6.1	Effect of clay content on $\tan \delta$ of LDPE-clay nanocomposites	164
6.2	Effect of clay content on thermal degradation of LDPE-clay composites	173
7.1	Swelling index of 70/30 PE/NR blend with various content of HVA-2	178
7.2	Interlayer spacing of MOMMT, OMMT, MOLDH and OLDH after blend with LDPE and NR	190
7.3	DMA properties of LDPE/NR nanocomposites	200
7.4	Effect of clay content on thermal degradation of LDPE/NR-clay nanocomposites	210

LIST OF FIGURES

Figure		Page
1.1	Schematic illustration of three types of polymer (nano)composites (Qutubuddin and Fu, 2001)	4
2.1	The relationship between monomer and polymer structure of isoprene	8
2.2	<i>Cis</i> configuration of 1,4-polyisoprene	8
2.3	Trans configuration of 1,4-polyisoprene	9
2.4	Steps in vulcanization process (RRIM,1979)	14
2.5	Structure features of vulcanizate network Mono (a), di- (b) and polysulfidic (c) crosslinks	15
2.6	Structures of polyethylene	17
2.7	Three dimensional polyhedra of 2:1 layer silicate assembling. (Moore, 1989)	21
2.8	Idealized 3D structure of montmorillonite (Gianellis, 1996)	22
2.9	3 Dimension structure of Mg ²⁺ octahedrally surrounded by six OH- anion (a) and the different octahedral share edges to form infinite sheets (brucite layer)	25
2.10	Structure of layered double hydroxides (You <i>et al.</i> 2001)	25
2.11	Alkyl chain aggregations in 2:1 clay minerals: monolayers (a), bilayers (b), and pseudotrimolecular layers (c) of chains lying flat on the surface, and paraffin-type monolayers (d) (Lagaly, 1986)	28
3.1	Apparatus set up for preparation of organoclay	49
3.2	Apparatus set up for self-assembly method	50
4.1	XRD patterns of Na-MMT (a) and tertiary amines treated MMT, CTA-MMT (b) and DDT-MMT (c)	66
4.2	XRD patterns of Na-MMT (a) and primary amines treated MMT, DDA-MMT (b) and ODA-MMT (c)	66

4.3	XRD Patterns of LDH with nitrate as interlayer anion, HLDH (a) and LDH with dodecylsulphate as a guest anion, OLDH (b)	69
4.4	FTIR spectra of Na-MMT (a) and MMT treated with tertiary amines; CTA-MMT(b), and DDT-MMT (c)	72
4.5	FTIR spectra of Na-MMT (a) and primary amines treated MMT; ODA-MMT(b), and DDT-MMT (c)	72
4.6	FTIR spectra of LDH with nitrate as interlayer anion, HLDH (a) and LDH treated with DS, OLDH (b)	74
4.7	Schematic representation of surfactant arrangement	77
4.8	Adsorption–desorption isotherms of Na-MMT (a) and CTA-MMT (b)	79
4.9	Adsorption–desorption isotherms of Na-MMT (a) and DDT-MMT (b)	79
4.10	Adsorption–desorption isotherms of Na-MMT (a) and DDA-MMT (b)	80
4.11	Adsorption–desorption isotherms of Na-MMT (a) and ODA-MMT (b)	80
4.12	Pore size distribution of Na-MMT (a) and CTA-MMT (b)	81
4.13	Pore size distribution of Na-MMT (a) and DDT-MMT (b)	81
4.14	Pore size distribution of Na-MMT (a) and DDA-MMT (b)	82
4.15	Pore size distribution of Na-MMT (a) and ODA-MMT (b)	82
4.16	Adsorption–desorption isotherms of HLDH (a) and OLDH (b)	83
4.17	Pore size distribution of HLDH (a) and OLDH (b)	83
4.18 (a)	SEM micrograph for Na-MMT at low magnification (1000X)	85
4.18 (b)	SEM micrograph for Na-MMT at high magnification (8000X)	85
4.19 (a)	SEM micrograph for CTA-MMT at low magnification (1000X)	86

4.19 (b)	SEM micrograph for CTA-MMT at high magnification (5000X)	86
4.20 (a)	SEM micrograph for DDA-MMT at low magnification (1000X)	87
4.20 (b)	SEM micrograph for DDA-MMT high magnification (5000X)	87
4.21 (a)	SEM micrograph for ODA-MMT at low magnification (1000X)	88
4.21 (b)	SEM micrograph for ODA-MMT at high magnification (5000X)	88
4.22 (a)	SEM micrograph for DDT-MMT at low magnification (1000X)	89
4.22 (b)	SEM micrograph for DDT-MMT at high Magnification (8000X)	89
4.23 (a)	SEM micrograph for OLDH at low magnification (1000X)	90
4.23 (b)	SEM micrograph for OLDH at and high magnification (8000X)	90
4.24 (a)	SEM micrograph for HLDH at low magnification (1000X)	91
4.24 (b)	SEM micrograph for HLDH at high magnification (5000X)	91
4.25	TGA and DTG thermograms of Na-MMT	93
4.26	TGA and DTG thermograms of CTA-MMT	93
4.27	TGA and DTG thermograms of DDT-MMT	94
4.28	TGA and DTG thermograms of DDA-MMT	94
4.29	TGA and DTG thermograms of ODA-MMT	95
4.30	TGA and DTG thermograms of HLDH	100
4.31	TGA and DTG thermograms of OLDH	100
4.32	XRD diffractograms of CTA-MMT (a) and MCTA-MMT (b)	102
4.33	XRD diffractograms of DDA-MMT (a) and MDDA-MMT (b)	102

4.34	XRD diffractograms of ODA-MMT (a) and MODA-MMT (b)	103
4.35	XRD diffractograms of DDT-MMT (a) and MDDT-MMT (b)	103
4.36	XRD diffractograms of OLDH (a) and MOLDH (b)	104
5.1	XRD diffractograms of CTA-MMT and its composites with NR (5 phr) prepared by solvent and melt intercalation methods	108
5.2	XRD diffractograms of ODA-MMT and its composites with NR (5 phr) prepared by solvent and melt intercalation methods	108
5.3	Tensile properties of nanocomposites of NR-CTA-MMT prepared by solvent and melt intercalation technique	110
5.4	Tensile properties of nanocomposites of NR-ODA-MMT prepared by solvent and melt intercalation technique	110
5.5	Torque value of the NR with Na-MMT (a), CTA-MMT (b), DDT-MMT (c) DDA-MMT (d) and ODA-MMT (e)	114
5.6	Torque value of the NR with HLDH (a) and OLDH (b)	114
5.7	X-ray diffractograms of nanocomposites of NR-CTA-MMT	118
5.8	X-ray diffractograms of nanocomposites of NR-ODA- MMT	118
5.9	X-ray diffractograms of nanocomposites of NR-DDT-MMT	119
5.10	X-ray diffractograms of nanocomposites of NR-DDA-MMT	119
5.11	X-ray diffractograms of nanocomposites of NR-OLDH	122
5.12	X-ray diffractograms of nanocomposites of NR-HLDH	122
5.13	X-ray diffractograms of nanocomposites of NR-Na-MMT	123
5.14	TEM image of NR-ODA-MMT (1phr) nanocomposites at high magnification	124
5.15	TEM images of NR-clay nanocomposites (3 phr) at low magnification. NR-ODA-MMT (a), NR-DDA-MMT (b), NR-CTA-MMT (c) NR- DDT-MMT and NR-OLDH (e)	125

5.16	TEM images of NR-clay (3 phr) nanocomposites at high magnification (25,000X) (a) NR-ODA-MMT, (b) NR-CTA-MMT, (c) NR-DDA-MMT, (d) NR-DDT-MMT and (e) NR-OLDH	126
5.17	TEM images of NR-Clay (7 phr) nanocomposites at low magnification NR-CTA-MMT (a), NR-ODA-MMT (b) and NR-HLDH (c)	127
5.18	TEM images of NR-clay macrocomposites (3phr), NR-Na-MMT (a) and NR-HLDH (b)	128
5.19	Effect of clay content on tensile strength of NR-OMMT composites	129
5.20	Effect of clay content on 300% modulus of NR-clay composites	130
5.21	Effect of clay content on 500% modulus of NR-clay composites	130
5.22	Effect of clay content on elongation at break of NR-clay composites	132
5.23	Tensile strength of NR/LDH composites	132
5.24	Modulus at 300% of NR/LDH nanocomposites	134
5.25	Modulus at 500% of NR/LDH nanocomposites	134
5.26	Effect of clay content on elongation at break of NR/LDH composites	135
5.27	Storage modulus of NR/CTA-MMT at various clay contents. Pure NR (a), 3 phr (b), 5 phr (c) and 10 phr (d)	136
5.28	Storage modulus of NR/DDT-MMT at various clay contents. Pure NR (a), 3 phr (b), 5 phr (c) and 10 phr (d)	136
5.29	Storage modulus of NR/DDA-MMT at various clay contents. Pure NR (a), 3 phr (b), 5 phr (c) and 10 phr (d)	137
5.30	Storage modulus of NR/DDA-MMT at various clay contents. Pure NR (a), 3 phr (b), 5 phr (c) and 10 phr (d)	137
5.31	Storage modulus of NR/OLDH at various clay contents. Pure NR (a), 3 phr (b), 5 phr (c) and 10 phr (d)	138
5.32	Tangent delta of NR nanocomposites with various organoclay at 5 pphr	140