



UNIVERSITI PUTRA MALAYSIA

**IMPREGNATION OF BAMBOO (*Gigantochloa scortechinii*) WITH
PHENOLIC RESIN FOR THE PRODUCTION OF DIMENSIONALLY
STABLE PLYBAMBOO**

MOHD KHAIRUN ANWAR BIN UYUP

FH 2008 8

IMPREGNATION OF BAMBOO (*Gigantochloa scortechinii*) WITH PHENOLIC RESIN FOR THE PRODUCTION OF DIMENSIONALLY STABLE PLYBAMBOO

MOHD KHAIRUN ANWAR BIN UYUP

**DOCTOR OF PHILOSOPHY
UNIVERSITI PUTRA MALAYSIA**

2008



**IMPREGNATION OF BAMBOO (*Gigantochloa scortechinii*) WITH
PHENOLIC RESIN FOR THE PRODUCTION OF DIMENSIONALLY
STABLE PLYBAMBOO**

By

MOHD KHAIRUN ANWAR BIN UYUP

**Thesis Submitted to the School of Graduates Studies, Universiti Putra
Malaysia, in Fulfilment of the Requirements for Degree of Doctor of
Philosophy**

March 2008



Specially dedicated to:

**My Father
HJ UYUP B. HJ SIAM**

My Beloved Late Mother

**HJH SITI ESAH BT. YASIN
(Al-Fatihah)**

and

My Family

**Suhana Mohd Salleh
Muhamad Rizqan
Muhamad Aqimi**

**Your love has made me a better and stronger person.
You are always in my heart.**

Abstract of thesis to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Doctor of Philosophy

IMPREGNATION OF BAMBOO (*Gigantochloa scortechinii*) WITH PHENOLIC RESIN FOR THE PRODUCTION OF DIMENSIONALLY STABLE PLYBAMBOO

By

MOHD KHAIRUN ANWAR BIN UYUP

March 2008

Chairman: Associate Professor Paridah Md. Tahir, PhD.

Faculty: Forestry

Low molecular weight phenol formaldehyde (LMwPF) resin was used to enhance the dimensional stability of bamboo strips (*Gigantochloa scortechinii*). Resin was impregnated into bamboo strips via vacuum process before the strips were converted into plybamboo. The present study was undertaken to develop a process to produce high dimensionally stable plybamboo. The work included evaluation of resin impregnation process, establishment of suitable drying/curing technique and final pressing of phenolic-treated bamboo strips. Evaluation of bonding properties, dimensional stability and mechanical properties of phenolic-treated plybamboo were also conducted. The bamboo strips were taken from basal and middle portions of bamboo culm. To treat the bamboo strips with LMwPF resin, firstly, a vacuum period of 1 hour was

applied before the strips were soaked in resin for at least 90 minutes. The samples were later dried in an oven at 60°C for 9 hours. The mean weight percent gain (WPG) and moisture content (MC) of dried phenolic-treated bamboo strips were 14.5% and 7%, respectively. Drying the phenolic-treated bamboo strips for > 9 hours resulted in cupping of the strips.

Phenolic-treated strips were then hot pressed for 5, 8, 11, 14 and 17 minutes at 14 kgm⁻² and 140°C. Water absorption (WA), thickness swelling (TS) and linear expansion (LE) of the strips decreased when the curing time was extended from 5 minutes to 17 minutes but antishrink efficiency (ASE) increased. The mean value of modulus of rupture (MOR) for untreated strips (177 Nmm⁻²) was significantly lower than the phenolic-treated strips (224 Nmm⁻²) after 17 minutes pressing time. However, no significant difference was observed in modulus of elasticity (MOE) and compression parallel to grain. Results showed that the optimum pressing time for phenolic-treated strips was 11 minutes.

This work also established an optimum pressing time to produce high dimensionally stable plybamboo. For this, phenolic-treated bamboo strips were glued together edge-to-edge using phenol resorcinol formaldehyde (PRF) resin to produce a veneer. The veneers were then assembled perpendicular to each other to form a 3-ply (12 mm) and 5-ply (20 mm) plybamboo using phenol formaldehyde resin as a binder. The plybamboos were hot pressed at an

optimum pressing condition of 140°C (pressure 14 kgm⁻²) for 22 (3-ply) and 33 (5-ply) minutes. The bonding strength of the plybamboo obtained in this study met the minimum requirement of MS 228-1991. WA, TS, and LE of phenolic-treated plybamboo were significantly lower compared to those of untreated plybamboo.

The MOR, MOE and compression parallel to grain of the phenolic-treated plybamboo were significantly higher compared to those of untreated plybamboo. For 3-ply, the values were 164 and 127 Nmm⁻² for MOR, and 19767 and 16778 Nmm⁻² for MOE, and 60 and 41 Nmm⁻² for compression parallel to grain, respectively. Similarly, for 5-ply phenolic-treated plybamboo the MOR, MOE and compression parallel to grain of were 38%, 30% and 33% respectively higher than those of untreated plybamboo. Generally, the treatment of bamboo strips with LMwPF resins were found to significantly improve the properties of plybamboo made from them.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia bagi memenuhi syarat untuk memperolehi keperluan untuk ijazah Falsafah ke Doktoran

IMPREGNASI BULUH (*Gigantochloa scortechinii*) MENGGUNAKAN PEREKAT FENOL BAGI MENGHASILKAN BULUH LAPIS YANG BERDIMENSI STABIL

Oleh

MOHD KHAIRUN ANWAR BIN UYUP

Mac 2008

Pengerusi: Profesor Madya Paridah Md Tahir, PhD.

Fakulti: Perhutanan

Fenol formaldehid yang berjisim molekul rendah (LMwPF) telah digunakan untuk mempertingkatkan mutu kestabilan dimensi bilahan buluh semantan (*Gigantochloa scortechinii*). Perekat tersebut telah dipadatkan ke dalam bilahan buluh melalui kaedah vakum sebelum dijadikan buluh lapis. Kajian ini adalah untuk menghasilkan buluh lapis yang stabil dimensinya. Kajian meliputi proses pepadatan, pengeringan/pematangan perekat dan penekanan bagi bilahan buluh yang dirawat. Penilaian kekuatan lekatan, kestabilan dimensi dan kekuatan buluh lapis telah dijalankan. Bilahan buluh diambil dari dua bahagian iaitu pangkal dan tengah.

Kaedah yang optimum untuk merawat buluh dengan LMwPF ialah secara vakum selama satu jam diikuti rendaman bagi tempoh 90 minit dan dikeringkan pada suhu 60°C di dalam ketuhar selama 9 jam. Purata peratus kenaikan berat (WPG) ialah 14.5% manakala kandungan kelembapan selepas 9 jam pengeringan ialah 7%. Pengeringan bilahan buluh rawat melebihi 9 jam akan menyebabkan bilahan buluh menggeleding.

Bilahan buluh yang dirawat ditekan panas pada tekanan 14 kgm⁻² bersuhu 140°C untuk jangka masa 5, 8, 11, 14 and 17 minit. Kadar penyerapan air (WA), pengembangan ketebalan (TS) dan kadar pengembangan arah bertentangan (LE) telah menurun manakala keupayaan menentang pengembangan (ASE) meningkat apabila masa pematangan bertambah daripada 5 kepada 17 minit. Nilai purata kekuatan pecahan (MOR) untuk bilahan yang tidak dirawat (177 Nmm⁻²) lebih rendah berbanding bilahan buluh yang dirawat (224 Nmm⁻²) selepas 17 minit ditekan panas. Manakala kadar kekuatan kenyalan dan tekanan bagi kedua-dua bilah buluh ini tiada perbezaan yang nyata. Kadar optimum tekan panas untuk bilah yang dirawat ialah 11 minit.

Kajian ini juga bagi mendapatkan masa tekanan panas yang optimum untuk menghasilkan buluh lapis berdimensi tinggi. Di bahagian tepi bilah buluh yang dirawat kemudian dilekatkan antara satu sama lain dengan menggunakan fenol resorsinol formaldehid (PRF) bagi menghasilkan sekeping lapisan.

Lapisan kemudian disusun bertentangan antara satu sama lain dan digam dengan menggunakan fenol formaldehid bagi menghasilkan buluh lapis yang berketebalan 12 mm (3 lapis) dan 20 mm (5 lapis). Masa optimum bagi penekanan panas buluh lapis ialah 22 minit (3 lapis) dan 33 minit (5 lapis). Kekuatan lekatan untuk semua buluh lapis (sama ada dirawat atau tidak) telah mencapai piawaian minimum dalam MS 228-1991. Kestabilan dimensi (kadar resapan, pengembangan ketebalan dan kadar pengembangan bagi buluh lapis dirawat adalah nyata berbeza berbanding buluh lapis yang tidak dirawat.

Kekuatan rekahan, modulus kekenyalan dan tekanan menunjukkan buluh lapis yang dirawat lebih kuat berbanding buluh lapis yang tidak dirawat. Bagi buluh lapis tiga lapisan, nilainya ialah 164 berbanding 127 Nmm⁻² untuk kekuatan kepecahan, 19767 berbanding 16778 Nmm⁻² bagi modulus kekenyalan serta 60 berbanding 41 Nmm⁻² bagi tekanan. Keadaan yang sama juga berlaku bagi buluh lapis lima lapisan dimana kekuatan rekahan, modulus kekenyalan dan tekanan bagi buluh yang dirawat mempunyai nilai lebih tinggi sebanyak 38%, 30% dan 33%, berturutan berbanding buluh lapis yang tidak dirawat. Secara keseluruhan, rawatan menggunakan fenol formaldehid yang berjisim molekul rendah (LMwPF) memberikan kesan penambahbaikan yang amat ketara terhadap ciri-ciri buluh lapis yang telah diuji.

ACKNOWLEDGEMENTS

Praise to Allah the mighty for without Him, I would not be able to complete this research. Special notes of gratitude to my main supervisor Associate Professor Dr. Paridah Md. Tahir, for never losing her patience and for never losing track of me. To all committee members, Dr. Hamdan Husain, Dr. Edi Suhaimi Bakar and Prof Ir. Dr. Mohd Sapuan Salit, thank you very much for your guidance.

Special thanks to the Director General of Forest Research Institute of Malaysia (FRIM) Dato' Dr. Abd. Latif Mohmod for the approval and assistance given. My thanks also go to my staff at Wood Finishing Laboratory, Siti Rafidah and Mat Yaacob for their dedication. To the following people whom I seek for answers when I couldn't find them anywhere especially to Associate Professor Dr. Zaidon (UPM), Dr. Zainul (LGM), Dr. Rowell, Dr. Hill, Dr. Fauzi Fabrianto, Dr. Omar, Dr. Wan Tarmeze, Dr. Salmiah, Dr. Grace and Dr. Dahlan. Also to my directors, Dr. Tan and Dr. Rahim, who always understand my situation and accept it. To Wood Composite Laboratory and Non-Wood Forest Product Unit in the preparation of raw material and plybamboo manufacturing i.e., Mohd Tamizi, Rahim, Khairoul, Saimin, Hamdan, Rosidi, Othman, Hassan, Mohd Nazri, Siti Hajar and many others whose name are not mentioned but are equally valued for their help.



I wish to also express my appreciation to Malaysian Adhesive and Chemical Sdn. Bhd especially to Dr. Nor Yuziah, Ruziah (JKL), Rafiuzaman (IBS), my friends (Hamid, Khairul, Farid, Jani, Baharudin, Syeed, Nik Zanariah, Norhafizah, Azrinawati) and many others for their enduring friendships and support. Also not forgetting my sponsors, FRIM, Yayasan Pahang and MOSTI for the financial assistance.

My greatest and deepest gratitude goes to my family: my brothers (Najmi, Naim, Azree, Fahmy and Amir). Also thanks to my parents in law (Hj. Mohd Sultan and Hjh. Zaharah) and my stepmother (Hjh. Roziah). To my wife Suhana, thank you for your patience and support while lifting my spirit during my difficult times. My two boys (Rizqan and Aqimi) for understanding the situation and a constant absence of their father. Last but not the least, to my father (Hj. Uyup b. Hj. Siam), who always give me support (and pressure) when I feel down and lazy. Finally, my deepest love goes to my beloved late mother (Hjh. Siti Esah bt. Yasin) who I know would be very proud of my achievement and ALLAH S.W.T. for the strength and courage.

Semoga ALLAH S.W.T membalas jasa baik kalian. Amin.



I certify that an Examination Committee met on 17 March 2008 to conduct the final examination of Mohd Khairun Anwar Bin Uyup on his Doctor of Philosophy thesis entitled “Impregnation of Bamboo (*Gigantochloa scortechinii*) with Phenolic Resin for the Production of Dimensionally Stable Plybamboo” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the Doctor of Philosophy.

Member of the Examination Committee were as follows:

Zaidon Ashaari, PhD

Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Chairman)

Mohd Hamami Sahri , PhD

Professor
Faculty of Forestry
Universiti Putra Malaysia
(Internal Examiner)

Nor Azowa Ibrahim, PhD

Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

Martin Philip Ansell, PhD

Department of Mechanical Engineering
University of Bath
United Kingdom
(External Examiner)

HASANAH MOHD. GHAZALI, PhD

Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 26 May 2008



This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirements for the degree of Doctor of Philosophy. The members of the Supervisory Committee were as follows:

Paridah Md Tahir, PhD
Associate Professor
Faculty of Forestry
Universiti Putra Malaysia
(Member)

Hamdan Husain, PhD
Head Unit
Forest Products Division
Forest Research Institute Malaysia
(Member)

Edi Suhaimi Bakar, PhD
Faculty of Forestry
Universiti Putra Malaysia
(Member)

Mohd Sapuan Salit, PhD
Professor
Faculty of Engineering
Universiti Putra Malaysia
(Member)

AINI IDERIS, PhD
Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia
Date: 12 June 2008



DECLARATION

I declare that the thesis is my original work except for quotations and citations, which have been duly acknowledge. I also declare that it has not been previously, and is not concurrently, submitted for any other degree at Universiti Putra Malaysia or at any other institution.

MOHD KHAIRUN ANWAR BIN UYUP

Date: 21 April 2008

LIST OF TABLES

Table		Page
1.1	Dimensional stability of bamboo strips (<i>Gigantochloa scortechinii</i>) and selected timbers	8
2.1	Comparing the efficiency of material for strength and stiffness	24
2.2	Mechanical properties of bamboo culms and timber species from different countries	25
2.3	Properties of some bamboo panel products	27
2.4	Bending strength of bamboo and wooden platform boards	27
2.5	Comparatively strength and stiffness of plybamboo and other structural composite materials	30
2.6	Dimensional stability and water absorption of bamboo plywood and merawan plywood during short- (2 h) and long-term (24 h) soaking	31
2.7	Methods and type of resin used in impregnation modifications	38
2.8	Mechanical properties of Scot pine impregnated with methylolated melamine and formaldehyde (MMF) resin	40
2.9	Effect of different levels of WPG on BC, MEE and ASE of bamboo	41
3.1	ANOVA for the effects of portion, coating and soaking duration	73
3.2	Mean of weight percent gain (WPG) of bamboo strips after being impregnating with low molecular weight phenol formaldehyde resin	74
4.1	Dimensions of bamboo strips for determination of physical properties	88
4.2	Dimensions of bamboo strips for determination of mechanical properties	95
4.3	Moisture content and specific gravity for untreated and phenolic- treated strip	100
4.4	Mechanical properties of untreated and phenolic-treated <i>G. scortechinii</i> strips	114



5.1	Analysis of variance (ANOVA) of surface wettability after 2 sec	133
5.2	Contact angle (°) on the inner and outer surface of phenolic-treated and untreated strip	134
5.3	Average values of plybamboo shear strength and wood failure of phenolic-treated plybamboo pressed at different pressing times	143
5.4	Curing behaviour of phenolic-treated plybamboo pressed at different durations	153
5.5	Water absorption and dimensional stability of phenolic-treated and untreated plybamboo after 24 hours water soaking	162
6.1	Processing sequence for the production of phenolic-treated plybamboo	176
6.2	Dimensions of plybamboo for determination of physical and mechanical properties	179
6.3	Density and moisture content of untreated and phenolic-treated plybamboo	188
6.4	Mechanical properties of untreated and phenolic-treated plybamboo	189
6.5	Specific strength of untreated and phenolic-treated plybamboo	191



LIST OF FIGURES

Figure		Page
2.1	The longitudinal section of a bamboo culm	16
2.2	Diagrammatic view of cell wall in bamboo (Parameswaran and Liese, 1976)	23
2.3	Models for the extent of chemical modification of wood	36
2.4	Process involved in the formation of phenol formaldehyde (Pizzi, 2003)	43
2.5	Reaction mechanism in resol phenol formaldehyde (Pizzi, 2003)	45
2.6	Resol PF molecular weight versus F/P and NaOH/P ratio (Gollob, 1989)	46
2.7	Typical polymer molecular weight distribution and corresponding average molecular weights	48
3.1	Experimental design used in Chapter 3	59
3.2	Sampling and cutting of bamboo culms	63
3.3	Cutting of bamboo strips	65
3.4	Heat flow versus temperature for LMwPF resin measured by DSC	71
3.5	Moisture content of phenolic-treated strips at basal and middle portions during drying at 60°C	77
3.6	Cross-linked process of LMwPF resin during drying at 60°C (Frihat, 2003)	78
4.1	Anticipated curing curve for LMwPF resin	83
4.2	Experimental design used in Chapter 4	85
4.3	Schematic diagram for the preparation of samples for physical tests	87
4.4	Water absorption percentage after 24-hour soaking for untreated and phenolic- treated strip	102
4.5	Thickness swelling percentage after 24-hour soaking for untreated and phenolic-treated strip	103
4.6	Linear expansion perpendicular to the grain percentage after 24-hour soaking for untreated and phenolic-treated strip	103
4.7	Antishrink efficiency after 24-hour soaking for phenolic-treated strips	104

4.8	A typical cross-linking process of LMwPF resin during drying at 60°C and 140°C (Frihat, 2003)	112
5.1	Experimental design used Chapter 5	118
5.2	Schematic illustration for the preparation of samples for contact angle	121
5.3	Typical diagram of a contact angle of a droplet	123
5.4	Schematic diagram for the preparation of samples for bond shear test evaluation	127
5.5	Measurement of thickness swelling and linear expansion (parallel and perpendicular to grain)	131
5.6	Contact angle vs. time (minutes) of phenolic-treated and untreated strips	135
5.7	Buffering capacity of bamboo strips in alkaline condition	139
5.8	Buffering capacity of bamboo strips in acidic condition	140
5.9	A propose schematic representation of an adhesive joint, showing the various “links” in the chain analogy in phenolic-treated plybamboo	151
5.10	Moisture content of phenolic-treated plybamboo for 3 and 5-ply	154
5.11	Water absorption of phenolic-treated plybamboo	156
5.12	Thickness swelling of phenolic-treated plybamboo	157
5.13	Linear expansion parallel to the grain of phenolic-treated plybamboo	158
5.14	Linear expansion perpendicular to the grain of phenolic-treated plybamboo	159
6.1	Experimental design used in Chapter 6	170
6.2	Cutting pattern of 3-ply untreated and phenolic-treated plybamboo (12 mm) specimens for the mechanical and physical test	180
6.3	Cutting pattern of 5-ply untreated and phenolic-treated plybamboo (20 mm) specimens for the mechanical and physical	181
6.4	Schematic diagram of static bending test for plybamboo	184
6.5	Typical stress distribution in a plybamboo caused by progressively increasing bending moment	192
6.6	Stress due to rolling shear (Fellmoser and Blaß, 2004)	198



LIST OF PLATES

Plate	Page
2.1 Portion of bamboo culms showing node and internode	15
2.2 Distribution of vascular bundles structure of 4 -year-old <i>G. scortechinii</i> (a) at 6 th (b) 14 th internode (Anwar <i>et al.</i> , 2005)	18
2.3 Cross section of <i>Gigantochloa scortechinii</i> (Abd. Latif, 1991; Anonymous, 1999 ^a)	19
3.1 <i>Gigantochloa scortechinii</i> clumps	61
3.2 Harvesting of bamboo culms	62
3.3 Storing of bamboo culms in the laboratory	64
3.4 Vacuum vessel used to impregnate the bamboo strips with LMwPF resin	66
3.5 The LMwPF resin squeeze out after drying for 9 hours	79
4.1 The scanning electron microscope (Philip XL30 ESEM)	92
4.2 The microtome and chemical used for slides preparation of phenolic-treated strips	93
4.3 The light microscope (Olympus AH-2)	94
4.4 Static bending test conducted on the phenolic-treated strip	96
4.5 Compression parallel to grain on the phenolic-treated strip	98
4.6 Excessive resin of phenolic-treated strips after pressing at 140°C for 11 minutes	101
4.7 Scanning electron micrograph of untreated strips (350X)	106
4.8 Resins were found at parenchyma cell with partially and fully filled in parenchyma cells- (350X)	106
4.9 Light micrograph of cross section for untreated strips (scale - 0.2 mm)	107
4.10 Light micrograph of transverse section for untreated strips (scale - 0.5 mm)	108
4.11 Light micrograph of cross section for phenolic-treated strips Note: The brownish colour surrounding the vascular bundle is LMwPF resin (scale - 0.2 mm)	108
4.12 Light micrograph of cross section for phenolic-treated strips. Note: The arrows show the form of resin in granules and patch (scale - 0.05 mm)	109

4.13	Light micrograph of transverse section for phenolic-treated strips. Note: The brownish colour is LMwPF resin (scale – 0.1 mm)	109
5.1	A L&W 4-1 used to determine contact angle of a droplet	122
5.2	Automatic laboratory titrator used in the study	124
5.3	Bonding shear test	128
5.4	Insufficient cure of LMwPF and PF resin at the edge of 5-ply phenolic-treated plybamboo after 11 minutes of pressing time at 140°C	144
5.5	A 5-ply phenolic-treated plybamboo after 11 minutes of pressing time	145
5.6	Bamboo failure of phenolic-treated plybamboo	148
5.7	Penetration of adhesive in the cross and parallel section of phenolic-treated plybamboo (50X)	164
5.8	Penetration of adhesive in the cross and parallel section of untreated plybamboo (50X)	165
5.9	The LMwPF resin deposited in the parenchyma of phenolic-treated plybamboo (1000X)	165
5.10	Parenchyma of untreated plybamboo (600X)	166
6.1	Sizing and splitting of bamboo culm	171
6.2	Planning of bamboo strips on a single face-planing machine	172
6.3	Bamboo strips were submerged in basin full with resin and placed in a vacuum chamber	173
6.4	A clamping jig used to clamp the bamboo strips for making bamboo veneer	174
6.5	Hot pressing of assembled phenolic-treated plybamboo	175
6.7	Phenolic-treated plybamboo for (A) 3- and (B) 5-ply	178
6.8	Static bending test for plybamboo	185
6.9	Compression parallel to grain test for phenolic-treated plybamboo	186
6.10	Failure of 3-ply phenolic-treated plybamboo in compression and tension after static bending test	194
6.11	Failure at 3-ply phenolic-treated plybamboo in compression (red mark) failure (99X)	194



6.12	Failure at 3-ply untreated plybamboo in compression (red mark) failure (99X)	195
6.13	Failure at 3-ply phenolic-treated plybamboo in tension (red mark) failure (23X)	195
6.14	Failure of 5-ply phenolic-treated plybamboo in compression and rolling shear at 4 th layer during static bending test	196
6.15	Failure at 5-ply phenolic-treated plybamboo in compression (100X)	197
6.16	Failure at 5-ply phenolic-treated plybamboo in rolling shear at 4 th layer (edge view) (80X)	197
6.17	Failure at 5-ply untreated plybamboo in compression and glueline shear at 4 th layer during static bending test	199
6.18	Failure at 5-ply untreated plybamboo in compression (60X)	200
6.19	Failure at 5-ply untreated plybamboo at glueline shear after static bending test (100X)	200
6.20	Failure of 5-ply phenolic-treated plybamboo in compression parallel to the grain test (edge view)	201
6.21	Fiber and parenchyma cell buckling due to intense compression along the grain at a high rate of strain for phenolic-treated plybamboo (65X)	203
6.22	Failure in compression parallel to grain for untreated plybamboo (65X)	203
6.23	Failure cracking between vascular bundles and parenchyma cells at adjacent layer (50X0)	204

LIST OF ABBREVIATIONS

ANOVA	Analysis of variance
ASE	Antishrink efficiency
CBR	Cyclic boil resistance
CL	Concentrated loading
CCA	Copper-chrome-arsenic
BC	Bulking coefficients
BB	Bamboo board
DSC	Different Scanning Calorimetry
EMC	Equilibrium moisture content
F/P	Formaldehyde to phenol
GPC	Gel permeation chromatography
GLM	General linear model
HCl	Hydrogen chloride
IR	Infrared spectroscopy
L	longitudinal
LSD	Least Significant Different
LMwPF	Low molecular weight phenol formaldehyde
LE	Linear expansion
MUF	Melamine urea formaldehyde
MEE	Moisture excluding efficiency
MMF	Methylolated melamine and formaldehyde
ml	Mililiter
MOR	Modulus of rupture
MOE	Modulus of elasticity



M_n	Number-average molecular weight
M_v	Viscosity-average molecular weight;
M_w	Weight-average molecular weight,
M_z	Average molecular weight
MWD	Molecular weight distribution
na	Not available
OSB	Oriented strand board
NaOH/P	Sodium hydroxide to phenol
NaOH	Sodium hydroxide
PF	Phenol formaldehyde
PRF	Phenol resorcinol formaldehyde
R	Radial
RH	Relative humidity
SAS	Statistical analysis system
SG	Specific gravity
SGL	Single glueline
SEM	Scanning electron microscope
T	Tangential
TS	Thickness swelling
UF	Urea formaldehyde
UL	Uniform loading
WA	Water absorption
WB	Wood board
WPG	Weight percent gain



CHAPTER 1

INTRODUCTION

1.1 Background

Bamboo has received tremendous attention as an alternative raw material due to its fast growth, availability, attractive and unique appearance and toughness (Tewari, 1992). Bamboo in its natural form is mainly used as construction material such as floorings, walls and other household items and utensils. Bamboo is one of the most easily available resources in rural areas. Fourteen out of 59 species are commonly used by the Malaysian bamboo industry for making poultry cages, vegetable baskets, incense sticks and joss papers, skewers and chopsticks, woven blind and handicrafts (Azmy *et al.*, 1994; Aminuddin, 1995).

Bamboo can potentially be converted into engineered products such as cement-bonded particleboard, particleboard, medium density fibreboard, laminated bamboo board, plybamboo, bamboo mat board, bamboo curtain board etc. Most bamboo producing countries such as China and India, lack the processing technology needed to produce high quality end products (Zhu, 1995). Commercialised products available on the market are laminated bamboo, bamboo mat, sliver board, bamboo particleboards, parquetry and plybamboo

