



UNIVERSITI PUTRA MALAYSIA

**EFFECT OF NANOPARTICULATES (Gd₂O₃, Eu₂O₃, Ce₂O₃) ADDITION
ON PROPERTIES OF (Bi_{1.6} Pb_{0.4})Sr₂ Ca₂ Cu₃ O₁₀ CERAMICS
SUPERCONDUCTORS**

SAEEDAH SADAT HOSSEINI RAVANDI

FS 2009 13

**EFFECT OF NANOPARTICULATES (Gd_2O_3 , Eu_2O_3 , Ce_2O_3) ADDITION ON
PROPERTIES OF $(Bi_{1.6}Pb_{0.4})Sr_2Ca_2Cu_3O_{10}$ CERAMICS
SUPERCONDUCTORS**

By

SAEEDAH SADAT HOSSEINI RAVANDI

**Thesis submitted to the senate of University Putra Malaysia
in fulfillment of the requirements for the degree of Master of Science**

May 2009



DEDICATIONS

To Prof. Dr. Halim,
for his guidance, patience and belief in me...

To my parents, Javad, Mahrokh and my lovely Mohammad,
for their love, support and understanding...



Abstract of thesis presented to the senate of University Putra Malaysia in fulfillment of requirements for the degree of Master of Science.

EFFECT OF NANOPARTICULATES (Gd_2O_3 , Eu_2O_3 , Ce_2O_3) ADDITION ON PROPERTIES OF $(Bi_{1.6}Pb_{0.4})Sr_2Ca_2Cu_3O_{10}$ CERAMICS SUPERCONDUCTORS

By

SAEEDAH SADAT HOSSEINI RAVANDI

May 2009

Chairman : Professor Abdul Halim bin Shaari

Faculty : Science

The effects of Rare Earth oxide (M) nanoparticulates addition in $(Bi_{1.6}Pb_{0.4})Sr_2Ca_2Cu_3O_{10} + xM$ with $M = Gd_2O_3, Eu_2O_3, Ce_2O_3$ and $x = 0.0-0.05$ system, prepared by the conventional solid state reaction method have been investigated for structural, electrical and magnetic properties. The sizes of nanoparticulates oxide are 150 nm, 4 nm and 50nm respectively for Gd_2O_3 , Eu_2O_3 and Ce_2O_3 . The samples were calcined at $800^\circ C$ and $830^\circ C$ for 48 hours followed by sintering at $850^\circ C$ for 120 hours. The morphological appearance of the samples with Gd_2O_3 addition generally showed platelet-like grains with random orientations, typically of 2223 phase's structure, and by increasing the amount of nanoparticulate the platelet tend to stick together. At high percentage of nanoparticulate addition in Gd_2O_3 the microstructure displayed grain size from to 1.5 μm to 10 μm and increased



number of pores. The morphologies of fractured surface of pellets of specimen from $x=0.00$ - $x=0.05$ Ce_2O_3 nanoparticulate, showed that the flaky nature of the grains gradually vanished and the edges of the grains become softer and the size of the grain changed from $10\ \mu\text{m}$ to $2\ \mu\text{m}$. At $x=0.03$ of Eu_2O_3 the grain size become larger in comparison with other samples.

The volume fraction of the high- T_C (2223) phase for addition of Gd_2O_3 decreased from 89% for $x=0.005$ to 58% for $x=0.05$ and in the low- T_C (2212) phase the volume increased from 3.4% to 41.2 % for $x=0.005$ and $x=0.05$, respectively. The c -axis parameter decreased from $37.1293\ \text{\AA}$ to $36.7800\ \text{\AA}$ at $x=0.005$ to $x=0.05$ for Gd_2O_3 addition on Bi-2223. For addition with Eu_2O_3 , we can observe some increasing in $x=0.03$, from $x=0.01$ - $x=0.03$ volume fractions increased from $x=0.01$ - $x=0.03$ according to following percentage of 83.2% to 94.3%, respectively. The lattice parameter in the c -axis increased for $x=0.00$ to $x=0.03$ in Eu_2O_3 addition from $37.1264\ \text{\AA}$ to $37.1432\ \text{\AA}$. In addition with Ce_2O_3 nanoparticulate in pure Bi-2223, with increasing in the amount, the volume fractions reduced from 92.67% for $x=0.00$ to 57% in $x=0.05$, the c -axis also decreased from $37.1193\ \text{\AA}$ to $36.8870\ \text{\AA}$ for $x=0.00$ - 0.05 .

The critical temperature with increasing amounts of Gd_2O_3 $x=0.00$ - $x=0.05$ decreased from 101 K to 96 K, respectively. For samples with the addition of Eu_2O_3 , T_C decreased from 101 K to 98 K and started to increase for $x=0.03$ with $T_C = 103.74$ K. When Ce_2O_3 content was further increased, the electrical behavior started to change. The onset

critical temperatures were reduced from 101 K to 93 K for $x=0.00$ - $x=0.05$, respectively. Measurements of AC magnetic susceptibility as a function of temperature and AC field amplitudes have been carried out for samples containing Gd_2O_3 nanoparticulate at constant frequency $f=333.3$ Hz. It is shown that with increasing addition content from $x=0.00$ - $x=0.05$, the diamagnetic onset temperature decreased from 107 K for pure sample to 97 K for Gd_2O_3 in last content. The analysis for comparison is based on the availability of higher percentage of the high- T_C (2223) phase in the sample, the suppression degree of diamagnetic behavior with respect to AC fields; rapid or slow shift of the summit in $\chi''_{(T)}$ to lower temperature with increasing field amplitude and the sharpness of $\chi'_{(T)}$ for the intergranular component for the same field amplitude.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
Sebagai memenuhi keperluan untuk ijazah Master Sains

**KESAN PENAMBAHAN NANOZARAH (Gd_2O_3 , Eu_2O_3 , Ce_2O_3) KE ATAS
SIFAT-SIFAT SUPERKONDUKTOR SERAMIK ($Bi_{1.6}Pb_{0.4}$) $Sr_2Ca_2Cu_3O_{10}$**

Oleh

SAEEDAH SADAT HOSSEINI RAVANDI

Mei 2009

Pengerusi: Professor Abdul Halim bin Shaari

Fakulti: Sains

Kesan penambahan nanozarah oksida nadir bumi (M) ke dalam sistem $(Bi_{1.6}Pb_{0.4})Sr_2Ca_2Cu_3O_{10} + xM$ dengan $M = Gd_2O_3, Eu_2O_3, Ce_2O_3$ dan $x = 0.0-0.05$, yang disediakan dengan kaedah tindakbalas keadaan pepejal yang konvensional telah dikaji struktur, sifat elektrik dan sifat magnetnya. Saiz oksida nanozarah adalah masing-masing 150 nm, 4 nm dan 50 nm untuk Gd_2O_3, Eu_2O_3 dan Ce_2O_3 . Sampel-sampel telah dikalsin pada $800^\circ C$ dan $830^\circ C$ selama 48 jam diikuti dengan persinteran pada suhu $850^\circ C$ selama 120 jam. Rupa bentuk morfologi sampel-sampel dengan penambahan Gd_2O_3 secara amnya menunjukkan butiran-butiran seperti platlet dengan orientasi yang rawak, khasnya untuk struktur fasa 2223, dan dengan menambahkan amoun nanozarah platlet tersebut cenderung untuk melekat bersama. Pada peratusan penambahan nanozarah Gd_2O_3 yang tinggi mikrostruktur menunjukkan saiz butiran dari 10 μm kepada



1.5 μm dan peningkatan bilangan keliangan. Morfologi permukaan retakan pelet bagi spesimen dengan nanozarah Ce_2O_3 dari $x = 0.00 - x = 0.05$, menunjukkan bahawa keadaan kelupasan pada butiran hilang secara beransur-ansur dan bahagian sisi butiran menjadi semakin licin dan saiz butiran berubah dari 10 μm kepada 2 μm . Bagi Eu_2O_3 pada $x = 0.03$ saiz butiran menjadi lebih besar berbanding dengan sampel-sampel lain.

Pecahan isipadu bagi fasa T_C -tinggi (2223) bagi penambahan Gd_2O_3 berkurang dari 89 % untuk $x = 0.005$ kepada 58 % untuk $x = 0.05$ dan dalam fasa T_C -rendah (2212) isipadu meningkat dari 3.4 % kepada 41.2 % bagi $x = 0.005$, $x = 0.05$, masing-masing. Pemalar paksi- c berkurang dari 37.1293 Å kepada 36.7800 Å pada $x = 0.005$, $x = 0.05$ bagi penambahan Gd_2O_3 ke atas Bi-2223. Untuk penambahan dengan Eu_2O_3 , dapat diperhatikan sejumlah peningkatan dalam $x = 0.03$, dari $x = 0.00$ kepada $x = 0.03$ pecahan isipadu meningkat menurut peratusan berikut iaitu 83.2 % kepada 94.3 %, masing-masing. Pemalar kekisi dalam paksi- c meningkat dengan penambahan Eu_2O_3 $x = 0.00$ kepada $x = 0.03$ dari 37.1264 Å kepada 37.1432 Å. Bagi penambahan dengan nanozarah Ce_2O_3 ke dalam Bi-2223 tulen, dengan penambahan amaunnya, pecahan isipadu berkurang dari 92.6 7% bagi $x = 0.00$ kepada 57 % bagi $x = 0.05$, paksi- c juga berkurang dari 37.1193Å kepada 36.8870Å bagi $x = 0.00-0.05$. Suhu genting dengan penambahan amaun Gd_2O_3 $x = 0.00 - x = 0.05$ berkurang dari 101 K kepada 96 K, masing-masing. Dengan penambahan Eu_2O_3 T_C berkurang dari 101 K kepada 98 K dan mula meningkat bagi $x = 0.03$ dengan $T_C = 103.74$ °K. Apabila kandungan Ce_2O_3 terus ditingkatkan, sifat elektrik akan mula berubah. Suhu genting permulaan berkurang dari 101 K to 93 K bagi $x = 0.00 - x = 0.05$, masing-masing. Pengukuran kerentanan magnet AC sebagai fungsi

suhu dan amplitud medan AC telah dijalankan bagi sampel-sampel yang mengandungi nanozarah Gd_2O_3 pada frekuensi malar $f = 333.3$ Hz. Dapat diperhatikan bahawa dengan peningkatan kandungan bahan penambah dari $x = 0.00 - x = 0.05$, suhu permulaan diamagnet berkurangan dari 107 K bagi sampel tulen kepada 97 K bagi kandungan Gd_2O_3 yang akhir. Analisis bagi perbandingan adalah berdasarkan kepada terdapatnya peratus fasa T_C -tinggi (2223) yang lebih tinggi di dalam sampel. Ketumpatan arus genting yang bergantung pada suhu telah diambil daripada data kerentanan AC bagi beberapa sampel terpilih; pengurangan darjah kelakuan diamagnet terhadap medan AC; laju atau perlahannya anjakan puncak kepada suhu lebih rendah dalam $\chi''_{(T)}$ dengan peningkatan amplitud medan dan ketajaman $\chi'_{(T)}$ bagi komponen antara butiran bagi amplitud medan yang sama.



ACKNOWLEDGMENT

In the name of Allah , the most Merciful and the most Gracious. Thanks of Allah, for giving me the strength and will to write and at last complete this thesis.

I am externally grateful to my supervisor, Professor Dr. Abdul Halim Shaari for, most all, believing in me. For all the patience, guidance, advice, ideas, encouragement and continuous discussion, my deepest gratitude goes to you. I also express my regards to my co-supervisor, Dr. Lim Kean Pah and Dr. Chen Soo Kien for their comment, suggestions and guidance throughout the research work.

My special thanks go to Dr. Walter Charles for his helping me on my project, I am grateful to Mr. Rafi for his favors in SEM examination. And my most gratitude to Mr. Zain for X-ray Diffraction, and Mr. Hanif for resistance measurement.

To my friends who never fail to encourage me until the end, Zalita, Hussain, Sewi, Kuan, Hojjat , Maryam, Kazem ,Parisa. I am very thankful to En. Razak and other technical staff in the Physics Department for their technical favors.

To my lovely parents, for their love , support and understanding to keep me going and my brother, Mohammad for his love. And last but not least, to my cousin Bahar and my dear Negar.



I certify that an Examination Committee has met on May 29th, 2009 to conduct the final examination of Saeedeh Sadat Hosseini Ravandi on her Master of Science thesis entitled “Effect of nanoparticulates (Gd_2O_3 , Eu_2O_3 , Ce_2O_3) addition on properties of $(Bi_{1.6}Pb_{0.4})Sr_2Ca_2Cu_3O_{10}$ ceramics superconductor” in accordance with Universiti Pertanian Malaysia(Higher Degree)Regulation 1981. The Committee recommends that the student be awarded the (Name of relevant degree)

Members of the Examination Committee were as follows:

ELIAS SAION, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

JUMIAH HASSAN, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

HALIMAH MOHAMED KAMARI, PhD

Lecture
Faculty of Science
Universiti Putra Malaysia
(Internal Examiner)

ROSIAN ABD SHUKOR, PhD

Professor
Faculty of Science and Technology
Universiti Kebangsaan Malaysia
Malaysia
(External Examiner)

BUJANG KIM HUAT, PhD

Professor and Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date:



This thesis was submitted do the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Master of Science. The members of Supervisory Committee were as follows:

ABDUL HALIM SHAARI, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

LIM KEAN PAH, PhD

Lecture
Faculty of Science
Universiti Putra Malaysia
(Member)

CHEN SOO KIEN, PhD

Lecture
Faculty of Science
Universiti Putra Malaysia
(Member)

HASANAH MOHD GHAZALI, PhD

Professor and Dean
School of Graduate Studies
Universiti Putra Malaysia



DECLARATION

I declare that the thesis is my original work except for quotations and citation which have been duly acknowledged. I also declare that it has not been previously, and is not concurrently, submitted for any other degree at Universiti Putra Malaysia or at any other institution.

SAEEDAH SADAT HOSSEINI RAVANDI

Date:



TABLE OF CONTENTS

	Page
DEDICATION.....	ii
ABSTRACT.....	iii
ABSTRAK.....	vi
ACKNOWLEDGMENTS.....	xi
APPROVAL.....	x
DECLARATION.....	xii
LIST OF TABLES.....	xvi
LIST OF FIGURES.....	xvii
LIST OF PLATES.....	xx
LIST OF SYMBOLS.....	xxi

CHAPTER

1 INTRODUCTION

1.1 What is Superconductivity?.....	1
1.2 Fundamental of Superconductivity.....	4
1.3 High T_C Superconductors (HTS).....	9
1.4 The BSCCO System.....	10
1.5 Objective of thesis	11

2 THEORIES

2.1 Meissner Effect.....	13
2.2 Type I and Type II Superconductors.....	14
2.3 BCS Theory (Bardeen-Cooper-Schrieffer)	17
2.4 Bean's Model.....	18
2.5 AC Determination: Critical Current Density.....	22



3 LITERATURE REVIEW

3.1 The effect of Rare Earth addition on BSCCO system.....	23
3.2 The effect of Rare Earth substitution on BSCCO system.....	27
3.3 The effect of Rare Earth doping on BSCCO system.....	31
3.4 The effect of elements doping on BSCCO system.....	33

4 PREPERATION AND CHARECTRIZATION TECHNIQUE

4.1 Sample Preparation and Experimental Details.....	38
4.2 Chemicals Powder Weighing.....	39
4.3 Calcinations.....	39
4.4 Sintering.....	41
4.5 Characterization technique	
4.5.1 Scanning Electron Microscopy	44
4.5.2 Energy Dispersive X-ray	45
4.5.3 X-ray Diffraction Analysis	45
4.5.4 Critical temperature measurement	47
4.5.5 AC Magnetic Susceptibility Measurement	48

5 RESULT AND DISCUSSION

5.1 Surface morphology	52
5.1.1 Effect of nanoparticulate Gd_2O_3 addition on ($Bi_{1.6} Pb_{0.4}$) $Sr_2 Ca_2 Cu_3 O_{10}$	52
5.1.2 Effect of nanoparticulate Eu_2O_3 addition on ($Bi_{1.6} Pb_{0.4}$) $Sr_2 Ca_2 Cu_3 O_{10}$	55
5.1.3 Effect of nanoparticulate Ce_2O_3 addition on ($Bi_{1.6} Pb_{0.4}$) $Sr_2 Ca_2 Cu_3 O_{10}$	58



5.2	Elements Analysis	60
5.2.1	Effect of nanoparticulate Gd_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	60
5.2.2	Effect of nanoparticulate Eu_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	62
5.2.3	Effect of nanoparticulate Ce_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	63
5.3	Crystalline Analysis	65
5.3.1	Effect of nanoparticulate Gd_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	65
5.3.2	Effect of nanoparticulate Eu_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	69
5.3.3	Effect of nanoparticulate Ce_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	72
5.4	Critical temperature measurement.....	76
5.4.1	Effect of nanoparticulate Gd_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	76
5.4.2	Effect of nanoparticulate Eu_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	78
5.4.3	Effect of nanoparticulate Ce_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	81
5.5	AC Magnetic Susceptibility Measurement	84
5.5.1	Effect of nanoparticulate Gd_2O_3 addition on $(Bi_{1.6} Pb_{0.4})Sr_2 Ca_2 Cu_3 O_{10}$	85
6	CONCLUSION AND SUGGESTIONS FOR FUTURE WORK	
6.1	Conclusions.....	91
6.2	Suggestion for future work.....	93
	BIBLIOGRAPHY.....	94
	PUBLISH PAPERS.....	97



LIST OF TABLES

Tables	Pages
1.1 Scientists and Nobel Prize in superconductivity area.....	4
5.1 The atomic percentage of specimen with $x=0.05$ Gd_2O_3 according to spectrum.....	61
5.2 The atomic percentage of specimen with $x=0.05$ Eu_2O_3 according to spectrum.....	62
5.3 The atomic percentage of specimen with $x=0.05$ Ce_2O_3 according to spectrum.....	64
5.4 Physical data of $(Bi_{1.6}Pb_{0.4})Sr_2Ca_2Cu_3O_{10}$ specimens Gd_2O_3	68
5.5 Physical data of $(Bi_{1.6}Pb_{0.4})Sr_2Ca_2Cu_3O_{10}$ specimens Eu_2O_3	71
5.6 Physical data of $(Bi_{1.6}Pb_{0.4})Sr_2Ca_2Cu_3O_{10}$ specimens Ce_2O_3	74



LIST OF FIGURES

Figures	Pages
1.1 Tendency of increasing of critical temperatures, T_C from 1910 until 1990.....	3
1.2 Qualitative behavior of resistivity (ρ) as a function of the temperature, T . (a) Normal conductor. (b) Superconductor.....	6
1.3 (a) Field distribution in the normally conducting with a homogeneous external magnetic field, H_e , (b) Distribution of the magnetic field after switching off the external magnetic field, H_e	8
1.4 Field distribution for (a) the normally conducting state with a homogenous external magnetic field, (b) In the superconducting state with a homogenous external magnetic field, (c) In the superconducting state with a external magnetic field while it is switched off.....	9
1.5 The crystal structure of LaFeAsO.....	10
2.1 Applied magnetic field in normal metal.....	14
2.2 Schematic phase diagram illustrating normal and superconducting regions of Type I superconductor.....	15
2.3 Magnetization versus applied magnetic field for a Type II superconductors.....	16
2.4 Type II superconductors $\langle B \rangle$ denotes the average magnetic field in the mixed state.....	16
2.5 Formation of Cooper pair. The two electrons are locked together resulting in virtual exchange of phonons and travel through the lattice.....	18
4.1 Graph of temperature ($^{\circ}\text{C}$) versus time for furnace heat treatment.....	42
4.2 Flow chart for heat treatment system for addition nanoparticulates.....	43
5.1 Spectrum at four areas for sample added Gd_2O_3 with $x=0.05$	61
5.2 Spectrum at four areas for sample added Eu_2O_3 with $x=0.05$	63
5.3 Spectrum at four areas for sample added Ce_2O_3 with $x=0.05$	64
5.4 XRD patterns for the (Bi, Pb)-2223, $0.00 \leq x \leq 0.05$ nanoparticulate Gd_2O_3	66



5.5	Volume percentage of 2223 high T_C -phase as a function of Gd_2O_3 addition for all specimens.....	68
5.6	XRD patterns for the (Bi, Pb)-2223, $0.00 \leq x \leq 0.05$ nanoparticulate Eu_2O_3	70
5.7	Volume percentage of 2223 high T_C -phase as a function of Eu_2O_3 addition for all specimens.....	72
5.8	XRD patterns for the (Bi, Pb)-2223, $0.00 \leq x \leq 0.05$ nanoparticulate Ce_2O_3	73
5.9	Volume percentage of 2223 high T_C -phase as a function of Ce_2O_3 addition for all specimens.....	75
5.10	$(Bi_{1.6} Pb_{0.4}) Sr_2 Ca_2 Cu_3 O_{10}$ samples resistance as a function of temperature for various concentration of Gd_2O_3	77
5.11	Normalised temperature dependence of the derivative of the resistance versus temperature for Gd_2O_3 addition on Bi-2223.....	78
5.12	$(Bi_{1.6} Pb_{0.4}) Sr_2 Ca_2 Cu_3 O_{10}$ samples resistance as a function of temperature for various concentration of Eu_2O_3	80
5.13	Normalised temperature dependence of the derivative of the resistance versus temperature for Eu_2O_3 addition on Bi-2223.....	80
5.14	$(Bi_{1.6} Pb_{0.4}) Sr_2 Ca_2 Cu_3 O_{10}$ samples resistance as a function of temperature for various concentration of Ce_2O_3	82
5.15	Normalised temperature dependence of the derivative of the resistance versus temperature for Ce_2O_3 addition on Bi-2223.....	83
5.16	AC susceptibility versus at different ac fields and frequency $f=333.3Hz$ for pure sample.....	88
5.17	AC susceptibility versus at different ac fields and frequency $f=333.3Hz$ for sample with $x=0.005 Gd_2O_3$	89
5.18	AC susceptibility versus at different ac fields and frequency $f=333.3Hz$ for sample with $x=0.01 Gd_2O_3$	89
5.19	AC susceptibility versus at different ac fields and frequency $f=333.3Hz$ for sample with $x=0.02 Gd_2O_3$	90



5.20 AC susceptibility versus at different ac fields and frequency $f=333.3\text{Hz}$ for
sample with $x=0.05 \text{ Gd}_2\text{O}_3$90



LIST OF PLATES

Plates	Pages
4.1 Carbolite tube furnace	40
4.2 Scanning Electron Microscopy	45
4.3 X-ray Diffraction machine	46
4.4 Resistometer system	47
4.5 AC susceptometer	51
5.1 SEM micrographs of the $(\text{Bi}_{1.6}\text{Pb}_{0.4})\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10} + x\text{Gd}_2\text{O}_3$ specimens after the final stage of heat treatment, (a) $x=0.00$ (b) $x=0.005$ (c) $x=0.01$ (d) $x=0.02$ (e) $x=0.03$ (f) $x=0.05$	54
5.2 SEM micrographs of the $(\text{Bi}_{1.6}\text{Pb}_{0.4})\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10} + x\text{Eu}_2\text{O}_3$ specimens after the final stage of heat treatment, (a) $x=0.00$ (b) $x=0.005$ (c) $x=0.01$ (d) $x=0.02$ (e) $x=0.03$ (f) $x=0.05$	57
5.3 SEM micrographs of the $(\text{Bi}_{1.6}\text{Pb}_{0.4})\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10} + x\text{Ce}_2\text{O}_3$ specimens after the final stage of heat treatment, (a) $x=0.00$ (b) $x=0.005$ (c) $x=0.01$ (d) $x=0.02$ (e) $x=0.03$ (f) $x=0.05$	59



LIST OF SYMBOLS

T	Temperature
T_C	Critical temperature
$T_{C(\text{on})}$	Onset critical temperature
$T_{C(R=0)}$	Zero resistance temperature
HTS	High T_C superconductor
BCS theory	Bardeen, Cooper and Schrieffer theory
BSCCO	Bi-Sr-Ca-Cu-O superconducting system
Bi(2212)	Family member in $\text{Bi}_2\text{Sr}_2\text{Ca}_n\text{Cu}_{n+1}\text{O}_{6-2n}$, $n=1$
Bi(2223)	Family member in $\text{Bi}_2\text{Sr}_2\text{Ca}_n\text{Cu}_{n+1}\text{O}_{6-2n}$, $n=2$
XRD	X-ray diffraction
SEM	Scanning Electron Microscopy
H	Applied magnetic field
H_e	External magnetic field
M	Magnetization
a, b, c	Lattice parameters
χ	Susceptibility
χ'	Real part of susceptibility
χ''	Imaginary part of susceptibility
AC	Alternating Current
V	Sample volume
\mathbf{d}_{hkl}	Reciprocal d vector
hkl	Miller indices





CHAPTER 1

INTRODUCTION

1.1 What is Superconductivity?

Superconductors are materials that have no resistance to the flow of electricity, are one of the last great frontiers of scientific discovery. Not only have the limits of superconductivity has not yet been reached, but the theories that explain superconductivity behavior seem to be constantly under review. In 1911 superconductivity was first observed in mercury (Hg) by Dutch physicist Heike Kamerlingh Onnes. When he cooled it to the temperature of liquid helium, 4 K (-452 F, -269 C), its resistance suddenly disappeared. The Kelvin scale represents an "absolute" scale of temperature. Therefore, it was necessary for Onnes to come within four degrees of the coldest temperature that is theoretically attainable to witness the phenomenon of superconductivity. Later, in 1913, he won a Nobel Prize in physics for his research in this area [Kristiana F, et al ; 2004].

In 1913, the element lead (Pb) was discovered to be superconducting at 7.2 K, this record was broken after 17 years with the element niobium (Nb) with T_C of 9.2 K. later the compounding Nb-Ti alloy was discovered to be superconducting. Among the compounds Nb with other elements, Nb₃Ge had the highest T_C of 22.3 K. The discovery of metals and alloys with zero resistance at low temperatures is an interesting phenomena and has wide applications for the future.



The first widely-accepted theoretical understanding of superconductivity was advanced in 1957 by American physicists John Bardeen, Leon Cooper, and John Schrieffer. Their theories of Superconductivity, known as the BCS theory, derived from the first letter of each man's last name - and won them a Nobel prize in 1972. The mathematically-complex BCS theory explained superconductivity at temperatures close to absolute zero for elements and simple alloys. The BCS theory describes superconductivity in low temperature metals such as mercury, based on an attractive interaction between electrons due to their coupling with phonon. However, at higher temperatures and with different superconductor systems, the BCS theory has subsequently become inadequate to fully explain how superconductivity is occurring. [Tinkham, et al; 1996]

Then in 1986, a truly breakthrough discovery was made in the field of superconductivity. Alex Müller and Georg Bednorz, researchers at the IBM Research Laboratory in Rüschlikon, Switzerland, created a brittle ceramic compound that superconductor at the highest temperature then known: 30 K. What made this discovery so remarkable was that ceramics are normally insulators. They don't conduct electricity well at all. So, researchers had not considered them as possible high-temperature superconductor candidates. The Lanthanum, Barium, Copper and Oxygen compound that Müller and Bednorz synthesized, behaved in a not-as-yet-understood way. It was later found that tiny amounts of this material were actually superconducting at 58 K, due to a small amount of lead having been added as a calibration standard - making the discovery even more noteworthy.

