

## **UNIVERSITI PUTRA MALAYSIA**

## MECHANICAL PROPERTIES OF THE AS-CAST QUARTZ PARTICULATE REINFORCED LM6 ALLOY MATRIX COMPOSITIES

M. SAYUTI.

FK 2005 15



## MECHANICAL PROPERTIES OF THE AS-CAST QUARTZ PARTICULATE REINFORCED LM6 ALLOY MATRIX COMPOSITES

By

M. SAYUTI

Thesis Submitted to the School of Graduate Studies, Universiti Putra Malaysia In Fulfilment of the Requirements for the Degree of Master of Science

October 2005



# In the Memory of

My Father, Allahyarham Fadhil Aziz
And
Allahyarham Saputra Zamani, Afzal Zikri

And

# Special Dedication to

My Mother, H. Cut Nurlaila
My Wife Malahayati
And
My Daughter, Nyak Intan Fazilati and Nyak Qurratu Aini

M. Sayuti 2005.



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of the requirement for the degree of Master of Science

## MECHANICAL PROPERTIES OF THE AS-CAST QUARTZ PARTICULATE REINFORCED LM6 ALLOY MATRIX COMPOSITES

By

#### M. SAYUTI

#### October 2005

Chairman : Associate Professor Shamsuddin Sulaiman, PhD

Faculty : Engineering

Metal matrix composites are engineered materials combine two or more materials, one of which is a metal, where the tailored properties can be attained by systematic combination of different constituents. A variety of methods available for producing these advanced materials includes the conventional casting process which is considered as the easiest processing technique. Preparation of these composite materials by foundry technology have the unique benefit of near-net shape fabrication in a simple and cost effective manner. Besides, casting processes lend themselves to manufacture large number of complex shaped components of composites at a faster rate required by the automotive, transportation, sports and other consumer oriented industries. In this study, quartz-silicon dioxide particulate reinforced LM6 alloy matrix composites were fabricated by carbon dioxide sand molding process by varying the particulate addition by volume fraction on percentage basis. Tensile and hardness tests and scanning electron microscopic studies were conducted to determine the maximum load, tensile strength, modulus of elasticity and



fracture surface analysis to characterize the morphological aspects of the test samples after tensile testing. Hardness values are measured for the quartz particulate reinforced LM6 alloy composites and it has been found that it gradually increases with increased addition of the reinforcement phase. The tensile strength of the composites decreases with the increase in addition of quartz particulate. In addition, particulate-matrix bonding and interface studies have been conducted to understand the mechanical behavior of the processed composite materials and it were well supported by the fractographs taken by the scanning electron microscope. The fractographs taken after the tensile test illustrates the particle pullout from the matrix due to lack of bonding and load deformation characteristic mechanism.



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Master Sains

## SIFAT MEKANIKAL BAGI ZARAHAN AS-CAST QUARZA YANG DIPERKUAT LM6 ALOI MATRIK KOMPOSIT

Oleh

#### M. SAYUTI

#### Oktober 2005

Pengerusi : Profesor Madya Shamsuddin Sulaiman, PhD

Fakulti : Kejuruteraan

Besi matrik komposit merupakan bahan kombinasi kejuteraan dua atau lebih bahan, salah satu dari padanya adalah logam, dimana kandungan yang dibuat boleh dicapai dengan kombinasi sistematik pelbagai bahan. Pelbagai kaedah yang sedia ada untuk mencipta bahan termaju ini, termasuk proses acuan konvensional yang dianggap sebagai teknik/proses yang paling mudah. Penyediakan bahan komposit ini dengan teknologi peleburan mempunyai kebaikan unik dengan bentuk fabrikasi "near-net" yang mudah dan jimat, selain itu proses acuan membantu dengan sendiri untuk mengeluarkan komponent berbentuk komplek yang besar komposit pada tahap yang cepat yang diperlukan oleh pihak automotif, pengangkutan, sukan dan lain-lain industri yang tumpukan pada cita rasa pengguna. Dalam kajian ini, quarza-zarahan silikon dioksida yang dikukuhkan dengan komposit matrik LM6 aloi bertetulang di fabrikasikan dengan proses pengacuan pasir karbon dioksida dengan mengubah campuran (zarahan) dengan kandungan berpandukan pada peratusan. Ujian tegangan dan ujian kekerasan serta mikroskop electron



imbasan telah dilaksanakan bagi menentukan berat masimum, kekuatan tegangan, modulus kekenyalan dan setelah ujian tarikan, dilakukan analisis permukaan patah untuk mengenal pasti ciri-ciri morfologi sample ujian. Nilai kekerasan bagi komposit aloi LM6 diperkuat zarahan kuarsa dan dapat disimpulkan bahawa, ia berkurangan dengan campuran bertambah dengan fasa penguatan. Kekuatan tegangan komposit berkurangan dengan pertambahan zarahan kuarza. Sebagai tambahan ikatan matrik dan kajian antara muka telah dijalankan bagi memahami proses kelakuan bahan mekanikal komposit dan ia telah di sokong oleh fraktograf yang diambil dengan mikroskop electron imbasan. Fraktograf yang diambil selepas ujian tegangan menunjukkan penarikan zarahan dari matriks, oleh kerana kekurangan ikatan dan mekanisme ubah bentuk beban.



#### **ACKNOWLEDGMENTS**

In the Name of Allah, Most Gracious, Most Merciful

First of all, I would like to express my sincere gratitude and deep thanks to my supervisor Associate Professor Dr. Shamsuddin Sulaiman and co-supervisor Prof. Dr. Abdel Magid Hamouda for their kind assistance, support, advice, encouragement, and suggestions for this work and during the preparation this entire thesis.

Furthermore, I would like to take this opportunity to show my deepest appreciation and gratitude to Dr. Hasan Yudie Sastra for his advice, valuable suggestion, and comments given by him time to time.

Besides, I would like to express my deep gratitude and sincere thanks to my colleague Mr Thoguluva Raghavan Vijayaram, full-time PhD Research Scholar in Department of Mechanical and Manufacturing Engineering Universiti Putra Malaysia and once again thank him for his consistent help and encouragement

I would like to convey my sincere thanks to Mr Saifuddin Ahmad, Technician of foundry lab for his valuable assistance and efforts given during the melting and pouring of composite castings.

Lastly but not least, to my wife, Malahayati, My Mother, Hj. Cut Nurlaila, my Daughter Nyak Intan Fazilati and Nyak Qurratu Aini for their continuous love, support and encouragement to complete my project thesis.

I convey my thanks to all of my colleagues, friends, housemate and UPM support staff.

M. SAYUTI



I certify that an Examination Committee met on 7<sup>th</sup> October 2005 to conduct the final examination of M. Sayuti on his Master of Science thesis entitled "Mechanical Properties of the As-cast Quartz Particulate Reinforced LM6 Alloy Matrix Composites" in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulation 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

### Ir. Barkawi Sahari, PhD

Professor Faculty of Engineering Universiti Putra Malaysia (Chairman)

### Ir. Mohammad Sapuan Salit, PhD

Associate Professor Faculty of Engineering Universiti Putra Malaysia (Member)

## Wong Shaw Voon, PhD

Associate Professor Faculty of Engineering Universiti Putra Malaysia (Member)

#### Ahmad Fauzi Mohd Noor, PhD

Associate Professor Faculty of Engineering Universiti Sains Malaysia (Independent Examiner)

ZAKARIAH ABDUL RASHID, PhD.

Professor/Deputy Dean School of Graduate Studies Universiti Putra Malaysia

Date:

27 DEC 2005



This thesis submitted to the senate of Universiti Putra Malaysia and has been accepted as fulfillment of requirement for the degree of Master of Science. The members of the Supervisory Committee are as follows:

## Shamsuddin Sulaiman, PhD

Associate Professor Faculty of Engineering Universiti Putra Malaysia (Chairman)

## Abdel Magid Hamouda, PhD

Professor Faculty of Engineering Universiti Putra Malaysia (Member)

## Hasan Yudie Sastra, PhD

Lecturer Faculty of Engineering Universiti Putra Malaysia (Member)

AINI IDERIS, PhD

Professor/Dean School of Graduate Studies Universiti Putra Malaysia

Date:

12 JAN 2006



## **DECLARATION**

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.

M. SAYUTI

Date: 23/11/2005

## LIST OF TABLES

Table	Page
2.1. List of common matrix materials used in composite application	22
2.2. Properties and application of MMC	28
2.3. The mechanical, thermal and electrical properties of LM6	32
2.4. Composition of LM6 (%)	33
2.5. The chemical composition of matrix alloy	33
2.6. LM6 chemical composition	34
2.7. Properties of S <sub>i</sub> O <sub>2</sub>	35
3.1. The weight ratio of S <sub>i</sub> O <sub>2</sub> into Al	53
4.1. Tensile properties of aluminum reinforced quartz particulate	66
4.2. The average result of Al+S <sub>i</sub> O <sub>2</sub> tensile test	70
4.3. Hardness test with varying % weight fraction of quartz	72



## LIST OF FIGURES

Figure	Page
2.1. Effect of particle volume fraction and size on the hardness	
of L6/Al <sub>2</sub> O <sub>3</sub> composite.	13
2.2. Ultimate tensile strength as a function of the Al2O3	
content and size	14
2.3. The relationship between Vicker's hardness and the volume	
percentage of the S <sub>i</sub> O <sub>2</sub> particles	15
2.4. Effect of S <sub>i</sub> O <sub>2</sub> particles content on the split tensile strength	15
2.5. Effect of reinforcement content on the hardness of Al-SiC	
composites	16
2.6. Effect of SiC particulates on the S-N behaviour of the	
specimens	17
2.7. The variation of hardness with Al2O3 particle content and size	18
2.8. Component of typical sand mould (drag top view)	38
2.9. Component of typical sand mould (side view)	38
3.1. Flow chart describes the plan to carry out the thesis work	42
3.2. Flow chart describes the composite fabrication process	43
3.3. Fluka quartz container	44
3.4. LM6 aluminium-silicon alloy ingots	45
3.5. Pattern for riser, sprue, basin and runner	47
3.6. Pattern	48
3.7. Plan view of mould wall	49
3.8. Tensile specimens as ASTM standards	56
3.9. Specimen before test	57
3.10. Specimen after test	58
3.11. Instron 8500 testing machine	60
4.1. Stress-strain curve of quartz particulate	67



4.2. Graph plot of tensile strength VS volume fraction of S <sub>i</sub> O <sub>2</sub>	68
4.3. Graph plot of young's modulus VS volume fraction of S <sub>i</sub> O <sub>2</sub>	68
4.4. Average tensile strength versus volume fraction of S <sub>i</sub> O <sub>2</sub>	71
4.5. Average young modulus versus volume fraction of S <sub>i</sub> O <sub>2</sub>	71
4.6. Hardness Rockwell VS quartz particulate addition	73
4.7. Fractograph of 5% S <sub>i</sub> O <sub>2</sub> particulate reinforced in S <sub>i</sub> O <sub>2</sub> -LM6 alloy	
matrix composite at 250X magnification by SEM after tensile test.	76
4.8. Fractograph of 10% S <sub>i</sub> O <sub>2</sub> particulate reinforced in S <sub>i</sub> O <sub>2</sub> -LM6 alloy	
matrix composite at 100X magnification by SEM after tensile test.	77
4.9. Fractograph of 15% S <sub>i</sub> O <sub>2</sub> particulate reinforced in S <sub>i</sub> O <sub>2</sub> -LM6 alloy	
matrix composite at 250X magnification by SEM after tensile test.	77
4.10 Fractograph of 20% S <sub>i</sub> O <sub>2</sub> particulate reinforced in S <sub>i</sub> O <sub>2</sub> -LM6 alloy	
matrix composite at 100X magnification by SEM after tensile test.	78
4.11. Fractograph of 25% S <sub>i</sub> O <sub>2</sub> particulate reinforced in S <sub>i</sub> O <sub>2</sub> -LM6	
alloy matrix composite at 250X magnification by SEM after	
tensile test.	78
4.12. Fractograph of 30% S <sub>i</sub> O <sub>2</sub> particulate reinforced in S <sub>i</sub> O <sub>2</sub> -LM6 alloy	
matrix composite at 250X magnification by SEM after tensile test	79

## LIST OF ABBREVIATIONS

## ASTM - American Society for Testing and Materials

Al – Aluminum

A - length of reduce section (mm)

B - length of grip section (mm)

C - width of grip section (mm)

C - Carbon

Cu - Copper

G – gage length (mm)

L – overall length (mm)

Mn - Manganese

P - Phosphorus

R - radius of fillet (mm)

S - Sulfur

T - Ton

Si - Silicone

 $Z_n - Zink$ 

V - volume (cc)

W - width (mm)

m - mass (kg)

t – thickness (mm)

 $\rho$  - density (gr/cm<sup>3</sup>)

MPa - Mega Pascal

kN - kilo Newton

MMC - metal matrix composite

SEM – scanning electron microscope

S<sub>i</sub>O<sub>2</sub> - silicon dioxide (quartz)

LM6 - Type of aluminium

μm – micrometer

v<sub>c</sub> - Volume fraction of composite (%)

v<sub>f</sub> - Volume fraction of fiber (%)

v<sub>m</sub> - Volume fraction of matrix (%)

 $\rho_c$  - Density of composite (gr/cm<sup>3</sup>)

 $\rho_f$  - Density of fiber (gr/cm<sup>3</sup>)

 $\rho_m$  - Density of matrix (gr/cm<sup>3</sup>)

## TABLE OF CONTENTS

DEDICATION ABSTRACT ABSTRAK ACKNOWLEDGMENTS APPROVAL DECLARATION LIST OF TABLE LIST OF FIGURE LIST OF ABBREVIATIONS			
СНА	APTER		
1.	INTRODUCTION	1	
	1.1. Background	1	
	1.2. Problem statement	5	
	1.3. Objective of research	5	
	1.3. Scope and limitation	6	
	1.2. Thesis layout	7	
2.	LITERATURE REVIEW	8	
	2.1. General	8	
	2.2. Metal matrix composite (MMC)	11	
	2.3. Classifications of composite	20	
	2.4. Significance of composite	23	
	2.5. Matrix/matrices	23	
	2.6. Reinforce phase	24	
	2.6.1. Factor affecting reinforcement	24	
	2.6.2. Particulate reinforcement	26	
	2.7. Application of metal matrix coposites	27	
	2.8. Materials selected for processing composite	30	
	2.8. 1. LM6 aluminum-115 silicon alloy 2.8.2. Silicon dioxide (S <sub>i</sub> O <sub>2</sub> )	31	
	2.8.3. Sodium silicate (CO <sub>2</sub> Process)	34 36	
	2.8.4. Pattern	36	
	2.8.9. CO <sub>2</sub> Sand moulds	37	
	2.9. Fracture surface morphology	39	
	2.10. Conclusion	39	
		J)	



3.	KES.	EARCH METHODOLOGY	41
	3.1.1	Material description for processing MMCs	44
	3.2. A	Analysis procedure	45
	3	.2.1. Preparation of specimen	45
	3	.2.2. Preparation of product pattern	46
	3	.2.3(i). Procedure to make product pattern	46
	3	.2.3(ii). Preparation of pouring basin, sprue, well base,	
		runners, ingates, and risers	47
	3	.2.3(iii). Mould wall	48
	3.3. I	Preparation of molding sand mixture	49
		Preparation of cope	50
		Preparation of drag	51
		Production method of metal matrix composite materials	51
		3.6.1. Fabrication process	52
		3.6.2. Characterization of silica	54
		3.6.3. Melting and casting	54
		Testing description	55
		3.7.1. Tensile Test of the prepared samples	55
	3.8.	Festing procedure	58
	3.9. Hardness measurement		60
	3.10.	Fracture surface analysis	60
		3.10.1. Preparation of specimen for SEM test	61
4.	RESULT AND DISCUSSIONS		
	4.1	Introduction	<b>65</b>
	4.2	Tensile test observation and data generation	65
	4.3	Hardness test	72
	4.4	Observation and analysis of the fracture surface of the	
		Test specimen by SEM after tensile testing	74
_	CON	ICI HOLONG AND DECOMMEND ATTOM	00
5.		CLUSIONS AND RECOMMENDATION	80
	5.1	Conclusions	80
	5.2	Recommendations	81
REF	FEREN	CES	83
RIA	DATA	OF THE AUTHOR	86



#### **CHAPTER 1**

#### INTRODUCTION

#### 1.1 Background

Industrial technology is growing at a very rapid rate and consequently there is an increasing demand and need for new materials. The metal-non metal composites represent a class of materials which can with stand high temperature and pressure besides its resistance to radiation effects and chemical reactivity. Metal matrix composites (MMC) are composed of an element or alloy matrix in which a second phase is embedded and distributed to achieve some property improvement. Based on the size, shape and amount of the second phase, the composite properties of the varies. Particulate reinforced composites, often called as discontinuously reinforced metal matrix composites, constitute 5 - 20 % of these new advanced materials. The microstructure of the processed composites influences and have a great effect on the mechanical properties. Generally, increasing the volume fraction of the second phase (reinforcement phase) in the matrix leads to an increased stiffness, yield strength and ultimate tensile strength. But the low ductility of particulate reinforced MMCs is the major drawback that prevents their usage as structural components in some applications [Rizkalla and Abdul.W, 1997]. Miller and Humpherys [1990] have carried out a detailed investigation on the strengthening mechanism of composites. They have found that the particle size and its volume fraction in metal matrix composites influences the generation of



dislocations due to thermal mismatch and as well as the effect influenced by the developed residual and internal stresses. The researchers have predicted that the dislocation density is directly proportional to the volume fraction and also due to the amount of mismatch. The resulting strengthening effect (quench strength) is proportional to the square root of the dislocation density. Consequently, this effect would be significant for fine particles and for higher volume fractions. Recent studies have shown that the matrix microstructure has a clear effect on the fracture details of the tested specimen.

Metal matrix composites have outstanding benefits due to the combined metallic and ceramic properties, thereby yielding improved physical and mechanical properties. Among the various types of MMCs, particulate-reinforced composites are the most versatile and economical one [Sharma et al., 1997].

During the past 40 years, materials design has shifted emphasis to pursue light weight, environment friendliness, low cost, quality, and performance materials. Parallel to this trend, metal-matrix composites have been attracting growing interest. MMC attributes include alterations in mechanical behavior (e.g., tensile and compressive properties, creep, notch resistance, and tribology) and physical properties (e.g., intermediate density, thermal expansion, and thermal diffusivity) by the reinforced filler phase. Apart from these advantages, MMCs have limitations on thermal fatigue, thermochemical compatibility, and posses lower transverse creep resistance [Ejofor and Reddy, 1997].



Fabrication of discontinuously reinforced Al-based MMCs can be achieved by standard metallurgical processing methods like powder metallurgy, direct casting, rolling, forging and extrusion, and further the products can be shaped, machined and drilled by using conventional machining facilities. Thus, they can be made available in suitable quantities particularly for automotive applications [Seah et el., 2003].

Composite materials are characterized by good mechanical properties over a wide range of temperature. The choice of the processing method depends on the property requirements, cost factor consideration and future applications prospects [Kaczmar et al., 2000].

Composite materials with a metal or an alloy matrix can be produced either by casting or by powder metallurgy methods. Metal matrix composites (MMC) are considered as potential material candidates for a wide variety of structural application in the transportation, automobile and sport goods manufacturing industries due to the superior range of mechanical properties they possess [Hasyim et al., 2003].

According to Cok [2004], metal matrix composites (MMC) represent a new generation of engineering materials in which a strong ceramic reinforcement is incorporated into a metal matrix to improve its properties including specific strength, specific stiffness, wear resistance, corrosion resistance and elastic modulus. MMCs combine metallic properties of matrix alloys (ductility and



toughness) with ceramic properties of reinforcements (high strength and high modulus), leads to greater strength in shear and compression and higher service-temperature capabilities. Thus, they have significant scientific, technological and commercial importance. During the last decade, because of their improved properties, MMC are being used extensively for high performance applications such as in aircraft engines and more recently in the automotive industries.

Aluminium oxide and silicon carbide powders in the form of fibers and particulates are commonly used as reinforcements in MMCs and the addition of these reinforcements to aluminum alloys has been the subject of a considerable amount of research work. Aluminium oxide and silicon carbide reinforced aluminum alloy matrix composites are applied in the automotive and aircraft industries as engine pistons and cylinder heads, where the tribological properties of these material are considered important. Therefore, the development of aluminum matrix composites is receiving considerable emphasis in meeting the requirements of various industries. Incorporation of hard second phase particles in the alloy matrices to produce MMCs has also been reported to be more beneficial and economical [Kok, 2004] due to its high specific strength and corrosion resistance properties. Metal matrix composites are materials that are attractive for a large range of engineering applications.



#### 1.2.Problem statement

In the past, various studies have been carried out on metal matrix composites. SiC, TiC, TaC, WC and B4C are the most commonly used particulates to reinforce metal or alloy matrix or matrices like aluminium or iron, while the study of silicon dioxide reinforcement in LM6 alloy is still rare and scarce. However, very limited studies have been reported and so the information and the data available on the mechanical properties and fracture surface analysis is scarce and hence makes this study a significant one. In this investigation quartz particulate reinforced LM6 alloy matrix composites test samples fabricated and processed by casting method are selected. So in this research work the parameter of different percentage of S<sub>i</sub>O<sub>2</sub> particulate addition in the LM6 alloy matrix is examined to study the mechanical behavior and fracture surface characteristic used tensile testing of the processed specimens.

#### 1.3. Research objectives

The overall objective of this experimental investigation is to study the technical viability of  $S_iO_2$  particulate reinforced LM6 aluminium alloy matrix composites and the specific objectives are as follows:

1. To determine the ultimate tensile strength and modulus of elasticity and hardness of  $S_iO_2$  particulate reinforced LM6 alloy matrix composites.



 To study the morphological features and characteristics of the fracture surfaces of the quartz reinforced LM6 alloy composites subjected to tensile testing by using scanning electron microscope (SEM).

### 1.4. Scope and limitation

In this project, LM6 alloy is used as a matrix material due to its better fluidity and castability. It contains 11-13% silicon as a major alloying element in the aluminium metal. It is an eutectic alloy having the lowest melting point as per the aluminium-silicon equilibrium phase diagram and available at reduced cost in the market. CO<sub>2</sub> process in employed to produce sand moulds for casting S<sub>i</sub>O<sub>2</sub>-particulate reinforced LM6 alloy composites. The advantages of CO<sub>2</sub> sand cast products possess good dampening properties, uniform strength in all directions and cheaper when compared to other manufacturing processes such as forging, welding, and rolling.

In this study, tensile testing and scanning electron microscopy are employed to evaluate the maximum load, young's modulus, tensile strength and to characterize the morphological features of the fracture surfaces in silicon dioxide (quartz) - particulate reinforced LM6 alloy composites after the tensile testing.



### 1.5. Thesis layout

This thesis has been structured into 5 chapters. The first one is the introduction chapter and chapter 2 presents a review of literature that relates to the investigation on the mechanical behavior of SiO<sub>2</sub>-particle reinforced LM6 alloy matrix composites. Chapter 3 presents the description of research methodology. The experimental results on tensile testing of the processed specimen and the fracture surface characteristic features after the tensile testing are presented in chapter 4. For the tensile test and SEM analysis an overall discussion is made and explained in chapter 4. The final conclusions of this study are mentioned in chapter 5 precisely.

