



**UNIVERSITI PUTRA MALAYSIA**

**EFFECTS OF GRAIN REFINEMENT ON THE COOLING RATE, AND  
MICROSTRUCTURAL AND MECHANICAL PROPERTIES OF AL-SI  
SAND CASTINGS**

**LIM YING PIO.**

**FK 2006 16**

**EFFECTS OF GRAIN REFINEMENT ON THE COOLING RATE, AND  
MICROSTRUCTURAL AND MECHANICAL PROPERTIES OF  
Al-Si SAND CASTINGS**

**By**

**LIM YING PIO**

**Thesis submitted to the School of Graduate Studies Universiti Putra Malaysia,  
in Fulfilment of the Requirement for the Degree of Doctor of Philosophy**

**January 2006**



Abstract of dissertation presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Doctor of Philosophy.

**EFFECTS OF GRAIN REFINEMENT ON THE COOLING RATE, AND  
MICROSTRUCTURAL AND MECHANICAL PROPERTIES OF  
Al-Si SAND CASTINGS**

By

**LIM YING PIO**

**January 2006**

**Chairman: Associate Professor Shamsuddin Bin Sulaiman, PhD**

**Faculty : Engineering**

This thesis covers the key areas of numerical simulation of sand casting process to evaluate the runner and gating system of sand mold. The major experimental work is focused on grain refinement and modification of LM6 Al-Si sand casting. The simulation software package used is MAGMAsoft and the sand casting process employed is CO<sub>2</sub> sand casting. The numerical results of MAGMAsoft match qualitatively with the experimental data. This validates the use of MAGMAsoft to simulate sand casting process to assist in mold design and prediction of flow and solidification characteristics.

The implementation of experimental work to ascertain flow and solidification characteristics of sand casting has been performed on a casting designed with varying thickness of different moduli. The casting metal used is LM6 Al-Si alloy. The cooling rate of sand casting has been correlated with the modulus of casting. The mechanical



mechanical properties of hardness and ultimate tensile strength have been correlated with the solidification rate. The secondary dendrites arm spacing (SDAS) is also found to have linear correlation with section modulus. This provides important and useful information to product design of sand casting about how to optimize the section thickness to achieve the desired mechanical properties.

An investigation is carried out to study how to further enhance the mechanical properties of LM6 Al-Si alloy sand casting by adding the commercial grain refiner of Al-5Ti-1B into the melt at different inoculation levels of 0.25, 0.5, 0.75 and 1.0% weight. The results show that 0.5% weight of Al-5Ti-1B grain refiner is the optimal level to grain refine and enhance the mechanical properties of LM6 sand casting. The microstructural analysis shows that grain size is reduced when the casting solidifies with faster cooling rate due to the addition of grain refiner. This renders significant effect to enhance the mechanical properties of the casting. The improvement of grain refinement is quantified by measuring the hardness, ultimate tensile strength (UTS) and elongation (strain) of the cast samples. Inoculation with 0.5% weight of Al-5Ti-1B grain refiner has attained UTS of 167.86 MPa, maximum hardness of 65.6 Rockwell and fracture strain of 0.0314. A further investigation has been carried out to add 0.5% weight of Al-10Sr and 0.5% weight of Al-5Ti-1B into the melt to cast the same part. Similar mechanical tests and microstructural analysis are performed to study the combination effect of strontium, titanium and boron on LM6 sand castings. It is discovered that the ultimate tensile strength of the castings is further improved



to 174.46 MPa and the morphology has been modified. However, the hardness of Sr-modified LM6 sand casting only achieves a maximum value of 63.34 Rockwell which is not a significant improvement. Modification of LM6 by strontium only alters the morphology of the silicon eutectic to be more fibrous instead of acicular so that the structure would not be brittle relative to unmodified structure and it is found that the ductility after modification achieves a fracture strain of 0.032 which is higher than the 0.0267 of unmodified LM6. The cooling curve shows that the solidification is dramatically transformed to eutectic solidification at temperature around 540 °C. This mixture of grain refiner and modifier is termed “*hybrid modifier*” by the author.



Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk Ijazah Doktor Falsafah.

**KESAN PENGHALUSAN BUTIRAN KE ATAS KADAR PEMBEKUAN DAN  
SIFAT-SIFAT MIKROSTRUKTUR DAN MEKANIKAL  
TUANGAN PASIR Al-Si**

Oleh

**LIM YING PIO**

**January 2006**

---

**Pengerusi : Professor Madya Shamsuddin Bin Sulaiman, PhD**

**Fakulti : Kejuruteraan**

Tesis ini merangkumi bidang simulasi numerikal untuk proses penuangan acuan pasir untuk menilai sistem larian dan get bagi acuan pasir. Ujikaji yang diberi tumpuan utama ialah penghalusan saiz butiran mikrostruktur dan modifikasi mikrostruktur bagi produk tuangan acuan pasir LM6 Al-Si. Perisian simulasi yang digunakan ialah MAGMAsoft dan proses penuangan acuan pasir ialah proses karbon dioksida. Keputusan numerikal MAGMAsoft dibandingkan secara kualitatif dengan data ujikaji menunjukkan mereka sepadan. Ini mengesahkan penggunaan MAGMAsoft untuk simulasi proses penuangan acuan pasir dapat membantu rekabentuk acuan dan meramalkan sifat pengaliran dan pembekuan proses tersebut.

Pelaksanaan kerja ujikaji untuk mengkaji proses pengaliran dan pembekuan acuan pasir telah dilakukan ke atas satu tuangan yang direkabentuk dengan ketebalan yang berbeza, iaitu modulus setiap keratannya berlainan. Bahan logam untuk tuangan

ialah aloi aluminium-silikon LM6. Kadar pembekuan tuangan telah dihubungkan dengan modulus keratannya. Sifat mekanikal seperti kekerasan dan kekuatan tegangan muktamad juga dihubungkan dengan kadar pembekuan. Jarak sekunder antara dendrit (SDAS) juga didapati mempunyai korelasi linear dengan modulus keratan. Ini memberikan maklumat yang penting dan berguna untuk rekabentuk acuan pasir supaya dapat mengoptimumkan modulus keratan demi mencapai sifat mekanikal yang dikehendaki.

Satu kajian telah dijalankan untuk mengkaji bagaimana memperbaiki sifat mekanikal aloi LM6 dalam tuangan acuan pasir secara menambahkan penghalus butiran mikrostruktur Al-5Ti-1B ke dalam peleburan pada peratusan berat 0.25, 0.5, 0.75 dan 1.0. Keputusan ujikaji menunjukkan peratusan berat sebanyak 0.5 Al-5Ti-1B adalah tahap yang optimum untuk menghaluskan saiz butiran mikrostruktur dan memperbaiki sifat mekanikal tuangan LM6. Analisis mikrostruktur menunjukkan saiz butiran mikrostruktur berkurang bila tuangan membeku dengan kadar yang lebih cepat akibat penambahan penghalus butiran mikrostruktur tersebut. Ini memberi kesan yang ketara dalam pembaikan sifat mekanikal tuangan. Penambahbaikan penghalusan saiz butiran mikrostruktur dinyatakan secara pengukuran kekerasan, kekuatan tegangan muktamad (UTS) dan keterikan sampel-sampel yang dihasilkan. Inokulasi dengan 0.5% keberatan Al-5Ti-1B penghalus butiran mencapai UTS 167.86 MPa, kekerasan maksima 65.6 Rockwell dan keterikan patah 0.0314. Penyelidikan lanjut dijalankan dengan menambahkan Al-10Sr dan Al-5Ti-1B

sebanyak 5 peratus keberatan masing-masing ke dalam peleburan untuk membuat tuangan yang sama. Ujian mekanikal dan analisis mikrostruktur yang sama dijalankan untuk mengkaji kesan penggabungan antara strontium, titanium dan boron ke atas tuangan LM6. Adalah didapati kekuatan tegangan muktamadnya meningkat ke 174.46 MPa dan bentuk mikrostrukturnya telah diubah. Walaubagaimanapun, kekerasannya hanya mencapai Nilai maksiam 63.34 Rockwell dan tidak menunjukkan kesan perbaikan yang ketara. Modifikasi LM6 dengan strontium hanya mengubah morfologi eutektik silicon kepada bentuk yang lebih halus dan bukan berbucu tajam supaya strukturnya tidak rapuh jika dibanding dengan structure yang tidak diubah; adalah didapati kelenturan selepas modifikasi mencapai keterikan patah 0.032 yang lebih tinggi daripada 0.0267 yang didapati pada LM6 asal. Graf suhu pembekuan menunjukkan proses pembekuan telah berubah kepada pembekuan eutektik pada suhu kira-kira 540°C. Campuran penghalus butiran mikrostruktur dan pengubah itu dinamakan sebagai "*hybrid modifier*".



## ACKNOWLEDGEMENTS

The author would like to take this opportunity to express his sincere gratitude to the project supervisor Associate Professor Dr. Shamsuddin Sulaiman for his willingness to help carry out the experiments, instructions to use laboratory equipment, supply of relevant materials on the subject matter, thorough checking of my writings, precious advices on necessary amendment and valuable encouragement, inspiration and motivation throughout the project. In fact, his superior supervision is unmatched and indispensable to the success of this project. Similar gratitude is also extended to members of supervisory committee Professor Dr. Abdel Majid Hamouda and Associate Professor Dr. Megat Mohamad Hamdan Megat Ahmad for their valuable feedbacks and discussions on the project's related matters.

The author is also greatly indebted to those who had duly helped in various aspects of the project, especially the technical staff of foundry and laboratory of mechanics of solid. They are Mr. Ahmad Shaifuddin Ismail, Mr. Muhammad Wildan Ilyas b. Mohamed Ghazali and Miss Nora. A sincere gratitude is also extended to Institute of Bioscience, Institute of Advanced Technology Universiti Putra Malaysia (ITMA) and SIRIM Malaysia for using their facilities of optical and scanning electron microscopes.

Thanks are also given to the author's family members for their financial support and encouragement in my study life.




I certify that an Examination Committee has met on 3<sup>rd</sup> January 2006 to conduct the final examination of Lim Ying Pio on his Doctor of Philosophy thesis entitled “Effects of Grain Refinement on the Cooling Rate, and Microstructural and Mechanical Properties of Al-Si Sand Castings” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

**Wong Shaw Voon, PhD**  
Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Ir. Barkawi Sahari, PhD**  
Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Napsiah Ismail, PhD**  
Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Internal Examiner)

**Nabil Bassim, PhD**  
Professor  
Department of Mechanical & Industrial Engineering  
University of Manitoba  
(External Examiner)

  
\_\_\_\_\_  
**HASANAH MOHD. GHAZALI**  
Professor/Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date : **27 MAR 2006**

This thesis submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee are as follows:

**Shamsuddin Bin Sulaiman, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Abdel Majid Hamouda, PhD**

Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)

**Megat Mohamad Hamdan Megat Ahmad, PhD**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)




---

**AINI IDERIS, PhD**  
Professor/Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date : **13 APR 2006**

## DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.



---

**LIM YING PIO**

Date: 28 / 02 / 2006

## TABLE OF CONTENTS

	<b>Page</b>
<b>ABSTRACT</b>	ii
<b>ABSTRAK</b>	v
<b>ACKNOWLEDGEMENTS</b>	viii
<b>APPROVAL</b>	ix
<b>DECLARATION</b>	xi
<b>LIST OF TABLES</b>	xv
<b>LIST OF FIGURES</b>	xvi
<b>LIST OF ABBREVIATIONS</b>	xxiii
<b>CHAPTER</b>	
1 <b>INTRODUCTION</b>	
1.1 Introduction	1-1
1.2 Problem Statements	1-3
1.3 Objectives	1-5
1.4 Thesis layout	1-6
2 <b>THEORETICAL BACKGROUND AND       LITERATURE REVIEW</b>	
2.1 Introduction	2-1
2.2 General aspects of casting process	2-2
2.3 Sand casting process	2-4
2.4 Carbon dioxide sand casting	2-5
2.5 Metal delivery system	2-8
2.5.1 Gating system	2-9
2.5.2 Feeding system	2-12
2.6 Thermodynamics of solidification	2-14
2.6.1 The undercooling requirement	2-14
2.6.2 Kinetic undercooling	2-15
2.6.3 Curvature undercooling	2-17
2.6.4 Thermal undercooling	2-18
2.6.5 Constitutional undercooling	2-18
2.7 Development of cast structure	2-19
2.7.1 Nucleation	2-20
2.7.2 Grain growth	2-21
2.8 Eutectic and peritectic solidifications	2-22
2.8.1 Eutectic solidification	2-23
2.8.2 Peritectic solidification	2-24
2.9 Solidification of aluminium-silicon alloys	2-24
2.10 Grain refinement of Al-Si alloys	2-27
2.10.1 Phase diagram theories	2-29
2.10.2 Particle theories	2-30



	2.10.3 Theories based on both phase diagram and particles	2-31
	2.10.4 Contemporary review of researches on mechanism of grain refinement	2-32
	2.11 Modification of Al-Si alloys	2-37
	2.12 Contemporary review of researches on numerical simulation of casting processes	2-38
	2.13 Conclusion and summary	2-43
<b>3</b>	<b>METHODOLOGY</b>	
	3.1 Methodology of Casting Simulation with MAGMAsoft	3-1
	3.2 Three-dimensional modeling of the Mold System	3-3
	3.3 Setting Simulation Parameters	3-5
	3.4 Experimental Procedure	3-6
	3.4.1 Mould Design and Construction	3-7
	3.4.2 Mould materials and molding process	3-8
	3.4.3 Melting process and cast material	3-8
	3.4.4 Temperature measurement	3-9
	3.4.5 Rate of solidification	3-10
	3.4.6 Types of specimens	3-10
	3.5 Hardness testing	3-11
	3.6 Ultimate tensile strength testing	3-11
	3.6.1 INSTRON 8500	3-12
	3.6.2 Gunt Hamburg Universal Material Tester	3-12
	3.7 Micrographs preparation	3-14
	3.8 Method of measurement for SDAS	3-15
<b>4</b>	<b>RESULTS FOR NUMERICAL SIMULATION</b>	
	4.1 Results and discussions for numerical simulation	4-1
	4.1.2 Mold filling	4-1
	4.1.3 Solidification	4-3
	4.2 Conclusions	4-4
<b>5</b>	<b>RESULTS FOR EXPERIMENTAL WORK</b>	
	5.1 Preliminary study of LM6 sand casting	5-1
	5.1.1 Cooling curve	5-1
	5.1.2 Hardness	5-3
	5.1.3 Metallurgical studies based on microstructural analysis	5-4
	5.2 Grain refinement of LM6 Al-Si alloy sand castings	5-5
	5.2.1 Cooling curve and solidification rate.	5-6
	5.2.2 Effect of grain refinement on mechanical properties	5-7

## LIST OF TABLES

<b>Tables</b>	<b>Page</b>
1 LM6 chemical compositions (in weight percentage).	3-27
2 Material variables of experiments.	3-27
3 Hardness of LM6 sand casting.	5-50
4 Cooling rates for LM6 sand casting.	5-51
5 Linear correlation equations between cooling rate ( $\epsilon$ , $^{\circ}\text{C/s}$ ) and grain refiner level (GRL,% wt).	5-51
6 UTS of LM6 sand casting for INSTRON 8500 and Gunt Hamburg	5-51
7 Hardness data for grain-refined LM6 sand casting (15T Rockwell Scale).	5-51
8 Linear correlation equations between SDAS ( $\lambda$ , micron) and modulus.	5-51
9 EDS spectrum analysis of original LM6 and 0.5wt% Al5Ti1B grain refined LM6 castings.	5-52
10 Comparison of Sr-Al and Na Modifiers in the Foundry	5-52
11 EDS spectrum analysis of 0.5wt% Al5Ti1B grain refined LM6 and Sr-modified LM6 castings.	5-52
12 Modulus of Elasticity for LM6 sand castings.	5-52

## LIST OF FIGURES

<b>Figures</b>	<b>Page</b>
1 Examples of aluminum alloy sand casting products ( <i>courtesy of Hayes Lemmerz International, Inc.</i> ).	2-45
2 Two forms of mold, (a) open mold ; (b) closed mold.	2-45
3 Schematic illustration of a sand mold, showing various features.	2-46
4 Purging CO <sub>2</sub> into sand mold to cure sodium silicate-sand mixture.	2-46
5 Various sprue base design.	2-47
6 Typical gating system with sprue well and runner extension.	2-48
7 Relation of casting shape factor to minimum effective riser volume expressed as a fraction of casting volume.	2-48
8 Feeding distance relationships for plates.	2-49
9 Kinetic undercooling.	2-50
10 Thermal undercooling.	2-50
11 Schematic region of a phase diagram for a solid solution alloy.	2-51
12 Change of free energy due to the formation of a spherical crystal.	2-51
13 Heterogeneous nucleation of a solid on a nucleating agent.	2-52
14 Schematic illustration of three cast structures of metals solidified in a square mold.	2-52
15 Schematic illustration of three basic types of cast structures.	2-53
16 Thermal equilibrium diagram for two metals forming a eutectic.	2-53
17 The equilibrium diagram involving a peritectic reaction.	2-54



18	Equilibrium phase diagram of Al-Si system.	2-55
19	Three possible eutectic growth morphologies.	2-56
20	Al-Ti phase diagram showing 0.15% Ti as the peritectic concentration.	2-57
21	Effect of Ti:B atomic ratio on DAS.	2-58
22	Macrograph of grain-refined and non-grain refined pure Al.	2-59
23	Interface morphology of the eutectic liquid/solid interface.	2-60
24	Temperature distribution during the filling of the wheel.	2-60
25	Critical areas for feeding due to isolated hot spots.	2-61
26	Boundary conditions for the load stress analysis.	2-61
27	Stress distribution in the wheel under the testing load	2-62
28	No more porosity detected after optimization with additional cooling channels	2-62
29	Stress in the optimized wheel under the test load, reduced by 50%.	2-63
30	Preliminary runner-gating system	2-63
31	Short shot filling test.	2-64
32	Cast thin-walled magnesium hand phone part with macro pore-free microstructure.	2-64
33	Flow chart of MAGMASoft simulation procedure.	3-16
34	Mold systems for M1 (left) and M2 (right) models.	3-16
35	Specific heat ( $C_p$ )	3-17
36	Thermal conductivity ( $k$ )	3-17
37	Density ( $\rho$ )	3-17

38	Molding system design and cast dimensions	3-18
39	Patterns and sand mould	3-18
40	Wood pattern of tensile test piece mold.	3-19
41	Carbon dioxide gas cylinder	3-19
42	Degassing of sand mold	3-20
43	Electrical furnace	3-20
44	Delogger connected with K-type thermocouples to measure and capture real-time temperature profiles	3-21
45	Solidification process of an alloy	3-22
46	Sectional plane on which hardness is tested	3-22
47	INTRON 8500 tensile tester equipped with digital control system	3-23
48	Tensile test specimen for Gunt Hamburg universal tester	3-23
49	Gunt Hamburg Universal Material Tester	3-24
50	The mounting of specimen at the gripping heads	3-24
51	Polishing machine	3-25
52	Optical microscope equipped with imaging system	3-25
53	Scanning electron microscope with EDS system	3-26
54	Illustration of eutectic phase and SDAS. The white phase is $\alpha$ -Al dendrite	3-26
55	20% cavity fill (model M1)	4-6
56	40% cavity fill (model M1)	4-6
57	60% cavity fill (model M1)	4-6
58	90% cavity fill (model M1)	4-6

59	70% cavity fill (model M2)	4-6
60	90% cavity fill (model M2)	4-6
61	Filling time (model M2)	4-7
62	Temperature contour at 100% solidification (model M1)	4-7
63	Temperature contour at 100% solidification (model M2)	4-7
64	Temperature profiles of control points (model M1)	4-7
65	Temperature profiles of control points (model M2)	4-7
66	Cooling curve of original LM6 sand casting for different modulus sections	5-23
67	Hardness vs. section modulus of LM6 sand casting	5-23
68	Linear correlation between hardness and section modulus of LM6 sand casting	5-24
69	LM6 Microstructure of section of modulus 2.25, magnified at 50x	5-24
70	LM6 Microstructure of section of modulus 4.08, magnified at 50x	5-25
71	LM6 Microstructure of section of modulus 6.9, magnified at 50x	5-25
72	LM6 Microstructure of section of modulus 8.96, magnified at 50x	5-26
73	Typical micrograph of unmodified commercial Al-Si alloy	5-26
74	SEM image and EDS analysis of micropore of LM6 sand casting (x50)	5-27
75	Cooling curve of section modulus 2.25 for LM6 sand casting grain-refined with Al-5Ti-1B	5-28
76	Cooling curve of section modulus 4.08 for LM6 sand casting grain-refined with Al-5Ti-1B	5-28

77	Cooling curve of section modulus 6.9 for LM6 sand casting grain-refined with Al-5Ti-1B	5-29
78	Cooling curve of section modulus 8.96 for LM6 sand casting grain-refined with Al-5Ti-1B	5-29
79	Solidification rate of LM6 sand casting grain-refined with Al-5T-1B	5-30
80	Linear correlation between solidification rate ( $^{\circ}\text{C}/\text{s}$ ) and grain refiner level (wt%)	5-30
81	UTS varies with grain refinement level for LM6 sand casting	5-31
82	Hardness varies with grain refinement level for LM6 sand casting	5-31
83	LM6 microstructure grain-refined by 0.25wt% Al-5Ti-1B, modulus 2.25, (x50)	5-32
84	LM6 microstructure grain-refined by 0.25wt% Al-5Ti-1B, modulus 4.08, (x50)	5-32
85	LM6 microstructure grain-refined by 0.25wt% Al-5Ti-1B, modulus 6.9, (x50)	5-33
86	LM6 microstructure grain-refined by 0.25wt% Al-5Ti-1B, modulus 8.96, (x50)	5-33
87	LM6 microstructure grain-refined by 0.5wt% Al-5Ti-1B, modulus 2.25, (x50)	5-34
88	LM6 microstructure grain-refined by 0.5wt% Al-5Ti-1B, modulus 4.08, (x50)	5-34
89	LM6 microstructure grain-refined by 0.5wt% Al-5Ti-1B, modulus 6.90, (x50)	5-35
90	LM6 microstructure grain-refined by 0.5wt% Al-5Ti-1B, modulus 8.96, (x50)	5-35
91	LM6 microstructure grain-refined by 0.75wt% Al-5Ti-1B, modulus 2.25, (x50)	5-36

92	LM6 microstructure grain-refined by 0.75wt% Al-5Ti-1B, modulus 4.08, (x50)	5-36
93	LM6 microstructure grain-refined by 0.75wt% Al-5Ti-1B, modulus 6.9, (x50)	5-37
94	LM6 microstructure grain-refined by 0.75wt% Al-5Ti-1B, modulus 8.96, (x50)	5-37
95	LM6 microstructure grain-refined by 1.0wt% Al-5Ti-1B, modulus 2.25, (x50)	5-38
96	LM6 microstructure grain-refined by 1.0wt% Al-5Ti-1B, modulus 4.08, (x50)	5-38
97	LM6 microstructure grain-refined by 1.0wt% Al-5Ti-1B, modulus 6.9, (x50)	5-39
98	LM6 microstructure grain-refined by 1.0wt% Al-5Ti-1B, modulus 8.96, (x50)	5-39
99	SDAS vs. section modulus for each grain refinement level for LM6 sand casting	5-40
100	Linear correlation between SDAS (micron) and modulus	5-40
101	SEM micrographs of LM6 sand casting (modulus 4.08)	5-41
102	SEM micrographs of 0.5wt% Al-5Ti-1B grain-refined LM6 sand casting (modulus 4.08)	5-41
103	EDS spectrum of original LM6 sand casting (modulus 4.08)	5-42
104	EDS spectrum of 0.5wt% Al-5Ti-1B grain-refined LM6 sand casting (modulus 4.08)	5-42
105	Cooling curve of Sr-modified LM6 sand casting	5-43
106	Cooling curve of 0.5wt% Al-5Ti-1B grain-refined LM6 sand casting	5-43
107	Pre-solidification cooling rates of modified and unmodified LM6	5-44

108	Effect of grain refiner and modifier on hardness	5-44
109	Effect of grain refiner and modifier on UTS	5-45
110	Effect of grain refiner and modifier on strain at fracture	5-45
111	Fracture surfaces of tensile test piece	5-46
112	Microstructures of Sr-modified LM6, modulus 2.25 (x50)	5-46
113	Microstructures of Sr-modified LM6, modulus 4.08, (x50)	5-47
114	Microstructures of Sr-modified LM6, modulus 6.9, (x50)	5-47
115	Microstructures of Sr-modified LM6, modulus 8.96, (x50)	5-48
116	Microstructural characteristics of Sr-modified LM6 sand casting	5-48
117	SDAS of original, grain-refined and Sr-modified LM6 sand castings	5-49
118	EDS spectrum of (0.5wt%Al-5Ti-1B + 0.5wt% Al-10Sr) modified LM6 sand casting	5-49
119	Histogram of modulus of elasticity	5-50
120	Specimen attached with strain gage	5-50

## LIST OF ABBREVIATIONS

$C, C_0$	Alloy composition
$C_v$	Specific heat at constant volume, ( $\text{J.kg}^{-1}.\text{K}^{-1}$ )
$D$	Species diffusivity ( $\text{m}^2.\text{s}^{-1}$ )
$E$	Internal energy ( $\text{J/mole}$ or $\text{J/m}^3$ )
$G$	Gibbs free energy ( $\text{J/mole}$ or $\text{J/m}^3$ )
$H$	Enthalpy ( $\text{J/mole}$ , $\text{J/m}^3$ , $\text{J/kg}$ )
$P$	Pressure (Pa)
$R$	Gas constant ( $\text{J/mol.K}$ )
$T$	Temperature (K or $^{\circ}\text{C}$ )
$T_L$	Liquidus temperature (K)
$T_S$	Solidus temperature (K)
$S$	Entropy ( $\text{J.mol}^{-1}.\text{K}^{-1}$ or $\text{J.m}^{-3}.\text{K}^{-1}$ )
$v$	Velocity (m/s)
$c$	Specific heat ( $\text{J.m}^{-3}.\text{K}^{-1}$ )
$f$	Mass fraction of phase
$g$	Volume fraction of phase
	Gravitational acceleration ( $\text{m.s}^{-2}$ )
$h$	Heat transfer coefficient ( $\text{W.m}^{-2}.\text{K}^{-1}$ )
$k$	Solute partition coefficient; Thermal conductivity ( $\text{W.m}^{-1}.\text{K}^{-1}$ )
$m$	Slope of liquidus line ( $\text{K.wt}\%^{-1}$ )



$n$	Number of atoms (moles)
$t$	time
$V$	volume ( $\text{m}^3$ )
$\Delta G_v$	change in volumetric free energy ( $\text{J}\cdot\text{m}^{-3}$ )
$L, H_f$	latent heat of fusion ( $\text{J}\cdot\text{kg}^{-1}$ )
$\Delta T$	Undercooling (K)
$\Gamma$	Gibbs-Thomson coefficient (m.K)
$\alpha$	Thermal diffusivity ( $\text{m}^2\cdot\text{s}^{-1}$ )
$\beta_T$	Thermal expansion coefficient ( $\text{K}^{-1}$ )
$\mu$	Dynamic viscosity ( $\text{N}\cdot\text{m}^{-2}\cdot\text{s}$ )
$\varepsilon$	Cooling rate (K/s)
$\lambda$	Interphase spacing (m)
$\Omega$	Spatial volume
$\gamma$	Surface tension (N/m)

**Subscript**

$L$	Liquid
$S$	Solid
$f$	Fusion
$k$	Kinetic



# CHAPTER 1

## INTRODUCTION

### 1.1 Introduction

Metal casting is basically a process in which molten metal is poured by gravity or injected with pressure into a mold cavity to produce the desired product. Most of the cast products are in finished goods form which requires minimum level of machining and surface finishing to achieve the desired tolerance and surface quality. The casting process often involves flow which is usually transient and non-isothermal with ongoing solidification as the molten material flows through the mold [1]. Many industrial parts and components are produced by the method of casting, including engine blocks, crankshafts, automotive components, railroad equipment, plumbing fixtures, power tools, very large components for hydraulic turbines and so on [2]. Most of the casting operations are carried out in foundries. Foundry operations involve two major separate activities for the manufacture of casting products. The first activity is pattern and mold making, traditionally performed manually by experienced workers, which now regularly utilize computer-aided design and manufacturing and rapid prototyping techniques in modern manufacturing environment. The approach of advanced manufacturing techniques such as CAE and rapid prototyping is vital to minimizing trial-and-error operations which is time

