



UNIVERSITI PUTRA MALAYSIA

**STRUCTURAL BEHAVIOUR OF PRECAST CONCRETE
SANDWICH PANELS WITH OPENINGS
UNDER AXIAL LOAD**

FARAH NORA AZNIETA BTE ABDUL AZIZ

ITMA 2002 3

**STRUCTURAL BEHAVIOUR OF PRECAST CONCRETE
SANDWICH PANELS WITH OPENINGS
UNDER AXIAL LOAD**

0277-83660

By

FARAH NORA AZNIETA BTE ABDUL AZIZ

**Thesis Submitted to the School of Graduate Studies,
Universiti Putra Malaysia
in Fulfilment of the Requirement for the Degree of Master of Science**

January 2002



*Very grateful to ALLAH for the blessing.....
To my family and everyone involved in my life,
Thank you.....*



Abstract of thesis presented to the Senate of Universiti Putra Malaysia in
fulfilment of the requirement for the degree of Master of Science

**STRUCTURAL BEHAVIOUR OF PRECAST CONCRETE
SANDWICH PANELS WITH OPENINGS
UNDER AXIAL LOAD**

By

FARAH NORA AZNIETA BTE ABDUL AZIZ

January 2002

Chairman: Professor Abang Abdullah Abang Ali, Ir.

Faculty: Institute of Advanced Technology

This research was conducted to study the structural behaviour of precast concrete sandwich panels with opening. Four types of sandwich panels involving panels without opening, panels with door opening, panels with window opening and panels with both door and window opening were studied. The size of the panels was 900mm x 1000mm x 120mm thick. The 120mm thickness consists of two concrete layers with a sandwich insulation layer 40mm thick.

The panels were tested under axial load until failure. During the experiment, the development of cracks was observed and the strain and dial gauges reading recorded. The values of experimental ultimate load for the panel without opening were compared to the theoretical ultimate load by a few researchers. For panels with opening, the experimental ultimate loads were compared to the theoretical equation for panels with opening by Saheb and Desayi. The

theoretical equation used was actually meant to estimate the ultimate load of ordinary reinforced concrete walls with opening. It was used in sandwich panels with the assumption that the total thickness of the panels was equal to the thickness of the concrete layers only.

From the calculations it was found that the theoretical equation by Saheb and Desayi for the ultimate load of ordinary reinforced concrete walls with opening gave very close values to the experimental results for panels with opening. This showed that the ultimate load equation for ordinary reinforced concrete wall with opening by Saheb and Desayi could be used to estimate the ultimate load of sandwich panels with opening. Beside the ultimate load, the lateral deflection and the strain distribution in the reinforcement and concrete surface were also observed and recorded.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Master Sains

**KELAKUAN STUKTUR PANEL APIT KONKRIT
PASANG SIAP DENGAN BUKAAN DI
BAWAH BEBANAN PAKSI**

Oleh

FARAH NORA AZNIETA BTE ABDUL AZIZ

Januari 2002

Pengerusi: Profesor Abang Abdullah Abang Ali, Ir.

Fakulti: Institut Teknologi Maju

Penyelidikan ini dijalankan untuk mengkaji dan mempelajari kelakuan stuktur panel apit konkrit pasang siap dengan bukaan. Terdapat empat jenis stuktur apit konkrit pasang siap di dalam kajian ini; panel tanpa bukaan, panel dengan bukaan pintu, panel dengan bukaan tingkap dan panel dengan bukaan pintu dan tingkap. Saiz setiap panel 900mm x 1000mm x 120mm tebal. Ketebalan 120mm adalah terdiri daripada satu lapisan penebatan yang diapit oleh dua lapisan konkrit pasang siap. Ketebalan tiap-tiap lapisan adalah 40mm.

Stuktur panel ini diuji dibawah beban paksi sehingga gagal. Sepanjang ujikaji, perkembangan retakan diperhatikan dan bacaan tolok dail dan tolok terikan direkodkan. Bagi stuktur panel tanpa bukaan, nilai beban muktamad yang diperolehi daripada ujikaji dibandingkan dengan beban muktamad daripada persamaan teori dari beberapa penyelidik. Bagi stuktur dengan bukaan, nilai

beban muktamad daripada ujikaji dibandingkan dengan nilai beban muktamad daripada persamaan teori bagi panel dengan bukaan. oleh Saheb dan Desayi. Persamaan teori yang digunakan sebenarnya adalah untuk menganggar beban muktamad struktur dinding konkrit tetulang biasa dengan bukaan. Persamaan ini digunakan untuk struktur panel apit konkrit dengan anggapan ketebalan keseluruhan panel adalah bersamaan dengan ketebalan dua lapisan konkrit sahaja.

Daripada pengiraan, didapati persamaan teori oleh Saheb dan Desayi bagi beban muktamad dinding konkrit tetulang biasa dengan bukaan memberikan nilai yang sangat hampir dengan nilai yang diperolehi daripada ujikaji bagi panel dengan bukaan. Ini menunjukkan persamaan beban muktamad bagi dinding konkrit tetulang biasa oleh Saheb dan Desayi boleh digunakan untuk menganggar beban muktamad panel apit konkrit dengan bukaan. Selain beban muktamad, pesongan sisi dan agihan terikan keatas tetulang dan permukaan konkrit juga diperhatikan dan direkodkan.

ACKNOWLEDGEMENTS

In the Name of Allah, The All Mighty.

The author would like to express her gratitude to her supervisor, Profesor Ir. Abang Abdullah Abang Ali for his valuable guidance, suggestions, passion and supervision throughout this research. Also, she extends her gratitude to Prof. Madya Dr. Abdul Aziz Abdul Samad and Dr. Saleh Jaafar for their guidance, comment and help in preparing this thesis.

She also wishes to express her sincere appreciation to Haji Ghazali Haji Said and Encik Halim for their help throughout the experimental work.

Lastly, she dedicates this thesis with grateful thanks to her husband, Mohd Sharif Mohd Kasim, and her son, Muhammad Luqman Hakim, for their love and support. Also to her parents and family for their support and encouragement for her studies.

I certify that an Examination Committee met on 3rd January 2002 to conduct the final examination of Farah Nora Aznieta Bte Abdul Aziz on her Master of Science thesis entitled “Structural Behaviour of Precast Concrete Sandwich Panels with Openings under Axial Load” in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

D N Trika, PhD
Professor,
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Abang Abdullah Abang Ali, Ir ,
Professor,
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Abdul Aziz Abdul Samad, Ph D
Associate Professor,
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Mohd Saleh Jaafar, Ir , Ph D
Associate Professor,
Faculty of Engineering
Universiti Putra Malaysia
(Member)




SHAMSHER MOHAMED RAMADILI, Ph D
Professor
Deputy Dean of Graduate School,
Universiti Putra Malaysia

Date **27 MAR 2002**



This thesis submitted to the Senate of Universiti Putra Malaysia has been accepted as fulfilment of the requirement for the degree of Master of Science.



AINI IDERIS, Ph.D,
Professor/
Dean of Graduate School
Universiti Putra Malaysia.

Date : 09 MAY 2009

DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.



FARAH NORA AZNIETA BTE ABDUL AZIZ

Date: 27 March 2002

TABLE OF CONTENTS

	Page
DEDICATION	ii
ABSTRACT	iii
ABSTRAK	v
ACKNOWLEDGEMENTS	vii
APPROVAL	viii
DECLARATION	x
LIST OF TABLES	xiii
LIST OF FIGURES	xiv
LIST OF NOTATIONS	xviii

CHAPTER

1	INTRODUCTION	1
	1.1 General	1
	1.2 Precast Concrete Sandwich Panel	2
	1.3 Precast Concrete Sandwich Panel With Opening	3
	1.4 Objective	4
2	LITERATURE REVIEW	5
	2.1 Introduction	5
	2.2 Historical Background	6
	2.3 Advantages Of Precast Concrete Sandwich Panel	7
	2.4 Previous Research Work	8
3	METHODOLOGY	25
	3.1 Introduction	25
	3.2 Specimen Design	25
	3.2.1 Precast Concrete Sandwich Panel With Door Opening	26
	3.2.2 Precast Concrete Sandwich Panel With Window Opening	27
	3.2.3 Precast Concrete Sandwich Panel With Door And Window Opening	27
	3.2.4 Precast Concrete Sandwich Panel Without Opening	27
	3.2.5 Specimen Details	30
	3.3 Materials	31
	3.3.1 Concrete	31
	3.3.2 Reinforcement	31
	3.3.3 Insulation	32
	3.4 Specimen Preparation	33



3.5	Test Setup	34
3.6	Instrumentation	34
3.6.1	Concrete Surface Strain Measurements	35
3.6.2	Reinforcement Strain Measurements	35
3.6.3	Displacement Measurements	36
3.6.4	Crack Patterns	36
4	RESULT AND DISCUSSION	45
4.1	Introduction	45
4.2	Material	45
4.3	Ultimate Load Analysis	47
4.3.1	Panel Without Opening	47
4.3.2	Panel With Opening	49
4.4	Experimental Test Result- Lateral Deflection	54
4.5	Experimental Test Result- Concrete Surface Strain	63
4.6	Experimental Test Result- Reinforcement Strain	71
4.7	Crack Pattern	74
5	CONCLUSION	88
6	RECOMMENDATION	92
	REFERENCES	93
	APPENDICES	96
A	Concrete Mix Design	94
B	Graph Of Strain Gauges On The Reinforcement Of Panels	97
	BIODATA OF THE AUTHOR	114



LIST OF TABLES

Table		Page
3.1	Specimen Details	30
4.1	Compressive Strength Of Concrete Cube	46
4.2	Yield Strength Of Steel	46
4.3	Experimental And Theoretical Ultimate Load For Panel Without Opening	48
4.4	Cracking And Failure Loads Of Panels With Openings	49
4.5	Analysis Of Panel With Opening(s)	51
4.6	Theoretical And Experimental Ultimate Loads For Panels With Opening	52



LIST OF FIGURES

Figure		Page
3.1(a)	Detailing Of Panel With Door Opening	28
3.1(b)	Detailing Of Panel With Window Opening	28
3.1(c)	Detailing Of Panel With Door And Window Openings	29
3.1(d)	Detailing Of Panel Without Opening	29
3.2(a)	Overall View Of The Test Frame	37
3.2(b)	Schematic View Of The Test Frame	38
3.3(a)	Strain Gauges On Concrete Surface For Panel With Door Opening (Back Face)	39
3.3(b)	Strain Gauges On Steel Bars For Panel With Door Opening	39
3.3(c)	Dial Gauges On Concrete Surface Of Panel With Door Opening (Back Face)	40
3.4(a)	Strain Gauges On The Concrete Surface For Panel With Window Opening (Back Face)	40
3.4(b)	Strain Gauges On Steel Bars For Panel With Window Opening	41
3.4(c)	Dial Gauges On Concrete Surface Of Panel With Window Opening (Back Face)	41
3.5(a)	Strain Gauges On Concrete Surface For Panel With Door And Window Opening (Back Face)	42
3.5(b)	Strain Gauges On Steel Bars For Panel With Door And Window Openings	42
3.5(c)	Dial Gauges On Concrete Surface For Panel With Door And Window Openings (Back Face)	43
3.6(a)	Strain Gauges On Concrete Surface For Panel Without Opening (Back Face)	43

3.6(b)	Strain Gauges On Steel Bars For Panel Without Opening	44
3.6(c)	Dial Gauges On Concrete Surface For Panel Without Opening (Back Face)	44
4.1	P_{uo}^e / P_{uc}^c verses α	52
4.2(a)	Deflection Vs. Dial Gauges Position For Panel OA1	57
4.2(b)	Deflection Vs. Dial Gauges Position For Panel OA 2	57
4.2(c)	Deflection Vs. Dial Gauges Position For Panel OA 3	58
4.3(a)	Deflection Vs. Dial Gauges Position For Panel OB1	58
4.3(b)	Deflection Vs. Dial Gauges Position For Panel OB 2	59
4.3(c)	Deflection Vs. Dial Gauges Position For Panel OB3	59
4.4(a)	Deflection Vs. Dial Gauges Position For Panel OC1	60
4.4(b)	Deflection Vs. Dial Gauges Position For Panel OC 2	60
4.4(c)	Deflection Vs. Dial Gauges Position For Panel OC3	61
4.5(a)	Deflection Vs. Dial Gauges Position For Panel WO1	61
4.5(b)	Deflection Vs. Dial Gauges Position For Panel WO2	62
4.5(c)	Deflection Vs. Dial Gauges Position For Panel WO3	62
4.6(a)	Concrete Compressive Strain For Panel OA1	65
4.6(b)	Concrete Compressive Strain For Panel OA2	65

4.6(c)	Concrete Compressive Strain For Panel OA3	66
4.7(a)	Concrete Compressive Strain For Panel OB1	66
4.7(b)	Concrete Compressive Strain For Panel OB2	67
4.7(c)	Concrete Compressive Strain For Panel OB3	67
4.8(a)	Concrete Compressive Strain For Panel OC1	68
4.8(b)	Concrete Compressive Strain For Panel OC2	68
4.8(c)	Concrete Compressive Strain For Panel OC3	69
4.9(a)	Concrete Tensile Strain For Panel WO1	69
4.9(b)	Concrete Tensile Strain For Panel WO2	70
4.9(c)	Concrete Tensile Strain For Panel WO3	70
4.10	Reinforcement Strain (Tension And Compression) For Panel With Door Opening	72
4.11	Reinforcement Strain (Tension And Compression) For Panel With Window Opening	72
4.12	Reinforcement Strain (Tension And Compression) For Panel With Door And Window Opening	73
4.13	Reinforcement Strain (Tension And Compression) For Panel Without Opening	73
4.14(a)	Crack Pattern Of Front Layer Of Panel OA1	76
4.14(b)	Crack Pattern Of Back Layer Of Panel OA1	76
4.15(a)	Crack Pattern Of Front Layer Of Panel OA2	77
4.15(b)	Crack Pattern Of Back Layer Of Panel OA2	77
4.16(a)	Crack Pattern Of Front Layer Of Panel OA3	78
4.16(b)	Crack Pattern Of Back Layer Of Panel OA3	78
4.17(a)	Crack Pattern Of Front Layer Of Panel OB1	79
4.17(b)	Crack Pattern Of Back Layer Of Panel OB1	79

4.18(a)	Crack Pattern Of Front Layer Of Panel OB2	80
4.18(b)	Crack Pattern Of Back Layer Of Panel OB2	80
4.19(a)	Crack Pattern Of Front Layer Of Panel OB3	81
4.19(b)	Crack Pattern Of Back Layer Of Panel OB3	81
4.20(a)	Crack Pattern Of Front Layer Of Panel OC1	82
4.20(b)	Crack Pattern Of Back Layer Of Panel OC1	82
4.21(a)	Crack Pattern Of Front Layer Of Panel OC2	83
4.21(b)	Crack Pattern Of Back Layer Of Panel OC2	83
4.22(a)	Crack Pattern Of Front Layer Of Panel OC3	84
4.22(b)	Crack Pattern Of Back Layer Of Panel OC3	84
4.23(a)	Crack Pattern Of Front Layer Of Panel WO1	85
4.23(b)	Crack Pattern Of Back Layer Of Panel WO1	85
4.24(a)	Crack Pattern Of Front Layer Of Panel WO2	86
4.24(b)	Crack Pattern Of Back Layer Of Panel WO2	86
4.25(a)	Crack Pattern Of Front Layer Of Panel WO3	87
4.25(b)	Crack Pattern Of Back Layer Of Panel WO3	87



LIST OF NOTATIONS

a	distance between centres of gravity of panels with and without opening
a_o	horizontal distance between centre of gravity of opening(s) and left vertical edge of panel
\bar{a}	horizontal distance of centre of gravity of panel with opening(s) and left vertical edge of opening
A_g	L_t , gross area of the wall panel section (mm^2)
A_o	L_{ot} , area of panel opening
A_{sv}	$\rho_v(L_t)$, area of vertical steel in wall section
C	an empirical constant or equation derived from tests
e	eccentricity of the load measured at right angles to the plane of the wall
f_{cu}	cube strength of concrete (N/mm^2)
f_c'	cylinder strength of the concrete (N/mm^2)
f_y	yield strength of steel (N/mm^2)
F_a	allowable direct compressive stress
F_1	0.55 is a capacity factor, a function of eccentricity
$F_2 = [1 - (l_c/40h)^2]$	represent the function of slenderness
H, l_c, h	height of the wall (mm)
h_o	height of opening
k	effective length factor, depends on length condition
k_1, k_2, k_3 and k_4	statistical constants derived from test data
L	length of wall panel
L_o	length of panel opening

m	$\frac{f_y}{f_c}$ = yield strength ratio of steel to concrete
n	E_s/E_c ,as modular ratio
P_u	design ultimate load of a wall in compression
$P_{uo}, P_{uo}^e, P_{uo}^c$	ultimate load of panel with opening and of those experimental and theoretical loads
P_{uc}^e, P_{uc}^c	experimental and theoretical ultimate load for panel without opening
P_{co}	experimental cracking load of panel with openings
t	thickness of the wall (mm)
α	non dimensional parameter
ϕ	capacity reduction factor
σ_m	ratio of yielded steel area to concrete gross area
σ_n	ratio of steel area which remain in elastic stress state
ρ_v	vertical reinforcement ratio in wall
ρ_h	horizontal reinforcement ratio in a wall
ACI	American Concrete Institute
BS	British Standard

CHAPTER 1

INTRODUCTION

1.1 General

Precast concrete components are widely used throughout the world, primarily in the building sector. The rapid growth of the building industry plus the increasing demand for quality buildings necessitates the building industry to continuously seek improvement, leading to industrialisation. The advent of industrial methods had shown that mass production of precast concrete components had increased the quality as well as reduced the cost of production. Cost is reduced due to lesser construction time and amount of labour.

Precast concrete is defined as concrete which is cast in some location other than its position in the finished structure. One of the building elements in a precast building system is precast concrete sandwich wall panel. The difference between precast concrete wall panel and precast concrete sandwich wall panel is the presence of an intervening layer of insulation.

1.2 Precast Concrete Sandwich Panel

Interest in precast concrete sandwich panel has been increasing in the past few years because manufacturers are looking for new products. Architects and engineers are pleased with the energy performance and general aesthetics of the panels and contractors have found that the use of sandwich panels allow their project site to be cleaner and easier to manage⁽¹⁾.

Precast concrete sandwich wall panel consists of a single layer of insulation sandwiched between two precast concrete layers. The two layers of precast concrete interconnected by a series of shear connectors, concrete webs or a combination of the two. The thickness of each layer depends on the function of the panel. Based on the application of the panel, the precast concrete sandwich wall panel could be categorised as non-composite, partially composite or fully composite.

The non-composite panel referred to the panels with two concrete layers acting independently when load is applied. The connectors have no capacity for longitudinal shear transfer. Normally, the two concrete layers have different thicknesses. The thicker layer resists the applied load and acts as the structural layer.

Partially composite panels are analysed and designed as composite or semi composite during handling but as non-composite for in-place loads. In the PCI Committee Report, it was mentioned that experience showed that early bond between certain insulation types and the concrete layers provide shear transfer for composite action during handling, but the bond is considered unreliable for the long term. The shear connectors can transfer between 0 to 100 percent of the longitudinal shear required for a composite panel.

The composite or fully composite panels referred to panels with two concrete layers acting as one unit when load is applied. This is accomplished by providing full shear transfer between the two layers. This type of panel may be used as load bearing structural panels.

1.3 Precast Concrete Sandwich Panel with Opening

This investigation involves the study of the behaviour of load bearing precast concrete sandwich panel with opening under static loading. The opening referred to a void in the panel, which represents the door or window. Twelve panels were prepared and tested. Three types of sandwich panels with openings were;

- 1) Precast concrete sandwich panel with door opening
- 2) Precast concrete sandwich panel with window opening
- 3) Precast concrete sandwich panel with window & door opening.

For each panel type, three specimens were tested. The size of these panels was fixed at 900mm x 1000mm by 120mm thick. This size was chosen due to the capacity limitation of the test equipment. The thickness of the panels consists of 40mm of polystyrene sandwiched by two layers of concrete of same thickness.

The sizes of the openings were;

- 1) 700mm x 300mm for the door
- 2) 460mm x 400mm for the window
- 3) 700mm x 300mm and 360mm x 400mm for the door and the window respectively.

Two concrete layers are connected through the insulation layer by continuous shear truss connector along the length of the panel.

1.4 Objective

The objective of this research work is to study the behaviour of precast concrete sandwich panels with openings under axial loading.

This involves:

1. Comparing the theoretical formulae for ultimate strength of the reinforced concrete wall with the experimental ultimate load of precast concrete sandwich panel tested.
2. Observing the mode of failure, cracking pattern, load-deflection relationship and strain distribution of the test specimens.

CHAPTER 2

LITERATURE REVIEW

2.1 Introduction

Precast concrete sandwich panel consists of two layer of high-density material sandwiched by a layer of low-density core material. Reinforced concrete is normally used as the high-density material while many different types of insulation material can be used as the low-density core material. The important criterion in selecting the insulation material is its heat transmissibility. Generally, the minimum thickness of 25mm is used⁽²⁾. The outer layers are connected to the insulation by the shear connector.

The structural behaviour of the panels depends on the strength and stiffness of the connectors. When the strength and stiffness of the connectors are sufficient to transfer the shear forces caused by bending between the outer and inner concrete layers, the panel is considered fully composite. Connectors with low shear resistance typically transfer minimal shear force from one concrete layer to the other. Panels utilising such connecting system are considered non-composite. Partially composite panels lie in between these two extremes and provide some shear transfer between the layers.