



UNIVERSITI PUTRA MALAYSIA

**EXPERIMENTAL DAMAGE INVESTIGATION OF COMPOSITE
PLATES
SUBJECTED TO IMPACT LOADING CONDITIONS**

RISBY MOHD SOHAIMI

ITMA 2003 3

**EXPERIMENTAL DAMAGE INVESTIGATION OF COMPOSITE PLATES
SUBJECTED TO IMPACT LOADING CONDITIONS**

By

RISBY MOHD SOHAIMI

**Thesis Submitted to the School of Graduate Studies, Universiti Putra
Malaysia, in Fulfilment of Requirements for the Degree of Master of
Science**

August 2003



DEDICATION

I would not be truly thankful if I did not express gratitude towards my mum and dad who always taught me to chase the dreams: when I caught it, learn to live with it. Also I would like to fully thank them for the necessary contributions made especially during my current studies.

Above all, my deepest gratitude and love goes to my wife, Siti Noor Adnalizawati. She is my inspiration and guiding light in everything I do. The many personal sacrifices she has made for me to accomplish this work is greatly appreciated. She has been there through it all, the good and the bad. I will be eternally thankful for her understanding and support.

Abstract of the thesis presented to the Senate of Universiti Putra Malaysia in
fulfilment of the requirements for the degree of Master of Science

**EXPERIMENTAL DAMAGE INVESTIGATION OF COMPOSITE PLATES
SUBJECTED TO HIGH AND LOW IMPACT LOADING CONDITIONS**

By

RISBY MOHD SOHAIMI

August 2003

Chairman : Associate Professor Abdel Magid Saleem Hammuda, Ph.D.

Institute : Advanced Technology

The use of synthetic fibers such as glass fiber and aramid fiber carbon fiber as composite reinforcement is being increasingly applied in high performance applications since they provide certain advantage of specific high strength and stiffness as compared to metallic materials. In contrast, implementation of natural fiber as reinforcement has not yet received adequate attention from the research community.

This study investigates the damage characterization and impact resistance of synthetic and natural fiber reinforced composite square plates subjected to the changes of impact loading and width over thickness (b/d) ratio of the composite. For low velocity impact, the testing was performed using Dynatup 8250 equipped with GRC 930-I Data Interpretation System on fabricated square plates with different impact energy levels and velocities. The severity of impact damage is

macroscopically and microscopically investigated. A compressed gas gun equipped with velocity measurement system was designed and fabricated in order to facilitate the high velocity impact testing experimentations.

From the results, it has been found that mechanical and impact properties of EFBC and CFC do not possess toughness and modulus as high as GRC. Although EFBC and CFC specimens exhibit total perforation to the specimens at most impact velocities, EFBC specimen with plate thickness of 8 millimetres was found to have penetration resistance at 22 Joules of impact energy level. This is due to the performance of Coir as reinforcement in polymer composites is unsatisfactory and not comparable with other natural fibers due to its mechanical properties. It can also be concluded that the impact response of EFBC and CFC specimen changes significantly as the composite thickness increases.

Impact damage was found to be in the forms of matrix cracking, fiber fracture and perforation. This study results can be a valuable reference in designing of lightweight composite structure and in developing a better understanding of test methods used to characterize impact behaviours.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Master Sains

**EXPERIMENTASI KEROSAKAN SECARA PENYIASATAN KEATAS PLAT
KOMPOSIT BERHUBUNGAN DENGAN HENTAMAN IMPAK**

Oleh

RISBY MOHD SOHAIMI

Ogos 2003

Pengerusi : Profesor Madya Abdel Majid Saleem Hammuda, Ph.D.

Institut : Teknologi Maju

Penggunaan komposit bergentian sintetik telah digunakan secara meluas semenjak diperkenalkan pada awal tahun tujuh puluh-an. Penggunaan gentian sintetik seperti gentian kaca, aramid dan gentian karbon sebagai tetulang komposit semakin meningkat terutama di industri aeroangkasa, ketenteraan, marin dan industri automotif. Ia telah memberikan peningkatan dari segi keutamaan terhadap ciri kekuatan spesifik dan ketelusan yang tinggi jika dibandingkan dengan bahan logam. Sebaliknya, implimentasi kegunaan gentian asli sebagai tetulang masih belum diberi perhatian yang sewajarnya dan masih tidak diketahui. Ini adalah salah satu faktor motivasi untuk tesis ini.

Tesis ini mengkaji ciri kerosakan, ketebalan dan kesan impak untuk komposit bergentian tetulang asli dan sintetik berhubungan dengan perubahan halaju impak dan nisbah lebar keatas ketebalan plat (b/d). Kerja ujikaji dilakukan dengan menggunakan Dynatup 8250 yang dilengkapi GRC 930-I Data Interpretation System dengan mengubah halaju impak yang berlainan dimana kesan kerosakan daripada impak dikaji secara makroskopik. Senapang gas termampat buatan sendiri digunakan untuk mengkaji kesan hentaman impak

halaju tinggi. Kerosakan yang berlaku dijangka dalam bentuk keretakan matriks, delaminasi, dan tahap penembusan.

Keputusan telah menunjukkan bahawa ciri-ciri mekanikal dan hentaman impak bagi EFBC (komposit bergentian sawit) dan CFC (komposit bergentian kelapa) tidak mempunyai modulus dan kekuatan yang tinggi berbanding dengan GRC (komposit bergentian kaca). Walaubagaimanapun, EFBC dan CFC menunjukkan tahap penembusan keseluruhan pada kebanyakan kelajuan impak, sample 8 milimeter EFBC telah didapati mempunyai tahap rintangan penembusan yang baik pada tahap hentaman impak 22 Joules. Tahap kegunaan Coir (sabut kelapa) sebagai tetulang dalam komposit berpolimer tidak memberangsangkan mungkin kerana ia mempunyai ciri-ciri mekanikal yang rendah berbanding dengan gentian asli yang lain. Kesimpulan daripada ujikaji ini menunjukkan respon terhadap kesan hentaman impak EFBC dan CFC berubah dengan peningkatan ketebalan. Kesimpulan yang didapati ini akan memberikan rujukan yang penting bagi rekabentuk komposit bergentian ringan bagi kegunaan aplikasi struktur dan bahan.

ACKNOWLEDGEMENTS

First of all Syukur Alhamdulillah to Allah S.W.T who have made all things possible for me to finish what I have worked over these years. I would like to express my utmost gratitude and thanks to my main supervisor Associate Prof. Dr. A.M.S Hamouda, his confidence in me which was reflected in his flexibility, his willingness to let me decide the direction of this research, and to pursue it in a manner that I felt most suitable. Without his assistance and optimistic ideas, most of the project objectives cannot be achieved. And to my co-supervisor, Dr. Elsadig Mahdi and Dr. Wong Sai Voon, for sharing their ideas and expressing interest in my research project.

I would like to thank the staffs of ITMA for their kind assistance and attention to my many request and queries. To my laboratory mates, thanks for the great ideas and comments and enjoyable times we had during the years. May we all find success and blessing in the future ahead.

I would also like to thank Prof. Thomas. J. Ahrens (California Institute of Technology), Prof. Masahiko Arakawa (Hokkaido University), Prof. Horacio Dante Espinosa (Northwestern University), Prof. Tsutomu Mashimo (Kumamoto University), Dr. Akihisa Abe (Kobe University), Dr. Hallock Swift (Physic Applications), Mr Masao Hatada and Mr Akiko Niizeki (NASDA) and Lt. Colonel Dr. Shuhaimi Abdullah (MINDEF) for providing the ideas and technical information needed in order for me to successfully design and fabricate the custom made light gas gun. Especially to Dr. Oliver Han (Schlumberger) for the valuable comments and assistance given during our correspondents.

I certify that an Examination Committee met on 28th August 2003 to conduct the final examination of Risby bin Mohd Sohami on his Master of Science thesis entitled "Experimental Damage Investigation of Composite Plates Subjected to Impact Loading Conditions" in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

Megat Mohamad Hamdan Megat Ahmad Ph.D.

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Abdel Magid Saleem Hammuda, Ph.D.


Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Wong Shaw Voon, Ph.D.

Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Elsadig Mahdi, Ph.D.

Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Member)



GULAM RUSUL RAHMAT ALI, Ph.D.
Professor/Deputy Dean
School of Graduate Studies
Universiti Putra Malaysia

Date **4 DEC 2003**

This thesis submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirements for the degree of Master of Science
The members of the Supervisory Committee are as follows

Abdel Magid Saleem Hammuda, Ph.D.

Associate Professor
Faculty of Engineering
Universiti Putra Malaysia
(Chairman)

Wong Shaw Voon, Ph.D.

Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Member)

Elsadig Mahdi, Ph.D.

Lecturer
Faculty of Engineering
Universiti Putra Malaysia
(Member)




AINI IDERIS, Ph.D.
Professor/Dean
School of Graduate Studies
Universiti Putra Malaysia

Date 15 DEC 2003

DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations, which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.



RISBY BIN MOHD SOHAIMI

Date: 28th August 2003

TABLE OF CONTENTS

	Page
DEDICATION	ii
ABSTRACT	iii
ABSTRAK	v
ACKNOWLEDGEMENTS	vii
APPROVAL	viii
DECLARATION	ix
LIST OF TABLES	xiii
LIST OF FIGURES	xiv
LIST OF ABBREVIATIONS	xvi
CHAPTER	
I. INTRODUCTION	1
Problem Statement	4
Importance of the Study	6
Objectives	7
Layout of the Thesis	8
II. LITERATURE REVIEW	9
Natural Fiber	9
Natural Fiber Composite	12
Impact Testing	15
Low Velocity Testing of Fiber Reinforced Composite	18
High Velocity Impact of Fiber Reinforced Composite	20
Projectile Acceleration Devices	21
Summary	22
III. MATERIALS AND METHDOLOGY	23
Plates and Test Specimen Fabrication	24
Low Velocity Impact Testing	25
Test Procedure	31
Tensile Properties of Fiber Reinforced Composite	32
Flexural Properties of Fiber Reinforced Composite	32
Measurement of Fiber Volume Fraction	34
Measurement of Density	34
High Velocity Impact Gun Work	35
Materials	36
Discussion	36
IV. DESIGN AND FABRICATION OF GAS COMPRESSED GUN	38
Theory of Light Gas Gun	38
Pressure Reservoir Unit	42

Triggering Valve	45
Launching Unit	45
Catch Chamber	46
Data Measurement Unit	48
Projectile Velocity Measurement Procedure	48
Fabrication Results and Discussion	50
Pressure Reservoir Unit	51
Triggering Unit	51
Gun Barrel and Catch Chamber	53
Velocity Measurement System	55
Discussion	56
Conclusion	57
V. RESULTS AND DISCUSSION	58
Mechanical Characterization	58
Tensile Test Results	58
Discussion	59
Flexural Test Results	59
Discussion	60
Density and Fiber Volume Fraction Results and Discussion	61
Low Velocity Impact Testing	64
Damage Characteristic Results	64
Impact Resistance Results	69
Discussion	79
Conclusion	88
High Velocity Impact Gun and Testing	88
Test results	88
Discussion	90
Conclusion	92
VI. GENERAL CONCLUSION AND FUTURE SUGGESTION	93
General Conclusion	93
Future Recommendation	94
REFERENCES	96
APPENDIX 1	108
APPENDIX 2	117
APPENDIX 3	118
VITA	119
PUBLISHED WORKS	120

LIST OF TABLES

Table	Page
Table 2.1: Composition of different plant based natural fibers	11
Table 2.2: Mechanical Properties of natural fibers compared to conventional fibers	13
Table 2.3: Mechanical properties of different composite	14
Table 4.1: Various driver gas speed of sound	41
Table 5.1: Average density results	61
Table 5.2: Composite specimens low velocity impact results	81
Table 5.3: Composite specimen low velocity impact result with changes in tup height	83
Table 5.4: Impact properties of tested composite at all thickness	85

LIST OF FIGURES

Figure	Page
Figure 2 1 The Haworth projection formula of cellulose	10
Figure 2 2 Typical Load vs deflection curve	15
Figure 2 3 Typical force vs time of several type of materials	16
Figure 2 4 Load and energy history of impact testing	17
Figure 2 5 Damage area as a function of maximum force for glass/polymer composite	19
Figure 3 1 Fiber arrangement before matrix lay-up	25
Figure 3 2 Flow chart describes the plan to carry out the thesis work	27
Figure 3 3 Flow chart describes the composite fabrication process	28
Figure 3 4 Flow chart describes the low velocity and mechanical properties test	29
Figure 3 5 (a) oil palm EFB fiber (b) Coir fiber	30
Figure 3 6 (a) mould with spacing (b) mould under loading of concrete weights	30
Figure 3 7 (a) composite panels from mould after 48 hour curing time (b) prepared composite plate for impact testing	30
Figure 3 8 Dynatup 8250 drop tower	31
Figure 3 9 Schematic diagram of Dynatup 8250	33
Figure 3 10 Flow chart describes work done for the high velocity impact machine and test	37
Figure 4 1 Gun parameters	39
Figure 4 2 Internally pressured, thick walled cylinder showing circumferential and radial stress for various radii	42
Figure 4 3 A schematic drawing of the proposed design for compressed gas gun	47
Figure 4 2 Schematic of the velocity measurement set-up	48
Figure 4 4 Compressed gas gun unit	50
Figure 4 5 Pressure reservoir unit and solenoid valve	53
Figure 4 6 (a) Breech unit (b) barrel tube	55
Figure 4 7 (a) catch chamber unit (b) impact base plate	55
Figure 4 8 Velocity measurement unit	56
Figure 5 1 Tensile stress vs strain curves of EFBC and CFC 6mm thick specimen	62
Figure 5 2 Tensile load vs displacement curves of EFBC and CFC 6mm thick specimen	62
Figure 5 3 Flexural load vs displacement curves of EFBC and CFC 6mm thick specimen	63
Figure 5 4 Flexural load vs displacement curves of EFBC and CFC 6mm thick specimen	63
Figure 5 5 CFC specimen damage (a) front and (b) back, at impacting energy 32 Joules	65
Figure 5 6 EFBC specimen damage (a) front and (b) back, at impacting energy 32 Joules	66

Figure 5.7 : GRC specimen damage (a) front and (b) back, at impacting energy 32 Joules	66
Figure 5.8 : Optical photograph of coir fiber in impacted CFC specimen at magnification at x 50	67
Figure 5.9 : Optical photograph of coir fiber in impacted CFC specimen at magnification at x 50	67
Figure 5.10 : Optical photograph of coir fiber in impacted CFC specimen at magnification at x 50	68
Figure 5.11 : Optical photograph of coir fiber in impacted CFC specimen at magnification at x 50	68
Figure 5.12 : Impact event scenario for perforated EFBC and CFC plates...	72
Figure 5.14 : Energy vs. time curve at 3.5 m/s impact velocity of EFBC and CFC 6 mm thick specimen	73
Figure 5.15 : Load vs. time curve at 3.5 m/s impact velocity of EFBC and CFC 8 mm thick specimen	74
Figure 5.16 : Energy vs. time curve at 3.5 m/s impact velocity of EFBC and CFC 8 mm thick specimen	74
Figure 5.17 : Load vs. time curve at 3.5 m/s impact velocity of EFBC and CFC 10 mm thick specimen	75
Figure 5.18 : Energy vs. time curve at 3.5 m/s impact velocity of EFBC and CFC 10 mm thick specimen	75
Figure 5.19 : Load vs. time curve at 3.5 m/s impact velocity of EFBC and CFC 12 mm thick specimen	76
Figure 5.20 : Energy vs. time curve at 3.5 m/s impact velocity of EFBC and CFC 12 mm thick specimen	76
Figure 5.21 : Load vs. time curve at several impacting tup height of EFBC 6mm thick specimen	77
Figure 5.22 : Load vs. time curve at several impacting tup height of EFBC 6mm thick specimen	77
Figure 5.23 : Load vs. time curve at 60 cm impacting of EFBC,CFC,GRC and EPOXY 6 mm thick specimen	78
Figure 5.24: Energy vs. time curve at 60 cm impacting of EFBC, CFC, GRC and EPOXY 6 mm thick specimen	78
Figure 5.25 : Energy profile of EFBC specimen at different b/d ratio	79
Figure 5.26 : Energy profile of CFC specimen at different b/d ratio	83
Figure 5.27 : Energy profile of EPOXY, CFC, EFBC and GRC 6mm thick specimens	83
Figure 5.28 : Contact duration and peak load vs. b/d ratio	87
Figure 5.29 : Total absorbed energy and impact toughness vs. b/d ratio	87
Figure 5.30 : Calibration chart for compressed gas gun	89
Figure 5.31 : (a) Pre impact (b) Post impact	91
Figure 5.32 : (a) EFBC front plate (b) GRC front plate	91
Figure 5.33 : (a) EFBC back plate (b) GRC back plate	91
Figure 5.34 : Representation of global deformation in low velocity impact (a) and local deformation in high velocity impact (b)	92

LIST OF ABBREVIATIONS

CFC	Coir Fiber Reinforced Composite
EFBC	Empty Fruit Bunch Reinforced Composite
GRC	Glass Fiber Reinforced Composite
E_p	Propagation Energy
E_i	Initiation Energy
Mpa	Mega Pascal
V_f	Fiber Volume Fraction
kN	Kilo Newton
MLP	Maximum load point
TP	Total point
GPa	GigaPascal
MPa	MegaPascal

CHAPTER ONE

INTRODUCTION

The work presented in this thesis focuses on the effects of width over thickness ratio (b/d) and different type of materials on the failure mechanism, failure mode and energy absorption during an impact event. This work is also carried out in order to study the damage characterization and impact resistance of Coir-Epoxy (CFC), Oil Palm Empty Fruit Bunch-Epoxy (EFBC) and Glass-Epoxy (GRC) reinforced composite square plates subjected to the changes of impact loadings by using low and high velocity testing methods. Low velocity testing will be conducted using Dynatup 8250 instrumented impact machine, whereas for high velocity impact testing, a compressed gas gun with velocity measurement system was designed and fabricated to facilitate this experimental work. Quasi-static tests were performed in order to determine the mechanical properties of the fabricated composite plates.

Since their introduction, composite materials have been applied to a variety of structural applications. Among the most performing is graphite or carbon fiber composite, which possess one of the highest specific moduli among synthetic fiber materials (Cantwell and Morton, 1989; Dorey et al., 1998). The specific strength and stiffness of graphite epoxy composites are significantly greater than monolithic materials such as steel and aluminum, which make them attractive for numerous weight critical applications. Unfortunately, composites of this type have relatively poor mechanisms for absorbing energy due to local impact damage where loading is normal to the fiber

plane. This is primarily due to the low strain to failure and low transverse shear strength of the graphite fiber and the brittle nature of the epoxy matrix (Zhou, 1998b).

Impact events can be categorized into four velocity ranges; low, high, ballistic, and hypervelocity. Low velocity impact may include situations such as a dropped tool (< 31 m/s) whereas high velocity impact might include a bird colliding with an airplane (31 - 240 m/s). Ballistic impact events include situations such as a projectile fired from a gun at speeds in excess of 240 m/s. Finally, orbital debris traveling in outer-space at velocities up to 15,240 m/s are considered to be hypervelocity impact events (Stilp and Hohler, 1990). Since the early 1970's, researchers have been looking for methods to improve impact properties of graphite composites such as fiber and matrix toughening, interface toughening, through-the thickness reinforcements, and hybridizing (Jacob et al., 2002).

For high-performance materials, carbon or aramid-polyamides fibers such as Kevlar are the fibers of choice. They are very strong and highly heat-resistant, so they can be used in applications where conditions are fierce, in aircraft such as the Euro Fighter 2000 for example (Robson et al., 1993). But they also tend to be expensive, so for more general applications the workhorse fiber for composite materials is glass (Gayer and Schuh, 1996; Robson et al., 1993).

Glass fibers have many benefits. They are cheap, strong and relatively easy to manufacture. But there are disadvantages too. They are very abrasive,



which makes them dangerous to work with and increases wear in machines used to cut products made from composites. More importantly, glass fibers could present a health risk to those working with them. Like asbestos fibers, they are very small and once breathed in can lodge in the lungs and be absorbed into the body, which is very hazardous (Bolton, 1994; Nickel et al., 1998).

But the biggest problem with glass and other synthetic fibers is how to dispose them at the end of their lifetimes. Glass fiber reinforced composite is not biodegradable and cannot be burned because the fibers are left behind as clinker, a nasty residue, which can ruin a furnace. Nor are glass fibers easy to recycle. They break easily during the rough and tumble of reprocessing (Gayer and Schuh, 1996).

This is where natural fibers can be introduced as a substitute material. They are abundant, renewable, cheap and low density and most interesting is that it is biodegradable. Even if they are burned at the end of their lives, rather than left to biodegrade, natural fibers have an environmental advantage. Natural fibers such as coir, jute, flax, kenaf and sisal, have been used for thousands of years to make paper, textiles, cordage and other products essential to societal development. Natural fiber reinforced composites or bio-composite are gaining acceptance from manufacturing industry especially the automotive and building industry building because they can be made stronger and cheaper than with traditional plastic and glass fiber (Ellison and McNaught, 2000).

These "green" composite materials turn fibers from plants into lightweight, strong and stiff materials through innovative research (Ellison and McNaught, 2000; Gassan and Bledzki, 1999; Robson et al., 1993). Biocomposite materials have several advantages and since they are renewable based, biocomposite would reduce dependency on petroleum, which is the source for synthetic fibers production. The cost for composite materials can be reduced with large-scale usage. Potential harmful effects related to materials processing and disposal could be eliminated due to their potential biodegradability (Bolton, 1994; Gassan and Bledzki, 1999).

Since there is growing need in military and civil applications for composite materials that not only possess good structural characteristics, but good penetration resistance and greater strength during impact are being profoundly studied by researchers (Mahfuz et al., 1998; Ramakrishna et al., 1995; Zhou, 1998a).

Problem Statement

Many engineering structures that used synthetic fibers as reinforcement are subjected to impact loads or collision during service that may compromise the structural integrity of the composite and will lead to failure. It is thus important for the composite material to maintain some structural integrity until the end of the service life and prevent catastrophic failure (Soares and Sutherland, 1999).

According to Jacob et al (2002), the ability to absorb impact energy and survive is termed as "crashworthiness" structure. Where as for high velocity collision, penetration resistance is much concerned. There is an important different between crashworthiness and penetration resistance. Crashworthiness is concerned with energy absorption of energy through controlled failure mechanisms and modes that enable the maintenance of a gradual decrease in the load profile during absorption. However penetration resistance is associated with the total absorption without allowing the projectile or fragment penetration to occur during the impact event (Beaumont et al., 1974).

Therefore now natural fibers are predicted to be a positive alternative for their artificial counterparts in impact related applications Unlike relatively simple synthetic fibers, natural fibers are much more complicated. They are made up of bundles of cellulose microfibrils, thin strands of cellulose, which are wound together and surrounded by layers of hemi-cellulose and lignin (Li et al., 2000). This built-in microstructure means natural fibers can absorb a lot of energy, so that weight for weight, they are may be as strong as glass ones. But, they are much less dense. So if panels made of natural fibers are to be as strong as those made of synthetic fibers, they have to be thicker (Gassan and Bledzki, 1999). This is one of major setbacks faced by natural fiber composite but can be rectified if extensive research in impact analysis are done in order to have a better understanding of the natural fiber engineering potentials and finding out ways of improving the resistance in natural fiber reinforced materials. Therefore in this study the parameter of

width over thickness (b/d) ratio is introduced to examine the effect subjected to changes in the test specimen dimensions.

Importance of the Study

Impact resistance is one of the most important properties for a part designer to consider, and without question the most difficult to quantify (Jacob et al., 2002). The impact resistance of a component is, in many applications, is a critical measure of service life. More importantly these days, it involves the perplexing problem of product safety and liability (Richardson and Wiseheart, 1996). In standard testing, such as tensile and flexural testing, the material absorbs energy slowly. In real life, materials often absorb applied forces very quickly: falling objects, blows, collisions, drops, etc. A product is more likely to fail when it is subjected to an impact blow, in comparison to the same force being applied more slowly. The purpose of impact testing is to simulate these conditions (Jacob et al., 2002; Sjoblom et al., 1988; Tai et al., 1998; Zhou and Davies, 1995).

Studies have shown that reinforcements of composite materials with natural fibers have various advantages which similar to its synthetic counterparts such as high specific strength and stiffness (Gassan and Bledzki, 1999). Local resources such as natural fibers (Coir and oil palm fibers) can be widely exploited and used to diversify its potentials in high performance composite application. (Abdul Khalil et al., 2001; Rozman et al., 1996; Rozman et al., 2000). Therefore, a more comprehensive study of the behaviour and characterization of natural fiber reinforced composite

subjected to impact and penetration condition is needed to evaluate its limitations

Objectives

This present research is to study the impact resistance potential of natural and synthetic fiber reinforced composite, which may produce significant result that would improve the utilization of natural fiber into a viable materials for industry. The objectives can be summarised as follows

- To design and fabricate a compressed gas gun for high velocity impact testing
- To determine the mechanical properties of natural fiber reinforced composite rectangular stripe (oil palm empty fruit bunch and coir) from tensile and flexural testing
- To examine the impact resistance, penetration behaviour and effect of width over thickness (b/d) ratio of natural fiber reinforced composite square plates (oil palm empty fruit bunch and coir) and synthetic fiber reinforced square plates (glass fiber) from low and high velocity testing. Epoxy resin square plates also will be tested in low velocity condition as control specimen
- To investigate damage characteristics of natural fibers and glass fiber reinforced composite subjected to low and high impact loading

Layout of the Thesis

This thesis is primarily divided into six chapters. Following this chapter, Chapter two present a review of literature, which related the previous work done in composite impact investigations using low velocity testing and development of high velocity testing using gas gun. Explanations of natural fiber and its composite are also discussed in this chapter.

Chapter three discusses the justification of the materials and methods of this research. A detail description of a custom-made compressed gas gun (pneumatic) is presented in Chapter four and is followed by the overall experimental works done for this research in chapter five. Detail results and discussions of the work done throughout the project are being presented in this chapter. Finally, the conclusion and recommendations are presented in Chapter six followed by publications of this thesis.