



**UNIVERSITI PUTRA MALAYSIA**

**ELECTRICAL TRANSPORT AND RELATED DIELECTRIC PHENOMENA  
IN COCONUT-SHELL ACTIVATED CARBON**

**W. MOHAMAD DAUD BIN W. YUSOFF**

**FSAS 1991 1**

**ELECTRICAL TRANSPORT AND RELATED DIELECTRIC PHENOMENA  
IN COCONUT-SHELL ACTIVATED CARBON**

**By**

**W. MOHAMAD DAUD BIN W. YUSOFF**

**Thesis Submitted in Fulfilment of the Requirements for  
the Degree of Doctor of Philosophy in the Faculty of  
Science and Environmental Studies  
Universiti Pertanian Malaysia**

**August 1991**



## ACKNOWLEDGEMENTS

I would like to express my gratitude to my supervisors, Professor Dr. Hj. Badri bin Muhammad and Dr. Mansor bin Hashim, for the invaluable guidance, continuing advice, encouragement and discussions they have given me throughout the course of this research.

I would also like to thank the following:

Dr. Sobri bin Hashim, Timbalan Ketua Pengarah of Unit Tenaga Nuklear, Bangi (until 1990) and his staff members for their kind help.

En. Abbas bin Ab. Rahman of Glass Blowing Workshop for his kind help.

En. Nordin bin Abdul Kadir and En. Shamsol Karib bin Kamaruddin of Mechanical and Electronic Workshop for their technical assistance.

Various colleagues and staff members of the Physics and Chemistry Department for their kind help and cooperation.

The Jabatan Perkhidmatan Awam and Universiti Pertanian Malaysia for financial support and study leave.

My wife and children for their patience and understanding.



## TABLE OF CONTENTS

	Page
ACKNOWLEDGEMENTS .....	ii
LIST OF TABLES .....	vii
LIST OF FIGURES .....	viii
LIST OF PLATES .....	xiii
LIST OF SYMBOLS AND ABBREVIATIONS .....	xiv
ABSTRACT .....	xviii
ABSTRAK .....	xxi
CHAPTER	
I THE BASIS AND OBJECTIVES OF THIS RESEARCH ...	1
II STRUCTURAL ASPECTS OF ACTIVATED CARBON .....	7
Introduction .....	7
Formation Process of Activated Carbon ....	8
Physical Properties of Activated Carbon ..	9
III SOME ASPECTS OF ELECTRICAL CONDUCTION AND DIELECTRIC POLARISATION IN SOLIDS .....	14
Introduction .....	14
DC Electrical Conductivity, $\sigma_{dc}$ .....	15
Amorphous Semiconductor .....	16



	Band Model .....	18
	Conduction Mechanisms in Amorphous Semiconductors .....	21
	Dielectric Response Parameters, $\epsilon'$ and $\epsilon''$ ..	25
	Polarisation .....	25
	Some Fundamental Equations of Dielectric Theory .....	29
	AC Electrical Conductivity, $\sigma_{ac}$ .....	48
	Thermoelectric Power, S .....	51
	Magnetoresistance, $\Delta\rho/\rho$ .....	55
	Brief Review: Electrical Properties of Carbon Materials .....	56
IV	<b>SAMPLE PREPARATION AND ANALYSIS OF STRUCTURE AND COMPOSITION .....</b>	<b>59</b>
	Introduction .....	59
	Preparation of Material and Samples .....	60
	Structural and Microstructural Analysis ..	63
	Compositional Analysis .....	64
V	<b>ELECTRICAL CONDUCTION EXPERIMENTS .....</b>	<b>65</b>
	<b>(Method, Apparatus and Techniques of Measurements)</b>	
	Introduction .....	65
	Preparation of Specimens and Apparatus ...	66
	Preparation of Specimens .....	66
	Experimental Set-ups and Apparatus ...	66
	Working Expression for $\sigma_{dc}$ , $\sigma_{ac}$ , $\epsilon'$ , $\epsilon''$ , S and $\Delta\rho/\rho$ .....	80



	Conductivity Experiments .....	83
	DC Conductivity Measurements .....	83
	Initial Investigation of Temperature Variation of DC Conductivity .....	87
	AC Measurement .....	90
	Errors of $\sigma_{dc}$ , $\sigma_{ac}$ , $\epsilon'$ and $\epsilon''$ .....	92
	Thermoelectric Power Experiment .....	99
	Experimental Technique .....	99
	Error of S .....	101
	Magnetoresistance Experiment .....	102
	Experimental Set-up and Measurement ..	102
	Error of $\Delta\rho/\rho$ .....	104
VI	EXPERIMENTAL RESULTS .....	106
	Introduction .....	106
	Results of Morphological and Compositional Analyses .....	107
	Results of DC Conductivity Measurement ...	120
	Results of AC Conductivity Measurement ...	129
	Frequency Response of Measured Conductivity, $\sigma_{ac}$ .....	129
	Temperature Dependence of AC Conductivity .....	136
	Analysis of $\sigma_{ac}$ Using Complex Plane ..	140
	Results of Deduced Dielectric Response ...	154
	Results of Thermoelectric Power Measurement	169
	Results of Magnetoresistance Measurement ..	173



	Probable Explanation for Conduction and Dielectric Behaviour .....	176
	Introduction .....	176
	DC and AC Electrical Conduction .....	177
	Dielectric Behaviour .....	190
	A Possible Model for Dielectric and Conduction Processes .....	195
	Summary of Main Results .....	205
	Conclusion .....	208
VII	FUTURE RESEARCH IN THE PHYSICS OF COCONUT-SHELL ACTIVATED CARBON .....	210
REFERENCES	.....	214
APPENDIX		
A	Equations of $G_M$ and $C_M$ .....	220
B	Equation of $G_{eff}$ due to series resistance ...	222
C	Published paper .....	224
VITA	.....	227



## LIST OF TABLES

Table		Page
1	A Brief Description of FTIR Spectrum.	113
2	Concentration of Trace Elements in Activated Carbon Sample.	115
3	Percentage of C, H and N.	117
4	Dimension of the Sample and Types of Electrode Used in Electrical Measurement.	121
5	Sample Conductivities at $1/T=0$ and Activation Energies in Various Temperature Ranges.	124
6	Low and High Frequency Conductance Data:	150
7	Impedance at Various Frequencies.	202





## LIST OF FIGURES

Figure		Page
1	Schematic diagram comparing: (a) a three-dimensional graphite lattice with (b) a turbostratic structure of activated carbon.	11
2	Secondary structure of activated carbon showing the carbon-carbon network attached with residual hydrocarbons and functional groups.	13
3	Examples of some functional groups present in activated carbon.	13
4	Band models in semiconductor materials.	17
5	Dependence of conductivity on temperature.	24
6	Model of conduction processes in amorphous semiconductor.	24
7	Polarisation types and effects in a dielectric.	28
8	Plots of $\epsilon'$ , $\epsilon''$ and $\tan \delta$ against $\omega\tau$ .	33
9	Schematic representation of the various types of dielectric response of solids.	37
10	Maxwell's two-layer condenser (a), and its electrical model (b).	41
11	Influence of DC conductivity on the losses in interfacial polarisation - DC conductivity increasing between I and IV.	41
12	Frequency dependence of $\tan \delta$ for various structures of binary mixture (i), and the model of binary mixture (ii).	42
13	Complex plane plots for series R-C circuit.	46



14	A typical plot of frequency dependence on conductivity.	52
15	Apparatus used for the preparation of activated carbon.	61
16	General experimental set-ups.	67
17	Schematic diagrams of electrodes cell.	70
18	Sample chamber and electrodes cell.	72
19	Thermoelectric power chamber and electrodes cell.	73
20	Temperature calibration set-up in cylinder heater.	76
21	Laboratory-assembled electrometer.	78
22	Electrical circuit for DC conductivity measurement.	86
23	Experimental current-versus-time plots.	86
24	Temperature dependence of DC conductivity for samples A1 and A2.	89
25	Temperature dependence of DC conductivity for sample A3.	89
26	Electrical circuit for AC measurements.	91
27	Measuring equivalent circuit.	96
28	Electrical circuit for thermoelectric power measurement.	100
29	Principal arrangement for measurement of thermoelectric power.	100
30	Electrical circuit for magnetoresistance measurement.	103
31	Calibration curve of magnetic field vs energising current.	105
32	X-ray diffraction pattern of coconut-shell activated carbon.	108



33	FTIR spectrum of coconut-shell activated carbon.	114
34	TGA profile of raw coconut-shell (a), and the prepared coconut-shell activated carbon (b).	119
35	Variation of DC conductivity against temperature for different samples.	122
36	Variation of DC conductivity against temperature for different samples using two-terminal electrodes.	125
37	Variation of DC conductivity against temperature for different samples using three-terminal electrodes.	126
38	Plots of DC conductivity against $T^{-1/4}$ for low temperature regions of Figure 36.	127
39	Plots of DC conductivity against $T^{-1/4}$ for low temperature regions of Figure 37.	127
40	Frequency dependence of conductivity of sample A7 at various temperatures.	130
41	Frequency dependence of conductivity of sample A9 at various temperatures.	131
42	Variation of AC conductivity with temperature after subtraction of frequency-independent conductivity at low frequencies.	135
43	Comparison of theoretical and experimental values of AC conductivity at 296K.	135
44	Temperature dependence of AC conductivity at different fixed frequencies.	137
45	Deduction of activation energy from conductivity-peak dispersion as in Figure 44(a).	139
46	Comparison of experimental conductivity and theoretical conductivity curves calculated from equation [78].	139
47	Complex impedance plots for sample A7.	142
48	Complex admittance plots for sample A7.	143



49	Complex impedance plots for sample A9.	144
50	Complex admittance plots for sample A9.	145
51	Schematic illustration of an equivalent circuit for series combination of volume (1) and barrier (2) admittance, represented by respective conductances, G, and capacitors, C. The complex impedance plot, Z, and complex admittance plot, Y, of its corresponding circuit are shown in the second and third rows, respectively.	146
52	Theoretical curve of frequency-dependent conductance.	149
53	Temperature dependence of low and high frequency conductivities.	151
54	Effect of DC bias on AC conductance.	153
55(a)	Relative permittivity, $\kappa'$ , and loss factor, $\kappa''$ , for sample A7 measured from 103 to 263K.	155
55(b)	Relative permittivity, $\kappa'$ , and loss factor, $\kappa''$ , for sample A7 measured from 296 to 485K.	156
56(a)	Relative permittivity, $\kappa'$ , and loss factor, $\kappa''$ for sample A9 measured from 126 to 272K.	157
56(b)	Relative permittivity, $\kappa'$ , and loss factor, $\kappa''$ , for sample A9 measured from 299 to 399K.	158
57	Variation of relative permittivity with temperature at different frequencies.	159
58	Temperature dependence of the dispersion of loss factor from Figure 55(b).	161
59	Temperature dependence of the dispersion of loss factor from Figures 56(a)-(b).	162
60	A plot of relaxation frequency against $10^3/T$ deduced from Figure 58.	163
61	A plot of relaxation frequency against $10^3/T$ deduced from Figure 59.	163
62	Cole-Cole plot showing the effect of DC conductivity on the plot shape.	165



63	Cole-Cole plot after subtraction of the effect of DC conductivity.	166
64	Master plot of relative permittivity, $\epsilon'$ , and loss factor, $\epsilon''$ , for various temperatures.	168
65	A plot of thermoelectric power against reciprocal temperature for two different samples.	170
66	Variation of magnetoresistance with magnetic fields at different temperatures.	174
67	Modulus plot of $M''$ against frequency at various temperatures.	181
68	Deduction of activation energy from dispersion of peak $M''$ in lower frequency region of Figure 67.	182
69	Logarithmic plot of the absolute value of the slope $s$ against temperature.	185
70	Model of electrical current flow in coconut-shell activated carbon.	197
71	RC circuit network for activated carbon.	203
72	Theoretical plots of capacitance, $C'$ , and $C''$ based on the circuit network of Figure 71.	203
73	Model of $\omega^2$ dependence of conductance.	222



## LIST OF PLATES

Plate		Page
1	Features of coconut-shell activated carbon revealed by SEM showing regions of highly dense surface.	110
2	Features of coconut-shell activated carbon revealed by SEM showing regions of highly porous surface structure.	111



## LIST OF SYMBOLS AND ABBREVIATIONS

$\epsilon$	dielectric permittivity (F/m)
$\epsilon_0$	permittivity of free space
$\epsilon_s$	static dielectric permittivity
$\epsilon_\infty$	dielectric permittivity at very high frequency
$\epsilon(\omega)$	dielectric permittivity as a function of angular frequency
$\chi'$	relative dielectric permittivity
$\chi''$	loss factor
$\chi^*$	complex dielectric permittivity
$\mu$	micron
$\rho$	resistivity (ohm/cm)
$\sigma$	conductivity (mho/cm)
$\sigma(\omega)$	conductivity as a function of angular frequency
$\tau$	relaxation time (sec)
$\omega$	angular frequency (Hz)
$\omega_p$	peak angular frequency
$\propto$	proportional to
$\text{\AA}$	Angstrom unit
eV	electron volt
exp	exponential
f	frequency (Hz)



$j$	$= \sqrt{-1}$
$k$	Boltzmann constant
kHz	kilohertz
ln	natural logarithm
log	logarithm
mHz	millihertz
AC	alternating current
B	susceptance (mho)
C	capacitance (F)
$C'$	real part of capacitance
$C''$	imaginary part of capaci
$C^*$	complex capacitance
$^{\circ}\text{C}$	degree Celsius
CFO	Cohen-Fritzsche-Ovshinky
CHN	carbon, hydrogen and nitrogen
DC	direct current
DVM	digital voltmeter
E	activation energy (eV)
$E_c$	energy at conduction band
$E_f$	Fermi energy
$E_v$	energy at valence band
FTIR	Fourier transform infrared
G	conductance (mho)
H	magnetic field (Tesla)
Hz	Hertz





I	current (ampere)
$I_m$	immaginary part
J	current density
K	Kelvin
MHz	megahertz
NAA	neutron activation analysis
OSC	oscillator
R	resistance (ohm)
$Re$	real part
SEM	scanning electron micrograph
T	absolute temperature (Kelvin)
TGA	thermogravimetric analysis
UPM	University Pertanian Malaysia
UTN	Unit Tenaga Nuklear
V	voltage (volt)
X	reactance (ohm)
XRD	x-ray diffraction
Y	admittance (mho)
$Y'$	real part of admittance
$Y''$	imaginary part of admittance
$Y^*$	complex admittance
Z	impedance (ohm)
$Z'$	real part of impedance
$Z''$	imaginary part of impedance
$Z^*$	complex impedance



### Subscripts

<b>eff</b>	<b>effective</b>
<b>long</b>	<b>longitudinal</b>
<b>MW</b>	<b>Maxwell-Wagner</b>
<b>max</b>	<b>maximum</b>
<b>p</b>	<b>parallel</b>
<b>s</b>	<b>series</b>
<b>tr</b>	<b>transverse</b>



Abstract of thesis submitted to the Senate of Universiti  
Pertanian Malaysia in fulfilment of the requirements for the  
degree of Doctor of Philosophy.

**ELECTRICAL TRANSPORT AND RELATED DIELECTRIC PHENOMENA  
IN COCONUT-SHELL ACTIVATED CARBON**

By

**W. MOHAMAD DAUD BIN W. YUSOFF**

August 1991

Supervisors : Professor Dr. Hj. Badri bin Muhammad.  
Dr. Mansor bin Hashim.

Faculty : Faculty of Science and Environmental Studies,  
Universiti Pertanian Malaysia.

The electrical properties of coconut-shell activated carbon have not been thoroughly investigated and are, therefore, not well understood. In order to study these properties meaningfully, a fairly satisfactory knowledge of the structure, microstructure and composition of the material is needed.

Since the material's constitution has been little studied and dealt with in the relevant published literature, investigation of the structure and composition of the material has to be done in a comprehensive manner. The experimental investigation is divided into two categories. Firstly, the basic experimental work, which is considered important in order to provide supportive evidence to any proposed model of charge-carrier conduction and dielectric behaviour, consists of



work on x-ray diffractometry, neutron activation analysis, Fourier transform infra-red spectroscopy, scanning electron microscopy, thermoelectric power and magnetoresistance. Secondly, the main experiments consist of work on direct current conductivity and alternating current conductivity measurement.

The results of the basic experiments indicate that activated carbon prepared from coconut shells is essentially amorphous, containing many functional groups, potassium, sodium and several other trace elements. It has a highly porous microstructure. The thermopower-temperature plot obtained suggests that holes are the majority carriers below 385K while at higher temperatures electrons are the majority carriers.

The experimental results of the variation of the direct current conductivity with temperature and the dependence of the alternating current conductivity upon frequency at various fixed temperatures reveal three distinguishable regions. First, a variable-range hopping conduction mechanism operates among localised states near the Fermi level at temperatures below 200K; second, a hopping conduction mechanism occurs among localised states in the band tail for temperatures between about 200 and 385K and third, a percolation conduction mechanism is dominant at and above the mobility edge for temperatures above 385K. The graph of alternating-current conductivity versus



temperature shows that the conductivity is strongly influenced by a certain polarisation process. The results of dielectric-response measurements and the results of the equivalent-circuit analysis show that interfacial polarisation is the most probable process responsible for the observed dielectric behaviour.



Abstrak tesis yang dikemukakan kepada Senat Universiti Pertanian Malaysia bagi memenuhi syarat untuk ijazah Doktor Falsafah.

**PENGANGKUTAN ELEKTRIK DAN FENOMENA DIELEKTRIK BERKAITAN  
DALAM KARBON AKTIF TEMPURUNG-KELAPA**

Oleh

**W. MORAMAD DAUD BIN W. YUSOFF**

Ogos 1991

Penyelia : Professor Dr. Hj. Badri bin Muhammad.  
: Dr. Mansor bin Hashim.

Fakulti : Fakulti Sains dan Pengajian Alam Sekitar,  
Universiti Pertanian Malaysia.

Sifat elektrik bagi karbon aktif dari tempurung kelapa didapati tidak diselidiki secara menyeluruh, oleh yang demikian sifat tersebut tidak diketahui dengan sepenuhnya. Untuk menyelidiki sifat elektrik ini secara bermakna, sedikit sebanyak pengetahuan tentang struktur, mikrostruktur dan kandungan bahan adalah diperlukan.

Oleh kerana sifat bahan hanya sedikit sahaja diketahui dan hanya boleh diperolehi dari penerbitan ilmiah yang bersesuaian, maka penyelidikan dari segi struktur dan kandungan bahan perlu dilakukan secara menyeluruh. Penyelidikan eksperimen ini terbahagi kepada dua kategori. Pertama, eksperimen asas, yang dianggap mustahak bagi menyokong sebarang cadangan model untuk kekonduksian pembawa-cas dan sifat dielektrik; iaitu pembelauan sinar-x, analisis pengaktifan neutron, spektroskopi jermuan



Fourier infra-merah, mikroskop elektron imbasan, kuasa termoelektrik dan magnetorintangan. Kedua, eksperimen utama yang terdiri dari pengukuran kekonduksian arus terus dan kekonduksian arus ulang alik.

Hasil eksperimen asas menunjukkan karbon aktif yang disediakan dari tempurung kelapa adalah bersifat amorfus, mengandungi banyak kumpulan berfungsi, kalium, naterium dan beberapa jumlah kecil unsur-unsur lain. Ianya juga mempunyai mikrostruktur dengan keliangan yang tinggi. Dari plot termokuasa melawan suhu didapati lohong adalah pembawa cas utama pada suhu di bawah 385K sementara pada suhu tinggi elektron adalah pembawa utama.

Hasil eksperimen perubahan kekonduksian arus terus terhadap suhu dan pergantungan kekonduksian arus ulang alik terhadap frekuensi pada beberapa suhu tertentu menunjukkan mekanisme kekonduksian dalam karbon aktif tempurung-kelapa terbahagi kepada tiga bahagian. Pertama, mekanisme kekonduksian loncatan julat-berubah berlaku di antara keadaan-keadaan tempatan yang berhampiran dengan paras Fermi pada suhu di bawah 200K; kedua, mekanisme kekonduksian loncatan berlaku di antara keadaan-keadaan tempatan dalam daerah jalur ekor untuk suhu sekitar 200 hingga 385K dan ketiga, mekanisme kekonduksian perkolasi yang menonjol pada dan bahagian atas sisi kelincahan untuk suhu melebihi 385K.

Graf konduksian arus ulang alik terhadap suhu menunjukkan konduksian sangat dipengaruhi oleh proses pengutapan tertentu. Hasil pengukuran sambutan-dielektrik dan hasil analisis litar-setara menunjukkan pengutapan antaramukaan adalah berkemungkinan besar bertanggungjawab bagi tabiat dielektrik yang diamati.



# CHAPTER I

## THE BASIS AND OBJECTIVES OF THIS RESEARCH

Activated carbons which are porous carbonaceous materials have been the subject of numerous laboratory investigations, particularly adsorption studies. A literature survey on the properties of activated carbon shows that the investigations were largely concerned with the materials' chemical behaviour. Only a few papers have been published on the studies on their physical properties. The latter type of study is mainly focused on the microscopic nature of electrical conduction. In addition, most of the works on the electrical properties of carbonaceous materials have been carried out on graphite, coke, carbon black and amorphous carbon thin films. Activated carbon (charcoal) prepared from biological materials such as wood, coconut shells, bamboo etc. have been the subject of still fewer electrical investigations. In this work, a material of this type will be the object for an experimental analysis.

At the outset, however, it must be stated that the research work will commence with a material whose structural details are far from clear, except for a generally accepted picture of disordered turbostratic structure (Mattson and Mark Jr., 1971).

