

Technical University of Denmark



Degradation studies of spray coated polymer films using cantilever sensors

Almdal, Kristoffer; Bose-Goswami, Sanjukta; Keller, Stephan Sylvest; Alstrøm, Tommy Sonne; Boisen, Anja

Publication date:
2015

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Almdal, K., Bose, S., Keller, S. S., Alstrøm, T. S., & Boisen, A. (2015). Degradation studies of spray coated polymer films using cantilever sensors. Poster session presented at Fourth International Symposium Frontiers in Polymer Science, Riva del Garda , Italy.

DTU Library
Technical Information Center of Denmark

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal


If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Degradation studies of spray coated polymer films using cantilever sensors

Kristoffer Almdal¹, Sanjukta Bose¹, Stephan S. Keller¹, Tommy Sonne Alstrøm², Anja Boisen¹


Technical University of Denmark. 1: Department of Nanotechnology, 2: Department of Applied Mathematics and Computer Science

Micromechanical sensors (cantilevers & strings) are versatile characterization tools for polymers. Miniaturized samples allow for fast and precise characterization of polymer degradation processes. Thin polymer layer are placed on cantilevers using a newly developed spray coating process. The spray coating process have been tested on various polymers - polyvinylpyrrolidone (PVP) and poly (D, L-lactide)



¹ Sanjukta Bose; Stephan S. Keller; Tommy Sonne Alstrøm; Anja Boisen & Kristoffer Almdal: Process Optimization of Ultrasonic Spray Coating of Polymer Films. *Langmuir*, **29**, 6911–6919 (2013)
² Sanjukta Bose; Stephan S. Keller; Anja Boisen & Kristoffer Almdal: Cantilever Sensors as a Tool to Measure Enzymatic Degradation of Poly (D, L-lactide) Coatings. *Polymer Degradation and Stability*, **119**, 1–8 (2015)
 Sanjukta Bose; Silvan Schmid; Tom Larsen; Stephan S. Keller; Anja Boisen & Kristoffer Almdal: Micromechanical fast quasi-static detection of alpha and beta relaxations with nanograms of polymer. *Journal of Polymer Science, Part B: Polymer Physics*, (2015) in press
 Sanjukta Bose; Silvan Schmid; Tom Larsen; Stephan S. Keller; Peter Sommer-Larsen; Anja Boisen & Kristoffer Almdal: Micromechanical String Resonators: Analytical Tool for Thermal Characterization of Polymers. *ACS Macro Letters*, **3**, 55–58 (2013)

Coating options



Blank cantilevers






Cantilever coated with ~4µm PDLLA

Masks available for:
Partial coating of cantilevers e.g


only coated at tip

only coated at the base


one or two cantilevers out of 8 left uncoated




Degradation in 50 µg/ml proteinase K, 37°C. Sample removed from solution for each measurement




Prehydration: 3 hours in buffer. 50 µg/ml proteinase K solution degradation



Finite element modeling of the sandwich structure is used to extract degradation rates for thickness and width of film independently




Proteinase K degradation of PDLLA



Optical micrographs; proteinase K, 37°C 10 µg/ml (a-c); 50 µg/ml (d-f). all pictures at same scale. 3 regime indicated in h.

Initial delay is followed by rapid degradation. This is apparently due to water swelling kinetics



Exposure to enzyme solution followed by buffer. x h E + y h B: x hours in enzyme solution followed by y hours in buffer

The enzyme will adsorb to the PDLLA film in relatively short time which allow the degradation to continue after washing


Getting a uniform sample on the cantilever:

Dry regime - similar to powder arriving at the surface:

solvent too volatile
substrate too hot
spraying nozzle-substrate distance too large


Wet regime - similar to pouring a solution on the substrate:

solvent not sufficiently volatile
substrate too cold
spraying nozzle-substrate




Optimum: enough flow to ensure a continuous film. Insufficient flow to generate capillary flow mediated accumulation of material at the edge

The spraying is accomplished using ultrasonic spray coating. The ultra sound driven nozzle produces very small solution drops




Cantilever theory - 1



Within linear elasticity:

$$EI \frac{\partial^4 U(x,t)}{\partial x^4} + \rho A \frac{\partial^2 U(x,t)}{\partial t^2} = 0$$

EI (assumed constant):
Young's modulus and $I = wh^3/12$
 $U(x,t)$: beam displacement
 ρ : density; $A = wh$




The eigenfrequencies

$$f_n = \frac{\lambda_n^2 h}{2\pi L^2} \sqrt{\frac{E}{12\rho}} = \frac{1}{2\pi} \sqrt{\frac{k_{eff}}{m_{eff}}}, n = 1, 2, \dots$$

λ_n constants representing the eigenfrequencies
 $\lambda_n = c_n L = 1.875, 4.694, 7.855, \dots; n = 1, 2, 3, \dots$
 $k_{eff} = k_{static} \lambda_n^4 / 12 = \lambda_n^4 E w h^3 / (4 \times 12 L^3)$
 $m_{eff} = \rho w h L / 4$ to give analogy with the harmonic oscillator

For the cantilevers used here (Micromotive GmbH, Octo500D), silicon 100 surface
 $E = 170 \text{ GPa}$ $w = 90 \mu\text{m}$ $h = 5.0 \pm 0.3 \mu\text{m}$ $L = 470 \mu\text{m}$

Cantilevers theory - 2



A coated cantilever leads to the following modifications:

$$k_{eff} = \sum_i \frac{\lambda_n^4 E_i w h_i (z_n - z_i)^2}{48 L^3} = \lambda_n^4 \sum_i \frac{E_i I_i}{4 L^3}$$

The moments of inertia have to be calculated relative to the neutral (zero strain) plane, z_n . For $E_{Si} I_{Si} \gg E_{pol} I_{pol}$ the neutral plane does not move and k_{eff} is unchanged compare to the uncoated cantilever. Note $E_{Si} \geq 50 E_{pol}$

$$m_{eff} = \frac{Lw}{4} \sum_i \rho_i h_i$$

⇒ Frequency change dominated by added coating mass



Conclusions

- An understanding on how to find optimum spray coating conditions for producing uniform micrometer thick films on cantilevers has been established. One needs to be on the borderline between "dry" and "wet" regimes.
- As long as the flexural stiffness of the polymer coat is small compared to the silicon cantilever, the cantilever eigenfrequency is a measure of mass
- The degradation process has an induction period which is due to water swelling kinetics and possibly enzyme absorption kinetics on the polymer
- A versatile platform for fast polymer degradation investigations have been established