

Title: Wrinkling Labyrinth Patterns on Elastomeric Janus Particles

Author(s): Trindade, A. C.^{1,2}; Canejo, J. P.³; Pinto, L. F. V.^{1,2}; Patrício, P.^{3,4}; Brogueira, P.^{5,6}; Teixeira, P. I. C.^{3,4}; Godinho, M. H.^{1,2}

Source: Macromolecules

Volume: 44 **Issue:** 7 **Pages:** 2220-2228 **DOI:** 10.1021/ma1025169 **Published:** Apr 12 2011

Document Type: Article

Language: English

Abstract: We describe a novel, low-cost and low-tech method for the fabrication of elastomeric Janus particles with diameters ranging from micrometers to millimeters. This consists of UV-irradiating soft urethane/urea elastomer spheres, which are then extracted in toluene and dried. The spheres are thus composed of a single material: no coating or film deposition steps are required. Furthermore, the whole procedure is carried out at ambient temperature and pressure. Long, labyrinthine corrugations ("wrinkles") appear on the irradiated portions of the particles' surfaces, the spatial periodicity of which can be controlled by varying the sizes of particles. The asymmetric morphology of the resulting Janus particles has been confirmed by scanning electron microscopy, atomic force microscopy, and optical microscopy. We have also established that the spheres behave elastically by performing bouncing tests with dried and swollen spheres. Results can be interpreted by assuming that each sphere consists of a thin, stiff surface layer ("skin") lying atop a thicker, softer substrate ("bulk"). The skin's higher stiffness is hypothesized to result from the more extensive cross-linking of the polymer chains located near the surface by the UV radiation. Textures then arise from competition between the effects of bending the skin and compressing the bulk, as the solvent evaporates and the sphere shrinks.

KeyWords Plus: Oil-Water Interface; Urethane/Urea Elastomer; Soft Matter; Spheres; Fabrication; Polymer

Reprint Address: Godinho, MH (reprint author), Univ Nova Lisboa, Dept Ciencia Mat, P-2829516 Caparica, Portugal.

Addresses:

1. Univ Nova Lisboa, Dept Ciencia Mat, P-2829516 Caparica, Portugal
2. Univ Nova Lisboa, CENIMAT I3N, Fac Ciencias & Tecnol, P-2829516 Caparica, Portugal
3. Inst Super Engn Lisboa, P-1959007 Lisbon, Portugal
4. Univ Lisbon, Ctr Fis Teor & Computac, P-1649003 Lisbon, Portugal
5. Univ Tecn Lisbon, Dept Fis, P-1049001 Lisbon, Portugal
6. Univ Tecn Lisbon, ICEMS, Inst Super Tecn, P-1049001 Lisbon, Portugal

Funding:

Funding Agency	Grant Number
Portuguese Science and Technology Foundation	SFRH/BD/37958/2007 SFRH/BPD/64330/2009 PTDC/CTM/099595/2008
CENIMAT/I3N	
ICEMS	
CFTC	

Publisher: Amer Chemical SOC

Publisher Address: 1155 16TH ST, NW, Washington, DC 20036 USA

ISSN: 0024-9297

Citation: TRINDADE, A. C.; CANEJO, J. P.; PINTO, L. F. V.; PATRÍCIO, P.; BROGUEIRA, P.; TEIXEIRA, P. I. C.; GODINHO, M. H. - Wrinkling Labyrinth Patterns on Elastomeric Janus Particles. Macromolecules. ISSN 0024-9297. Vol. 44, nº7 (2011) p.2220-2228.