

Tropical Journal of Pharmaceutical Research, June 2006; 5 (1): 561-573

© Pharmacotherapy Group,
Faculty of Pharmacy, University of Benin,
Benin City, Nigeria.

All rights reserved.

Available online at <http://www.tjpr.freehosting.net>

Research Article

Nanoparticles – A Review

VJ Mohanraj^{1*} and Y Chen²

¹Orchid Chemicals & Pharmaceuticals Limited, Chennai, India

²School of Pharmacy, Curtin University of Technology, Perth, Australia

Abstract

For the past few decades, there has been a considerable research interest in the area of drug delivery using particulate delivery systems as carriers for small and large molecules. Particulate systems like nanoparticles have been used as a physical approach to alter and improve the pharmacokinetic and pharmacodynamic properties of various types of drug molecules. They have been used in vivo to protect the drug entity in the systemic circulation, restrict access of the drug to the chosen sites and to deliver the drug at a controlled and sustained rate to the site of action. Various polymers have been used in the formulation of nanoparticles for drug delivery research to increase therapeutic benefit, while minimizing side effects. Here, we review various aspects of nanoparticle formulation, characterization, effect of their characteristics and their applications in delivery of drug molecules and therapeutic genes.

Key words: nanoparticles, drug delivery, targeting, drug release

*Corresponding Author: E-mail: mohanraj_67@hotmail.com, Tel: +91-9840464216

INTRODUCTION

Nanoparticles are defined as particulate dispersions or solid particles with a size in the range of 10-1000nm. The drug is dissolved, entrapped, encapsulated or attached to a nanoparticle matrix. Depending upon the method of preparation, nanoparticles, nanospheres or nanocapsules can be obtained. Nanocapsules are systems in which the drug is confined to a cavity surrounded by a unique polymer membrane, while nanospheres are matrix systems in which the drug is physically and uniformly dispersed. In recent years, biodegradable polymeric nanoparticles, particularly those coated with hydrophilic polymer such as poly(ethylene glycol) (PEG) known as long-circulating particles, have been used as potential drug delivery devices because of their ability to circulate for a prolonged period time target a particular organ, as carriers of DNA in gene therapy, and their ability to deliver proteins, peptides and genes¹⁻⁴.

The major goals in designing nanoparticles as a delivery system are to control particle size, surface properties and release of pharmacologically active agents in order to achieve the site-specific action of the drug at the therapeutically optimal rate and dose regimen. Though liposomes have been used as potential carriers with unique advantages including protecting drugs from degradation, targeting to site of action and reduction toxicity or side effects, their applications are limited due to inherent problems such as low encapsulation efficiency, rapid leakage of water-soluble drug in the presence of blood components and poor storage stability. On the other hand, polymeric nanoparticles offer some specific advantages over liposomes. For instance, they help to increase the stability of drugs/proteins and possess useful controlled release properties^{5, 6}. The advantages of using nanoparticles as a drug delivery system include the following:

1. Particle size and surface characteristics of nanoparticles can be easily manipulated to achieve both passive and active drug targeting after parenteral administration.

2. They control and sustain release of the drug during the transportation and at the site of localization, altering organ distribution of the drug and subsequent clearance of the drug so as to achieve increase in drug therapeutic efficacy and reduction in side effects.

3. Controlled release and particle degradation characteristics can be readily modulated by the choice of matrix constituents.

Drug loading is relatively high and drugs can be incorporated into the systems without any chemical reaction; this is an important factor for preserving the drug activity.

4. Site-specific targeting can be achieved by attaching targeting ligands to surface of particles or use of magnetic guidance.

5. The system can be used for various routes of administration including oral, nasal, parenteral, intra-ocular etc.

In spite of these advantages, nanoparticles do have limitations. For example, their small size and large surface area can lead to particle-particle aggregation, making physical handling of nanoparticles difficult in liquid and dry forms. In addition, small particles size and large surface area readily result in limited drug loading and burst release. These practical problems have to be overcome before nanoparticles can be used clinically or made commercially available. The present review details the latest development of nanoparticulate drug delivery systems, surface modification issues, drug loading strategies, release control and potential applications of nanoparticles.

Preparation of Nanoparticles

Nanoparticles can be prepared from a variety of materials such as proteins, polysaccharides and synthetic polymers. The selection of matrix materials is dependent on many factors including⁷: (a) size of nanoparticles required; (b) inherent properties of the drug, e.g., aqueous solubility and stability; (c) surface characteristics such as charge and permeability; (d) degree of biodegradability, biocompatibility and toxicity; (e)

Drug release profile desired; and (f) Antigenicity of the final product.

Nanoparticles have been prepared most frequently by three methods: (1) dispersion of preformed polymers; (2) polymerization of monomers; and (3) ionic gelation or coacervation of hydrophilic polymers. However, other methods such as supercritical fluid technology⁸ and particle replication in non-wetting templates (PRINT)⁹ have also been described in the literature for production of nanoparticles. The latter was claimed to have absolute control of particle size, shape and composition, which could set an example for the future mass production of nanoparticles in industry.

Dispersion of preformed polymers: Dispersion of preformed polymers is a common technique used to prepare biodegradable nanoparticles from poly (lactic acid) (PLA); poly (D,L-glycolide), PLG; poly (D, L-lactide-co-glycolide) (PLGA) and poly (cyanoacrylate) (PCA),¹⁰⁻¹². This technique can be used in various ways as described below.

Solvent evaporation method: In this method, the polymer is dissolved in an organic solvent such as dichloromethane, chloroform or ethyl acetate which is also used as the solvent for dissolving the hydrophobic drug. The mixture of polymer and drug solution is then emulsified in an aqueous solution containing a surfactant or emulsifying agent to form an oil in water (o/w) emulsion. After the formation of stable emulsion, the organic solvent is evaporated either by reducing the pressure or by continuous stirring. Particle size was found to be influenced by the type and concentrations of stabilizer, homogenizer speed and polymer concentration¹³. In order to produce small particle size, often a high-speed homogenization or ultrasonication may be employed¹⁴.

Spontaneous emulsification or solvent diffusion method: This is a modified version of solvent evaporation method¹⁵. In this method, the water-miscible solvent along with a small amount of the water immiscible organic solvent is used as an oil phase. Due to the spontaneous diffusion of solvents an interfacial turbulence is created

between the two phases leading to the formation of small particles. As the concentration of water miscible solvent increases, a decrease in the size of particle can be achieved.

Both solvent evaporation and solvent diffusion methods can be used for hydrophobic or hydrophilic drugs. In the case of hydrophilic drug, a multiple w/o/w emulsion needs to be formed with the drug dissolved in the internal aqueous phase.

Polymerization method

In this method, monomers are polymerized to form nanoparticles in an aqueous solution. Drug is incorporated either by being dissolved in the polymerization medium or by adsorption onto the nanoparticles after polymerization completed. The nanoparticle suspension is then purified to remove various stabilizers and surfactants employed for polymerization by ultracentrifugation and re-suspending the particles in an isotonic surfactant-free medium. This technique has been reported for making polybutylcyanoacrylate or poly (alkylcyanoacrylate) nanoparticles^{16,17}. Nanocapsule formation and their particle size depends on the concentration of the surfactants and stabilizers used¹⁸.

Coacervation or ionic gelation method

Much research has been focused on the preparation of nanoparticles using biodegradable hydrophilic polymers such as chitosan, gelatin and sodium alginate. Calvo and co-workers developed a method for preparing hydrophilic chitosan nanoparticles by ionic gelation^{19, 20}. The method involves a mixture of two aqueous phases, of which one is the polymer chitosan, a di-block co-polymer ethylene oxide or propylene oxide (PEO-PPO) and the other is a polyanion sodium tripolyphosphate. In this method, positively charged amino group of chitosan interacts with negative charged tripolyphosphate to form coacervates with a size in the range of nanometer. Coacervates are formed as a result of electrostatic interaction between two aqueous phases, whereas, ionic gelation involves the material undergoing transition from liquid to gel

due to ionic interaction conditions at room temperature.

Production of nanoparticles using supercritical fluid technology

Conventional methods such as solvent extraction-evaporation, solvent diffusion and organic phase separation methods require the use of organic solvents which are hazardous to the environment as well as to physiological systems. Therefore, the supercritical fluid technology has been investigated as an alternative to prepare biodegradable micro- and nanoparticles because supercritical fluids are environmentally safe²¹.

A supercritical fluid can be generally defined as a solvent at a temperature above its critical temperature, at which the fluid remains a single phase regardless of pressure²¹. Supercritical CO₂ (SC CO₂) is the most widely used supercritical fluid because of its mild critical conditions ($T_c = 31.1\text{ }^\circ\text{C}$, $P_c = 73.8\text{ bars}$), non-toxicity, non-flammability, and low price. The most common processing techniques involving supercritical fluids are supercritical anti-solvent (SAS) and rapid expansion of critical solution (RESS). The process of SAS employs a liquid solvent, eg methanol, which is completely miscible with the supercritical fluid (SC CO₂), to dissolve the solute to be micronized; at the process conditions, because the solute is insoluble in the supercritical fluid, the extract of the liquid solvent by supercritical fluid leads to the instantaneous precipitation of the solute, resulting the formation of nanoparticles⁸. Thote and Gupta (2005) reported the use of a modified SAS method for formation of hydrophilic drug dexamethasone phosphate drug nanoparticles for microencapsulation purpose²².

RESS differs from the SAS process in that its solute is dissolved in a supercritical fluid (such as supercritical methanol) and then the solution is rapidly expanded through a small nozzle into a region lower pressure²¹, Thus the solvent power of supercritical fluids dramatically decreases and the solute eventually precipitates. This technique is clean because the precipitate is basically solvent free. RESS and its modified

process have been used for the product of polymeric nanoparticles²³. Supercritical fluid technology technique, although environmentally friendly and suitable for mass production, requires specially designed equipment and is more expensive.

Effect of Characteristics of Nanoparticles on Drug Delivery

Particle size

Particle size and size distribution are the most important characteristics of nanoparticle systems. They determine the *in vivo* distribution, biological fate, toxicity and the targeting ability of nanoparticle systems. In addition, they can also influence the drug loading, drug release and stability of nanoparticles.

Many studies have demonstrated that nanoparticles of sub-micron size have a number of advantages over microparticles as a drug delivery system²⁴. Generally nanoparticles have relatively higher intracellular uptake compared to microparticles and available to a wider range of biological targets due to their small size and relative mobility. Desai et al found that 100 nm nanoparticles had a 2.5 fold greater uptake than 1 μm microparticles, and 6 fold greater uptake than 10 μm microparticles in a Caco-2 cell line²⁵. In a subsequent study²⁶, the nanoparticles penetrated throughout the submucosal layers in a rat *in situ* intestinal loop model, while microparticles were predominantly localized in the epithelial lining. It was also reported that nanoparticles can cross the blood-brain barrier following the opening of tight junctions by hyper osmotic mannitol, which may provide sustained delivery of therapeutic agents for difficult-to-treat diseases like brain tumors²⁷. Tween 80 coated nanoparticles have been shown to cross the blood-brain barrier²⁸. In some cell lines, only submicron nanoparticles can be taken up efficiently but not the larger size microparticles²⁹.

Drug release is affected by particle size. Smaller particles have larger surface area, therefore, most of the drug associated would be at or near the particle surface, leading to fast drug release. Whereas, larger particles have large cores which allow more drug to be encapsulated and slowly

diffuse out³⁰. Smaller particles also have greater risk of aggregation of particles during storage and transportation of nanoparticle dispersion. It is always a challenge to formulate nanoparticles with the smallest size possible but maximum stability.

Polymer degradation can also be affected by the particle size. For instance, the rate of PLGA polymer degradation was found to increase with increasing particle size *in vitro*³¹. It was thought that in smaller particles, degradation products of PLGA formed can diffuse out of the particles easily while in large particles, degradation products are more likely remained within the polymer matrix for a longer period to cause autocatalytic degradation of the polymer material. Therefore, it was hypothesized that larger particles will contribute to faster polymer degradation as well as the drug release. However, Panyam et al prepared PLGA particles with different size ranges and found that the polymer degradation rates *in vitro* were not substantially different for different size particles³².

Currently, the fastest and most routine method of determining particle size is by photon-correlation spectroscopy or dynamic light scattering. Photon-correlation spectroscopy requires the viscosity of the medium to be known and determines the diameter of the particle by Brownian motion and light scattering properties³³. The results obtained by photon-correlation spectroscopy are usually verified by scanning or transmission electron microscopy (SEM or TEM).

Surface properties of nanoparticles

When nanoparticles are administered intravenously, they are easily recognized by the body immune systems, and are then cleared by phagocytes from the circulation³⁴. Apart from the size of nanoparticles, their surface hydrophobicity determines the amount of adsorbed blood components, mainly proteins (opsonins). This in turn influences the *in vivo* fate of nanoparticles^{34, 35}. Binding of these opsonins onto the surface of nanoparticles called opsonization acts as a bridge between nanoparticles and phagocytes. The association of a drug to conventional carriers leads to

modification of the drug biodistribution profile, as it is mainly delivered to the mononuclear phagocytes system (MPS) such as liver, spleen, lungs and bone marrow. Indeed, once in the blood stream, surface non-modified nanoparticles (conventional nanoparticles) are rapidly opsonized and massively cleared by the macrophages of MPS rich organs³⁶. Generally, it is IgG, complement C₃ components that are used for recognition of foreign substances, especially foreign macromolecules.

Hence, to increase the likelihood of the success in drug targeting by nanoparticles, it is necessary to minimize the opsonization and to prolong the circulation of nanoparticles *in vivo*. This can be achieved by (a) surface coating of nanoparticles with hydrophilic polymers/surfactants; (b) formulation of nanoparticles with biodegradable copolymers with hydrophilic segments such as polyethylene glycol (PEG), polyethylene oxide, polyoxamer, poloxamine and polysorbate 80 (Tween 80).

Studies show that PEG conformation at the nanoparticle surface is of utmost importance for the opsonin repelling function of the PEG layer. PEG surfaces in brush-like and intermediate configurations reduced phagocytosis and complement activation whereas PEG surfaces in mushroom-like configuration were potent complement activators and favoured phagocytosis^{2, 37}.

The zeta potential of a nanoparticle is commonly used to characterise the surface charge property of nanoparticles³⁸. It reflects the electrical potential of particles and is influenced by the composition of the particle and the medium in which it is dispersed. Nanoparticles with a zeta potential above (+/-) 30 mV have been shown to be stable in suspension, as the surface charge prevents aggregation of the particles. The zeta potential can also be used to determine whether a charged active material is encapsulated within the centre of the nanocapsule or adsorbed onto the surface.

Drug loading

Ideally, a successful nanoparticulate system should have a high drug-loading capacity thereby reduce the quantity of matrix materials for administration. Drug loading can be done by two methods:

- Incorporating at the time of nanoparticles production (incorporation method)
- Absorbing the drug after formation of nanoparticles by incubating the carrier with a concentrated drug solution (adsorption/absorption technique).

Drug loading and entrapment efficiency very much depend on the solid-state drug solubility in matrix material or polymer (solid dissolution or dispersion), which is related to the polymer composition, the molecular weight, the drug polymer interaction and the presence of end-functional groups (ester or carboxyl)^{39 40 41}. The PEG moiety has no or little effect on drug loading⁴². The macromolecule or protein shows greatest loading efficiency when it is loaded at or near its isoelectric point when it has minimum solubility and maximum adsorption¹⁹. For small molecules, studies show the use of ionic interaction between the drug and matrix materials can be a very effective way to increase the drug loading^{43, 44}.

Drug release

To develop a successful nanoparticulate system, both drug release and polymer biodegradation are important consideration factors. In general, drug release rate depends on: (1) solubility of drug; (2) desorption of the surface-bound/adsorbed drug; (3) drug diffusion through the nanoparticle matrix; (4) nanoparticle matrix erosion/degradation; and (5) combination of erosion/diffusion process. Thus solubility, diffusion and biodegradation of the matrix materials govern the release process.

In the case of nanospheres, where the drug is uniformly distributed, the release occurs by diffusion or erosion of the matrix under sink conditions. If the diffusion of the drug is faster than matrix erosion, the mechanism of release is largely controlled by a diffusion process. The rapid initial release or 'burst' is mainly attributed to weakly bound or adsorbed drug to the large

surface of nanoparticles⁴⁵. It is evident that the method of incorporation has an effect on release profile. If the drug is loaded by incorporation method, the system has a relatively small burst effect and better sustained release characteristics⁴⁶. If the nanoparticle is coated by polymer, the release is then controlled by diffusion of the drug from the core across the polymeric membrane. The membrane coating acts as a barrier to release, therefore, the solubility and diffusivity of drug in polymer membrane becomes determining factor in drug release. Furthermore release rate can also be affected by ionic interaction between the drug and addition of auxiliary ingredients. When the drug is involved in interaction with auxiliary ingredients to form a less water soluble complex, then the drug release can be very slow with almost no burst release effect⁴³; whereas if the addition of auxiliary ingredients e.g., addition of ethylene oxide-propylene oxide block copolymer (PEO-PPO) to chitosan, reduces the interaction of the model drug bovine serum albumin (BSA) with the matrix material (chitosan) due to competitive electrostatic interaction of PEO-PPO with chitosan, then an increase in drug release could be observed²⁰.

Various methods which can be used to study the *in vitro* release of the drug are: (1) side-by-side diffusion cells with artificial or biological membranes; (2) dialysis bag diffusion technique; (3) reverse dialysis bag technique; (4) agitation followed by ultracentrifugation/centrifugation; (5) Ultra-filtration or centrifugal ultra-filtration techniques. Usually the release study is carried out by controlled agitation followed by centrifugation. Due to the time-consuming nature and technical difficulties encountered in the separation of nanoparticles from release media, the dialysis technique is generally preferred.

Applications of Nanoparticulate Delivery Systems

Tumor targeting using nanoparticulate delivery systems

The rationale of using nanoparticles for tumor targeting is based on 1) nanoparticles will be able to deliver a concentrate dose of drug in the

vicinity of the tumor targets via the enhanced permeability and retention effect or active targeting by ligands on the surface of nanoparticles; 2) nanoparticles will reduce the drug exposure of health tissues by limiting drug distribution to target organ.

Verdun et al demonstrated in mice treated with doxorubicin incorporated into poly (iso-hexylcyanoacrylate) nanoparticles that higher concentrations of doxorubicin manifested in the liver, spleen and lungs than in mice treated with free doxorubicin⁴⁷. Studies show that the polymeric composition of nanoparticles such as type, hydrophobicity and biodegradation profile of the polymer along with the associated drug's molecular weight, its localization in the nanospheres and mode of incorporation technique, adsorption or incorporation, have a great influence on the drug distribution pattern *in vivo*. The exact underlying mechanism is not fully understood but the biodistribution of nanoparticles is rapid, within ½ hour to 3 hours, and it likely involves MPS and endocytosis/phagocytosis process⁴⁸.

Recently Bibby et al reported the biodistribution and pharmacokinetics (PK) of a cyclic RGD-doxorubicin-nanoparticle formulation in tumor-bearing mice⁴⁹. Their biodistribution studies revealed decreasing drug concentrations over time in the heart, lung, kidney and plasma and accumulating drug concentrations in the liver, spleen and tumor. The majority injected dose appeared in the liver (56%) and only 1.6% in the tumour at 48 hrs post injection, confirming that nanoparticles have a great tendency to be captured by liver. This indicates the greatest challenge of using nanoparticles for tumour targeting is to avoid particle uptake by mononuclear phagocytic system (MPS) in liver and spleen.

Such propensity of MPS for endocytosis/phagocytosis of nanoparticles provides an opportunity to effectively deliver therapeutic agents to these cells. This biodistribution can be of benefit for the chemotherapeutic treatment of MPS-rich organs/tissues localized tumors like hepatocarcinoma, hepatic metastasis arising from

digestive tract or gynaecological cancers, bronchopulmonary tumors, primitive tumors and metastasis, small cell tumors, myeloma and leukemia. It has been proved that using doxorubicin loaded conventional nanoparticles was effective against hepatic metastasis model in mice. It was found there was greater reduction in the degree of metastasis than when free drug was used. The underlying mechanism responsible for the increased therapeutic efficacy of the formulation was transfer of doxorubicin from healthy tissue, acting as a drug reservoir to the malignant tissues⁵⁰. Histological examination showed a considerable accumulation of nanoparticles in the lysosomal vesicles of Kupffer cells, whereas nanoparticles could not be clearly identified in tumoral cells⁵⁰. Thus Kupffer cells, after a massive uptake of nanoparticles by phagocytosis, were able to induce the release of doxorubicin, leading to a gradient of drug concentration, favorable for a prolonged diffusion of the free and still active drug towards the neighboring metastatic cells⁵⁰.

When conventional nanoparticles are used as carriers in chemotherapy, some cytotoxicity against the Kupffer cells can be expected, which would result in deficiency of Kupffer cells and naturally lead to reduced liver uptake and decreased therapeutic effect with intervals of less than 2 weeks administration⁵¹. Moreover, conventional nanoparticles can also target bone marrow (MPS tissue), which is an important but unfavorable site of action for most anticancer drugs because chemotherapy with such carriers may increase myelosuppressive effect. Therefore, the ability of conventional nanoparticles to enhance anticancer drugs efficacy is limited to targeting tumors at the level of MPS-rich organs. Also, directing anticancer drug-loaded nanoparticles to other tumoral sites is not feasible if a rapid clearance of nanoparticles occurs shortly after intravenous administration.

Long circulating nanoparticles

To be successful as a drug delivery system, nanoparticles must be able to target tumors which are localized outside MPS-rich organs. In the past decade, a great deal of work has been devoted to developing so-called "stealth"

particles or PEGylated nanoparticles, which are invisible to macrophages or phagocytes⁵². A major breakthrough in the field came when the use of hydrophilic polymers (such as polyethylene glycol, poloxamines, poloxamers, and polysaccharides) to efficiently coat conventional nanoparticle surface produced an opposing effect to the uptake by the MPS^{52, 53}. These coatings provide a dynamic "cloud" of hydrophilic and neutral chains at the particle surface which repel plasma proteins^{54, 55}. As a result, those coated nanoparticles become invisible to MPS, therefore, remained in the circulation for a longer period of time. Hydrophilic polymers can be introduced at the surface in two ways, either by adsorption of surfactants or by use of block or branched copolymers for production of nanoparticles^{51, 52}.

Studies show nanoparticles containing a coat of PEG not only have a prolonged half-life in the blood compartment but also be able to selectively extravasate in pathological sites such as tumors or inflamed regions with a leaky vasculature⁵¹. As a result, such long-circulating nanoparticles have increased the potential to directly target tumors located outside MPS-rich regions⁵¹. The size of the colloidal carriers as well as their surface characteristics are the critical to the biological fate of nanoparticles. A size less than 100 nm and a hydrophilic surface are essential in achieving the reduction of opsonisation reactions and subsequent clearance by macrophages⁵². Coating conventional nanoparticles with surfactants or PEG to obtain a long-circulating carrier has now been used as a standard strategy for drug targeting *in vivo*.

Extensive efforts have been devoted to achieving "active targeting" of nanoparticles in order to deliver drugs to the right targets, based on molecular recognition processes such as ligand-receptor or antigen-antibody interaction. Considering that fact that folate receptors are over expressed on the surface of some human malignant cells and the cell adhesion molecules such as selectins and integrins are involved in metastatic events, nanoparticles bearing specific ligands such as folate may be used to target

ovarian carcinoma while specific peptides or carbohydrates may be used to target integrins and selectins⁵⁶. Oyewumi et al demonstrated that the benefits of folate ligand coating were to facilitate tumor cell internalization and retention of Gd-nanoparticles in the tumor tissue⁵⁷.

Targeting with small ligands appears more likely to succeed since they are easier to handle and manufacture. Furthermore, it could be advantageous when the active targeting ligands are used in combination with the long-circulating nanoparticles to maximize the likelihood of the success in active targeting of nanoparticles.

Reversion of multidrug resistance in tumour cells

Anticancer drugs, even if they are located in the tumour interstitium, can turn out to be of limited efficacy against numerous solid tumour types, because cancer cells are able to develop mechanisms of resistance⁵⁸. These mechanisms allow tumours to evade chemotherapy. Multidrug resistance (MDR) is one of the most serious problems in chemotherapy. MDR occurs mainly due to the over expression of the plasma membrane p-glycoprotein (Pg_p), which is capable of extruding various positively charged xenobiotics, including some anticancer drugs, out of cells⁵⁸. In order to restore the tumoral cells' sensitivity to anticancer drugs by circumventing Pg_p-mediated MDR, several strategies including the use of colloidal carriers have been applied. The rationale behind the association of drugs with colloidal carriers, such as nanoparticles, against drug resistance derives from the fact that Pg_p probably recognizes the drug to be effluxed out of the tumoral cells only when this drug is present in the plasma membrane, and not when it is located in the cytoplasm or lysosomes after endocytosis^{59, 60}.

Nanoparticles for oral delivery of peptides and proteins

Significant advances in biotechnology and biochemistry have led to the discovery of a large number of bioactive molecules and vaccines based on peptides and proteins. Development of suitable carriers remains a challenge due to the

fact that bioavailability of these molecules is limited by the epithelial barriers of the gastrointestinal tract and their susceptibility to gastrointestinal degradation by digestive enzymes. Polymeric nanoparticles allow encapsulation of bioactive molecules and protect them against enzymatic and hydrolytic degradation. For instance, it has been found that insulin-loaded nanoparticles have preserved insulin activity and produced blood glucose reduction in diabetic rats for up to 14 days following the oral administration⁶¹.

The surface area of human mucosa extends to 200 times that of skin⁶². The gastrointestinal tract provides a variety of physiological and morphological barriers against protein or peptide delivery, e.g., (a) proteolytic enzymes in the gut lumen like pepsin, trypsin and chymotrypsin; (b) proteolytic enzymes at the brush border membrane (endopeptidases); (c) bacterial gut flora; and (d) mucus layer and epithelial cell lining itself⁶³. The histological architecture of the mucosa is designed to efficiently prevent uptake of particulate matter from the environment. One important strategy to overcome the gastrointestinal barrier is to deliver the drug in a colloidal carrier system, such as nanoparticles, which is capable of enhancing the interaction mechanisms of the drug delivery system and the epithelia cells in the GI tract.

Targeting of nanoparticles to epithelial cells in the GI tract using ligands

Targeting strategies to improve the interaction of nanoparticles with adsorptive enterocytes and M-cells of Peyer's patches in the GI tract can be classified into those utilizing specific binding to ligands or receptors and those based on non-specific adsorptive mechanism. The surface of enterocytes and M cells display cell-specific carbohydrates, which may serve as binding sites to colloidal drug carriers containing appropriate ligands. Certain glycoproteins and lectins bind selectively to this type of surface structure by specific receptor-mediated mechanism. Different lectins, such as bean lectin and tomato lectin, have been studied to enhance oral peptide adsorption^{64 65}. Vitamin B-12 absorption from the gut under physiological conditions occurs via

receptor-mediated endocytosis. The ability to increase oral bioavailability of various peptides (e.g., granulocyte colony stimulating factor, erythropoietin) and particles by covalent coupling to vitamin B-12 has been studied^{66, 67}. For this intrinsic process, mucoprotein is required, which is prepared by the mucus membrane in the stomach and binds specifically to cobalamin. The mucoprotein completely reaches the ileum where resorption is mediated by specific receptors.

Absorption enhancement using non-specific interactions

In general, the gastrointestinal absorption of macromolecules and particulate materials involves either paracellular route or endocytotic pathway. The paracellular route of absorption of nanoparticles utilises less than 1% of mucosal surface area. Using polymers such as chitosan⁶⁸, starch⁶⁹ or poly(acrylate)⁷⁰ can increase the paracellular permeability of macromolecules. Endocytotic pathway for absorption of nanoparticles is either by receptor-mediated endocytosis, that is, active targeting, or adsorptive endocytosis which does not need any ligands. This process is initiated by an unspecific physical adsorption of material to the cell surface by electrostatic forces such as hydrogen bonding or hydrophobic interactions⁷¹. Adsorptive endocytosis depends primarily on the size and surface properties of the material. If the surface charge of the nanoparticles is positive or uncharged, it will provide an affinity to adsorptive enterocytes though hydrophobic, whereas if it is negatively charged and hydrophilic, it shows greater affinity to adsorptive enterocytes and M-cells. This shows that a combination of size, surface charge and hydrophilicity play a major role in affinity. This is demonstrated with poly (styrene) nanoparticles and when it is carboxylated⁷².

Nanoparticles for gene delivery

Polynucleotide vaccines work by delivering genes encoding relevant antigens to host cells where they are expressed, producing the antigenic protein within the vicinity of professional antigen presenting cells to initiate immune response. Such vaccines produce both

humoral and cell-mediated immunity because intracellular production of protein, as opposed to extracellular deposition, stimulates both arms of the immune system⁷³. The key ingredient of polynucleotide vaccines, DNA, can be produced cheaply and has much better storage and handling properties than the ingredients of the majority of protein-based vaccines. Hence, polynucleotide vaccines are set to supersede many conventional vaccines particularly for immunotherapy. However, there are several issues related to the delivery of polynucleotides which limit their application. These issues include efficient delivery of the polynucleotide to the target cell population and its localization to the nucleus of these cells, and ensuring that the integrity of the polynucleotide is maintained during delivery to the target site.

Nanoparticles loaded with plasmid DNA could also serve as an efficient sustained release gene delivery system due to their rapid escape from the degradative endo-lysosomal compartment to the cytoplasmic compartment⁷⁴. Hedley et al.⁷⁵ reported that following their intracellular uptake and endolysosomal escape, nanoparticles could release DNA at a sustained rate resulting in sustained gene expression. This gene delivery strategy could be applied to facilitate bone healing by using PLGA nanoparticles containing therapeutic genes such as bone morphogenic protein.

Nanoparticles for drug delivery into the brain

The blood-brain barrier (BBB) is the most important factor limiting the development of new drugs for the central nervous system. The BBB is characterized by relatively impermeable endothelial cells with tight junctions, enzymatic activity and active efflux transport systems. It effectively prevents the passage of water-soluble molecules from the blood circulation into the CNS, and can also reduce the brain concentration of lipid-soluble molecules by the function of enzymes or efflux pumps⁷⁶. Consequently, the BBB only permits selective transport of molecules that are essential for brain function.

Strategies for nanoparticle targeting to the brain rely on the presence of and nanoparticle interaction with specific receptor-mediated transport systems in the BBB. For example polysorbate 80/LDL, transferrin receptor binding antibody (such as OX26), lactoferrin, cell-penetrating peptides and melanotransferrin have been shown capable of delivery of a self non transportable drug into the brain via the chimeric construct that can undergo receptor-mediated transcytosis⁷⁷⁻⁸¹. It has been reported poly(butylcyanoacrylate) nanoparticles was able to deliver hexapeptide dalargin, doxorubicin and other agents into the brain which is significant because of the great difficulty for drugs to cross the BBB⁷⁷. Despite some reported success with polysorbate 80 coated NPs, this system does have many shortcomings including desorption of polysorbate coating, rapid NP degradation and toxicity caused by presence of high concentration of polysorbate 80.³⁷ OX26 MAbs (anti-transferrin receptor MAbs), the most studied BBB targeting antibody, have been used to enhance the BBB penetration of liposomes⁸². However, recently, Ji *et al.* demonstrated that brain uptake of lactoferrin, an iron-binding glycoprotein belonging to the transferrin (Tf) family, is twice that of OX26 and transferrin *in vivo*⁷⁹. It is possible soon we will see these BBB specific molecules used for targeting nanoparticles to the brain.

CONCLUSION

The foregoing show that nanoparticulate systems have great potentials, being able to convert poorly soluble, poorly absorbed and labile biologically active substance into promising deliverable drugs. The core of this system can enclose a variety of drugs, enzymes, genes and is characterized by a long circulation time due to the hydrophilic shell which prevents recognition by the reticular-endothelial system. To optimize this drug delivery system, greater understanding of the different mechanisms of biological interactions, and particle engineering, is still required. Further advances are needed in order to turn the concept of nanoparticle technology into a realistic practical application as the next generation of drug delivery system.

References

- Langer R. Biomaterials in drug delivery and tissue engineering: one laboratory's experience. *Acc Chem Res* 2000; 33: 94-101.
- Bhadra D, Bhadra S, Jain P, Jain NK. Pegnology: a review of PEG-ylated systems. *Pharmazie* 2002; 57: 5-29.
- Kommareddy S, Tiwari SB, Amiji MM. Long-circulating polymeric nanovectors for tumor-selective gene delivery. *Technol Cancer Res Treat* 2005; 4: 615-25.
- Lee M, Kim SW. Polyethylene glycol-conjugated copolymers for plasmid DNA delivery. *Pharm Res* 2005; 22: 1-10.
- Vila A, Sanchez A, Tobio M, Calvo P, Alonso MJ. Design of biodegradable particles for protein delivery. *J Control Release* 2002; 78: 15-24.
- Mu L, Feng SS. A novel controlled release formulation for the anticancer drug paclitaxel (Taxol(R)): PLGA nanoparticles containing vitamin E TPGS. *J Control Release* 2003; 86: 33-48.
- Kreuter J. Nanoparticles. In *Colloidal drug delivery systems*, J, K., Ed. Marcel Dekker: New York, 1994; pp 219-342.
- Reverchon E, Adami R. Nanomaterials and supercritical fluids. *The Journal of Supercritical Fluids* 2006; 37: 1-22.
- Rolland JP, Maynor BW, Euliss LE, Exner AE, Denison GM, DeSimone JM. Direct fabrication and harvesting of monodisperse, shape-specific nanobiomaterials. *J. Am. Chem. Soc.* 2005; 127: 10096-10100
- Kompella UB, Bandi N, Ayalasomayajula SP. Poly (lactic acid) nanoparticles for sustained release of budesonide. *Drug Deliv. Technol.* 2001; 1: 1-7.
- Ravi MN, Bakowsky U, Lehr CM. Preparation and characterization of cationic PLGA nanospheres as DNA carriers. *Biomaterials* 2004; 25: 1771-1777.
- Li YP, Pei YY, Zhou ZH, Zhang XY, Gu ZH, Ding J, Zhou JJ, Gao, XJ, PEGylated polycyanoacrylate nanoparticles as tumor necrosis factor-[alpha] carriers. *J Control Release* 2001; 71: 287-296.
- Kwon, HY, Lee JY, Choi SW, Jang Y, Kim JH. Preparation of PLGA nanoparticles containing estrogen by emulsification-diffusion method. *Colloids Surf. A: Physicochem. Eng. Aspects* 2001; 182: 123-130.
- Zambaux M, Bonneaux F, Gref R, Maincent P, Dellacherie E, Alonso M, Labrude P, Vigneron C. Influence of experimental parameters on the characteristics of poly(lactic acid) nanoparticles prepared by double emulsion method. *J. Control. Release* 1998; 50: 31-40.
- Niwa T, Takeuchi H, Hino T, Kunou N, Kawashima Y. Preparation of biodegradable nanoparticles of water-soluble and insoluble drugs with D,L-lactide/glycolide copolymer by a novel spontaneous emulsification solvent diffusion method, and the drug release behavior. *J. Control. Release* 1993; 25: 89-98.
- Zhang Q, Shen Z, Nagai T. Prolonged hypoglycemic effect of insulin-loaded polybutylcyanoacrylate nanoparticles after pulmonary administration to normal rats. *Int. J. Pharm.* 2001; 218: 75-80.
- Boudad H, Legrand P, Lebas G, Cheron M, Duchene D, Ponchel G. Combined hydroxypropyl-[beta]-cyclodextrin and poly(alkylcyanoacrylate) nanoparticles intended for oral administration of saquinavir. *Int J. Pharm.* 2001; 218: 113-124.
- Puglisi G, Fresta M, Giammona G, Ventura CA. Influence of the preparation conditions on poly(ethylcyanoacrylate) nanocapsule formation. *Int. J. Pharm.* 1995; 125: 283-287.
- Calvo P, Remunan-Lopez C, Vila-Jato JL, Alonso MJ. Novel hydrophilic chitosan-polyethylene oxide nanoparticles as protein carriers. *J. Appl. Polymer Sci.* 1997; 63: 125-132.
- Calvo P, Remunan-Lopez C, Vila-Jato JL, Alonso MJ. Chitosan and chitosan/ethylene oxide-propylene oxide block copolymer nanoparticles as novel carriers for proteins and vaccines. *Pharm Res.* 1997; 14: 1431-1436.
- Jung J, Perrut M. Particle design using supercritical fluids: Literature and patent survey. *J. Supercritical Fluids* 2001; 20: 179-219.
- Thote AJ, Gupta RB. Formation of nanoparticles of a hydrophilic drug using supercritical carbon dioxide and microencapsulation for sustained release. *Nanomedicine: Nanotech. Biology Medicine* 2005; 1: 85-90.
- Sun Y, Mezan M, Pathak P, Qu L. Polymeric nanoparticles from rapid expansion of supercritical fluid solution. *Chemistry* 2005; 11: 1366-73.
- Panyam J, Labhasetwar V. Biodegradable nanoparticles for drug and gene delivery to cells and tissue. *Adv Drug Deliv Rev* 2003; 55: 329-47.
- Desai MP, Labhasetwar V, Walter E, Levy RJ, Amidon G L. The mechanism of uptake of biodegradable microparticles in Caco-2 cells is size dependent. *Pharm Res* 1997; 14: 1568-73.
- Desai MP, Labhasetwar V, Amidon GL, Levy RJ. Gastrointestinal uptake of biodegradable microparticles: effect of particle size. *Pharm Res* 1996; 13: 1838-45.
- Kroll RA, Pagel MA, Muldoon LL, Roman-Goldstein S, Fiamengo SA, Neuwelt EA. Improving drug delivery to intracerebral tumor and surrounding brain in a rodent model: a comparison of osmotic versus bradykinin modification of the blood-brain and/or blood-tumor barriers. *Neurosurgery* 1998; 43: 879-86; discussion 886-9.
- Kreuter J, Ramge P, Petrov V, Hamm S, Gelperina SE, Engelhardt B, Alyautdin R, von Briesen H, Begley DJ. Direct evidence that polysorbate-80-coated poly(butylcyanoacrylate) nanoparticles deliver drugs to the CNS via specific mechanisms requiring prior binding of drug to the nanoparticles. *Pharm Res* 2003; 20: 409-16.
- Zauner W, Farrow NA, Haines AM. In vitro uptake of polystyrene microspheres: effect of particle size, cell line and cell density. *J Control Release* 2001; 71: 39-51.
- Redhead HM, Davis SS, Illum L. Drug delivery in poly(lactide-co-glycolide) nanoparticles surface modified with poloxamer 407 and poloxamine 908:

- in vitro characterisation and in vivo evaluation. *J Control Release* 2001; 70: 353-363.
31. Dunne M, Corrigan OI, Ramtoola Z. Influence of particle size and dissolution conditions on the degradation properties of polylactide-co-glycolide particles. *Biomaterials* 2000; 21: 1659-1668.
 32. Panyam J, Dali MM, Sahoo S K, Ma W, Chakravarthi SS, Amidon GL, Levy RJ, Labhasetwar V. Polymer degradation and in vitro release of a model protein from poly(L-lactide-co-glycolide) nano- and microparticles. *J Control Release* 2003; 92: 173-187.
 33. Swarbrick J, Boylan J. *Encyclopedia of pharmaceutical technology*. 2nd ed.; Marcel Dekker: New York, 2002.
 34. Muller RH, Wallis KH. Surface modification of i.v. injectable biodegradable nanoparticles with poloxamer polymers and poloxamine 908. *Int. J. Pharm.* 1993; 89: 25-31.
 35. Brigger I, Dubernet C, Couvreur P. Nanoparticles in cancer therapy and diagnosis. *Adv. Drug Deliv. Rev.* 2002; 54: 631-651.
 36. Grislain L, Couvreur P, Lenaerts V, Roland M, Deprez-Decampeneere D, Speiser P. Pharmacokinetics and distribution of a biodegradable drug-carrier. *Int. J. Pharm.* 1983; 15: 335-345.
 37. Olivier JC. Drug transport to brain with targeted nanoparticles. *NeuroRx* 2005; 2: 108-119.
 38. Couvreur P, Barratt G, Fattal E, Legrand P, Vauthier C. Nanocapsule technology: a review. *Crit Rev Ther Drug Carrier Syst* 2002; 19: 99-134.
 39. Govender T, Stolnik S, Garnett MC, Illum L, Davis SS. PLGA nanoparticles prepared by nanoprecipitation: drug loading and release studies of a water soluble drug. *J. Control. Rel.* 1999; 57: 171-185.
 40. Govender T, Riley T, Ehtezazi T, Garnett MC, Stolnik S, Illum L, Davis SS. Defining the drug incorporation properties of PLA-PEG nanoparticles. *Int J Pharm* 2000; 199: 95-110.
 41. Panyam J, Williams D, Dash A, Leslie-Pelecky D, Labhasetwar V. Solid-state solubility influences encapsulation and release of hydrophobic drugs from PLGA/PLA nanoparticles. *J Pharm Sci* 2004; 93: 1804-14.
 42. Peracchia M, Gref R, Minamitake Y, Domb A, Lotan N, Langer R. PEG-coated nanospheres from amphiphilic diblock and multiblock copolymers: investigation of their drug encapsulation and release characteristics. *J Control Release* 1997; 46: 223-231
 43. Chen Y, McCulloch, RK, Gray BN. Synthesis of albumin-dextran sulfate microspheres possessing favourable loading and release characteristics for the anti-cancer drug doxorubicin. *J Control Release* 1994; 31: 49-54.
 44. Chen Y, Mohanraj VJ, Parkin JE. Chitosan-dextran sulfate nanoparticles for delivery of an antiangiogenesis peptide. *Letters in Peptide Science* 2003; 10: 621-627.
 45. Magenheimer B, Levy MY, Benita S. A new in vitro technique for the evaluation of drug release profile from colloidal carriers - ultrafiltration technique at low pressure. *Int. J. Pharm.* 1993; 94: 115-123.
 46. Fresta M, Puglisi G, Giammona G, Cavallaro G, Micali N, Furneri PM. Pefloxacin mesilate- and ofloxacin-loaded polyethylcyanoacrylate nanoparticles; characterization of the colloidal drug carrier formulation. *J. Pharm. Sci.* 1995; 84: 895-902.
 47. Verdun C, Brasseur F, Vranckx H, Couvreur P, Roland M. Tissue distribution of doxorubicin associated with polyhexylcyanoacrylate nanoparticles. *Cancer Chemother. Pharmacol* 1990; 26: 13-18.
 48. Couvreur P, Kante B, Lenaerts V, Scaiteur V, Roland M, Speiser P. Tissue distribution of antitumor drugs associated with polyalkylcyanoacrylate nanoparticles. *J Pharm Sci* 1980; 69: 199-202.
 49. Bibby DC, Talmadge JE, Dalal MK, Kurz SG, Chytil KM, Barry SE, Shand DG, Steiert M. Pharmacokinetics and biodistribution of RGD-targeted doxorubicin-loaded nanoparticles in tumor-bearing mice. *Int. J. Pharm.* 2005; 293: 281-290.
 50. Chiannilkulchai N, Ammoury N, Caillou B, Devissaguet JP, Couvreur P. Hepatic tissue distribution of doxorubicin-loaded nanoparticles after i.v. administration in reticulosarcoma M 5076 metastasis-bearing mice. *Cancer Chemother Pharmacol* 1990; 26: 122-6.
 51. Moghimi SM, Hunter AC, Murray JC. Long-circulating and target-specific nanoparticles: theory to practice. *Pharmacol Rev* 2001; 53: 283-318.
 52. Storm G, Belliot S, Daemen T, Lasic D. Surface modification of nanoparticles to oppose uptake by the mononuclear phagocyte system. *Adv. Drug Deliv. Rev.* 1995; 17: 31-48.
 53. Torchilin V, Trubetsky V. Which polymer can make nanoparticulate drug carriers long circulating? *Adv. Drug Deliv. Rev.* 1995; 16: 141-155.
 54. Jeon SI, Lee JH, Andrade JD, De Gennes PG. Protein-surface interactions in the presence of polyethylene oxide : I. Simplified theory. *J. Colloid Interface Sci.* 1991; 142: 149-158.
 55. Jeon SI, Andrade JD. Protein-surface interactions in the presence of polyethylene oxide : II. Effect of protein size. *J. Colloid Interface Sci.* 1991; 142: 159-166.
 56. Stella B, Arpicco S, Peracchia M, Desmaele D, Hoebeke J, Renoir M, d'Angelo J, Cattel L, Couvreur P. Design of folic acid-conjugated nanoparticles for drug targeting. *J. Pharm. Sci* 2000; 89: 1452-1464.
 57. Oyewumi MO, Yokel RA, Jay M, Coakley T, Mumper RJ. Comparison of cell uptake, biodistribution and tumor retention of folate-coated and PEG-coated gadolinium nanoparticles in tumor-bearing mice. *J Control Release* 2004; 95: 613-626.
 58. Krishna R, Mayer L. Multidrug resistance (MDR) in cancer-mechanisms, reversal using modulators of MDR and the role of MDR modulators in influencing the pharmacokinetics of anticancer drugs. *Eur. J. Cancer Sci* 2000; 11: 265-283.
 59. Larsen AK, Escargueil AE, Skladanowski A. Resistance mechanisms associated with altered intracellular distribution of anticancer agents. *Pharmacol Ther* 2000; 85: 217-29.

60. Bennis S, Chapey C, Couvreur P, Robert J. Enhanced cytotoxicity of doxorubicin encapsulated in polyisohexylcyanoacrylate nanospheres against multidrug-resistant tumour cells in culture. *Eur J Cancer* 1994; 30A: 89-93.
61. Dange C, Michel C, Aprahamian M, Couvreur P, Devissaguet JP. Nanocapsules as carriers for oral peptide delivery. *J. Control. Release* 1990; 13: 233-239.
62. Brandtzaeg P, Berstad A, Farstad I, Haraldsen G, Helgeland L, Jahnsen F, Johansen F, Natvig I, Nilsen E, Rugtveit J. Mucosal immunity – a major adaptive defense mechanism. *Behring Inst. Mitt* 1997; 98: 1-23.
63. Lee V, Yamamoto A. Penetration and enzymatic barriers to peptide and protein absorption. *Adv. Drug Deliv. Rev.* 1990; 4: 171-207.
64. Haltner E, Easson J, Lehr C. Lectins and bacterial invasion factors for controlling endo- and transcytosis of bioadhesive drug carrier systems. *Eur. J. Pharm. Biopharm* 1997; 44: 3-13.
65. Hussain N, Jani PU, Florence AT. Enhanced oral uptake of tomato lectin-conjugated nanoparticles in the rat. *Pharm Res* 1997; 14: 613-8.
66. Russell-Jones GJ, Arthur L, Walker H. Vitamin B12-mediated transport of nanoparticles across Caco-2 cells. *Int. J. Pharm.* 1999; 179: 247-255.
67. Russell-Jones GJ. The potential use of receptor-mediated endocytosis for oral drug delivery. *Adv. Drug Deliv. Rev.* 2001; 46: 59-73.
68. Schipper N, Olsson S, Hoogstrate J, de Boer A, Varum K, Artursson P. Chitosans as absorption enhancers for poorly absorbable drugs. 3: Influence of mucus on absorption enhancement. *Eur J Pharm Sci* 1999; 8: 335-43.
69. Lehr C, Bowstra J, Tukker J, Junginer H. Intestinal transit of bioadhesive microspheres in an in situ loop in the rat *J Control Release* 1990; 13: 51-62.
70. Bjork E, Isakkson U, Edman P, Artursson P. Starch microspheres induce pulsatile delivery of drugs and peptides across the epithelial barrier by reversible separation of the tight junctions. *J Drug Target* 1995; 6: 501-507.
71. Florence AT, Hussain, N. Transcytosis of nanoparticle and dendrimer delivery systems: evolving vistas. *Adv Drug Deliv Rev* 2001; 50 Suppl 1: S69-89.
72. Jani P, Halbert GW, Langridge J, Florence AT. The uptake and translocation of latex nanospheres and microspheres after oral administration to rats. *J Pharm Pharmacol* 1989; 41: 809-12.
73. Gurunathan S, Wu C, Freidag B. DNA vaccines: a key for inducing long-term cellular immunity. *Curr. Opin. Immunol*, 2000; 12: 442-447.
74. Panyam J, Zhou WZ, Prabha S, Sahoo SK, Labhasetwar V. Rapid endo-lysosomal escape of poly(DL-lactide-co-glycolide) nanoparticles: implications for drug and gene delivery. *Faseb J* 2002; 16: 1217-26.
75. Hedley M, Curley J, Urban R. Microspheres containing plasmid-encoded antigens elicit cytotoxic T-cell responses. *Nat Med* 1998; 4: 365-368.
76. Chen Y, Dalwadi G, Benson H. Drug delivery across the blood-brain barrier. *Current Drug Delivery* 2004; 1: 361-376.
77. Kreuter J. Influence of the surface properties on nanoparticle-mediated transport of drugs to the brain. *J Nanosci Nanotechnol* 2004; 4: 484-8.
78. Pardridge WM. Drug and gene targeting to the brain with molecular Trojan horses. *Nat Rev Drug Discov* 2002; 1: 131-9.
79. Ji B, Maeda J, Higuchi M, Inoue K, Akita H, Harashima H, Suhara T. Pharmacokinetics and brain uptake of lactoferrin in rats. *Life Sciences* 2006; 78: 851-855.
80. Scherrmann JM, Temsamani J, The use of Pep: Trans vectors for the delivery of drugs into the central nervous system. *International Congress Series* 2005; 1277: 199-211.
81. Gabathuler R, Arthur G, Kennard M, Chen Q, Tsai S, Yang J, Schoorl W, Vitalis TZ, Jefferies WA. Development of a potential protein vector (NeuroTrans) to deliver drugs across the blood-brain barrier. *International Congress Series* 2005; 1277: 171-184.
82. Pardridge WM. Drug and gene targeting to the brain via blood-brain barrier receptor-mediated transport systems. *International Congress Series* 2005; 1277: 49-62.