## Construction of hybrid g-C<sub>3</sub>N<sub>4</sub>/CdO nanocomposite with improved photodegradation activity of RhB dye under visible light irradiation

Thurga Devi Munusamy, Chin Sim Yee, Md. Maksudur Rahman Khan
College of Engineering, Universiti Malaysia Pahang, 26300 Gambang, Pahang,
Malaysia

## **ABSTRACT**

The hybrid graphitic carbon nitride-cadmium oxide (g-C<sub>3</sub>N<sub>4</sub>/CdO) nanocomposite was fabricated using chemical precipitation and self-assembly method. The photocatalysts were characterised by XRD, XPS, FTIR, BET, TEM, FESEM, UV-Vis and PL spectroscopy. Based on the optical study, visible light harvesting was improved and the band gap of bulk g-C<sub>3</sub>N<sub>4</sub> to hybrid g-C<sub>3</sub>N<sub>4</sub>/CdO nanocomposite was greatly reduced from 2.72 eV to 2.35 eV, signifying a better charge carrier mobility. The photocatalytic activity were further assessed by conducting rhodamine B (RhB) photodegradation reaction using visible light. An excellent dye removal efficiency of 96% was achieved when 1.5 g/L of hybrid g-C<sub>3</sub>N<sub>4</sub>/CdO nanocomposite was used with an initial concentration of 10 ppm for 120 min whereas only 66% of RhB was removed by bulk g-C<sub>3</sub>N<sub>4</sub> within the same operating conditions. Besides, reusability tests were carried out and evidenced that hybrid g-C<sub>3</sub>N<sub>4</sub>/CdO nanocomposite can be recycled up to four times by retaining the degradation efficiency. The scavenging studies confirmed that the RhB photodegradation using hybrid g-C<sub>3</sub>N<sub>4</sub>/CdO nanocomposite was controlled by valance band h<sup>+</sup> and •O<sup>2-</sup> oxidation reactions. Conclusively, the inclusion of CdO onto g-C<sub>3</sub>N<sub>4</sub> resulted in remarkable photocatalytic activity for dye degradation applications.

## **KEYWORDS**

Hybrid; g-C<sub>3</sub>N<sub>4</sub>/CdO; Photodegradation; Rhodamine B; Mechanism

## **ACKNOWLEDGEMENT**

We are thankful to the Ministry of Higher Education Malaysia for funding the research project through the Trans-disciplinary Grant Scheme RDU191802-1 (TRGS/1/2018/UMP/02/2/1).