

2021

## Experimental validation of bulk-graphene as a thermoelectric generator

Muhammad Uzair Khan

Amir Naveed

Syed Ehtisham Gillani  
*Edith Cowan University*

Dawar Awan

Muhammad Arif

*See next page for additional authors*

Follow this and additional works at: <https://ro.ecu.edu.au/ecuworkspost2013>



Part of the [Engineering Commons](#)

---

[10.1088/2053-1591/abfc03](https://doi.org/10.1088/2053-1591/abfc03)

Khan, M. U., Naveed, A., Gillani, S. E., Awan, D., Arif, M., Afridi, S., ... Ahad, Z. (2021). Experimental validation of bulk-graphene as a thermoelectric generator. *Materials Research Express*, 8(5), article 056302. <https://doi.org/10.1088/2053-1591/abfc03>

This Journal Article is posted at Research Online.  
<https://ro.ecu.edu.au/ecuworkspost2013/10351>

---

**Authors**


Muhammad Uzair Khan, Amir Naveed, Syed Ehtisham Gillani, Dawar Awan, Muhammad Arif, Shaista Afridi, Muhammad Hamyun, Muhammad Asif, Saadia Tabassum, Muhammad Sadiq, Muhammad Lais, Muhammad Aslam, Saeed Ullah Jan, and Zeeshan Ahad

PAPER • OPEN ACCESS

## Experimental validation of bulk-graphene as a thermoelectric generator

To cite this article: Muhammad Uzair Khan *et al* 2021 *Mater. Res. Express* **8** 056302

View the [article online](#) for updates and enhancements.



**IOP | ebooks™**

Bringing together innovative digital publishing with leading authors from the global scientific community.

Start exploring the collection—download the first chapter of every title for free.



## PAPER

## Experimental validation of bulk-graphene as a thermoelectric generator



## OPEN ACCESS

RECEIVED  
2 March 2021REVISED  
24 April 2021ACCEPTED FOR PUBLICATION  
27 April 2021PUBLISHED  
10 May 2021

Original content from this work may be used under the terms of the [Creative Commons Attribution 4.0 licence](#).

Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI.



Muhammad Uzair Khan<sup>1</sup>, Amir Naveed<sup>2,\*</sup> , Syed Ehtisham Gillani<sup>3</sup>, Dawar Awan<sup>1</sup>, Muhammad Arif<sup>2</sup> , Shaista Afridi<sup>2</sup>, Muhammad Hamyun<sup>2</sup>, Muhammad Asif<sup>4</sup>, Saadia Tabassum<sup>5</sup>, Muhammad Sadiq<sup>6</sup>, Muhammad Lais<sup>1</sup>, Muhammad Aslam<sup>2</sup>, Saeed Ullah Jan<sup>7</sup> and Zeeshan Ahad<sup>8</sup>

<sup>1</sup> Department of Electrical Engineering Technology, University of Technology, Nowshera, Pakistan

<sup>2</sup> Centre for Advanced Studies in Energy, University of Engineering and Technology, Peshawar, Pakistan

<sup>3</sup> School of Engineering, Edith Cowan University, WA, Australia

<sup>4</sup> Department of Electronics, University of Peshawar, Pakistan

<sup>5</sup> Department of Electronics Engineering Technology, University of Technology, Nowshera, Pakistan

<sup>6</sup> Department of Mechanical Engineering, University of Engineering and Technology, Peshawar, Khyber Pakhtunkhwa, Pakistan

<sup>7</sup> Department of Physics, Islamia College University Peshawar, Pakistan

<sup>8</sup> Department of Civil Engineering, IQRA National University Peshawar, Pakistan

\* Author to whom any correspondence should be addressed.

E-mail: [amirkhattak@uetpeshawar.edu.pk](mailto:amirkhattak@uetpeshawar.edu.pk)

**Keywords:** thermopower (TEP), figure of merit (FOM), thermoelectric generator, graphene

## Abstract

Quest for alternate energy sources is the core of most of the research activities these days. No matter how small or large amount of energy can be produced by utilizing the non-conventional techniques and sources, every bit of innovation can reshape the future of energy. In this work, experimental analysis of the thermoelectric (TE) properties of bulk-graphene in the temperature range of (303 to 363) K is presented. Graphene powder was pressed to form a pellet which was used to fabricate the TE device. The effects of temperature on the Seebeck coefficient, electrical and thermal conductivities, and the dimensionless figure of merit (FOM) were measured. The increasing value of the Seebeck coefficient (thermopower) with temperature is indicant of the metallic behavior. Additionally, the observed thermopower (TEP) is positive, which shows that the majority charge carriers are holes and peaked to a value of  $56 \mu\text{V K}^{-1}$  at 363 K. The thermopower of the pellet is four times larger than the previously reported values for single layer graphene (SLG) and few layer graphene (FLG). In addition to this, low values of the thermal conductivity were observed for the pellet which is one of the requirements of a good TE material. Besides this, an upward trend is observed with increasing temperature for FOM, which attains a peak value of 0.0016 at 363 K, which is almost ten times that of the previously reported values.

## 1. Introduction

Energy has been the most important part of human society since long. The modern-day lifestyle of humanity cannot survive without continuous supply of energy. From personal mobile phones and electronic gadgets to country level power houses and defence, energy is being utilized in one form or the other, and the demand is rising with each passing day [1]. Depletion is one among other drawbacks associated with the conventional energy sources [2]. A solution to such energy crisis is to develop renewable energy resources which include the wind, tides, sunlight, waves, and geothermal heat. These areas of energy production are the focus of many researches since decades. Thermoelectric generators (TEGs), which can use waste heat to generate electrical energy is one another highly appreciated way of energy generation. It can use the waste heat generated during combustion processes, chemical reactions and other heat generating systems, and can play a vital role in solving the present-day energy problem. TEGs convert the waste heat energy directly into useful electrical power [3]. However, TEGs cannot replace the conventional generators due to their low conversion efficiencies, but can be



Figure 1. Graphene pellet.

used in cogeneration systems where they can convert waste heat into useful energy thus improving the overall efficiency of the generation system. Efforts are needed to develop highly efficient TEGs so that they can function as stand-alone power systems.

Here we present an experimental study on the thermoelectric (TE) properties of graphene, a two-dimensional (2D) crystalline monolayer of graphite having a thickness of 0.34 nm [4, 5]. The structure of graphene resembles a honeycomb lattice in which each carbon atom is covalently bonded to three other carbon atoms [6]. The intriguing properties of the graphene result from its unique structure [7–10]. The remarkable physical properties of graphene and its potential applications in solar cells [11–13], transistors [14–17], and sensors [18–23] have garnered the interest of the researchers in the recent years. For graphene fabricated by a scotch tape method, charge carrier mobility attains a peak value of  $10^6 \text{ cm}^2/\text{Vs}$  at  $T = 15 \text{ K}$  [24]. However, this mobility is greatly dependent on the substrate on which graphene is deposited [25]. It should be noted that the mobility of electrons is the same as the mobility of holes in graphene. Due to crystalline structure and the light weight of the carbon atoms which form graphene, it is predicted theoretically that graphene exhibits high thermal conductivity at room temperature [26, 27]. Besides the theoretical studies, few experimental studies on single-layer graphene (SLG) reported that the thermal conductivity of graphene varies from (600–5300)  $\text{W mK}^{-1}$  [27, 28].

In the recent years, TE properties of graphene remained the subject of intensive research and it was theoretically predicted that the dimensionless figure of Merit (FOM) could be greater than 4 [29–32]. However, experimental results are not that much assuring as the FOM values are much less than 1 [33, 34]. Low thermopower (TEP) of graphene and its high thermal conductivity are the main factors contributing to the low values of the dimensionless FOM. However, efforts are needed to reduce the thermal conductivity and enhance the TEP, to get high FOM for graphene-based TE devices [35]. Previously, measurement of the TE properties of graphene involved either single-layer graphene (SLG) [36, 37] or few-layer graphene (FLG) [38–40]. Here, we have investigated TE properties of bulk-graphene pressed in pellet form, for the first time and noted that the TEP varies linearly with the temperature. A maximum TEP of  $56 \mu\text{V K}^{-1}$  is observed for the graphene pellet (GP) at 363 K which is comparable with the maximum reported value of  $80 \mu\text{V K}^{-1}$  in the temperature range of (475–575) K for FLG [40]. The TEP of the bulk-graphene is found to be greater than the SLG [36] and FLG [38]. This shows that an increase in the dimensionality of the graphene sample from SLG or FLG to bulk-graphene tends to increase the TEP of graphene.

## 2. Experimental setup

Powder graphene was used to fabricate pellet using a manual hydraulic pressing machine. The die filled with a weighted amount of graphene powder was kept under a pressure of 600 bars for 180 s. The pellet formed had a diameter of 17 mm while the thickness was 1.5 mm. Copper (Cu) electrodes (due to their high electrical conductivity) were fine-tuned on the pellet affixed to a glass substrate. The distance between the Cu electrodes was equal to 11 mm. Figure 1 shows the fabricated graphene pellet. For thermoelectric measurements, a rectangular sample with dimensions equal to  $17 \times 6 \text{ mm}^2$ , was cut from the pellet.

In this experimental work, heat was provided to both ends of the pellet using two separate resistors (each 5 W) powered by separate DC supplies. The amount of heat generated by each heater was controlled using the




Figure 2. Schematic view of the experimental setup.

current supplied by the power supplies. When a difference of temperature was established between the two ends of the pellet, a voltage was generated due to Seebeck effect. The generated voltage was measured with the help of Fluke 88 digital multimeters while, the heat at each end of the pellet was measured with a UT33C digital thermometer. TEP values of graphene pellet were determined by using the differential method relative to Cu electrodes [38, 41]. The absolute values of the TEP of Cu in the temperature range of (303–363) K had been taken into account while calculating the TEP of the graphene pellet. During the experiment, a temperature difference of 10 K was maintained between the hot and cold end of the pellet for calculating the TEP. The experimental setup used in our experiment is shown in figure 2. Electrical conductivity was measured using four-point probe method while thermal conductivity was measured using longitudinal steady state technique.

### 3. Results and discussion



Seebeck effect is defined as the generation of the voltage by a material when a temperature gradient is established across its ends. The ability of the material to generate a voltage when a temperature gradient is established across its ends is characterized by the Seebeck coefficient (thermopower). Mathematically the Seebeck coefficient is formulated as  $\alpha = V/\Delta T$ , where  $\alpha$ ,  $V$ , and  $\Delta T$  are the Seebeck coefficient, the voltage generated by the TE material, and the temperature gradient between the hot and cold end of the TE material respectively.

Figure 3 illustrates the relationship between the Seebeck coefficient and average temperature  $T$  of the graphene pellet. Besides the TEP of the GP, the TEP of SLG [36] and FLG [38] is also shown for comparison. The TEP of the graphene based TE device is found to be gradually increasing from (23–56)  $\mu\text{V K}^{-1}$  as the temperature increases from (303–363) K. But for SLG and FLG, a slight increase in the TEP with increasing temperature is observed. The TEP of SLG and FLG is (3–5) order of magnitude smaller than that of the GP. Enhancement in the TEP of the graphene pellet is attributed to the entrapped air within the pellet and increase in the number of layers of graphene which causes an increase in the density of defects in the sample [40]. Since graphene pellet also has multiple layers of graphene that's why the density of defects in GP is greater than SLG and FLG ultimately resulting in enhanced TEP for the GP. This is also evident from the TEP of SLG, which is smaller in magnitude than the TEP of the FLG as illustrated by figure 3. Similar to SLG and FLG, the TEP of graphene pellet is positive for the entire temperature range which illustrates that the dominant charge carriers are holes.

For a temperature less than the Fermi temperature ( $T_F$ ), the Seebeck coefficient of the metal is given by equation 1. Where  $k_B$ ,  $T$ , and  $E_F$  are the Boltzmann constant, average temperature between the hot and cold end of the TE material, and Fermi energy respectively. The TEP of the metals is generally less than  $k_B/e \approx 87 \mu\text{V/K}$  [42].

$$\alpha \approx \frac{k_B}{e} \frac{k_B T}{E_F} \quad (1)$$


Equation 1, clearly illustrates that the thermopower of the metals increases linearly with temperature. It is reported in by Berger *et al*, that the Fermi temperature ( $T_F$ ) of epitaxial graphene is 2490 K [43]. So, the Fermi energy of graphene is calculated as  $E_F \approx 214 \text{ meV}$  using the relation of  $E_F = k_B \times T_F$ . Using these values for the constants in equation 1, the TEP for graphene was calculated and this mathematically simulated (SIM) TEP is shown in figure 4. The simulated TEP increases moderately with the increase in the temperature. The experimentally (EXP) observed TEP is also shown for comparison. R G Vaidya *et al* reported that if the TEP of a material varies linearly with temperature, then it represents that the TEP is dominated by the diffusive



component while the phonon drag component contributes a little to the effective TEP [44]. Therefore, we can say that the linear increase in TEP indicates metallic diffusion behavior while the contribution by the phonon drag is negligible due to weak electron-phonon coupling [45, 46] in graphene pellet. The experimentally observed TEP is clearly following the predicted TEP.

Figure 5 shows the voltage-temperature gradient characteristics of the graphene pellet. Load voltage was measured across a load resistor connected to the TE device. This load is approximately equal to the internal resistance of the graphene pellet. It can be seen that the magnitude of the open-circuit voltage and load voltage is rising as the temperature gradient is varied from (6–11) K, however, the magnitude of load voltage is smaller than the magnitude of the open-circuit voltage. Maintaining a temperature gradient of 6 K across the GP,





generates an open-circuit voltage of 0.15 mV while the same temperature gradient produces a load voltage of 0.1 mV. These values increase steadily to 0.25 mV and 0.15 mV respectively, when the temperature gradient increases to 8 K. Establishing a temperature difference across the GP, results in the diffusion of the charge carriers from the hot end towards the cold end. When the charge carriers diffuse from the hot end towards the cold end, opposite charges are left at the hot end. As a result, a potential difference is generated between the two ends of GP. When the temperature difference across the pellet is increased, the rate of diffusion of the charge carriers increases and hence causes an increase in the voltage generated. The open-circuit voltage and load voltage attain a peak value of 0.4 mV and 0.3 mV respectively at a temperature gradient of 11 K. The linear relationship between the voltage generated by the graphene pellet and the temperature gradient verifies its thermo-electric origin.

The electrical conductivity ( $\sigma$ ) of the graphene pellet was measured using four-point probe method. The dependence of electrical conductivity on temperature is shown in figure 6. It is clear from figure 6 that the electrical conductivity of the graphene pellet increases dramatically as the temperature is increased, which is indicative of the semiconducting behavior. At a temperature of 303 K, the pellet exhibits an electrical conductivity of  $0.3 \text{ s m}^{-1}$ . The electrical conductivity of the graphene pellet reaches its peak value of  $4.3 \text{ S m}^{-1}$  when the temperature reaches to 363 K. Xiao *et al* reported the electrical conductivity of single layer graphene (SLG) films in the range of  $(4 \times 10^4 - 6 \times 10^4) \text{ S m}^{-1}$  which is higher than the values for few layer graphene (FLG) films i.e.,  $(4 \times 10^4 - 5 \times 10^4) \text{ S m}^{-1}$  [40]. The reason for high electrical conductivity of SLG films as compared to FLG films was the low density of structural defects in SLG films. Since the pellet has multiple layers of graphene, therefore higher density of structural defects and entrapped air within the pellet results in the reduction of the electrical conductivity as compare to SLG and FLG films while increasing its thermopower.

The thermal conductivity ( $\kappa$ ) of the graphene pellet was measured using longitudinal steady state technique [47]. Figure 7 shows the dependence of the thermal conductivity on temperature. The thermal conductivity of graphene pellet is  $0.38 \times 10^{-3} \text{ W mK}^{-1}$  at 303 K however, it linearly rises to a peak value of  $3.02 \times 10^{-3} \text{ W mK}^{-1}$  at a temperature of 363 K. Previously, very high values of thermal conductivity were reported for SLG i.e.,  $(3000 - 5000) \text{ W mK}^{-1}$  [48, 49]. The thermal conductivity of bulk-graphene goes on decreasing with the increase in the number of graphene layers and the thickness of the sample. This decrease is due to cross-plane coupling of the low-energy phonons and corresponding changes in the phonon Umklapp scattering in bulk graphene [50, 51]. The effect of cross-plane coupling of phonons in bulk-graphene is evident from the thermal conductivity of the graphene pellet as it shows very small values. The greater density of pores in the pellet would cause further lowering of the thermal conductivity of graphene pellet. A decrease in the thermal conductivity is one of the important requirements for good TE materials. Graphene pellet has very low thermal conductivity and thus can be considered for TE applications.






Figure 6. Temperature-electrical conductivity relationship of the graphene pellet.





Figure 7. Temperature-thermal conductivity relationship of graphene pellet.

The dimensionless FOM of a TE material is formulated as  $ZT = (\alpha^2\sigma/\kappa)T$  where  $\alpha$ ,  $\sigma$ ,  $\kappa$ , and  $T$  are the Seebeck coefficient, electrical conductivity, thermal conductivity, and average temperature of the graphene pellet. The measured electrical and thermal conductivities of the graphene pellet were used to determine the FOM, which is shown in figure 8. As expected, a linear relationship exists between the FOM of the graphene pellet and the temperature. The FOM of the TE device is  $130.3 \times 10^{-6}$  at 303 K which further increases by 12 times when the temperature is increased by 60 K. The FOM achieve its maximum value of 0.0016 at 363 K. This value is 10 times higher than the previously reported FOM for graphene [52, 53]. The high value of FOM can be attributed to the large density of pores and entrapped air within the pressed pellet which decreases the thermal conductivity by a great factor and to a large value of the TEP as compares to previously reported values. But this value is not comparable with the best TE materials. In principle, high value of thermopower and very low



thermal conductivity could have resulted in high value of ZT for graphene pellet but this is not the case here as the electrical conductivity is very low which makes the power factor ( $\alpha^2 \times \sigma$ ) very small. In order to increase the FOM of the bulk-graphene, a further study is needed to increase the electrical conductivity while still keeping the thermal conductivity to low values.

#### 4. Conclusion

Thermoelectric properties of bulk-graphene based TE device fabricated using manual hydraulic pressing machine, were measured. The TEP of the graphene was found to be linearly varying between (23–56)  $\mu\text{V K}^{-1}$  when the temperature of TE device was increased from (303–363) K. The positive TEP of the graphene pellet shows that the majority charge carriers are holes. The TEP of the pellet is found to be four times larger than the previously reported values for single layer graphene (SLG) and few layer graphene (FLG). Graphene pellet shows metals like thermopower as its thermopower linearly increased with the temperature. Furthermore, it should be noted that the large value of the FOM of the pellet is due to its porous structure, which results in lowering the thermal conductivity ultimately enhancing the FOM by 10 times as compared to the previously reported values.

#### 5. Future perspective

This work has several potential areas worth exploring for improvement. An important one among them is the porosity of the pellet that can control the thermal conductivity and hence improve the FOM of the graphene pellet. The main factors that can control the thermal conductivity of the graphene pellet include the pressure applied, and the time for which the pressure has been applied during the fabrication of the pellet. In addition to this, the physical dimensions of the pellet will also affect the thermal and electrical conductivity.

Due to smaller value of FOM, the concept of using TEGs based on bulk graphene (fabricated in the form of pellet) can be utilized in low and medium power devices. Potential application includes sensors requiring less power and light weight TEGs.

#### Data availability statement

All data that support the findings of this study are included within the article (and any supplementary files).

## ORCID iDs

Amir Naveed  <https://orcid.org/0000-0002-8014-3831>

Muhammad Arif  <https://orcid.org/0000-0002-1566-1675>

## References

- [1] Kong L B, Li T, Hng H H, Boey F, Zhang T and Li S 2014 Waste thermal energy harvesting (II): pyroelectric effect and others *Waste Energy Harvesting* (Berlin: Springer) 405–80
- [2] Martins F, Felgueiras C, Smitkova M and Caetano N 2019 Analysis of fossil fuel energy consumption and environmental impacts in European countries *Energies* **12** 964
- [3] Kanimba E and Tian Z 2019 A new dimensionless number for thermoelectric generator performance *Appl. Therm. Eng.* **152** 858–64
- [4] Neto A H C, Guinea F, Peres N M R, Novoselov K S and Geim A K 2009 The electronic properties of graphene *Rev. Mod. Phys.* **81** 109
- [5] Schedin F *et al* 2007 Detection of individual gas molecules adsorbed on graphene *Nat. Mater.* **6** 652–5
- [6] Guan L-Z, Zhao L, Wan Y-J and Tang L-C 2018 Three-dimensional graphene-based polymer nanocomposites: preparation, properties and applications *Nanoscale* **10** 14788–811
- [7] Wang J, Mu X and Sun M 2019 The thermal, electrical and thermoelectric properties of graphene nanomaterials *Nanomaterials* **9** 218
- [8] Akinwande D *et al* 2017 A review on mechanics and mechanical properties of 2D materials—graphene and beyond *Extrem. Mech. Lett.* **13** 42–77
- [9] Papageorgiou D G, Kinloch I A and Young R J 2017 Mechanical properties of graphene and graphene-based nanocomposites *Prog. Mater. Sci.* **90** 75–127
- [10] Zhang Y, Tan Y-W, Stormer H L and Kim P, 2005 Experimental observation of the quantum hall effect and Berry's phase in graphene *Nature* **438** 201–4
- [11] Sakorikar T, Kavitha M K, Tong S W, Vayalamkuzhi P, Loh K P and Jaiswal M 2018 Graphene interfaced perovskite solar cells: Role of graphene flake size *AIP Conf. Proc.* **1942** 140067
- [12] Liu T *et al* 2017 A graphene quantum dot decorated SrRuO<sub>3</sub> mesoporous film as an efficient counter electrode for high-performance dye-sensitized solar cells *J. Mater. Chem. A* **5** 17848–55
- [13] Kazmi S A, Hameed S, Ahmed A S, Arshad M and Azam A 2017 Electrical and optical properties of graphene-TiO<sub>2</sub> nanocomposite and its applications in dye sensitized solar cells (DSSC) *J. Alloys Compd.* **691** 659–65
- [14] Liu Y, Duan X, Huang Y and Duan X 2018 Two-dimensional transistors beyond graphene and TMDs *Chem. Soc. Rev.* **47** 6388–409
- [15] Haslam C, Damiati S, Whitley T, Davey P, Ifeachor E and Awan S A 2018 Label-free sensors based on graphene field-effect transistors for the detection of human chorionic gonadotropin cancer risk biomarker *Diagnostics* **8** 5
- [16] Piccinini E, Bliem C, Reiner-Rozman C, Battaglini F, Azzaroni O and Knoll W 2017 Enzyme-polyelectrolyte multilayer assemblies on reduced graphene oxide field-effect transistors for biosensing applications *Biosens. Bioelectron.* **92** 661–7
- [17] Chandrasekhar P 2018 Graphene applications in displays and transparent, conductive films/substrates *Conducting Polymers, Fundamentals and Applications* (Berlin: Springer) pp 147–8
- [18] Huang X *et al* 2018 Graphene oxide dielectric permittivity at GHz and its applications for wireless humidity sensing *Sci. Rep.* **8** 1–7
- [19] Yan T, Wang Z, Wang Y-Q and Pan Z-J 2018 Carbon/graphene composite nanofiber yarns for highly sensitive strain sensors *Mater. Des.* **143** 214–23
- [20] Chen Y, Pötschke P, Pionteck J, Voit B and Qi H 2018 Smart cellulose/graphene composites fabricated by *in situ* chemical reduction of graphene oxide for multiple sensing applications *J. Mater. Chem. A* **6** 7777–85
- [21] Shahrokhian S and Salimian R 2018 Ultrasensitive detection of cancer biomarkers using conducting polymer/electrochemically reduced graphene oxide-based biosensor: Application toward BRCA1 sensing *Sensors Actuators B Chem.* **266** 160–9
- [22] Baig N and Saleh T A 2018 Electrodes modified with 3D graphene composites: a review on methods for preparation, properties and sensing applications *Microchim. Acta* **185** 1–21
- [23] Yan Y, Potts M, Jiang Z and Sencadas V 2018 Synthesis of highly-stretchable graphene-poly (glycerol sebacate) elastomeric nanocomposites piezoresistive sensors for human motion detection applications *Compos. Sci. Technol.* **162** 14–22
- [24] Mayorov A S *et al* 2012 How close can one approach the Dirac point in graphene experimentally? *Nano Lett.* **12** 4629–34
- [25] Bolotin K I *et al* 2008 Ultrahigh electron mobility in suspended graphene *Solid State Commun.* **146** 351–5
- [26] Jiang J-W, Wang J-S and Li B 2009 Thermal conductance of graphene and dimerite *Phys. Rev. B* **79** 205418
- [27] Peres N M R, Dos Santos J M B L and Stauber T 2007 Phenomenological study of the electronic transport coefficients of graphene *Phys. Rev. B* **76** 73412
- [28] Faugeras C, Faugeras B, Orlita M, Potemski M, Nair R R and Geim A K 2010 Thermal conductivity of graphene in corbino membrane geometry *ACS Nano* **4** 1889–92
- [29] Ni X, Liang G, Wang J-S and Li B 2009 Disorder enhances thermoelectric figure of merit in armchair graphene nanoribbons *Appl. Phys. Lett.* **95** 192114
- [30] Snyder G J and Toberer E S 2011 Complex thermoelectric materials. In materials for sustainable energy: a collection of peer-reviewed research and review articles from *World Sci.* (Germany: Nature Publishing Group) pp 101–10
- [31] Sootsman J R, Chung D Y and Kanatzidis M G 2009 New and old concepts in thermoelectric materials *Angew. Chemie Int. Ed.* **48** 8616–39
- [32] Dresselhaus M S *et al* 2007 New directions for low-dimensional thermoelectric materials *Adv. Mater.* **19** 1043–53
- [33] Wei P, Bao W, Pu Y, Lau C N and Shi J 2009 Anomalous thermoelectric transport of Dirac particles in graphene *Phys. Rev. Lett.* **102** 166808
- [34] Xu X, Gabor N M, Alden J S, Van Der Zande A M and McEuen P L 2010 Photo-thermoelectric effect at a graphene interface junction *Nano Lett.* **10** 562–6
- [35] Deng S, Cai X, Zhang Y and Li L 2019 Enhanced thermoelectric performance of twisted bilayer graphene nanoribbons junction *Carbon N. Y.* **145** 622–8
- [36] Xu X *et al* 2010 Phonon transport in suspended single layer graphene accepted (arXiv:1012.2937)
- [37] Wu X, Hu Y, Ruan M, Madiomanana N K, Berger C and Heer W A D 2011 Thermoelectric effect in high mobility single layer epitaxial graphene *Appl. Phys. Lett.* **99** 133102

- [38] Babichev A V, Gasumyants V E and Butko V Y 2013 Resistivity and thermopower of graphene made by chemical vapor deposition technique *J. Appl. Phys.* **113** 076101
- [39] Wang Z et al 2011 Thermal transport in suspended and supported few-layer graphene *ACS Publ.* **11** 113–8
- [40] Xiao N et al 2011 Enhanced thermopower of graphene films with oxygen plasma treatment *ACS Publ.* **5** 2749–55
- [41] Gasumyants V, Elizarova M and Suryanarayanan R 2000 Effect of praseodymium on the normal-state and superconducting properties of a comparative study of the role of the Pr ion on R and Ba sites *Phys. Rev. B - Condens. Matter Mater. Phys.* **61** 12404–11
- [42] Chaikin P M 1990 An introduction to thermopower for those who might want to use it to study organic conductors and superconductors *Organic Superconductivity* (Boston: , Springer US) pp 101–15
- [43] Berger C et al 2006 Electronic confinement and coherence in patterned epitaxial graphene *Science* **312** 1191–6
- [44] Vaidya R G et al 2010 Diffusion thermopower in graphene *Semicond. Sci. Technol.* **25** 092001
- [45] Wu X, Hu Y, Ruan M, Madiomanana N K, Berger C and Heer W A D 2011 Thermoelectric effect in high mobility single layer epitaxial graphene *Appl. Phys. Lett.* **99** 133102
- [46] Fletcher R 1999 Magnetothermoelectric effects in semiconductor systems *Semicond. Sci. Technol.* **14** 1
- [47] Zhao D, Qian X, Gu X, Ayub Jajja S and Yang R Measurement techniques for thermal conductivity and interfacial thermal conductance of bulk and thin film materials *J. Electron. Packag.* **138** 040802
- [48] Ghosh S et al 2008 Extremely high thermal conductivity of graphene: prospects for thermal management applications in nanoelectronic circuits *balandingroup.ucr.edu* **92** 151911
- [49] Balandin A A et al 2008 Superior thermal conductivity of single-layer graphene *ACS Publ.* **8** 902–7
- [50] Ghosh S, Bao W, Nika D, Subrina S, Pokatilov E.P, Lau C N and Balandin A A 2010 Dimensional crossover of thermal transport in few-layer graphene *Nature Materials* **9** 555–8
- [51] Balandin A A 2011 Thermal properties of graphene and nanostructured carbon materials *Nature Materials* **10** 569–81
- [52] Kageshima H 2010 Study on thermoelectric properties of graphene *Jpn. J. Appl. Phys.* **49** 1002071–3
- [53] Aldun Sevinçli H and Sevik C 2014 Electronic, phononic, and thermoelectric properties of graphyne sheets *Appl. Phys. Lett.* **105** 223108