

We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

5,600

Open access books available

137,000

International authors and editors

170M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com



Introductory Chapter: Flame Retardant and Thermally Insulating Polymers

Yanfei Xu

1. Introduction

Flame retardant and thermally insulative polymers are of technological importance and fundamental interest [1, 2]. Polymers continue to infiltrate modern technologies such as aviation, automotive industry, building construction, electronics, to name a few, thanks to their unique combination of properties not available from any other known materials [3]. Polymers are lightweight, durable, easy to process, electrically insulative and corrosion resistant [4]. Common polymers are also thermally insulative [5]. However, polymers are combustible because of their chemical structures that are made up by carbon and hydrogen atoms [6–8]. To meet flammability standards, flame retardants for fireproof polymers have been developed [9, 10].

To protect human life and property, flame retardant polymers are generally made by adding flame retardants into polymers [11, 12]. There are drawbacks in common halogenated flame retardants, which associate with the release of toxic or corrosive by-products [13–18]. There are environment and health concerns caused by these released toxic gases [19]. Therefore, developing high-performance, non-toxic, low-cost, and environmentally friendly flame retardants are needed [19, 20]. Understanding mechanisms for fire retardancy is essential for developing new effective flame retardants. Improving fire retardant behaviors of polymers play key roles in future industrial applications such as furnishings, transportation products and building construction materials [9, 21–25].

Over the past decades, different flame retardants for polymers have been developed [20]. Mechanisms of polymer flame retardancy have been further investigated [9, 20, 26, 27]. Flame retardants have been generally broken into categories based on chemical compositions, which are grouped based on whether they contain bromine, chlorine, phosphorus, nitrogen, boron, or inorganic fillers (metals, etc.) [28]. It is widely recognized that all categories of flame retardants act either in vapor phase or condensed phase to inhibit or to stop combustion processes through a chemical and/or physical mechanism [29]. Flame retardants can interfere with combustion during a particular stage, e.g., during heating, pyrolysis, ignition, or flame spread [9, 20, 27, 30]. Flame retardants can either act chemically (reaction in the condensed or gas phase) and/or physically (by cooling, formation of a protective layer or fuel dilution) [17]. The polymer flammability properties have been investigated by their ignitability, flame spread and heat release characterizations [20]. Depending on the targeted application of polymers, one or more of specific flammability criteria (e.g. ASTM's fire and flammability standards) need to be satisfied [31].

In addition to flame retardancy, thermal insulation property of polymers can be another significant function that can defend targets against heat damage and save lives [32–35]. Fully understanding the flame retardance and thermal insulation

mechanisms in polymers remain challenging. Advanced polymers with combined properties of flame retardancy, mechanical strength and heat insulation are needed. Such polymers will provide broader prospect in civil applications than single-function polymers, for example, building insulation applications [36–38].

This introductory chapter not only aims to present the current landscape flame retardant and thermally insulative polymers, but also highlights next generation of flame retardant and thermally insulative polymers for fire protections applications. This introductory chapter summarize fundamental interests and technological importance of flame retardant and thermally insulative polymers, which include principles of polymer flammability, theory of flame retardance, thermally insulative and fire-retardant polymers, and critical discussion and outlook.

2. History and perspective of flame retardant and thermally insulative polymers

2.1 Principles of polymer flammability

Three ingredients — heat, oxygen, and fuel — are required to initiate and continue a fire [12]. Polymer starts to degrade, when it is heated by external ignition sources and reaches a characteristic temperature [39]. The surrounding oxygen amount plays key roles on polymer surface decompositions (e.g., thermo-oxidative degradation of polymers and/or thermal degradation of polymers). The amount of oxygen for polymer decomposition depends on the specific polymer used. Combustible gases as fuels may be produced at a rate dependent upon polymer decomposition rate and diffuse to the flame front [12]. After ignition and removal of the ignition source, combustion could be self-propagating if there is sufficient heat generated and polymer can absorb enough heat to sustain its decomposition processes. Polymer combustion processes could involve vapor phase and condensed phase reactions [39].

2.2 Theory of flame retardance

2.2.1 Vapor phase flame inhibition

The combustion process of premixed methane-oxygen flame is well investigated [40, 41]. The methane oxygen system can be used as a model for studying more complex polymer flames [41, 42]. Methane combustion is a free-radical chain reaction, which mainly consists of propagation, chain branching, and termination processes [43]. Any flame-retardant material which either decreases the concentration of these chain carrying radicals or increases the rate of termination will inhibit the flame reaction. This is thought to be mechanisms by which vapor phase flame inhibitors [39, 44].

2.2.2 Condensed phase flame inhibition

Cooling and char barrier formation are two main modes in solid phase flame inhibition [39, 44, 45]. We discuss cooling mode first. One important cooling mode used in condensed phase flame inhibition is the use of materials which decompose endothermically in the pyrolysis zone of the burning polymer [39]. For example, due to polyvinyl alcohol's ability to endothermically form water molecules, polyvinyl alcohol is less flammable than the isomeric polyethylene oxide [39, 46]. During

polymer burning processes, cooling mode can be also achieved by adding thermally conductive fillers into polymers [39]. Fillers have higher thermal conductivities than that of polymers. Fillers conduct heat better than polymers. Fillers conduct heat away from hot regions more efficiently than unfilled polymers. Fillers enable polymer-filler composites difficult to burn. However, fillers at high volume fraction loadings are needed for good cooling effect, which might lead to limited use [39, 47]. Dripping is another cooling mechanism [39, 48]. Polymers that drip easily during burning processes are more difficult to burn. For example, a regular candle will not burn with no wick, due to its high dripping tendency. This is because heat is dissipated from flaming areas. However, dripping could be a hazard by resulting in the spreading of a fire and thus of limited use [39, 49].

2.3 Thermally insulative polymers with high flame retardancy

Thermally insulative polymer-based materials with high flame retardancy are attracting significant attention [50]. This is because thermally insulative materials can protect overheating damage from burn injuries and save lives [34, 51–58]. There are drawbacks for available fire-resistant polymers. Some flame retardant polymers could be expensive [57]. Some flame retardant polymers have relatively low decomposition temperatures and decompose nearby 400°C [57]. Thus, highly thermally insulative, thermally stable and flame retardant polymer-based materials are desired for advanced thermal management applications [17, 50, 57].

Flame retardant and thermally insulative polymer-based composites have been developed [50, 56, 59–62]. For example, PC–PDMS copolymers have flame-retardant behaviors. Chars can prevent more volatile fuel production and serve as a thermal insulator preventing the temperature from rising [59]. When a specimen of PC–PDMS was in combustion, a lot of fine bubbles and char were formed. These fine bubbles are good for thermal insulation [59]. Moreover, silica particles in situ produced by thermal decomposition of PDMS mostly stay in char layers, which improve the quantity of oxidation-resistant char coatings [59]. The resulting bubble structures and silica materials in the char layer prevented volatile and flammable fuel production, which served as an effective thermal insulator [59]. Although there are progresses on developing flame retardant and thermally insulative polymer-based materials, further understanding flame retardancy and thermal insulation mechanisms will play key roles increasing next generation of thermally insulative and flame retardant polymers with outstanding performance. With unique combined properties including simple manufacturing process, low cost, excellent thermal insulation, flame retardancy, superior physical and mechanical properties, thermally insulative and flame retardant polymers will provide new opportunities for existing and unforeseen applications.

2.4 Critical discussion and outlook

To achieve the high-performance fire retardancy of polymers, different strategies have been developed [63]. Followings are selected strategies.

1. By modifying the reaction scheme of pyrolysis of polymers to produce non-combustible, and/or non-volatile products that dilute the supply of oxygen [40, 63].
2. By stopping the combustion through dilution of the combustible gases, or the formation of a char which suppress the oxygen supply [63, 64].

3. By introducing active radical-trapping effects both in the gaseous phase and/or in the condensed phase [63, 65].
4. By reducing the thermal conductivity of the material to limit heat transfer [34, 63].

The different types of flame retardants in polymers based on halogens, heavy phosphorus-organic compounds and/or transition metals have shown good flame retardance performance [26]. However, toxic gases and smoke are formed during burning processes [66]. Environmental safety of flame retardants in polymers is a major issue [22, 63]. Fire-retardant polymer-based materials are desired to have high resistance to ignition, low combustion rate, retention of low flammability, acceptability in properties and appearance, no health safety and environmental issues, and little (or no) economic penalty.

IntechOpen

Author details

Yanfei Xu

Mechanical and Industrial Engineering Department, Chemical Engineering Department, University of Massachusetts Amherst, Amherst, MA, USA

*Address all correspondence to: yanfeixu@umass.edu

IntechOpen

© 2021 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/3.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited. 

References

- [1] Yuan Hu, X.W., *Flame-retardant polymeric materials*. 2020: CRC Press.
- [2] Bourbigot, S. and S. Duquesne, *Fire retardant polymers: recent developments and opportunities*. Journal of Materials Chemistry, 2007. **17**(22): p. 2283-2300.
- [3] Peplow, M., *The plastics revolution: how chemists are pushing polymers to new limits*. Nature, 2016. **536**(7616): p. 266-8.
- [4] Sperling, L.H., *Introduction to Physical Polymer Science, Fourth Edition*. John Wiley & Sons, Inc., 2005.
- [5] Xu, Y., et al., *Nanostructured polymer films with metal-like thermal conductivity*. Nature Communications, 2019. **10**(1): p. 1771.
- [6] Wehrmann, F., *Organic polymer chemistry, K. J. Saunders, Chapman and Hall, London, 1973, 473 pp*. Journal of Polymer Science: Polymer Letters Edition, 1975. **13**(10): p. 634-635.
- [7] Hilado, C.J., *Flammability handbook for plastics*. 1998: CRC Press.
- [8] Charles A. Wilkie, A.B.M., *Fire Retardancy of Polymeric Materials*. CRC Press, 2009.
- [9] Vahidi, G., et al., *Advancements in traditional and nanosized flame retardants for polymers—A review*. Journal of Applied Polymer Science, 2021. **138**(12): p. 50050.
- [10] M Le Bras, S.B., G Camino, R Delobel, *Fire Retardancy of Polymers*. 1998: Woodhead Publishing
- [11] Kashiwagi, T., et al., *Nanoparticle networks reduce the flammability of polymer nanocomposites*. Nature Materials, 2005. **4**(12): p. 928-933.
- [12] Khanna, Y.P. and E.M. Pearce, *Flammability of Polymers*, in *Applied Polymer Science*. 1985, American Chemical Society. p. 305-319.
- [13] Birnbaum Linda, S. and F. Staskal Daniele, *Brominated flame retardants: cause for concern?* Environmental Health Perspectives, 2004. **112**(1): p. 9-17.
- [14] Ames, A.B.a.B.N., *Flame-retardant additives as possible cancer hazards*. Science, 1977. **195**: p. 17-23.
- [15] Osimitz, T.G., S. Kacew, and A.W. Hayes, *Assess flame retardants with care*. Science, 2019. **365**(6457): p. 992.
- [16] Shaw, S.D., et al., *Halogenated flame retardants: do the fire safety benefits justify the risks?* Rev Environ Health, 2010. **25**(4): p. 261-305.
- [17] Laoutid, F., et al., *New prospects in flame retardant polymer materials: From fundamentals to nanocomposites*. Materials Science and Engineering: R: Reports, 2009. **63**(3): p. 100-125.
- [18] Blum, A., *The fire retardant dilemma*. Science, 2007. **318**(5848): p. 194-5.
- [19] Kiliaris, C.D.P.a.P., *Polymer Green Flame Retardants*. Elsevier B.V. . 2014.
- [20] Lu, S.-Y. and I. Hamerton, *Recent developments in the chemistry of halogen-free flame retardant polymers*. Progress in Polymer Science, 2002. **27**(8): p. 1661-1712.
- [21] Lazar, S.T., T.J. Kolibaba, and J.C. Grunlan, *Flame-retardant surface treatments*. Nature Reviews Materials, 2020. **5**(4): p. 259-275.
- [22] Xiong, P., et al., *A Review of Environmental Occurrence, Fate, and Toxicity of Novel Brominated Flame Retardants*. Environmental Science & Technology, 2019. **53**(23): p. 13551-13569.

- [23] Price, A.R.H.a.D., *Advances in Fire Retardant Materials*. Woodhead Publishing, 2008.
- [24] Wang, D.-Y., *Novel Fire Retardant Polymers and Composite Materials*. 2016, Cambridge, UNITED KINGDOM: Elsevier Science & Technology.
- [25] Morgan, A.B. and C.A. Wilkie, *The Non-Halogenated Flame Retardant Handbook*. 2014, Somerset, UNITED STATES: John Wiley & Sons, Incorporated.
- [26] Camino, G. and L. Costa, *Performance and mechanisms of fire retardants in polymers—A review*. *Polymer Degradation and Stability*, 1988. **20**(3): p. 271-294.
- [27] Camino, G., L. Costa, and M.P. Luda di Cortemiglia, *Overview of fire retardant mechanisms*. *Polymer Degradation and Stability*, 1991. **33**(2): p. 131-154.
- [28] Visakh, P.M., Arao, Yoshihiko, *Flame Retardants*. Springer, 2015.
- [29] Kashiwagi, T., *Polymer combustion and flammability—Role of the condensed phase*. Symposium (International) on Combustion, 1994. **25**(1): p. 1423-1437.
- [30] Kausar, A., et al., *Recent Developments in Different Types of Flame Retardants and Effect on Fire Retardancy of Epoxy Composite*. *Polymer-Plastics Technology and Engineering*, 2016. **55**(14): p. 1512-1535.
- [31] Babrauskas, V. and R.D. Peacock, *c*. *Fire Safety Journal*, 1992. **18**(3): p. 255-272.
- [32] Shi, H.-G., et al., *Multifunctional Flame-Retardant Melamine-Based Hybrid Foam for Infrared Stealth, Thermal Insulation, and Electromagnetic Interference Shielding*. *ACS Applied Materials & Interfaces*, 2021.
- [33] Wicklein, B., et al., *Thermally insulating and fire-retardant lightweight anisotropic foams based on nanocellulose and graphene oxide*. *Nature Nanotechnology*, 2015. **10**(3): p. 277-283.
- [34] Zhao, H.-B., M. Chen, and H.-B. Chen, *Thermally Insulating and Flame-Retardant Polyaniline/Pectin Aerogels*. *ACS Sustainable Chemistry & Engineering*, 2017. **5**(8): p. 7012-7019.
- [35] Weil, E.D., *Flame Retardants for Plastics and Textiles 2E: Practical Applications*. 2015: Hanser Publications.
- [36] Jelle, B.P., *Traditional, state-of-the-art and future thermal building insulation materials and solutions – Properties, requirements and possibilities*. *Energy and Buildings*, 2011. **43**(10): p. 2549-2563.
- [37] Weil, E.D. and S.V. Levchik, *Flame Retardants for Plastics and Textiles : Practical Applications*. 2015, München, GERMANY: Hanser.
- [38] *International Energy Agency. Technology Roadmap: Energy Efficient Building Envelopes*. 2013.
- [39] Factor, A., *The chemistry of polymer burning and flame retardance*. *Journal of Chemical Education*, 1974. **51**(7): p. 453.
- [40] Wall, L.A., *The Mechanisms of Pyrolysis, Oxidation, and Burning of Organic Materials*. Forgotten Books
- [41] Westenberg, A.A. and R.M. Fristrom, *METHANE-OXYGEN FLAME STRUCTURE. IV. CHEMICAL KINETIC CONSIDERATIONS*. *The Journal of Physical Chemistry*, 1961. **65**(4): p. 591-601.
- [42] Westenberg, R.M.F.a.A.A., *Flame structure*. McGraw-Hill.
- [43] Korobeinichev, O.P., et al., *Chain-branching reactions in the processes of promotion and inhibition of hydrogen combustion*. *Combustion, Explosion,*

and Shock Waves, 2010. **46**(2): p. 140-148.

[44] Morgan, C.A.W.a.A.B., *Fire Retardancy of Polymeric Materials, Second Edition*. CRC Press.

[45] Wilkie, C.A., *Fire retardancy of polymers*. Materials Today, 2009. **12**(4): p. 46.

[46] Holland, B.J. and J.N. Hay, *The thermal degradation of poly(vinyl alcohol)*. Polymer, 2001. **42**(16): p. 6775-6783.

[47] Rothon, R. and P. Hornsby, *Chapter 9 - Fire Retardant Fillers for Polymers*, in *Polymer Green Flame Retardants*, C.D. Papaspyrides and P. Kiliaris, Editors. 2014, Elsevier: Amsterdam. p. 289-321.

[48] Matzen, M., et al., *Influence of Flame Retardants on the Melt Dripping Behaviour of Thermoplastic Polymers*. Materials (Basel, Switzerland), 2015. **8**(9): p. 5621-5646.

[49] Liu, B.-W., et al., *Eco-friendly synergistic cross-linking flame-retardant strategy with smoke and melt-dripping suppression for condensation polymers*. Composites Part B: Engineering, 2021. **211**: p. 108664.

[50] Morgan, A.B. and J.W. Gilman, *An overview of flame retardancy of polymeric materials: application, technology, and future directions*. Fire and Materials, 2013. **37**(4): p. 259-279.

[51] Wi, S., et al., *Evaluation of environmental impact on the formaldehyde emission and flame-retardant performance of thermal insulation materials*. Journal of Hazardous Materials, 2021. **402**: p. 123463.

[52] Akdogan, E., et al., *Rigid polyurethane foams with halogen-free flame retardants: Thermal insulation, mechanical, and flame retardant*

properties. Journal of Applied Polymer Science, 2020. **137**(1): p. 47611.

[53] Fan, B., et al., *Fabrication of Cellulose Nanofiber/AlOOH Aerogel for Flame Retardant and Thermal Insulation*. Materials, 2017. **10**(3).

[54] Wang, D., et al., *Biomimetic structural cellulose nanofiber aerogels with exceptional mechanical, flame-retardant and thermal-insulating properties*. Chemical Engineering Journal, 2020. **389**: p. 124449.

[55] Wei, H., et al., *Benzotriazole-based conjugated microporous polymers as efficient flame retardants with better thermal insulation properties*. Journal of Materials Chemistry A, 2018. **6**(18): p. 8633-8642.

[56] Kashiwagi, T., et al., *Flame retardant mechanism of silica gel/silica*. Fire and Materials, 2000. **24**(6): p. 277-289.

[57] Illeperuma, W.R.K., et al., *Fire-Resistant Hydrogel-Fabric Laminates: A Simple Concept That May Save Lives*. ACS Applied Materials & Interfaces, 2016. **8**(3): p. 2071-2077.

[58] Morgan, A.B., *The Future of Flame Retardant Polymers – Unmet Needs and Likely New Approaches*. Polymer Reviews, 2019. **59**(1): p. 25-54.

[59] Nodera, A. and T. Kanai, *Flame retardancy of a polycarbonate–polydimethylsiloxane block copolymer: The effect of the dimethylsiloxane block size*. Journal of Applied Polymer Science, 2006. **100**(1): p. 565-575.

[60] Zhu, Z., et al., *Ionic liquid and magnesium hydrate incorporated conjugated microporous polymers nanotubes with superior flame retardancy and thermal insulation*. Polymer, 2020. **194**: p. 122387.

[61] Wang, F., et al., *Monolithic nanoporous polymers bearing POSS*

moiety as efficient flame retardant and thermal insulation materials. Reactive and Functional Polymers, 2019. 143: p. 104345.

[62] Wang, S.-X., et al., *Inherently flame-retardant rigid polyurethane foams with excellent thermal insulation and mechanical properties. Polymer, 2018. 153: p. 616-625.*

[63] Zaikov, G.E. and S.M. Lomakin, *New Types of Ecologically Safe Flame-Retardant Polymer Systems, in Fire and Polymers II. 1995, American Chemical Society. p. 186-198.*

[64] Salmeia, K.A., et al., *An Overview of Mode of Action and Analytical Methods for Evaluation of Gas Phase Activities of Flame Retardants. Polymers, 2015. 7(3).*

[65] Guo, Z., Z. Wang, and Z. Fang, *Fabrication of 9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide-decorated fullerene to improve the anti-oxidative and flame-retardant properties of polypropylene. Composites Part B: Engineering, 2020. 183: p. 107672.*

[66] Pethsangave, D.A., et al., *Novel Approach toward the Synthesis of a Phosphorus-Functionalized Polymer-Based Graphene Composite as an Efficient Flame Retardant. ACS Sustainable Chemistry & Engineering, 2019. 7(13): p. 11745-11753.*