

University of Groningen

From Shear Lag to Atomic Fit

Bronsveld, P.M.; Hosson, J.Th.M. De

Published in:
Acta Crystallographica Section A

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
1993

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):
Bronsveld, P. M., & Hosson, J. T. M. D. (1993). From Shear Lag to Atomic Fit. *Acta Crystallographica Section A*, 49(suppl.).

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

13-Defects, Microstructures and Textures

357

PS-13.01.08 FROM SHEAR LAG TO ATOMIC FIT. By P.M. Bronsveld* and J.Th.M. De Hosson, Department of Applied Physics, University of Groningen, Nijenborgh 4, 9747 AG Groningen, The Netherlands.

Already for some time now people are trying to improve aluminum by adding a ceramic reinforcement as SiC or Al₂O₃ to make so-called DRA or discontinuously reinforced aluminum [J. of Metals, January 1993]. The idea then is to make use of the strength properties of the ceramic particle while maintaining the ductility of the base metal. Crucial is the transfer of the load from the base metal to the reinforcement. A whole series of macroscopic models have been applied, e.g. the shear lag model in which the load transfer takes place via a kind of press-fit between both phases. Residual stress measurements on the Al/SiC system using neutron diffraction [T. Lorentzen, J., Neutron Res. 1(1993)13] clearly show an initial strain in the aluminum base, subsequently taken over by the strain in the ceramic particles. In order to understand what happens on the atomic scale, a study has been undertaken applying high resolution electron microscopy. In this analysis one observes the atomic fit between the metal and ceramic structures and tries to interpret it starting from the distinctive space groups, unit cells, lattice parameters and orientation relationships. Subsequently one tries to measure the displacement between both phases and searches for misfit dislocations. It may happen that one particular type of atom diffuses towards the interface, e.g. Mg, being a surfactant [Delannay et al. J. Mat. Sci. 22(1987)1], positions itself preferably at the interface and via the formation of MgO may give rise to a reaction layer causing a lower fracture toughness. We have studied the Al/SiC and Al/Al₂O₃ systems and found that when the production method is one in which fine powder is cold-pressed and subsequently hot-extruded, one finds indeed an interface being a more or less abrupt transition from metal to ceramic.

The so-called liquid route of manufacturing gives a reaction layer which for the Al/Al₂O₃ system turns out to be the spinel MgAl₂O₄ as was confirmed by comparison of the experimental results with the EMS and MacTempas HREM simulation programs.

PS-13.01.09 TEXTURED THIN FILM OF C₆₀ GROWN BY VACUUM DEPOSITION. By W.L. Zhou*, W. Zhao, Y.Q. Zhou, K.K. Fung and L.Q. Chen, Institute of Physics and Beijing Laboratory of Electron Microscopy, Chinese Academy of Sciences, P.O.Box 603, Beijing 100080, People's Republic of China

The reports of straightforward procedure for synthesizing macroscopic quantities of C₆₀ and its superconductivity in alkali-doped solids have triggered an intense concentration of physicists, chemists, etc. As the thin films of C₆₀ prepared by vacuum deposition are free from solvents and also have a potential application toward new electronic devices, it is very important to know the crystallization and structure of the thin film. Different thicknesses of C₆₀ thin films on NaCl (001) substrates have been produced by us. The thin films were grown by sublimating the pure C₆₀ powder to NaCl (001) cleavage surface with pretreatment of eliminating residual solvent at 10⁻³ torr. Transmission electron microscopy study showed that at the initial stage the C₆₀ thin film tended to crystallize randomly with few hexagonal phases and as it grew thicker, it formed [110] texture thin film with multiply twin particles and fewer hexagonal phases. Twins, microtwins, stacking faults and five fold twin particles were studied by high resolution electron microscopy (HREM). As the C₆₀ is bounded by van der Waals force, the lattice bending structure and disorder cores due to the strain releasing in five fold twin particles were found by HREM. The large cages of C₆₀ experienced to the strong electron beam were also observed by HREM.

References

- [1]. W.Kratschmer, L.D.Lamb, K.Fostirpoulos and D.R.Huffman, Nature 347 (1990) 354.
- [2]. Y.Saito, Y.Ishikawa, A.Ohshita, H. Shinohara and H. Nagashima, Phys. Rev. B. 46 (1992) 1846.

PS-13.01.10 REASONABLY GOOD DISLOCATION IMAGES IN LACBED PATTERNS AND EFFECTS OF ITS STRAIN FIELD ON THE REFLECTION CONTOURS. By Y. Xin* and X.F. Duan Beijing Laboratory of electron microscopy, Chinese Academy of Sciences, P.O. Box 2724, Beijing, 100080, China

Large-angle convergent beam electron diffraction (LACBED) comprises real and reciprocal space information and therefore is useful to the study of defects in crystals. Dislocations parallel to the reflection rocking curve contours have been studied by an improved LACBED technique. Shadow images of dislocations of reasonably good spatial resolution superimposed on LACBED patterns have been obtained at the diffraction plane. It has been found that only when the shadow image of the dislocation is parallel and close to a low-order reflection contour with $g \cdot b \neq 0$ can it be formed with reasonably good contrast in the LACBED patterns. Both the image of the dislocation and the changes of the reflection contours clear in one LACBED pattern make it convenient to study the strain field of a dislocation. The strain fields of dislocations in Si and GaAs crystals have been investigated. Different effects are observed.

PS-13.01.11 SUPERLATTICE VARIANTS IN Sr₂CuO₂(CO₃) - AN ELECTRON MICROSCOPY STUDY

O. Milat*, G. Van Tendeloo, J. Van Landuyt and S. Amelinckx, EMAT University of Antwerp (RUCA), Belgium; *also at: Institute of Physics, University of Zagreb, Croatia

The compound Sr₂CuO₂(CO₃) has a layered structure based on that of perovskite lattice ($a_p = 3.9$ Å); it consists of lamellae with the intralamellar stacking sequence: ... - (CuO₂-Sr-CO₃-Sr) - (CuO₂- ...). The lamella thickness is $c_p = 2a_p$; the basic lattice is double perovskite, primitive tetragonal (a_p, a_p, c_p).

Electron microscopy and diffraction investigations revealed three intensity levels of the diffraction spots (associated with three sublattices in reciprocal space); they can be related to the levels in the crystal structure: the basic structure, the modulated -Sr-CuO₂-Sr- block-layer structure, and the superstructure due to the CO₃ planar arrangement, (O. Milat, G. Van Tendeloo, S. Amelinckx, T.G.N. Babu, C. Greaves, submitted in J. Solid State. Chem.). The unit cell of the modulated block-layer structure is body-centred, while the superlattice cell of the CO₃ planar arrangement is found to be either body-centred or primitive, with the same cell parameters: $2a_p, 2a_p, 2c_p$.

The appearance of two types of superlattice cells can be accounted for by a model of the layered arrangement of CO₃-triangles between two enclosing block-layers (fig.1). A sense can be attributed to the arrangement of the CO₃-triangles and two opposite senses may coexist in the successive CO₃-layers within block-layers of the same underlying structure. The Sr-displacement modulation of the block layer structure is a consequence of the mutual interaction between the basic perovskite, and CO₃ planar substructures. Of the different superlattice variants, two special cases were frequently observed: the body-centred superlattice variant, where the CO₃-arrangements in all layers are of the same sense and the primitive superlattice variant, where the CO₃-arrangements of opposite senses alternate in successive layers. More complicated regular stackings (with a long period superlattice: $c_s = nc_p$) were also observed, and result in closely spaced satellites around the primitive superlattice spot positions (fig.2). An irregular stacking of the CO₃-layers induces streaking of the corresponding superlattice spots in the diffraction patterns.