

University of Groningen

Associations of stereoregular polymethylmethacrylates

Boer, Albert de

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version

Publisher's PDF, also known as Version of record

Publication date:

1976

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Boer, A. D. (1976). *Associations of stereoregular polymethylmethacrylates*. s.n.

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

SUMMARY

This thesis describes the association of stereoregular poly(methyl methacrylates) in dilute solutions and in bulk. It is known that isotactic and syndiotactic poly(methyl methacrylate) (i- and s-PMMA) have complementary structures and that specific interactions occur between i- and s-PMMA (Chapter 1).

Stereocomplex formation of i- and s-PMMA can take place in dilute solutions far below the homogeneous segmental distribution concentration, which was demonstrated by means of viscometric and turbidimetric measurements. As the solvent appeared to influence considerably the degree of association, an empirical division was made into 3 groups: A - strongly complexing solvents (e.g. acetone, DMF, DMSO, acetonitrile, methyl isobutyrate and monomer MMA); B - weakly complexing solvents (e.g. toluene and benzene); C - non-complexing solvents (e.g. chloroform) (Chapter 2). The tacticity of s-PMMA appears to influence the association process strongly whereas a narrower molecular weight distribution of i-PMMA has only little influence (Appendix 1).

Based upon the results of differential scanning calorimetry (d.s.c.) and X-ray powder diffraction patterns we conclude that in dilute type A solutions i- and s-PMMA chains partly associate in an i/s ratio of about 1:1 and that at the same time liquid induced crystallization of s-PMMA occurs (Chapter 3).

Thermal analysis showed that material associated in dilute type A solutions had 3 endotherms at temperatures not depending on the composition of the sample. The endotherm at $\approx 210^{\circ}\text{C}$ is caused by the melting of the stereocomplex, the endotherm at $\approx 185^{\circ}\text{C}$ by the melting of solvent stabilized s-PMMA, while the endotherm at $\approx 280^{\circ}\text{C}$ is caused by the degradation of PMMA (Chapter 3).

Association of i- and s-PMMA can also occur in bulk as demonstrated by means of calorimetric and dynamic - mechanical measurements. The rate of complex formation is maximal at 140°C and the extent of complex formation is maximal at a composition somewhat lower than the i/s ratio of

1:1. The high rate of complex formation in bulk - more than half of the complex has been formed within 2 minutes at 140°C - is remarkable the more so as the separate components do not crystallize at all under these conditions (Chapter 4).

As mechanism for complex formation in bulk it is proposed that chain segments of *i*-PMMA form nuclei by adopting the favourable 5_1 helix conformation, whereupon chain segments of *s*-PMMA associate with these favourable places yielding a fringed micelle like structure. As the association continues the crystalline regions are extended appearing from the fact that annealed and non-annealed samples had about the same value of the storage modulus (G') above the glass transition temperature (Chapter 4).

In order to compare the properties of the stereocomplex with those of pure *i*- and *s*-PMMA, the crystallization of *i*- and *s*-PMMA was studied. *i*-PMMA is a very slowly crystallizing polymer with a maximal growth rate ($G = 1 \times 10^{-3} \mu\text{m}/\text{min}$) of the crystals at 120°C, while the estimated (equilibrium) melting temperature (T_m^0) is 220°C (Chapter 5). The crystallization of *s*-PMMA from the melt appeared to be even more troublesome. Therefore *s*-PMMA was treated with borderline solvents (heptanone-4, methyl isobutyrate and toluene). This material which had not been fully dried, showed an endotherm at $\approx 190^\circ\text{C}$ as recorded by d.s.c. and a reflection at $2\theta = 4^\circ 30'$ in the X-ray diffractogram. Drying the sample further resulted in the disappearance of endotherm and reflection. From this it may be concluded that some crystalline structure of *s*-PMMA is stabilized by solvent (Appendix 2).

IR spectroscopy showed that upon complex formation in dilute type A solutions *s*-PMMA mostly takes on a planar structure with a glide plane, whereas *i*-PMMA has a 5_1 helix conformation in the stereocomplex and that association of *i*- and *s*-PMMA occurs over long distances along the chains. Preliminary fibre diffraction measurements showed that the *c* axis of the unit cell of the stereocomplex is $\approx 1 \text{ \AA}$ shorter than that of *i*-PMMA (Chapter 6).

The difference in configuration and conformation of *i*- and *s*-PMMA also appeared to influence the mixing behaviour of PMMA and PVC [poly(vinylchloride)]. *i*-PMMA and PVC form an incompatible system, whereas *s*-PMMA and PVC form a compatible system up to a composition corresponding with a monomer unit ratio of 1:1 (PVC : *s*-PMMA) (Chapter 7).