



Opportunities for polymer-based nanowires in optoelectronics and nanophotonics

Jean-Luc Duvail, Alexandre Garreau, J.M. Lorcy, F. Massuyeau, Stéphane Cordier, Y. Molard, A. Bulou, John Bignon, Nolwenn Huby, Bruno Bêche, et al.

► **To cite this version:**

Jean-Luc Duvail, Alexandre Garreau, J.M. Lorcy, F. Massuyeau, Stéphane Cordier, et al.. Opportunities for polymer-based nanowires in optoelectronics and nanophotonics. Frontier 2012 : Opportunities for polymer-based nanowires in optoelectronics and nanophotonics, Dec 2012, Rennes, France. Frontier 2012, pp.2012-9, 2012. <hal-01073473>

HAL Id: hal-01073473

<https://hal.archives-ouvertes.fr/hal-01073473>

Submitted on 7 Nov 2014

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Opportunities for polymer-based nanowires in optoelectronics and nanophotonics

JL Duvail¹, A Garreau¹, J.M. Lorcy¹, F Massuyeau¹, S Cordier², Y Molard², A Bulou³, J. Bignon⁴, N Huby⁴, B Bêche⁴, C Ewels¹, JY Mevellec¹, J Wéry¹, E Faulques¹

¹ Institut des Matériaux Jean Rouxel, Université de Nantes, CNRS, France

² Sciences Chimiques de Rennes, Université de Rennes, CNRS, France

³ IMMM/LPEC, Université du Maine, CNRS, France

⁴ Institut de Physique de Rennes, Université de Rennes, CNRS, France

E-mail: duvail@cncrs-imn.fr

One-dimensional polymer and hybrid nanostructures, such as nanowires (NWs) and nanotubes (NTs), represent attractive building blocks for nanoscale optoelectronic and photonic devices. They exhibit promising functionalities namely field effect in transistors and sensors, field emission, active waveguiding, optically pumped lasing and photodetection. Recent advances in the synthesis of hybrid nanostructures open the way to investigate and ultimately to control the optical features by the choice of materials and their respective location in complex architectures.

In this scope, we report on the design and study of the (opto)electronic and photonic properties of different polymer-based nanowires and nanotubes. The elaboration of nanowires and nanotubes with different architectures reported in this work has been achieved by template strategies.

Conducting poly(3,4-ethylene-dioxythiophene) PEDOT nanowires were synthesized by electropolymerization confined within nanopores. The effect of the nanowire diameter on the electrical properties has been determined, with a shift from an insulating behavior for 190 nm diameter to a metal-like behavior for the 35 nm one. This has been attributed to molecular and supermolecular improvement induced by the confined synthesis, as shown by spectroscopic studies.[1]

Semi-conducting poly-(p-phenylene-vinylene) (PPV) nanowires and nanotubes were elaborated by a solvent-assisted wetting of nanopores. The study of their photoluminescence PL behaviors has shown that the nanotube exhibit unique PL features: a new band located at 460 nm with a decay time which can be analyzed with a single component. This can be explained by the polymer chain alignment along the NT axis and to inhibited exciton migration.[2] This ability for the template strategy to align polymer chains has been extended to carbon nanotubes (SWNTs) in PPV-SWNT nanocomposite nanofibers. It results in an enhancement of the photoconductivity by a factor larger than 150.[3] Finally, the magnetic manipulation of luminescent NWs was demonstrated by synthesizing a nickel core within a PPV shell.[4]

Recently, we develop an original concept to restrain the charge and energy transfer between two luminophores for controlling the color of emission nanowires.[5] This has been achieved by a spectral and spatial control of the two luminophores. A coaxial geometry results in yellow NWs while the core is a nanocomposite (metal-compound clusters of Mo₆Br₈F₆ within a PMMA matrix) with a red PL signal and the shell is green-emitting PPV.

[1] J.L. Duvail et al., Appl. Phys. Lett. 90, 102114 (2007)

[2] F. Massuyeau et al., Nanotechnology 20, 155701 (2009)

[3] F. Massuyeau et al., *under revision*

[4] J.M. Lorcy et al., Nanotechnology 20, 405601 (2009)

[5] A. Garreau et al., *under revision*