

Spanish Conference on Nanophotonics - CEN2021. September 20-22 2021, Vigo.

Nanostructure strategies for improved perovskite solar cells

Z. Hu¹, L. Aigouy¹, J.M. García-Martín², M.-U. González², H.-J. Lin¹, M. Schoenauer-Sebag¹, L. Billot¹, P. Gredin³, M. Mortier³, Z. Chen¹ and A. García-Martín²

(1) LPEM, ESPCI Paris, PSL Research University, CNRS, Sorbonne Universités, Paris, France

(2) Instituto de Micro y Nanotecnología IMN-CNM, CSIC (CEI UAM+CSIC), Tres Cantos, Madrid, Spain

(3) Chimie ParisTech, PSL Research University, CNRS, Institut de Recherche de Chimie Paris, Paris, France

Organic-inorganic hybrid perovskite solar cells have attracted much attention due to their high power conversion efficiency (>23%) and low-cost fabrication. Directions to further improve these solar cells include strategies to enhance their stability and their efficiency by modifying either the perovskite absorber layer or the electron/hole transport layer. For example, the transparent electron transport layer (ETL) can be an important tuning knob influencing the charge extraction, [1] light harvesting, [2] and stability [3] in these solar cells, or the use of up-conversion nanoparticles to get better performance in the near IR part of the visible spectrum. [4] Here we present two strategies based on nanostructuration, first a fundamental study of upconversion fluorescence enhancement effects near Au nanodisks by scanning near-field optical microscopy and second the effects of a nanocolumnar TiO₂ layer on the performance and the stability of Cs_{0.05}(FA_{0.83}MA_{0.17})_{0.95}Pb(I_{0.83}Br_{0.17})₃ perovskite solar cells. For the first case, the enhancement and localization of light near the metallic structures are directly visualized by using a single Er/Yb-codoped fluorescent nanocrystal glued at the end of a sharp scanning tip. [5] For the second we find that, compared to devices with planar TiO₂ ETLs, the TiO₂ nanocolumns can significantly enhance the power conversion efficiency of the perovskite solar cells by 17 % and prolong their shelf life. By analyzing the optical properties, solar cells characteristics, as well as transport/recombination properties by impedance spectroscopy, we observed light-trapping and reduced carrier recombination in solar cells associated with the use of TiO₂ nanocolumn arrays. [6]

References:

- [1] S.S. Mali, et al., *Chemistry of Materials* 27, 1541 (2015).
- [2] C. Liu, et al., *Journal of Materials Chemistry A* 5, 15970 (2017).
- [3] M. Salado, et al., *Nano Energy* 35, 215 (2017)
- [4] M. Bauch et al., *Plasmonics* 9, 781 (2014)
- [5] L. Aigouy, et al., *Nanoscale* 11, 10365 (2019)
- [6] Z. Hu, et al., *ACS Appl. Mater. Interfaces* 12, 5979 (2020)