Aalborg Universitet



Hydrothermal kraft lignin depolymerization with glycerol as a capping agent

Ahlbom, Anders; Hasani, Merima; Theliander, Hans; Nielsen, Rudi P.; Maschietti, Marco

Publication date: 2022

Link to publication from Aalborg University

Citation for published version (APA):

Ahlbom, A., Hasani, M., Theliander, H., Nielsen, R. P., & Maschietti, M. (2022). *Hydrothermal kraft lignin depolymerization with glycerol as a capping agent*. Poster presented at LignoCOST Lignin Conference Meeting, Wageningen, Netherlands.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
 You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.



CHALMERS UNIVERSITY OF TECHNOLOGY

CHALMERS UNIVERSITY OF TECHNOLOGY SE-412 96 Gothenburg, Sweden +46 (0)31 772 10 00, www.chalmers.se

Hydrothermal kraft lignin depolymerization with glycerol as a capping agent

Introduction

To make use of aromatic units from lignin as chemicals or fuel additives, the molecular structure of lignin needs to be broken down.

Aim

To investigate structural and molecular weight changes of kraft lignin in hydrothermal liquefaction at short residence times with glycerol as a capping agent to expand on

Hydrothermal liquefaction (HTL), where the lignin is depolymerized in hot pressurized water, is one way to break the lignin structure. However, the depolymerized material is reactive and suffers from repolymerization.

We here investigate one method to mitigate repolymerization by means of short residence times in the reactor and by adding glycerol as a capping agent.

Structural changes


Typical inter-unit ether linkages in lignin are cut already after 1 min of residence time in the reactor. previous work made with isopropanol as a capping agent at short residence times.^{1,2}


Conclusion


The depolymerization is quick, with molecular weight changes occurring within one minute. Also, inter-unit ether linkages are broken within the first minute of residence time in the reactor. This opens up for HTL processing of kraft lignin at short residence times.

Molecular weight

Large molecular weight fractions are lost after only 1 min of residence time.







Molecular weights of the LignoBoost lignin and char fractions.




Softwood kraft lignin, isolated with the LignoBoost process, was depolymerized using hydrothermal liquefaction at the following conditions

290°C	6 wt% lignin
250 bar	1 wt% NaOH
1-12 min residence time	16 wt% glycerol

99 ml batch reactor $1.6wt\% Na_2CO_3$

The reaction mixture was quickly heated in a custom-made batch reactor by pumping the lignin mixture into pre-heated material in the reactor. The reaction products were ejected after the specified residence time and quickly quenched in an ice-bath.

Inter-unit aliphatic region of 2D-NMR spectra of LignoBoost lignin and char. Annotations for lignin according to Mattsson et al..³



Anders Ahlbom, anders.ahlbom@chalmers.se Merima Hasani, Hans Theliander

Department of Chemistry and Chemical Engineering, Chalmers University of Technology, Gothenburg, Sweden

Rudi Nielsen, Marco Maschietti

Aalborg University, Chemistry and Bioscience, Esbjerg, Denmark

- 1. Ahlbom, A., Maschietti, M., Nielsen, R., Lyckeskog, H., Hasani, M. and Theliander, H., **Energies** 14, 932 (2021).
- Ahlbom, A., Maschietti, M., Nielsen, R., Hasani, M. & Theliander, H., Holzforschung 76, 37–48 (2022).
- 3. Mattsson, C. et al., Biomass and Bioenergy 95, 364–377 (2016).



